



# Standard Specification for Naval Brass Rod, Bar, and Shapes<sup>1</sup>

This standard is issued under the fixed designation B21/B21M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification establishes the requirements for naval brass rod, bar, and shapes produced from Copper Alloy UNS Nos. C46200, C46400, C46750, C47940, C48200, or C48500.

1.1.1 For piston-finish rod or shafting refer to the Other Requirements Section.

1.1.2 For hot forging material, refer to Specification [B124/B124M](#).

1.2 *Units*—The values stated in inch-pound units or SI units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.3 **Warning**—Mercury is a definite health hazard in use and disposal (see Performance Requirements).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[B124/B124M](#) Specification for Copper and Copper Alloy Forging Rod, Bar, and Shapes

[B154](#) Test Method for Mercurous Nitrate Test for Copper Alloys

[B249/B249M](#) Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Sept. 1, 2014. Published September 2014. Originally approved in 1918. Last previous edition approved in 2012 as B21/B21M – 12. DOI: 10.1520/B0021\_B0021M-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[B601](#) Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

[B858](#) Test Method for Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys

[E8/E8M](#) Test Methods for Tension Testing of Metallic Materials

[E18](#) Test Methods for Rockwell Hardness of Metallic Materials

[E62](#) Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)<sup>3</sup>

[E478](#) Test Methods for Chemical Analysis of Copper Alloys

## 3. General Requirements

3.1 The following sections of Specification [B249/B249M](#) constitute a part of this specification:

3.1.1 Terminology,

3.1.2 Materials and Manufacture,

3.1.3 Workmanship, Finish, and Appearance,

3.1.4 Sampling,

3.1.5 Number of Tests and Retests,

3.1.6 Specimen Preparation,

3.1.7 Test Methods,

3.1.8 Significance of Numerical Limits,

3.1.9 Inspection,

3.1.10 Rejection and Rehearing,

3.1.11 Certification,

3.1.12 Mill Test Report,

3.1.13 Packaging and Product Marking, and

3.1.14 Supplementary Requirements.

3.2 In addition, when a section with a title identical to that referenced in 3.1, above, appears in this specification, it contains additional requirements which supplement those appearing in Specification [B249/B249M](#).

## 4. Ordering Information

4.1 Include the following specified choices when placing orders for product under this specification, as applicable:

4.1.1 ASTM designation and year of issue,

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard

- 4.1.2 Copper Alloy UNS No. designation (Scope),
- 4.1.3 Temper (Temper Section and related Tables),
- 4.1.4 Form—cross-section such as round, hexagonal, square, and so forth,
- 4.1.5 Diameter or distance between parallel surfaces, width and thickness (Dimensions and Permissible Variations),
- 4.1.6 Length (Dimensions and Permissible Variations),
- 4.1.7 Edge contours (Dimensions and Permissible Variations),
- 4.1.8 Quantity—number of pieces or total weight, for each size and form, and
- 4.1.9 Intended application.

4.2 The following options are available, but may not be included, unless specified at the time of placing of the order when required:

- 4.2.1 Tensile test for product ½ in. [12 mm] and over, for the alloys and tempers listed in **Table 4**.
- 4.2.2 Residual stress test (Performance Requirements section),
- 4.2.3 Piston finish rod or shafting (Other Requirements section),
- 4.2.4 Certification (Specification **B249/B249M**),
- 4.2.5 Mill test report (Specification **B249/B249M**),
- 4.2.6 Heat identification or traceability details (Specification **B249/B249M**), and
- 4.2.7 If product is purchased for agencies of the U.S. government (Other Requirements—Purchases for U.S. Government).

## 5. Chemical Composition

5.1 The material shall conform to the chemical composition requirements specified in **Table 1** for the Copper Alloy UNS No. designation specified in the ordering information.

5.2 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier, and purchaser.

5.3 For alloys in which zinc is listed as the “remainder,” either copper or zinc may be taken as the difference between the sum of results of all other elements determined and 100 %. When copper is so determined, that difference value shall conform to the requirements given in **Table 1**.

5.4 When all the elements listed in **Table 1** for the Copper Alloy No. are determined, the sum of the results shall be 99.6 % minimum except for C46750, which shall be 99.5 % minimum.

## 6. Temper

6.1 The standard tempers for products described in this specification, as defined in Classification **B601**, are shown in **Tables 2 and 3**.

## 7. Mechanical Property Requirements

7.1 Product furnished under this specification shall conform to the mechanical property requirements prescribed in **Tables 2-4**.

7.1.1 *Rockwell Hardness Requirements*—For the alloys and tempers listed, the product ½ in. [12 mm] and over in diameter or distance between parallel surfaces should conform with the requirements prescribed in **Table 4**, when tested in accordance with Test Methods **E18**.

7.1.1.1 For the alloys, tempers, and sizes listed in **Table 4**, Rockwell hardness may be used as the basis of acceptance or rejection for mechanical properties except when the tensile test is specified in the contract or purchase order.

7.1.1.2 Hardness test results outside the ranges of **Table 4** shall not be cause for rejection if the tensile property requirements of **Tables 2 and 3** are met.

7.1.2 *Tensile Strength Requirements*—The product shall conform with the requirements of **Tables 2 and 3**, when tested in accordance with Test Methods **E8/E8M**. Whenever tensile test results are obtained from both full-size and from machined test specimens and they differ, the results obtained from full-size test specimens shall be used to determine conformance to the requirements of this specification.

## 8. Performance Requirements

8.1 *Residual Stress Test:*

8.1.1 When specified in the contract or purchase order, product in drawn tempers shall be tested for residual stress according to the requirements of Test Method **B154** or Test Method **B858** and show no signs of cracking.

8.1.2 Unless otherwise agreed upon between the manufacturer, or supplier, and the purchaser, the manufacturer shall have the option of using either the Mercurous Nitrate Test or the Ammonia Vapor Test. When the Ammonia Vapor Test is

**TABLE 1 Chemical Requirements**

Element, %	Copper Alloy UNS No.					
	C46200	C46400	C46750	C47940	C48200	C48500
Copper	62.0–65.0	59.0–62.0	59.2–62.5	63.0–66.0	59.0–62.0	59.0–62.0
Tin	0.50–1.0	0.50–1.0	1.00–1.80	1.2–2.0	0.50–1.0	0.50–1.0
Lead	0.20 max	0.20 max	0.25 max	1.0–2.0	0.40–1.0	1.3–2.2
Zinc	remainder	remainder	remainder	remainder	remainder	remainder
Iron	0.10 max	0.10 max	0.10 max	0.10–1.0	0.10 max	0.10 max
Nickel <sup>a</sup>	...	...	0.50 max	0.10–0.50	...	...
Antimony	...	...	0.05–0.15	...	...	...
Phosphorus	...	...	0.05–0.15	...	...	...

<sup>a</sup> Including cobalt.

**TABLE 2 Tensile Requirements, Inch-pound**

Temper Designation		Diameter or Distance	Tensile	Yield Strength at 0.5 %	Elongation in 4 ×
Code	Name	Between Parallel <sup>A</sup> Surfaces, in.	Strength, min, ksi	Extension Under Load, min, ksi	Diameter or Thickness of Specimen, min, % <sup>B</sup>
Copper Alloy UNS No. C46200					
M30	as-hot extruded	all forms, all sizes	50	20	30
O60	soft anneal	rods and bars, all sizes	48	16	30
O50	light anneal	rods and bars:			
		0.500 and under	58	27	22
		over 0.500 to 1.000, incl	56	27	25
		over 1.000 to 2.000, incl	54	26	25
		over 2.000 to 3.000, incl	52	25	27
		over 3.000 to 4.000, incl	50	22	30
		over 4.000	50	20	30
H60	cold heading, forming	rods, all sizes	48	18	22
H02	half-hard	rods and bars:			
		0.500 and under	58	27	22
		over 0.500 to 1.000, incl	56	27	25
		over 1.000 to 2.000, incl	54	26	25
		over 2.000 to 3.000, incl	52	25	27
		over 3.000 to 4.000, incl	50	22	30
		over 4.000	50	20	30
H04	hard	rods and bars:			
		0.500 and under	64	40	13
		over 0.500 to 1.000, incl	62	38	13
		over 1.000 to 2.000, incl	58	34	18
Copper Alloy UNS No. C46400					
M30	as-hot extruded	all forms, all sizes	52	20	30
O60	soft anneal	rods and bars:			
		1.000 and under	54	20	30
		over 1.000 to 2.000, incl	52	20	30
		over 2.000	50	20	30
		shapes, all sizes	52	20	30
O50	light anneal	rods and bars:			
		0.500 and under	60	27	22
		over 0.500 to 1.000, incl	60	27	25
		over 1.000 to 2.000, incl	58	26	25
		over 2.000 to 3.000, incl	54	25	25
		over 3.000 to 4.000, incl	54	22	27
		over 4.000	54	22	30
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	58	25	20
H02	half-hard	rods and bars:			
		0.500 and under	60	27	22
		over 0.500 to 1.000, incl	60	27	25
		over 1.000 to 2.000, incl	58	26	25
		over 2.000 to 3.000, incl	54	25	25
		over 3.000 to 4.000, incl	54	22	27
		over 4.000	54	22	30
H04	hard	rods and bars:			
		1.000 and under	67	45	13
		over 1.000 to 2.000, incl	62	37	18
Copper Alloy UNS No. C46750					
M30	as hot extruded	all forms, all sizes	48	20	15
O60	soft annealed	rod and bar, all sizes	49	20	15
O61	annealed	rod and bar, all sizes	49	20	15
H50	hot extruded and drawn	rod and bar:			
		over 0.300 to .500	48	20	5
		over 0.500 to 1.000	48	20	10
		over 1.000	48	20	15
Copper Alloy UNS No. C47940					
M30	as-hot extruded	all forms, all sizes	50	20	30
O60	soft anneal	rods and bars, all sizes	48	20	30
O50	light anneal	rods and bars:			
		0.500 and under	58	30	18
		over 0.500 to 1.000, incl	56	30	20
		over 1.000 to 2.0, incl	54	25	22
		over 2.000	50	25	25
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	56	25	20
H02	half-hard	rods and bars:			
		0.500 and under	58	30	18
		over 0.500 to 1.000, incl	56	30	20
		over 1.000 to 2.000, incl	54	25	22
		over 2.000	50	25	25
H04	hard	rods and bars:			
		0.500 and under	70	55	10
		over 0.500 to 1.000, incl	65	52	13
		over 1.000 to 2.000, incl	62	45	15

**TABLE 2** *Continued*

Temper Designation		Diameter or Distance Between Parallel <sup>A</sup> Surfaces, in.	Tensile Strength, min, ksi	Yield Strength at 0.5 % Extension Under Load, min, ksi	Elongation in 4 × Diameter or Thickness of Specimen, min, % <sup>B</sup>
Code	Name				
Copper Alloy UNS No. C48200					
M30	as-hot extruded	all forms, all sizes	52	20	25
O60	soft anneal	rods and bars:			
		1.000 and under	54	20	25
		over 1.000 to 2.000, incl	52	20	25
		over 2.000	50	20	25
		shapes, all sizes	52	20	25
O50	light anneal	rods and bars:			
		1.000 and under	60	27	18
		over 1.000 to 2.000, incl	58	26	20
		over 2.000 to 3.000, incl	54	25	20
		over 3.000 to 4.000, incl	54	22	20
		over 4.000	54	22	25
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	58	25	15
H02	half-hard	rods and bars:			
		1.000 and under	60	27	18
		over 1.000 to 2.000, incl	58	26	20
		over 2.000 to 3.000, incl	54	25	20
		over 3.000 to 4.000, incl	54	22	20
		over 4.000	54	22	25
H04	hard	rods and bars:			
		1.000 and under	67	45	11
		over 1.000 to 2.000, incl	62	37	15
Copper Alloy UNS No. C48500					
M30	as-hot extruded	all forms, all sizes	52	20	20
O60	soft anneal	rods and bars:			
		1.000 and under	54	20	20
		over 1.000 to 2.000, incl	52	20	20
		over 2.000	50	20	20
		shapes, all sizes	52	20	20
O50	light anneal	rods and bars:			
		1.000 and under	60	27	12
		over 1.000 to 2.000, incl	58	26	20
		over 2.000 to 3.000, incl	54	25	20
		over 3.000 to 4.000, incl	54	22	20
		over 4.000	54	22	20
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	58	25	15
H02	half-hard	rods and bars:			
		1.000 and under	60	27	12
		over 1.000 to 2.000, incl	58	26	20
		over 2.000 to 3.000, incl	54	25	20
		over 3.000 to 4.000, incl	54	22	20
		over 4.000	54	22	20
H04	hard	rods and bars:			
		1.000 and under	67	45	10
		over 1.000 to 2.000, incl	62	37	13

<sup>A</sup> For rectangular bar, the Distance Between Parallel Surfaces refers to thickness.

<sup>B</sup> In any case, a minimum gage length of 1 in. shall be used.

<sup>C</sup> This temper does not apply to hollow shapes.

used, the test pH value appropriate for the intended application shall be 10 unless otherwise specified by the purchaser. (**Warning**—Mercury has been designated by many regulatory agencies as a hazardous material that can cause serious medical issues. Mercury, or its vapor, has been demonstrated to be hazardous to health and corrosive to materials. Caution should be taken when handling mercury and mercury containing products. See the applicable product Safety Data Sheet (SDS) for additional information. Users should be aware that selling mercury and/or mercury containing products into your state or country may be prohibited by law.)

NOTE 1—A residual stress test provides information about the adequacy of the stress relief of the material. Bar straightening is a method of mechanical stress relief. Stress relief annealing is a method of thermal stress relief.

## 9. Other Requirements

### 9.1 Piston-Finish Rod and Shafting:

9.1.1 When so specified in the contract or order, round rods over 1/2-in. [12 mm] diameter shall be furnished as piston-finish rods or shafting.

9.1.2 Piston-finish rods shall have a special surface produced by turning or grinding and shall comply with the special diameter tolerances specified in Piston-Finish Rod Section under Dimensions and Permissible Variations.

9.1.3 The straightness tolerances for piston-finish rod are subject to agreement between the manufacturer or supplier and the purchaser.

### 9.2 Purchases for U.S. Government:

**TABLE 3 Tensile Requirements, SI**

Code	Temper Designation Name	Diameter or Distance Between Parallel <sup>A</sup> Surfaces, mm	Tensile Strength, min, MPa	Yield Strength at 0.5 % Extension Under Load, min, MPa	Elongation in 4x Diameter or Thickness of Specimen, min, % <sup>B</sup>
Copper Alloy UNS No. C46200					
M30	as-hot extruded	all forms, all sizes	345	140	30
O60	soft anneal	rods and bars, all sizes	330	110	30
O50	light anneal	rods and bars:			
		12 and under	400	185	22
		over 12 to 25, incl	385	185	25
		over 25 to 50, incl	370	180	25
		over 50 to 75, incl	360	170	27
		over 75 to 100, incl	345	150	30
		over 100	345	140	30
H60	cold heading, forming	rods, all sizes	330	125	22
H02	half-hard	rods and bars:			
		12 and under	400	185	22
		over 12 to 25, incl	385	185	25
		over 25 to 50, incl	370	180	25
		over 50 to 75, incl	360	170	27
		over 75 to 100, incl	345	150	30
		over 100	345	140	30
H04	hard	rods and bars:			
		12 and under	440	275	13
		over 12 to 25, incl	425	260	13
		over 25 to 50, incl	400	235	18
Copper Alloy UNS No. C46400					
M30	as-hot extruded	all forms, all sizes	360	140	30
O60	soft anneal	rods and bars:			
		25 and under	370	140	30
		over 25 to 50, incl	360	140	30
		over 50	345	140	30
O50	light anneal	shapes, all sizes	360	140	30
		rods and bars:			
		12 and under	415	185	22
		over 12 to 25, incl	415	185	25
		over 25 to 50, incl	400	180	25
		over 50 to 75, incl	370	170	25
		over 75 to 100, incl	370	150	27
		over 100	370	150	30
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	400	170	20
H02	half-hard	rods and bars:			
		12 and under	415	185	22
		over 12 to 25, incl	415	185	25
		over 25 to 50, incl	400	180	25
		over 50 to 75, incl	370	170	25
		over 75 to 100, incl	370	150	27
		over 100	370	150	30
H04	hard	rods and bars:			
		25 and under	460	310	13
		over 25 to 50, incl	425	255	18
Copper Alloy UNS No. C46750					
M30	as hot extruded	all forms, all sizes	315	140	15
O60	soft annealed	rod and bar, all sizes	335	140	15
O61	annealed	rod and bar, all sizes	335	140	15
H50	hot extruded and drawn	rod and bar:			
		over 8 to 12	315	140	5
		over 13 to 25	315	140	10
		over 25	315	140	15
Copper Alloy UNS No. C47940					
M30	as-hot extruded	all forms, all sizes	345	140	30
O60	soft anneal	rods and bars, all sizes	330	140	30
O50	light anneal	rods and bars:			
		12 and under	400	210	18
		over 12 to 25, incl	390	210	20
		over 25 to 50, incl	375	175	22
		over 50	345	175	25
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	390	175	20
H02	half-hard	rods and bars:			
		12 and under	400	210	18
		over 12 to 25, incl	390	210	20
		over 25 to 50, incl	375	175	22
		over 50	345	175	25
H04	hard	rods and bars:			
		12 and under	485	380	10
		over 12 to 25, incl	450	360	13
		over 25 to 50, incl	430	310	15

**TABLE 3** *Continued*

Temper Designation		Diameter or Distance	Tensile	Yield Strength at 0.5 %	Elongation in 4×
Code	Name	Between Parallel <sup>A</sup> Surfaces, mm	Strength, min, MPa	Extension Under Load, min, MPa	Diameter or Thickness of Specimen, min, % <sup>B</sup>
Copper Alloy UNS No. C48200					
M30	as-hot extruded	all forms, all sizes	360	140	25
O60	soft anneal	rods and bars:			
		25 and under	370	140	25
		over 25 to 50, incl	360	140	25
		over 50	345	140	25
		shapes, all sizes	360	140	25
O50	light anneal	rods and bars:			
		25 and under	415	185	18
		over 25 to 50, incl	400	180	20
		over 50 to 75, incl	370	170	20
		over 75 to 100, incl	370	150	20
		over 100	370	150	25
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	400	170	15
H02	half-hard	rods and bars:			
		25 and under	415	185	18
		over 25 to 50, incl	400	180	20
		over 50 to 75, incl	370	170	20
		over 75 to 100, incl	370	150	20
		over 100	370	150	25
H04	hard	rods and bars:			
		25 and under	460	310	11
		over 25 to 50, incl	425	255	15
Copper Alloy UNS No. C48500					
M30	as-hot extruded	all forms, all sizes	360	140	20
O60	soft anneal	rods and bars:			
		25 and under	370	140	20
		over 25 to 50, incl	360	140	20
		over 50	345	140	20
		shapes, all sizes	360	140	20
O50	light anneal	rods and bars:			
		25 and under	415	185	12
		over 25 to 50, incl	400	180	20
		over 50 to 75, incl	370	170	20
		over 75 to 100, incl	370	150	20
		over 100	370	150	20
H50 <sup>C</sup>	extruded and drawn <sup>C</sup>	shapes, all sizes	400	170	15
H02	half-hard	rods and bars:			
		25 and under	415	185	12
		over 25 to 50, incl	400	180	20
		over 50 to 75, incl	370	170	20
		over 75 to 100, incl	370	150	20
		over 100	370	150	20
H04	hard	rods and bars:			
		25 and under	460	310	10
		over 25 to 50, incl	425	255	13

<sup>A</sup> For rectangular bar, the Distance Between Parallel Surfaces refers to thickness.

<sup>B</sup> In any case, a minimum gage length of 25 mm shall be used.

<sup>C</sup> This temper does not apply to hollow shapes.

9.2.1 Product purchased for agencies of the U.S. Government shall conform to the additional requirements prescribed in the Supplementary Requirements section of Specification **B249/B249M**.

## 10. Dimensions and Permissible Variations

10.1 The dimensions and tolerances for product described by this specification shall be as specified in the current edition of Specification **B249/B249M**, with particular reference to the following tables and related paragraphs in that specification:

10.2 *Diameter or Distance Between Parallel Surfaces:*

10.2.1 *Rod: Round, Hexagonal, Octagonal*—See Table 1.

10.2.2 *Rod, M30 (As-Hot Extruded)*—See Table 4.

10.2.3 *Piston-Finish Rod*—See Table 3.

10.2.4 *Bar: Rectangular and Square*—See Tables 8 and 10.

10.2.5 *Bar, M30 (As-Hot Extruded)*—See Table 4.

10.3 *Shapes*—The dimensional tolerances for shapes shall be as agreed upon by the manufacturer or supplier and the purchaser, and shall be specified in the order.

10.4 *Length of Rod, Bar, and Shapes*—See Tables 13 and 14.

10.5 *Straightness:*

10.5.1 *Rod and Bar*—See Table 16.

10.5.2 *Shafting Rod*—See Table 17.

10.5.3 *M30 (As-Hot Extruded)*—Rod, bar, and shapes shall be commercially straight.

**TABLE 4 Rockwell Hardness Requirements**

NOTE 1—Rockwell Hardness Requirements are not established for diameters less than ½ in. [12 mm].

Copper Alloy UNS No.	Temper Designation		Diameter or Distance Between Parallel Surfaces <sup>A</sup>		Rockwell B Hardness Determined on the Cross Section Midway Between Surface and Center
	Code	Name	in.	mm	
C46400	H02	half-hard	0.500 to 1.000, incl over 1.000	12 to 25, incl over 25	60–80 55–80
	H04	hard	0.500 to 1.000, incl over 1.000	12 to 25, incl over 25	70–90 65–90
C48200	H02	half-hard	0.500 to 1.000, incl over 1.000	12 to 25, incl over 25	65–85 60–85
	H04	hard	0.500 to 1.000, incl over 1.000	12 to 25, incl over 25	70–90 65–90
C48500	H02	half-hard	0.500 to 1.000, incl over 1.000	12 to 25, incl over 25	65–85 60–85
	H04	hard	0.500 to 1.000, incl over 1.000	12 to 25, incl over 25	70–90 65–90

<sup>A</sup> For rectangular bar, the Distance Between Parallel Surfaces refers to thickness.

10.6 *Edge Contours*—See Edge Contours Section.

## 11. Specimen Preparation

11.1 In the tensile test, all material shall be pulled in full size when practicable. Full-size or machined test specimens shall be as specified in the Test Specimen Section of Test Methods **E8/E8M**.

11.2 Residual stress test specimens shall be of the full size of the product, and tested without bending, springing, polishing or any other preparation, except as allowed by the test method.

## 12. Test Methods

### 12.1 Chemical Analysis:

12.1.1 In cases of disagreement, determine the composition using the following methods:

Element	ASTM Test Method
Antimony	<b>E62</b>
Copper	<b>E478</b>
Iron	<b>E478</b>
Lead	<b>E478 (AA)</b>
Nickel	<b>E478</b>
Phosphorus	<b>E62</b>
Tin	<b>E478 (titrimetric)</b>
Zinc	<b>E478 (titrimetric)</b>

12.1.2 Test method(s) to be followed for the determination of element(s) resulting from contractual or purchase order agreement shall be agreed upon between the manufacturer or supplier and purchaser.

## 13. Keywords

13.1 naval brass; naval brass bar; naval brass rod; piston-finish rod; shafting; shapes; UNS No. C46200; UNS No. C46400; UNS No. C46750; UNS No. C47940; UNS No. C48200; UNS No. C48500

## SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B21/B21M – 12) that may impact the use of this standard. (Approved Sept. 1, 2014.)

(1) Added UNS Alloy No. C46750 to **1.1**, **5.4**, **Table 1**, **Table 2**, **Table 3**, **12.1.1**, and Section **13**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*