



Standard Test Method for Apparent Porosity in Cemented Carbides¹

This standard is issued under the fixed designation B276; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method specifies procedures for the metallographic determination of apparent porosity in cemented carbides.

NOTE 1—The term “apparent porosity” is construed to mean all microstructures observed on a properly prepared, unetched surface, including structures resulting from uncombined carbon, non-metallic inclusions, etc., as well as true, inherent porosity.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[B243 Terminology of Powder Metallurgy](#)

[B665 Guide for Metallographic Sample Preparation of Cemented Tungsten Carbides](#)

2.2 *ASTM Adjunct:*³

[ADJB0276A Apparent Porosity \(4 prints of 4 photomicrographs each\)](#)

3. Terminology

3.1 *Definitions*—Definition of powder metallurgy terms can be found in Terminology [B243](#).

4. Significance and Use

4.1 Cemented carbide materials may contain small voids that, depending on the application, may affect the performance of the product. To assist users in specifying the maximum

acceptable level of porosity, this test method illustrates a broad range of porosity levels for each of three porosity types. This test method is not intended to be used as a specification, but the levels shown here may be cited in specifications written by producers and users of cemented carbides.

5. Interferences

5.1 Lack of adequate pressure on the specimen during polishing may result in material being torn from the surface of the specimen. This condition may be erroneously interpreted as porosity.

6. Apparatus

6.1 A metallographic microscope permitting observation and measurement up to a magnification of 200 \times .

6.2 Equipment for the metallographic preparation of test specimens.

7. Specimen Preparation

7.1 Where possible, specimens should be metallographically mounted in a plastic material, so that they can be polished without rounding the edges. Larger specimens may be polished without mounting. When the specimens are too large, they shall be sectioned using a diamond cut-off wheel or by fracturing (appropriate safety precautions shall be utilized when fracturing a specimen). The area selected for examination should represent, as nearly as possible, the entire cross section.

7.2 The specimen shall be prepared for metallographic examination. A suitable procedure is described in Practice [B665](#). The surface to be examined shall be unetched and free of grinding and polishing marks.

8. Procedure

8.1 Pore size shall be defined as the maximum dimension of the pore. Make special reference to the presence of cracks and slits, as well as nonmetallic inclusions.

8.2 Classification of Type “A” and “C” apparent porosity is based entirely on comparison of the microstructures found with the illustrations in Figs. 1, 3 and 4 of [ADJB0276A](#)³ with due consideration to the difference in field of view of the microscope compared to the area of the illustrations. This can be

¹ This test method is under the jurisdiction of ASTM Committee [B09](#) on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee [B09.06](#) on Cemented Carbides.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1954. Last previous edition approved in 2010 as B276 – 91(2010). DOI: 10.1520/B0276-05R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ Available from ASTM International Headquarters. Order Adjunct No. [ADJB0276A](#).

accomplished by scanning the specimen surface under the microscope at the appropriate magnification, and noting which of the illustrations most nearly represents the fields observed. Choose an area fully representative of the specimen surface for comparison with the illustrations.

NOTE 2—The illustrations in Figs. 1–4 of [ADJB0276A](#) represent only a portion of the field of view typically observed in modern microscopes. Typically, the field of view of a microscope is ~6.5× larger than the area in these figures. The exact relationship between the area observed at any given magnification in the microscope and the area of the illustrations can be determined using the method in [Annex A1](#).

8.2.1 Classify pores ≤10 μm as Type A (see Fig. 1 of [ADJB0276A](#) and examine at a magnification of 200×. Report the porosity level by reference to the appropriate illustration with consideration to the relationship of area between the illustration and that observed in the microscope, and designate as A02, A04, A06, or A08. If the level of Type A pores is less than 50 % of that shown in the illustration for A02, then designate this as A00. If the porosity is not uniform over the area of the test-piece section being examined, identify the location of the section, for example, as top, bottom, edge, rim (case), core, and so forth.

8.2.2 Classify pores in the range from >10 to ≤25 μm as Type B (see Fig. 2 of [ADJB0276A](#) and examine at a magnification of 100×.

8.2.2.1 If the number of “B” pores appears to be less than or equal to that represented by B02, with consideration to the relationship of area between the illustrations in Fig. 2 of [ADJB0276A](#) and that observed in the microscope (see [A1.3](#)), count the number of “B” pores in a representative area (≥0.25 cm²). Divide this count by the area examined (see [A1.3](#)) to obtain the number of “B” pores/cm². If this number is less than 70 pores/cm², designate this as B00-#, where # is the number of “B” pores/cm² so obtained. If the number is greater than or equal to 70 pores/cm², designate this as B02. If no “B” pores are observed, designate this as B00-0.

8.2.2.2 If the number of “B” pores appears to be greater than that represented by B02, with consideration to the relationship

of area between the illustrations in Fig. 2 of [ADJB0276A](#) and that observed in the microscope (see [A1.4](#)), classify the “B” porosity as B04, B06, or B08 with reference to the illustrations in Fig. 2 of [ADJB0276A](#). If the porosity is not uniform over the area of the test-piece section being examined, identify the location of the section, for example, as top, bottom, edge, rim (case), core, and so forth.

8.2.3 Count and report pores larger than 25 μm as the number of pores per cm². Choose the size ranges as follows: >25 to ≤75 μm, >75 to ≤125 μm, and over 125 μm.

8.2.4 Classify porosity resulting from uncombined carbon as Type C (see Figs. 3 and 4 of [ADJB0276A](#) and examine at a magnification of 100 or 200×. Report the porosity level by reference to the appropriate illustration with consideration to the relationship of area between the illustrations in Figs. 3 and 4 of [ADJB0276A](#) and that observed in the microscope, and designate as C02, C04, C06, or C08. If the porosity of uncombined carbon is not uniform over the area of the test-piece section being examined, identify the location of the section, for example as top, bottom, edge, rim (case), core, and so forth. If no uncombined carbon is observed, designate this as C00.

9. Report

9.1 The report shall include the following:

9.1.1 Reference to this test method,

9.1.2 Complete identification of the test specimen,

9.1.3 Results obtained, and

9.1.4 Details of any occurrence that may have affected the result.

10. Precision and Bias

10.1 A precision and bias statement cannot be made for this test method.

11. Keywords

11.1 apparent porosity; cemented carbides; hardmetals; microstructure; powder metallurgy

ANNEX

(Mandatory Information)

A1. DETERMINATION OF THE FIELD OF VIEW OF MICROSCOPE

A1.1 Using a metallograph, view a stage micrometer.

A1.2 Determine the diameter (*D*) of the field of view to a precision of 0.002 cm.

A1.3 Calculate the area of the field of view using the formula:

$$A = \pi(D/2)^2 \quad (\text{A1.1})$$

where:

A = area of field of view, cm², and

D = diameter of field of view, cm.

A1.4 Determine the number of photomicrographs equivalent to the field of view of the microscope at the appropriate magnification using the following:

At 100×:

photographs = $A/0.00676 \text{ cm}^2$ using [ADJB0276A](#)

At 200×:

photographs = $A/0.0017 \text{ cm}^2$ using [ADJB0276A](#)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>