



Standard Specification for Appearance of Electroplated Plastic Surfaces¹

This standard is issued under the fixed designation B532; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification limits the amounts and types of visual defects that can be tolerated on decoratively electroplated surfaces of plastic products. The quantity of defects permitted shall be specified by the purchaser.

2. Referenced Documents

2.1 *ASTM Standards*:²

B374 Terminology Relating to Electroplating

D883 Terminology Relating to Plastics

3. Terminology

3.1 *Definitions*—See Terminology **B374** for terms relating to electroplating. For terms not relating to electroplating, see Terminology **D883**.

4. Classification of Surfaces

4.1 The appearance of surfaces will be separately evaluated depending on the prominence of the surface under conditions of ordinary use.

4.1.1 *Surface A*—The surface that appears most prominent to the observer, or most likely to be noticed at first glance.

4.1.2 *Surface B*—The surface (usually adjacent to Surface A) which is somewhat less prominent to the observer.

4.1.3 *Surface C*—The surface not readily seen by the observer except at an angle, or by special observation.

¹ This specification is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.08 on Metallic Coatings.

Current edition approved May 1, 2014. Published May 2014. Originally approved in 1970. Last previous edition approved in 2007 as B532 – 79(2007). DOI: 10.1520/B0532-85R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4.1.4 *Surface D*—The surface not visible to the observer under conditions of normal use.

5. Significance and Use

5.1 Where electroplated plastics are used for decorative purposes, the appearance after plating is important. This standard provides a means of evaluating the appearance of the substrate and the coating.

6. Method of Evaluation

6.1 The part under test shall be evaluated in the same relative position as it will normally be viewed under usual conditions of use.

6.2 After proper positioning, the part under test shall be evaluated at a distance of not less than 600 mm nor more than 900 mm from the observer, using diffused daylight-type fluorescent lighting or 1500 to 1600 lm/m² at the surface of the part being inspected.

6.3 The observer shall have 20/20 vision at a distance of 600 to 900 mm, corrected with eyeglasses if necessary.

7. Appearance Guide

7.1 **Table 1** limits the extent to which various defects are acceptable on each of the four surface classifications described in Section 4.

7.2 In **Table 1** the term “some” assumes that the defects cited are not outstanding, too numerous, or located too closely together. The specific number of defects permitted, and their spacing, shall be specified by the purchaser. The term “no” indicates that the defect cited is not normally acceptable. The term “yes” indicates that the defect cited is normally acceptable.

8. Keywords

8.1 appearance; electroplated plastic

TABLE 1 Evaluation of Appearance of Electroplated Plastic Surfaces

Defect	Surface			
	A	B	C	D
Cold shot ^A	no	no	some	yes
Ejection marks ^A	no	no	yes	yes
Flash ^A	no	no	no	no
Gate mark ^A	no ^B	some	yes	yes
Parting time ^A	no ^B	some	yes	yes
Sink marks ^C	no ^B	no ^B	yes	yes
Splay ^A	no	no	some	yes
Weld line ^A	no ^B	some	yes	yes
Burnt deposit ^C	no	no	some	some
Cracks ^C	no	no	no	no ^D
Peeling ^C	no	no	no	no ^D
Pits ^C	no	no	some	yes
Roughness ^C	no	no	some	yes
Scratches, nicks ^C	no	some	some	yes
Staining ^{C,E}	no	no	some	yes
Voids ^C	no	no	some	yes
Blisters ^F	no	no	no	no ^D
Visible intermediate deposits ^F	no	no	no	some ^G
Off color ^F	no	no	some	yes
Rack mark ^F	no	no	no	yes
Stardusting ^F	no	no	some	yes

^A These defects arise primarily in the plastic-molding operation.

^B Existence of these defects should be noted and resolved prior to tool manufacture. A change of design may be required.

^C These defects arise in either the plastic-molding or electroplating operation.

^D Blisters, or peeling, or cracks in the gate area or in the electroplating-rack contact area may be acceptable if the given area is covered or otherwise hidden after assembly.

^E Not removable by wiping or cleaning.

^F These defects arise primarily in the electroplating operation.

^G May occur at rack contacts or low current-density areas.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).