



# Standard Specification for Copper-Cobalt-Beryllium Alloy and Copper-Nickel-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar<sup>1</sup>

This standard is issued under the fixed designation B534; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

<sup>ε1</sup> NOTE—Footnote A in Tables 3 and 4 was corrected editorially in March 2015.

## 1. Scope\*

1.1 This specification establishes the requirements for plate, sheet, strip, and rolled bar. The following alloys are included:<sup>2</sup>

Copper Alloy UNS No.	Previously Used Designation	Nominal Composition, %			
		Beryllium	Cobalt	Nickel	Iron
C17500	Alloy 10	0.6	2.5	...	...
C17510	Alloy 3 or 14	0.4	...	1.8	...
C71700	...	0.5	...	31.0	0.70

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following safety hazard caveat pertains only to the test methods described in this specification:

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

**B194** Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar

**B248** Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved April 1, 2014. Published May 2014. Originally approved in 1970. Last previous edition approved in 2012 as B534 – 12. DOI: 10.1520/B0534-14E01.

<sup>2</sup> The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

- [B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast](#)
- [B846 Terminology for Copper and Copper Alloys](#)
- [E8/E8M Test Methods for Tension Testing of Metallic Materials](#)
- [E18 Test Methods for Rockwell Hardness of Metallic Materials](#)
- [E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

## 3. General Requirements

3.1 The following sections of Specification B248 constitute a part of this specification:

- 3.1.1 Terminology,
- 3.1.2 Materials and Manufacture,
- 3.1.3 Dimensions and Permissible Variations,
- 3.1.4 Workmanship, Finish, and Appearance,
- 3.1.5 Sampling,
- 3.1.6 Number of Tests and Retests,
- 3.1.7 Specimen Preparation,
- 3.1.8 Test Methods,
- 3.1.9 Significance of Numerical Limits,
- 3.1.10 Inspection,
- 3.1.11 Rejection and Rehearing,
- 3.1.12 Certification,
- 3.1.13 Mill Test Report,
- 3.1.14 Packaging and Package Marking, and
- 3.1.15 Heat Identification.

3.2 In addition, when a section with a title identical to that referenced in 3.1 appears in this specification, it contains additional requirements that supplement those appearing in Specification B248.

## 4. Terminology

4.1 For definitions of terms relating to copper and copper alloys, refer to Terminology B846.

## 5. Ordering Information

5.1 Include the following information when placing orders for product under this specification as applicable:

\*A Summary of Changes section appears at the end of this standard

- 5.1.1 ASTM designation and year of issue,
- 5.1.2 Quantity,
- 5.1.3 Copper Alloy UNS Number designation (1.1),
- 5.1.4 Form of material: plate, sheet, strip, or rolled bar,
- 5.1.5 Temper (8.1),
- 5.1.6 Dimensions: thickness and width, and length if applicable,
- 5.1.7 How furnished: rolls, stock lengths with or without ends, specific lengths with or without ends, and
- 5.1.8 When material is ordered for agencies of the U.S. government.

5.2 The following options are available and should be specified in the contract or purchase order when required:

- 5.2.1 Type of edge, if required: slit, sheared, sawed, square corners, rounded corners, rounded edges, or full-rounded edges (12.6),
- 5.2.2 Type of width and straightness tolerances, if required: slit-metal tolerances, square-sheared-metal tolerances, sawed-metal tolerances, straightened or edge-rolled-metal tolerances (12.5),
- 5.2.3 Special thickness tolerances, if required (12.2),
- 5.2.4 Tension test or hardness as applicable (Section 10),
- 5.2.5 Certification if required (see Specification B248),
- 5.2.6 Mill Test Report, if required (see Specification B248),
- 5.2.7 Specification number and year of issue, and
- 5.2.8 Special tests or exceptions, if any.

## 6. Materials and Manufacture

### 6.1 Material:

6.1.1 The material of manufacture shall be Copper Alloy No. C17500, C17510, or C71700 cast and worked, and of such purity and soundness as to be suitable for processing into the products prescribed herein.

6.1.2 Heat traceability shall be maintained and reported on the Mill Test Report or Certification.

### 6.2 Manufacture:

6.2.1 The product shall be produced with a combination of hot working, cold working, and thermal processing to produce a uniform wrought structure, and the specified temper.

## 7. Chemical Composition

7.1 The material shall conform to the chemical requirements specified in Table 1.

**TABLE 1 Chemical Requirements**

Element	Composition, %		
	Copper Alloy UNS No. C17500	Copper Alloy UNS No. C17510	Copper Alloy UNS No. C71700
Beryllium	0.4–0.7	0.2–0.6	0.30–0.7
Cobalt	2.4–2.7	0.3 max	...
Silicon, max	0.20	0.20	...
Nickel	...	1.4–2.2	29.0–33.0 (Incl Co)
Iron	0.10 max	0.10 max	0.40–1.0
Aluminum, max	0.20	0.20	...
Manganese, max	...	...	1.0
Zinc, max	...	...	1.0
Copper	balance	balance	balance

7.2 These specification limits do not preclude the presence of other elements. Limits for unnamed elements may be established by agreement between manufacturer or supplier and purchaser.

7.3 Copper may be given as remainder and may be taken as the difference between the sum of all elements analyzed and 100 %.

7.4 When all the elements in Table 1 are analyzed, their sum shall be 99.5 % minimum.

## 8. Temper

8.1 Standard tempers for product described in this specification are given in Tables 2–6. Tempers are TB00 (solution heat treated), or TD02 and TD04 (varying degrees of cold work), TF00 or TH02 and TH04 (precipitation heat treated from the appropriate tempers), or TM02 and TM04 (mill hardened).

## 9. Precipitation Heat Treatment Requirements

9.1 Solution-heat-treated or solution-heat-treated and cold-worked material is normally precipitation hardened by the purchaser after forming or machining. For the purpose of determining conformance to specified mechanical properties of Table 3, a sample of this material shall be heat treated as shown in Table 6. Other heat-treating temperatures and times may be preferred for end products of this material.

9.2 Special combinations of properties may be obtained by special precipitation heat-treating techniques. Mechanical property requirements of Table 3 do not apply to material so treated.

## 10. Mechanical Property Requirements

### 10.1 Tensile Strength Requirements:

10.1.1 When specified, product furnished under this specification shall conform to the tensile requirements prescribed in Tables 2–4 when tested in accordance with Test Method E8/E8M. Values in Table 2 are in the solution-heat-treated, and solution-heat-treated and cold-worked condition, in Table 3 after precipitation heat treatment and in Table 4 in the

**TABLE 2 Mechanical Property Requirements for Material in the Solution-Heat-Treated or Solution-Heat-Treated and Cold-Worked Condition**

Temper Designation	Former	Tensile Strength		Elongation <sup>A</sup> in 2 in. (50 mm), %	Rockwell Hardness <sup>B</sup>	
		ksi <sup>D</sup>	MPa <sup>E</sup>		B	30T
Copper Alloy UNS No. C17500 and C17510						
TB00	A	35–55	(240–380)	20–35	45 max	45 max
TD02	½ H	60–75	(415–520)	5–10	65–77	60–68
TD04	H	70–85	(480–585)	2–8	78–88	69–75
Copper Alloy UNS No. C71700						
TD04	H	84–112	(580–770)	2–8	85–100	73–83

<sup>A</sup> Elongation requirement applies only to material 0.004 in. (0.102 mm) and thicker.  
<sup>B</sup> The thickness that may be tested in the case of the Rockwell hardness scales is as follows:

B Scale 0.045 in. (1.14 mm) and over.

30 T Scale 0.032 to 0.045 in. (0.812 to 1.14 mm), excl.

Hardness values shown apply only to direct determinations, not converted values.

<sup>C</sup> Standard designations defined in Classification B601.

<sup>D</sup> ksi = 1000 psi.

<sup>E</sup> See Appendix X1.

**TABLE 3 Mechanical Property Requirements After Precipitation Heat Treatment<sup>A</sup>**

Temper Designation		Tensile Strength		Yield Strength, ksi min, 0.2 % Offset		Elongation <sup>B</sup> in 2 in. (50 mm), % min	Rockwell Hardness <sup>C</sup>	
Standard	Former	ksi <sup>D</sup>	MPa <sup>E</sup>	ksi <sup>D</sup>	MPa <sup>E</sup>		B	30T
Copper Alloy UNS No. C17500 and C17510								
TF00	AT	100–130	(690–895)	80	(550)	10	92–100	77–82
TH02	½ HT	110–140	(760–965)	95	(655)	8	95–102	79–83
TH04	HT	110–140	(760–965)	95	(655)	8	95–102	79–83
Copper Alloy UNS No. C71700								
Standard	Former	ksi <sup>D</sup>	MPa <sup>E</sup>	ksi <sup>D</sup>	MPa <sup>E</sup>		C	30N
TH04	HT	145–170	(1000–1175)	125	(860)	10	28–38	48–58

<sup>A</sup> These values apply to mill products (Section 17). See Section 10 for exceptions in end products.

<sup>B</sup> Elongation requirement applies only to material 0.004 in. (0.102 mm) and thicker.

<sup>C</sup> The thickness that may be tested in the case of the Rockwell hardness scales is as follows:

B and C Scale 0.045 in. (1.14 mm) and over.

30 T and 30 N Scale 0.032 to 0.045 in (0.812 to 1.14 mm) excl.

Hardness values shown apply only to direct determinations, not converted values.

<sup>D</sup> ksi = 1000 psi.

<sup>E</sup> See Appendix X1.

**TABLE 4 Mechanical Property Requirements—Mill-Hardened Condition<sup>A</sup>**

Temper Standard	Designation Former	Tensile Strength		Yield Strength		Elongation <sup>B</sup> in 2 in. (50 mm) min. %
		ksi <sup>C</sup>	MPa <sup>D</sup>	ksi <sup>C</sup>	MPa <sup>D</sup>	
Copper Alloy UNS No. C17500 and C17510						
TM02	½ HM	95–120	(655–827)	85–110	(586–758)	10
TM04	HM	110–135	(758–931)	100–125	(689–862)	6

<sup>A</sup> These values apply to mill products (Section 17). See Section 10 for exceptions in end products.

<sup>B</sup> Elongation requirement applies only to material 0.004 in. (0.102 mm) and thicker.

<sup>C</sup> ksi = 1000 psi.

<sup>D</sup> See Appendix X1.

**TABLE 5 Electrical Conductivity**

Temper	IACS, min, %
Copper Alloy UNS No. C17500 and C17510	
TF00 (AT)	45
TH02 (1/2 HT)	48
TH04 (HT)	48
TM02	50
TM04	50
Copper Alloy UNS No. C71700	
TH04 (HT)	3.5

**TABLE 6 Precipitation-Heat-Treatment Time for Acceptance Tests**

Standard (Before Precipitation Heat Treatment)	Former	At 850°F (454°C) to 900°F (482°C) <sup>A</sup> , h
Copper Alloy UNS No. C17500 and C17510		
TB00	A	3
TD02	½ H	2
TD04	H	2
Copper Alloy UNS No. C71700		
		At 950°F, h
TD04	H	2

<sup>A</sup> Specific temperature used must conform with supplier's certification.

mill-hardened conditions. Precipitation heat treatment parameters are specified in Section 9.

10.1.2 Tension tests are required for material equal to or less than 0.050 in. (1.27 mm) in thickness.

10.2 Rockwell Hardness Requirements:

10.2.1 For material thicker than 0.050 in. (1.27 mm), and except when the tension test is specified by the purchaser at the

time the order is placed or when agreement cannot be reached on hardness values, products furnished under this specification shall conform to the Rockwell hardness requirements prescribed in Tables 2 and 3, when tested in accordance with Test Methods E18.

**11. Performance Requirements**

11.1 Electrical Conductivity:

11.1.1 The electrical conductivity of this material after precipitation heat-treatment in accordance with Section 9 shall conform to Table 5.

**12. Dimensions and Permissible Variations**

12.1 The dimensions and tolerances for material covered by this specification shall be as prescribed in the current edition of Specification B248, with particular reference to Section 5 and the following tables of that specification:

12.2 Thickness—See Table 2, and for special tolerances, Table 3.

12.3 Width:

12.3.1 Slit Metal and Slit Metal with Rolled Edges—See Table 4.

12.3.2 Square-Sheared Metal—See Table 5.

12.3.3 Sawed Metal—See Table 6.

12.4 Length:

12.4.1 Specific and Stock Lengths With and Without Ends—See Table 7.

12.4.2 Schedule of Lengths (Specific and Stock) With Ends—See Table 8.

12.4.3 Length Tolerances for Square-Sheared Metal—See Table 9.

12.4.4 Length Tolerances for Sawed Metal—See Table 10.

12.5 Straightness:

12.5.1 Slit Metal or Edge-Rolled Metal—See Table 11.

12.5.2 Square-Sheared Metal—See Table 12.

12.5.3 Sawed Metal—See Table 13.

12.6 Edges:

12.6.1 Square Edges—See Table 14.

12.6.2 Rounded Corners—See 5.6.2 and Table 15.

12.6.3 Rounded Edges—See Table 16.

12.6.4 *Full-Rounded Edges*—See 5.6.4 and Table 17.

### 13. Workmanship, Finish, and Appearance

13.1 The product shall be free of defects, but blemishes of a nature that do not interfere with the intended application are acceptable.

### 14. Sampling

14.1 Sampling shall be in accordance with Specification B248 Section 7, except that the heat size is defined as 12 000 lb (5455 kg) or fraction thereof.

14.2 Sample pieces shall be taken from a heat and lot of material processed simultaneously in the same equipment, as follows:

14.2.1 *Heat*—A heat shall be the result of castings poured simultaneously from the same source of molten metal.

14.2.2 *Lot*—The lot shall be a heat or fraction thereof.

### 15. Number of Tests and Retests

15.1 Specification B248 constitutes a part of this specification.

15.2 Test specimens shall be taken from sample pieces selected in accordance with 14.1.

### 16. Specimen Preparation

16.1 Specimen preparation shall be in accordance with Specification B248 Section 9, with the preferred test specimen direction having its longitudinal axis parallel to the rolling direction.

### 17. Test Method

17.1 Section 10 of Specification B248 constitutes a part of this specification.

17.2 *Chemical Analysis*—The test method for determining chemical analysis for compliance and preparation of certifications and test reports shall be at the discretion of the reporting laboratory.

17.2.1 10.2 of Specification B248 is amended to include in the group of chemical analysis techniques found in Specification B194, Annex.

17.3 When analysis for unnamed or residual elements is required in the purchase order, the method of analysis shall be mutually agreed upon between manufacturer or supplier and purchaser.

### 18. Keywords

18.1 C17500; C17510; C71700; copper-beryllium; copper plate; copper rolled bar; copper strip; flat product

## APPENDIX

### (Nonmandatory Information)

#### X1. METRIC EQUIVALENTS

X1.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force which when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ( $N = \text{kg}\cdot\text{m}/\text{s}^2$ ). The derived SI unit for pressure or

stress is the newton per square metre ( $\text{N}/\text{m}^2$ ), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since  $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$ , the metric equivalents are expressed as megapascal (MPa), which is the same as  $\text{MN}/\text{m}^2$  and  $\text{N}/\text{mm}^2$ .

## SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B534 – 12) that may impact the use of this standard (Approved April 1, 2014).

(1) Section 1.2 has been removed from the specification. This is not applicable since alloy C71700 was added.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*