



Standard Terminology Relating to Electrical Contacts and Their Use¹

This standard is issued under the fixed designation B542; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 The terms included in this list are those that are peculiar to electric contacts or general terms that have a specific meaning when related to electric contacts. The definitions were prepared assuming that the reader has a general knowledge in a physical science but is unfamiliar with the terminology of the literature of electric contacts.

2. Significance and Use

2.1 The terms in this standard are used in standards and literature related to electric contacts, materials for electric contacts and test methods for evaluating electric contacts. These terms may be difficult to locate in a general purpose dictionary or the definition in such a dictionary may not cover the meaning applied in the field of electric contacts.

3. Terminology

a-spot—the areas of two mating contacts through which current flows from one contact to the other.

activation—a process in which contamination of the surface of contacts causes arcing at lower than usual voltage or arcing persists at lower than usual current, or both. For example, palladium contacts operated in an organic vapor produce arcs at voltage and current less than the minimum arcing voltage and current because of the presence of carbon on the contact surfaces.

anode fall—the potential difference between the anode and the electrical discharge plasma.

anodic (anode) material transfer—see **material transfer**.

arc discharge—a self-sustaining, high current density, high temperature discharge, uniquely characterized by a cathode fall nearly equal to the ionization potential of the gas or vapor in which it exists.

arc, anode—the arc that occurs at less than a critical electrode spacing (see **arc, cathode**), and results in anode material loss.

¹ This terminology is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.91 on Editorial and Terminology.

Current edition approved Feb. 1, 2013. Published March 2013. Originally approved in 1932. Last previous edition approved in 2007 as B542–07. DOI: 10.1520/B0542-13.

arc, cathode—the arc that occurs at greater than a critical electrode spacing (see **arc, anode**), and results in cathode material loss.

arc, shortest—a limiting state of an arc in which the total arc voltage approaches the sum of the cathode and anode falls.

blowout—the displacement and lengthening of an arc to facilitate its extinction. The blowout effect can be achieved by a magnetic field, air blast, etc.

brush—a sliding contact member consisting of one or more sliders (see **sliders**).

cathode fall—the potential difference between the cathode and the electric discharge plasma.

cathodic (cathode) material transfer—see **material transfer**.

constriction resistance—the increase in resistance arising from a change in current density distribution. In electric contacts it is that portion of contact resistance resulting from the convergence of current into the a-spots.

contact, n—(a) a generic term that applies to a device or part of a device and that has the capability of completing or interrupting the flow of an electrical signal in a circuit, (b) may also be used with modifiers such as: electrical contact, arcing contact, noble metal contact, separable contact, etc.

contact, adj—contact area, the part of an electrical device that is actually touching and where the electrical signal is expected to pass. Contact member, one of the electrical path parts that can make or break an electrical path.

contact, arcing—an electrical contact whose primary mode of wearout occurs on the contacting surfaces as a result of an arc formed between separating or closing contact pairs.

contact bounce—the unwanted operation of contacts immediately following intentional operation.

contact(s), butting—a type of contacts in which the direction of the motion of the moving contact is perpendicular to the contact faces. The contacts close and open with no appreciable sliding or rolling action.

contact chatter—the unwanted operation of contacts resulting from external forces operating on them. For example, vibration may cause contacts to open and close or “chatter.”

contact-closing force—the transient force between contacts during closure. At the first instant of closure this force is zero. It then builds up to a maximum value dependent on the forces and inertia of the contact system and finally stabilizes at the static contact force.

contact, composite—a contact made of two or more distinct materials or alloys bonded to each other. For example, a contact with a facing of a precious metal bonded to a base-metal backing.

contact force—the force to close, maintain, or open contacts. See also **insertion force**, **withdrawal force**, and **normal force**.

contact noise—a varying voltage across a pair of electric contacts due to conditions at their interface.

contact, non-arcing—mating electrical contact surfaces that do not experience wearout due to arc erosion that is opposite of arcing contacts.

contact, pitted—a contact that has numerous discrete hollows in its surface.

contact pressure—the force per unit area of physical contact between two contacts. This term is frequently but improperly used when contact force is meant. The area of physical contact is usually difficult to determine and quite different from the apparent area of contact.

contact resistance—the resistance to current flow offered by the contact interface, comprising the sum of the constriction resistance plus the film resistance.

NOTE 1—In a practical measurement, correction must be made for bulk resistance consisting of contact material, lead wires, etc.

contact, screw—a contact fabricated with an external thread for attachment to a support member or for adjustment.

contact, sliding—an electric contact which is expected to do its primary function during sliding.

contact, solid—a monolithic contact member.

contact, spring—a contact system in which one piece of material is used for both the driving spring and electric contact.

contact, static—an electric junction designed for infrequent separation and connection.

contacts, wiping—contacts that have some sliding motion during opening or closing.

contact wipe—relative tangential motion between contacting surfaces that occurs during the normal course of contact closure.

corona (discharge)—a self-sustaining discharge characterized by highly asymmetrical electric fields with the result that ionization predominantly occurs near the electrode with the higher potential gradient.

crimp, v—to establish an electrical and mechanical attachment between the two members by mechanically deforming one

contact member around another. In most cases, one member is a stranded or solid wire, or a group of wires, the other is a hollow cylinder or partial cylinder that is deformed around the wire(s).

dark (or Townsend) discharge—a discharge which may or may not be self-sustaining. It is characterized by a uniform field, current in the microampere range, and a nonluminous inter-electrode space.

electromigration—(1) Current-induced atomic diffusion in a solid metal due to electron momentum and the potential gradient, (2) electrochemical process of growth of metallic path across an insulating surface under imposed electric field.

DISCUSSION—The solid state process may cause significant material transport in regions of high current density such as a-spots in contacts. In devices with electrical contacts, the electrochemical process may form shorts between conductors under certain environmental conditions.

film resistance—that portion of the contact resistance that is due to the presence of contaminants on one or both of the contact members.

fine transfer—see **material transfer, bridge**.

fretting, n—small amplitude oscillatory motion, usually tangential, between two solid surfaces in contact.

DISCUSSION—Here the term **fretting** refers only to the nature of the motion without reference to the wear, corrosion, or other damage that may ensue. The term fretting is often used to denote **fretting corrosion** and other forms of fretting wear. Usage in this sense is discouraged because of the ambiguity that may arise.

fretting corrosion—a form of fretting wear in which corrosion plays a significant role.

DISCUSSION—In electrical contact interfaces involving non-noble metals, fretting corrosion can cause rapid and substantial increases in contact resistance as a result of localized appearance of insulating oxides and other corrosion products at the interface.

fretting wear—wear arising as a result of fretting. See **fretting**.

friction polymerization—the process by which organic compounds (such as adsorbed air pollutants) on mating surfaces that move relative to each other polymerize to yield compounds of high molecular weight.

NOTE 2—When this occurs on electrical contacts and the materials formed remain on the surface, contact resistance may increase substantially. The solid materials that are produced by the polymerization process are called “friction polymers” or “frictional polymers.”

fritting (A-fritting)—an electric breakdown between mating metallic contacts, separated by an insulating film, which occurs when the field strength exceeds approximately 1 000 000 V/cm. Metallic bridges are produced through the film if the fritting voltage is above the contact melting voltage.

fritting voltage—the voltage at which fritting occurs.

glow discharge—a self-sustaining discharge characterized by essentially symmetrical electrodes, low current density, and a high cathode fall of about 200 V.

glowing connection (or contact), *n*—one that sustains emission of both visible light and heat while conducting electrical current.

high resistance—contact resistance exceeding an arbitrary, specified limit.

inrush current—a transient current that exists at the instant of contact closure and persists for a relatively short time.

insertion force—the force required to mate two connector halves.

material transfer—a general term to describe the carry-over of material from one electrical contact to another.

NOTE 3—When the discussion becomes specific, the term “gain” or “loss” is used with respect to a particular contact (for d-c application, anode or cathode; for a-c application, stationary contact or movable contact). For example, anode gain, anode loss, stationary contact gain.

material transfer, negative—see **material transfer**.

material transfer, positive—see **material transfer**.

material transfer, bridge—material transfer that occurs without the presence of a gaseous electric discharge. The filament of molten contact material that connects the two separating contacts does not rupture in the middle; thus there is a gain of material on one contact and a loss of material from the other.

material transfer, cathode—movement of contact metal from the cathode by means of a cathode arc.

material transfer, needle—material transfer that results in a buildup with a smaller diameter and a relatively great length.

noise—See **contact noise**.

normal force—that component of the force between contacting bodies perpendicular to their interface.

opening force—the force available to open the contacts.

plasma—a partially or totally ionized gas or vapor.

porosity—in metallic coatings, the presence of any discontinuity, crack, or hole in the coating that exposes a different underlying metal.

positive column—that region of an electric discharge between the cathode and anode falls.

screw contact—see **contact, screw**.

self-sustaining discharge—a discharge in which all carriers necessary for the transport of current in the discharge are produced by this discharge itself.

showering—a particular form of corona discharge characterized by strongly ionized streamers or streams of luminous plasma. It generally occurs at a field value just below that which is required for a complete breakdown.

slider—that member of a sliding contact pair, normally the smaller, which may be moved through a range of locations on the opposing member.

sliding electrical contacts—contacting members that perform their function while undergoing relative tangential motion.

slip ring—a continuous metal ring by means of which electrical current can be conducted to or from brush contacts. One electrical contact member is designed to rotate with respect to the other.

slip ring assembly—two or more slip rings with connecting leads or terminals that have been mounted to a common structure.

slip ring capsule—an assembly that includes a slip ring assembly, brushes, and bearings for conducting current on multiple circuits from a stationary body to one that may rotate.

spark, discharge—a non-self-sustaining discharge characterized by high luminosity and a ratio of lateral dimension to length that is substantially smaller than unity.

sulfide creep—in electrical contacts, spontaneous migration of a sulfide based corrosion product that occurs at elevated humidity across a gold rich surface.

DISCUSSION—This process often involves copper sulfide produced by corrosion on a copper alloy spring that, under severe conditions, can completely cover a gold contact mounted on the spring.

tarnish—the chemical compound on the surface of a contact resulting from the reaction of the contact material and the inorganic constituents of the surrounding atmosphere.

tweak—to make a mechanical adjustment of a spring arm of an electrical contact assembly to adjust the force or position of the contact.

wiper—see **slider**. The term “wiper” is sometimes used interchangeably with the more preferred term “slider.”

withdrawal force—the force required to separate two mated connector halves.

4. Terminology Defined In Individual Standards For Electric Contact Test Methods And Electric Contact Materials

4.1 The following terms are defined in the terminology sections of indicated standards.

Aluminum	B812
Bulk Resistance	B539, B812
Conductor	B868
Connectability	B896
Connection Resistance	B539
Contact Noise	B615
Contact Performance	B868
Contact Resistance	B667
Contact Resistance Probe	B667
Corrosion Products	B735, B799, B920
Crimp	B913
Crimp Barrel	B913
Crimped Connection	B913
Crimp Tab	B913
Crimp Terminal	B913
Decorations	B741, B798
Dry Circuit	B539
Edge Noise	B615
Edgcard Connector	B885
Event	B878
Fretting	B896
Intermittence	B854
Lot	B476
Measurement Area	B735, B741, B798, B799
Metallic Coatings	B735, B741, B798, B799, B920

Mixed Flowing Gas Test	B845
Open-Circuit Voltage	B539
Porosity	B735, B741, B798, B799, B920
Pressure Connection System	B812
Printed Wiring Board (Pwb) Contacts	B885
Printed Wiring Board (Pwb) Fingers	B885
Rated Current	B539
Reference Conductor	B812
Residential Applications	B812
Significant Surface	B735, B741, B798, B799
Standard Test Current	B539
Static Contacts	B539
Switching Noise	B615
Underplate	B735, B741, B798, B799, B920

Junction Resistance	B539
Low Level Contact Resistance	B539
Mass Change	B810
Metallic	B868
Metallic Coatings	B741
Mixed Environmental Testing	B812
Mixed Flowing Gas	B845, B827
Mixed Flowing Gas Testing	B810, B826
Mixed Stress Testing	B812
Monitoring Environmental Tests	B825
Nanosecond Events	B878
Nanosecond Intermittences	B878
Neutral Bar	B812
Nitric Acid Vapor (Porosity) Test	B735

5. Index Of Keywords Used In Individual Standards For Electric Contact Test Methods

Accelerated Testing	B810, B845
Air Velocity	B827, B845
Aluminum	B812
Aluminum Connections	B812
Arc Erosion	B576
Arcing Contacts	B576
Atmospheric Corrosion	B810, B825, B845
Atmospheric Corrosion Monitor	B826
Atmospheric Corrosion Testing	B826
Atmospheric Test Evaluation	B825
Bit Rate Error	B854
Cathodic Reduction	B825
Chlorine	B827, B845
Circuit	B615
Classification	B868
Cleaning Technique	B810
Clorox	B920
Closed Arcing Contacts	B497
Conductor	B868
Connectability	B896
Connection Resistance	B539
Connector	B845, B868, B539
Contact Resistance	B539, B667, B885, B896
Contact Resistance Probe	B667
Contacts	B539, B576, B615, B810, B812, B868
Contamination	B885
Control Coupon Evaluation	B825
Copper	B810
Corrosion	B827, B845
Corrosion Film Analysis	B825
Corrosion Monitor	B808
Corrosive Gas Testing	B827, B845
Corrosivity	B827
Corrosivity Monitor	B826, B827
Coulometry	B827
Creep	B896
Edgecard Connector	B885
Electrical	B615
Electrical Conductor	B896
Electrical Connection Systems	B868
Electrical Contacts	B576, B615, B810, B845, B868, B920
Electrical Erosion	B576
Electrical Noise	B854
Electrical Resistance	B539
Electrical Resistance Probe	B826
Electrography	B741, B798
Environmental	B827, B845
Environmental Testing	B812, B825, B826
Event Detection	B878
Fretting Sensitivity	B896
Gel	B798
Gel Electrography	B798
Gold Coatings	B735, B741, B798, B799, B920
Gold Platings	B735, B741, B799, B920
Humidity	B827, B845
Humidity Testing	B812
Hydrogen Sulfide	B827, B845
Hypochlorite	B920

Nitrogen Dioxide	B845
Nitrogen Oxide	B827
Noise	B615
Palladium Coatings	B798, B799, B920
Palladium Platings	B798, B799, B920
Paper	B741
Paper Electrography	B741
Piezoelectric Crystals	B808
Plated Contacts	B920
Plating	B798
Plating Porosity	B735, B741, B799, B920
Pollutant	B827, B845
Pore Corrosion	B827
Pore Corrosion Test	B735, B799, B920
Pore Counting	B920
Porosity	B798
Porosity Screen Testing	B920
Porosity Testing	B735, B741, B798, B799, B920
Pressure Connections	B812
Printed Wiring Board Fingers	B885
Quartz Crystal Microbalance	B827
Reliability	B845, B854
Resistance	B615, B854, B868
Resistance Monitor	B827
Resistance Monitor Probe	B826
Sensors	B808
Separable Connections	B539
Sliding	B615
Stress Relaxation	B896
Stress Testing	B812
Sulfur	B827, B845
Sulfur Dioxide	B827, B845
Sulfur Dioxide Test	B799
Sulfurous Acid/So ₂ Test	B799
Tarnish	B827, B845
Temperature	B845
Temperature Testing	B827
Test Calibration	B810
Testing	B845
Thermal Cycling	B812
Thinfilm Monitor	B808
Twist-On Connector	B812
Voltage	B615
Voltage Drop	B497
Weight Gain	B810

6. Index Of Keywords Used In Individual Standards For Electric Contact Materials

analysis	B712, B772
arcing contacts	B617, B662, B663, B780
brushes	B613
cadmium	B781
cadmium oxide	B712, B781
chemical composition	B772
clad materials	B731
coin silver alloy	B617
composite materials	B613
compositions	B617, B628
conductivity	B780
contact alloy	B522, B683, B685
contact	B742

contact material	B731	precious metal	B540, B617, B628, B731, B780
contacts	B277, B476, B477, B540, B541, B563, B596, B631, B662, B663, B693, B702, B712, B772, B780, B844	refined gold	B562
copper	B702	refined iridium	B671
copper-tungsten	B702	refined palladium	B589
electrical contact	B742	refined platinum	B561
electrical contact alloy	B477, B522, B683, B685	refined rhodium	B616
electrical contact materials	B277, B476, B540, B596, B684, B693	refined ruthenium	B717
electrical contacts	B541, B563, B613, B617, B628, B662, B663, B664, B692, B693, B772, B780	rhodium	B616
fine silver	B742	ruthenium	B717
gold	B562	silver	B631, B662, B663, B664, B692, B712, B781, B844, B742
gold alloy	B477, B541, B596	silver alloy	B617, B731, B780
gold coin	B596	silver copper alloy	B617, B628
gold-silver-platinum	B522, B541, B563	silver tungsten carbide	B663
graphite	B664, B692	silver-cadmium oxide	B781
hardness	B277	silver-copper alloy	B780
impurities	B617, B628, B693	silver-nickel	B693
internal oxidation	B781, B844	silver-tin oxide	B844
iridium	B671	silver-tungsten	B631
iridium alloy	B684	silver-cadmium oxide	B712
low contact resistance	B541, B563, B596	sliding contacts	B613, B664, B692
low energy contact	B541, B563, B596	sodium	B712
medical material	B684	sponge	B561, B589, B616, B671, B717
microhardness	B277	tin oxide	B844
molybdenum	B662	tungsten	B631, B702
molybdenum silver	B662	tungsten carbide	B663
non arcing contact	B541, B563, B596	tungsten carbide silver	B663
palladium	B589, B683, B685	tungsten-copper	B702
palladium alloy	B731, B540, B563	tungsten-silver	B631
palladium copper	B685	wire	B780
platinum	B561	wrought	B742, B781, B844
platinum alloy	B684	wrought precious metal	B476
platinum iridium alloy	B684		
potassium	B712		
powder metallurgy	B631, B662, B663, B702, B781, B844		

7. Keywords

7.1 definitions; electric contacts; terminology

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).