



Standard Specification for Coin Silver Electrical Contact Alloy¹

This standard is issued under the fixed designation B617; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers 90 % silver-10 % copper alloy tubing, rod, wire, strip, and sheet material for electrical contacts.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B277 Test Method for Hardness of Electrical Contact Materials

B476 Specification for General Requirements for Wrought Precious Metal Electrical Contact Materials

3. Manufacture

3.1 Raw materials shall be of such quality and purity that the finished product will have the properties and characteristics prescribed in this specification.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials.

Current edition approved May 1, 2016. Published May 2016. Originally approved in 1977. Last previous edition approved in 2010 as B617–98 (2010). DOI: 10.1520/B0617-98R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2 The material shall be finished by such operations (cold working, heat treating, annealing, turning, grinding, or pickling) as are required to produce the prescribed properties.

4. Chemical Composition

4.1 Material produced under this specification shall meet the requirements for chemical composition prescribed in [Table 1](#).

5. Mechanical Requirements

5.1 Mechanical properties shall conform to the listings of [Table 2](#) or [Table 3](#).

5.2 All test specimens shall be full thickness or diameter when practical.

5.3 All tests are to be conducted at room temperature, about 68°F (20°C).

6. General Requirements

6.1 The provisions of Specification [B476](#) shall apply to all materials produced to this specification.

7. Inspection and Testing

7.1 Material furnished under this specification shall be inspected by the manufacturer as detailed in the applicable provisions of Specification [B476](#) and as listed as follows:

7.1.1 Visual inspection at 10 \times .

7.1.2 Temper test (hardness or tension, but not both). A tension test is recommended for strip below 0.030-in. (0.8-mm) thickness and for wire of any diameter.

7.1.3 Dimensional tests.

7.1.4 Spectrographic or chemical analysis when indicated by the purchaser order.

8. Keywords

8.1 arcing contacts; coin silver alloy; compositions; electrical contacts; impurities; precious metals; silver alloy; silver copper alloy

TABLE 1 Chemical Composition^A

Element	Weight %
Silver	89.6 to 91.0
Copper	9.0 to 10.4
Zinc	0.06 max
Iron	0.05 max
Cadmium	0.05 max
Lead	0.03 max
Nickel	0.01 max
Aluminum	0.005 max
Phosphorus	0.02 max
Total others	0.06 max

^A Analysis is regularly made for the elements for which specific limits are listed. If, however, the presence of "other" elements is suspected or indicated in the course of routine analysis, further analysis shall be made to determine that the total of these "other" elements and the listed impurities are not in excess of the total impurities limit.

TABLE 2 Mechanical Properties of Sheet and Strip

Temper	Reduction in B & S Numbers (Reference)	Percent Reduction (Reference)	Ultimate Tensile Strength, psi (MPa)		Minimum Elongation in 2 in., %	Hardness, Rockwell 30T
			min	max		
A	0	0	36 000 (250)	47 000 (320)	20	42 to 50
½ H	2	21	47 000 (320)	57 000 (390)	4	56 to 64
¾ H	3	29	53 000 (370)	63 000 (430)	2	58 to 67
Hard	4	37	58 000 (400)	68 000 (470)	1	61 to 69
Spring	8	60	67 000 (460)	75 000 (520)	1	64 to 72

TABLE 3 Mechanical Properties of Wire, Rod, and Tubing

Temper	Reduction in B & S Numbers (Reference)	Percent Reduction (Reference)	Ultimate Tensile Strength, psi (MPa)		Minimum Elongation in 2 in., %	Hardness, Rockwell 30T
			min	max		
A	0	0	36 000 (250)	47 000 (320)	20	42 to 50
⅛ H	½	11	42 000 (290)	52 000 (360)	8	49 to 57
¼ H	1	21	47 000 (320)	57 000 (390)	4	56 to 64
½ H	2	37	56 000 (390)	66 000 (460)	4	58 to 66
¾ H	3	50	61 000 (420)	71 000 (490)	3	61 to 72
Hard	4	60	65 000 (450)	74 000 (510)	2	64 to 72
Spring	8	84	74 000 (510)	82 000 (570)	1	68 to 76

SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply only when specified by the purchaser in the inquiry, contract, or order, for agencies of the U.S. Government.

S1. Referenced Documents

S1.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

S1.1.1 *U.S. Federal Standards:*³

Fed. Std. No. 102 Preservation, Packaging and Packing Levels

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

S1.1.2 *U.S. Military Standards:*³

MIL-STD-129 Marking for Shipment and Storage

S2. Quality Assurance

S2.1 *Responsibility for Inspection*—Unless otherwise specified in the contract or purchase order, the manufacturer is responsible for the performance of all inspection and test requirements specified. Except as otherwise specified in the

³ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.

contract or purchase order, the manufacturer may use his own or any other suitable facilities for the performance of the inspection and test requirements, unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections and tests set forth when such inspections and tests are deemed necessary to assure that the material conforms to prescribed requirements.

S3. Preparation for Delivery

S3.1 *Preservation, Packaging, and Packing:*

S3.1.1 *Civil Agencies*—The requirements of Fed. Std. No. 102 shall be referenced for definitions of the various levels of packaging protection.

S3.2 *Marking:*

S3.2.1 *Military Agencies*—In addition to any special marking required by the contract or purchase order, marking for shipment shall be in accordance with MIL-STD-129.

S3.2.2 *Civil Agencies*—In addition to any special marking required by the contract or purchase order, marking for shipment shall be in accordance with Fed. Std. No. 123.

APPENDIX
(Nonmandatory Information)
X1. TYPICAL PROPERTY VALUES

X1.1 The following is a list of typical property values which are useful for engineering calculations in electrical contact design and application.

Electrical conductivity, % IACS	83
Resistivity, $\Omega \cdot \text{cmil/ft}$	13
$\mu\Omega \cdot \text{cm}$	2.1
Solidus temperature, °C	777
Liquidus temperature, °C	870
Density, g/cm^3	10.3
tr oz/in. ³	5.43

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>