



Standard Specification for 80 % Silver-20 % Graphite Sliding Contact Material¹

This standard is issued under the fixed designation B664; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification defines the criteria for composition and other requirements for brushes with a nominal silver content of 80 %, by weight, with the balance being substantially graphite.

1.2 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B613 Guide for Preparing Specifications for Miniature Brushes of Composite Materials for Sliding Electric Contacts

E18 Test Methods for Rockwell Hardness of Metallic Materials

2.2 *ANSI Standard:*

C64.1 Brushes for Electrical Machines³

3. Requirements

3.1 *Chemical Composition*, shall be as follows:

Silver	80 ± 3 % (weight)
Graphite	balance
Total metal impurities	1 % max
Percent ash in graphite (ANSI C64.1)	5 % max

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials.

Current edition approved May 1, 2012. Published May 2012. Originally approved in 1979. Last previous edition approved in 2006 as B664 – 81 (2006). DOI: 10.1520/B0664-90R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

3.2 *Physical Properties*—The following lot average properties must be met. Unless otherwise agreed between the producer and the user, the number of samples shall be five.

3.2.1 *Density*—The minimum acceptable density shall be 5.15 g/cm³ as determined by the measurement and weight method defined by ANSI C64.1.

3.2.2 *Shear Strength*:

3.2.2.1 The shear strength for the normal and transverse directions shall be measured for rectangular parallelepipeds and shall be 2000 psi (14 MPa), minimum.

3.2.2.2 The shear strength for the longitudinal shear direction shall be measured for cylinders and shall be 1000 psi (6.9 MPa), minimum.

3.3 *Microstructure*—Parts shall be visually free of structural defects, cracks, etc., upon examination at 50×. The press direction, as evidenced by laminations, shall be as defined by the purchase order. Also the brush material shall not contain abrasive particles that will sliver a metal alloy ring with a hardness ≥110 HK₁₀₀ when the brush force is equal to 30 g or that necessary for 5.0 psi (34 kPa) pressure, whichever is greater. A sliver is defined as a loose wear particle with one dimension ≥50× the next smaller dimension. Although slivering can be caused by coarse abrasive particles, other parameters can contribute to slivering (for example, very high brush force).

3.4 Source or grade of raw materials (for example, graphite) or methods of manufacture shall not be changed without notifying users.

4. Reference Properties

4.1 Because of their size, the following properties for miniature brushes cannot always be determined; however, these properties are typical for larger parts.

4.1.1 *Superficial Hardness*—The typical Rockwell superficial hardness for this material is 44 R15W as determined by Test Method E18 with a 1/8-in. steel ball.

4.1.2 *Specific Resistance*—The typical specific resistance for the material is 4 × 10⁻⁶ Ω-in. (1 × 10⁻⁷ Ω-m) as determined by the method detailed in ANSI C64.1.

5. Certification

5.1 Material supplied under this specification shall be certified as meeting the requirements of this specification by the producer of the material.

6. Keywords

6.1 electrical contacts; graphite; silver; sliding contacts

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).