



Designation: B671 – 81 (Reapproved 2017)

Standard Specification for Refined Iridium¹

This standard is issued under the fixed designation B671; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers refined iridium as sponge and powder in two grades as follows:

1.1.1 *Grade 99.80 (UNS PO6100)*—Iridium having a purity of 99.80 %.

1.1.2 *Grade 99.90*—Iridium having a purity of 99.90 %.

NOTE 1—For the purposes of determining conformance with this specification, an observed value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding method of Practice E29.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials.

Current edition approved April 1, 2017. Published April 2017. Originally approved in 1980. Last previous edition approved in 2010 as B671 – 81 (2010). DOI: 10.1520/B0671-81R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Materials and Manufacture

3.1 The metal may be produced by any refining process that yields a product capable of meeting the chemical requirements of this specification. The purchaser, upon request, shall be informed of the refining process used.

4. Chemical Composition

4.1 The refined iridium shall conform to the chemical composition prescribed in Table 1.

5. Sampling

5.1 The value of this material is such that special attention must be paid to sampling procedures. The purchaser and manufacturer shall agree upon sampling procedures used.

5.2 Sampling lots shall consist of the following:

5.2.1 *Sponge*—A single refining lot.

5.2.2 *Powder*—A single refining lot.

6. Method of Analysis

6.1 Pending the development of standard ASTM methods of chemical or spectrographic analysis, or both, the methods to be used shall be a matter of agreement between manufacturer and the purchaser.

7. Rejection and Rehearing

7.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for rehearing.

7.1.1 If the iridium satisfies the requirements of this specification, it shall not be condemned for defects in the products in which it is used.

7.2 *Investigation of Claims*—In a question of chemical composition, a new sample shall be drawn by representatives of both parties in accordance with Section 5. The properly mixed and quartered sample shall be divided into three parts, each of which shall be placed in a sealed package, one for the manufacturer, one for the purchaser, and one for an umpire, if necessary.

TABLE 1 Chemical Requirements

Element ^A	Composition, %	
	Grade 99.80 (UNS PO6100)	Grade 99.90
Iridium, min (by difference)	99.80	99.90
Rhodium, max	0.15	0.05
Platinum, max	0.10	0.05
Palladium, max	0.05	0.05
Ruthenium, max	0.05	0.05
Lead, max	0.02	0.015
Silicon, max	0.02	0.01
Tin, max	0.01	0.01
Zinc, max	0.01	0.01
Arsenic, max	0.01	0.005
Bismuth, max	0.01	0.005
Cadmium, max	0.01	0.005
Iron, max	0.01	0.01
Silver, max	—	0.02
Gold, max	—	0.02
Copper, max	—	0.02
Nickel, max	—	0.02
Chromium, max	—	0.02

^A By agreement between manufacturer and purchaser, analyses may be required and limits established for elements or compounds not specified in this table.

8. Product Marking

8.1 The material container shall be legibly identified by a label or tag with the following information: Iridium (Ir), Grade _____, lot number, and weight to the nearest 0.001 troy oz (0.03 g).

9. Keywords

9.1 iridium; refined iridium; sponge

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/