



# Standard Specification for Nickel-Chromium-Molybdenum-Cobalt-Tungsten- Iron-Silicon Alloy (UNS N06333) Bar<sup>1</sup>

This standard is issued under the fixed designation B719; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers wrought alloy UNS N06333 in the form of hot-finished and cold-finished bars and flats intended for heat resisting applications and general corrosive service.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys](#)

[E8 Test Methods for Tension Testing of Metallic Materials](#)

[E10 Test Method for Brinell Hardness of Metallic Materials](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Sclero-](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 1, 2014. Published October 2014. Originally approved in 1983. Last previous edition approved in 2009 as B719 – 00 (2009). DOI: 10.1520/B0719-00R14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[scope Hardness, and Leeb Hardness](#)

[E1473 Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys](#)

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bars, n*—material of round, hexagonal, octagonal, or square solid section, furnished in straight lengths, ¼ in. (6.35 mm) and over in diameter or size.

3.1.2 *flats, n*—material ¼ to 10 in. (6.35 to 254 mm), inclusive, in width and 120 in. (3.05 mm) and over in thickness.

## 4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

4.1.1 Alloy name or UNS number.

4.1.2 Quantity.

4.1.3 ASTM Designation and year of issue.

4.1.4 Section (round, square, hexagonal, and so forth).

4.1.5 Dimensions, including length.

4.1.6 Finish, hot or cold.

4.1.7 *Certification*—state if certification is required (Section 16).

4.1.8 *Samples for Product (Check) Analysis*—State whether samples shall be furnished.

4.1.9 *Purchaser Inspection*—If a purchaser wishes to witness tests or inspections of material at the place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed.

## 5. Material and Manufacture

5.1 All material shall be furnished in the annealed condition, except that cold-drawn hexagons may be given a cold draw sizing pass subsequent to the final anneal.

NOTE 1—Hot-finished rectangular bar in widths 10 in. (254 mm) and under may be furnished as hot-finished plate with sheared or cut edges.

**6. Chemical Requirements**

6.1 The material shall conform to the requirements as to chemical composition specified in **Table 1**.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations per Specification **B880**.

**7. Mechanical and Other Requirements**

7.1 The mechanical properties of the material at room temperature shall conform to those shown in **Table 2**.

**8. Permissible Variations in Dimensions**

8.1 All bars shall conform to the permissible variations in dimensions specified in **Tables 3-8**, inclusive.

**9. Workmanship, Finish, and Appearance**

9.1 The material shall be uniform in quality and condition, smooth, commercially straight, and free from injurious imperfections.

**10. Sampling**

10.1 *Lot Definitions:*

10.1.1 A lot for chemical analysis shall consist of one heat.

10.1.2 A lot for mechanical properties shall consist of material from one heat of the same condition and cross section, and no more than 40 000 lb (18 100 kg) in mass.

10.2 *Test Material Selection:*

10.2.1 *Chemical Analysis*—Representative samples from each lot shall be taken during pouring or subsequent processing.

10.2.1.1 Product (check) analysis shall be wholly the responsibility of the purchaser.

10.2.2 *Mechanical Properties*—Samples of the material to provide test specimens for mechanical properties shall be taken from such locations in each lot as to be representative of that lot.

**11. Number of Tests**

11.1 *Chemical Analysis*—One test per lot.

11.2 *Mechanical Properties*—One test per lot.

**TABLE 1 Chemical Requirements**

Element	Composition Limits, %
Carbon	0.10 max
Manganese	2.0 max
Phosphorus	0.03
Sulfur	0.03
Silicon	1.5 max
Chromium	24.0–27.0
Nickel	44.0–48.0
Molybdenum	2.5–4.0
Cobalt	2.5–4.0
Tungsten	2.5–4.0
Iron <sup>A</sup>	remainder

<sup>A</sup> Element may be determined arithmetically by difference.

**TABLE 2 Mechanical Properties**

Tensile Strength, min psi (MPa)	Yield Strength, 0.2 % offset, min. psi (MPa)	Elongation in 2 in. or 50 mm, or 4D, min%	Hardness <sup>A</sup>
80 000 (551)	35 000 (241)	30	75 to 95 HRB

<sup>A</sup> Hardness values are informative only and not to be construed as the basis for acceptance.

**12. Specimen Preparation**

12.1 Tension-test specimens shall be taken from material in the final condition and tested in the direction of fabrication.

12.1.1 All material shall be tested in full cross-section size when possible. When a full cross-section size test cannot be performed, the largest possible round specimen in Test Methods **E8** shall be used.

**13. Test Methods**

13.1 Determine the chemical composition, mechanical, and other properties of the material as enumerated in this specification, in case of disagreement, in accordance with the following methods:

Test	ASTM Designation
Chemical analysis	<b>E1473</b>
Tension	<b>E8</b>
Brinell Hardness	<b>E10</b>
Rockwell Hardness	<b>E18</b>
Hardness Conversion	<b>E140</b>
Rounding procedure	<b>E29</b>
Requirement	Rounded-Off Unit for Observed or Calculated Value
Chemical composition and tolerances (when expressed in decimals)	Nearest unit in the last right-hand place of figures of the specified limit. If two choices are possible, as when the digits dropped are exactly a 5 or a 5 followed only by zeros, choose the one ending in an even digit with zero defined as an even digit.
Tensile and yield strengths	Nearest 1000 psi (6.9 MPa)
Elongation	Nearest 1 %

**14. Inspection**

14.1 Inspection of the material by the purchaser shall be as agreed upon by the purchaser and the supplier as part of the purchase contract.

**15. Rejection and Rehearing**

15.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

**16. Certification**

16.1 When specified in the purchase order or contract, a producer’s or supplier’s certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification and has

**TABLE 3 Permissible Variations in Size of Hot-Rolled Round and Square Bars**

NOTE 1—Out of round is the difference between the maximum and minimum diameters of the bar, measured at the same cross section.

NOTE 2—Out of square section is the difference in the two dimensions at the same cross section of a square bar, each dimension being the distance between opposite faces.

NOTE 3—Size tolerances for rounds in the size range from 1/4 in. (6.4 mm) to approximately 5/8 in. (15.9 mm), which are produced on rod mills in coils, are not shown herein.

NOTE 4—Variations in size of coiled product made on rod mills are greater than size tolerances for product made on bar mills.

Specified Size		Size Tolerance				Out of Round (Note 1 ) or Out of Square Section (Note 2)	
in.	mm	Over		Under		in.	mm
		in.	mm	in.	mm		
1/4 to 5/16	6.4 to 7.9	0.005	0.13†	0.005	0.13	0.008	0.20
Over 5/16 to 7/16	7.9 to 11.1	0.006	0.15	0.006	0.15	0.009	0.23
Over 7/16 to 5/8	11.1 to 15.9	0.007	0.18	0.007	0.18	0.010	0.25
Over 5/8 to 7/8	15.9 to 22.2	0.008	0.20	0.008	0.20	0.012	0.30†
Over 7/8 to 1	22.2 to 25.4	0.009	0.23	0.009	0.23	0.013	0.33†
Over 1 to 1 1/8	25.4 to 28.6	0.010	0.25	0.010	0.25	0.015	0.38
Over 1 1/8 to 1 1/4	28.6 to 31.8	0.011	0.28	0.011	0.28	0.016	0.41
Over 1 1/4 to 1 3/8	31.8 to 34.9	0.012	0.30†	0.012	0.30†	0.018	0.46
Over 1 3/8 to 1 1/2	34.9 to 38.1	0.014	0.36	0.014	0.36	0.021	0.53
Over 1 1/2 to 2	38.1 to 50.8	1/64	0.4	1/64	0.4	0.023	0.58
Over 2 to 2 1/2	50.8 to 63.5	1/32	0.8	0		0.023	0.58
Over 2 1/2 to 3 1/2	63.5 to 88.9	3/64	1.2	0		0.035	0.89
Over 3 1/2 to 4 1/2	88.9 to 114.3	1/16	1.6	0		0.046	1.17
Over 4 1/2 to 5 1/2	114.3 to 139.7	5/64	2.0	0		0.058	1.46
Over 5 1/2 to 6 1/2	139.7 to 165.1	1/8	3.2	0		0.070	1.78
Over 6 1/2 to 8	165.1 to 203.2	5/32	4.0	0		0.085	2.16

† Editorially corrected.

**TABLE 4 Permissible Variations in Thickness and Width for Hot-Rolled Flat Bars**

Specified Widths, in.	Thickness Tolerances, in., for Given Thickness										
	1/8 to 1/2, incl	Over 1/2 to 1, incl	Over 1 to 2, incl	Over 2 to 4, incl		Over 4 to 6, incl		Over 6 to 8, incl		Width Tolerance	
	Over and Under			Over	Under	Over	Under	Over	Under	Over	Under
To 1, incl	0.008	0.010	...	...	...	...	...	...	...	0.015	0.015
Over 1 to 2, incl	0.012	0.015	0.031	...	...	...	...	...	...	0.031	0.031
Over 2 to 4, incl	0.015	0.020	0.031	0.062	0.031	...	...	...	...	0.062	0.031
Over 4 to 6, incl	0.015	0.020	0.031	0.062	0.031	0.093	0.062	...	...	0.093	0.062
Over 6 to 8, incl	0.016	0.025	0.031	0.062	0.031	0.093	0.062	0.125	0.156	0.125	0.156
Over 8 to 10, incl	0.021	0.031	0.031	0.062	0.031	0.093	0.062	0.125	0.156	0.156	0.187
	Thickness Tolerances, mm, for Given Thickness										
	3.2 to 12.7, incl	Over 12.7 to 25.4, incl	Over 25.4 to 50.8, incl	Over 50.8 to 101.6, incl		Over 101.6 to 152.4, incl		Over 152.4 to 203.2, incl		Width Tolerance	
	Over and Under			Over	Under	Over	Under	Over	Under	Over	Under
To 25.4, incl	0.20	0.25	...	...	...	...	...	...	...	0.38	0.38
25.4 to 50.8, incl	0.31	0.38	0.80	...	...	...	...	...	...	0.80	0.80
50.8 to 101.6, incl	0.38	0.51	0.80	1.58	0.80	...	...	...	...	1.58	0.80
101.6 to 152.4, incl	0.38	0.51	0.80	1.58	0.80	2.36	1.58	...	...	2.36	1.58
152.4 to 203.2, incl	0.41	0.64	0.80	1.58	0.80	2.36	1.58	3.18	3.96	3.18	3.96
203.2 to 254.0, incl	0.53	0.80	0.80	1.58	0.80	2.36	1.58	3.18	3.96	3.96	4.75

been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

**17. Packaging and Package Marking**

17.1 Material shall be bundled or boxed in such a manner as to assure undamaged delivery to its destination when properly transported by a common carrier.

17.2 Each bundle or shipping container shall be marked with the grade of the material or UNS number and heat number.

**18. Keywords**

18.1 N06333; bar

**TABLE 5 Permissible Variations in Size of Cold-Finished Round Bars**

NOTE 1—Size tolerances are over and under as shown in the table. Also, rounds can be produced to tolerances all over and nothing under, or all under and nothing over, or any combination of over and under, if the total spread in size tolerance for a specified size is not less than the total spread shown in the table.

NOTE 2—When it is necessary to heat treat or heat treat and pickle after cold finishing, size tolerances are double those shown in the table.

Specified Size		Size Tolerance (Note 1)			
in.	mm	Over		Under	
		in.	mm	in.	mm
Over ½ to 1, incl	12.7 to 25.4	0.002	0.05	0.002	0.05
1 to 1½, incl	25.4 to 38.1	0.0025	0.06	0.0025	0.06
1½ to 4, incl	38.1 to 101.6	0.003	0.08	0.003	0.08

**TABLE 6 Permissible Variations in Length of Hot-Finished or Cold-Finished Bars**

NOTE 1—Tolerances in this table apply when specific lengths are ordered. When random lengths are ordered, the length range is not less than 24 in. (610 mm).

Specified Sizes of Rounds, Squares, Hexagons, Octagons, and Widths of Flats, <sup>A</sup> in. (mm)	Permissible Variations in Length, in. (mm)				
	To 12 ft (3.66 m), incl		Over 12 to 25 ft (3.66 to 7.62 m), incl		
	Over	Under	Over	Under	
To 2, incl	51	½ (13)	0	¾ (19)	0
Over 2 to 4, incl	51 to 102	¾ (19)	0	1 (25)	0
Over 4 to 6, incl	102 to 152	1 (25)	0	1¼ (32)	0
Over 6 to 9, incl	152 to 229	1¼ (32)	0	1½ (38)	0
Over 9 to 10, incl	229 to 254	1½ 38	0	2 (51)	0

<sup>A</sup> The maximum width of bar flats is 10 in. (254 mm)].

**TABLE 7 Permissible Variations in Length of Hot-Finished or Cold-Finished Bars Machine-Cut after Machine Straightening**

NOTE 1—Tolerances in this table apply when specific lengths are ordered. When random lengths are ordered, the length range is not less than 24 in. (610 mm).

Specified Sizes of Rounds, Squares, Hexagons, Octagons, and Widths of Flats, <sup>A</sup> in. (mm)	Permissible Variations in Length, in. (mm)				
	To 12 ft (3.66 m), incl		Over 12 ft to 25 ft (3.66 to 7.62 m), incl		
	Over	Under	Over	Under	
To 3, incl	76	⅛ (3.2)	0	⅜ (9.5)	0
Over 3 to 6, incl	76 to 152	⅜ (9.5)	0	¼ (6.4)	0
Over 6 to 9, incl	152 to 229	¼ (6.4)	0	⅝ (7.9)	0
Over 9 to 12, incl	229 to 305	½ (12.7)	0	½ (12.7)	0

<sup>A</sup> The maximum width of bar flats is 10 in. (254 mm).

**TABLE 8 Permissible Variations in Straightness (Camber) of Hot-Finished Bars and Cold-Finished Bars**


NOTE 1—Measurement is taken on the concave side of the bar with a straightedge, and it represents the greatest deviation of the side from a straight line.

Hot-Finished Bars:

⅛ in. in any 5 ft, but may not exceed (⅛ × number of feet in length)/5 (3.2 mm in any 1.5 m, but may not exceed (2.1 mm × number of metres in length)/5)

Cold-Finished Bars:

¼ in. in any 5 ft, but may not exceed (¼ × number of feet in length)/5 (1.6 mm in any 1.5 m, but may not exceed (1.05 mm × number of metres in length)/5)

 **B719 – 00 (2014)**

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*