



Standard Specification for Powder Metallurgy (PM) Titanium Alloy Structural Components¹

This standard is issued under the fixed designation B 817; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers powder metallurgy (PM) structural components fabricated from commercially pure (CP) titanium powder mixed with master alloy powder and elemental powders in appropriate quantity to yield combined material chemical compositions comparable to ingot metallurgy (I/M) alloys Titanium 6Al-4V and Titanium 6Al-6V-2Sn.

1.2 This specification covers the following materials:

1.2.1 Two types depending on alloy composition as detailed in **Table 1**.

1.2.1.1 Type I is comparable to I/M Ti-6Al-4V.

1.2.1.2 Type II is comparable to I/M Ti-6Al-6V-2Sn.

1.2.2 Two grades of each type that result from the specific titanium powder used are as follows:

1.2.2.1 Grade 1 is made from sponge fines with residual levels of chlorine and sodium.

1.2.2.2 Grade 2 is made from hydride/dehydride (HDH) or other process titanium with significantly lower chlorine and sodium content.

1.2.3 Two classes as a function of density (see **Table 2**) are as follows:

1.2.3.1 Class A density ratio is 94 % minimum.

1.2.3.2 Class B density ratio is 99 % minimum. (**Warning**—CP titanium powder may be pyrophoric; its use may involve an explosion hazard.)

1.3 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific precautionary statements are given in 1.2.3.2.*

¹ This specification is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.11 on Near Full Density Powder Metallurgy Materials.

Current edition approved Nov. 1, 2008. Published December 2008. Originally approved in 1991. Last previous edition approved in 2003 as B 817 – 03.

TABLE 1 Chemical Composition Requirements

Element	Composition, Weight % ^A			
	Grade 1		Grade 2	
	Type I	Type II	Type I	Type II
Aluminum	5.50/6.75	5.0/6.0	5.50/6.75	5.0/6.0
Vanadium	3.50/4.50	5.0/6.0	3.50/4.50	5.0/6.0
Tin	N/A ^B	1.5/2.5	N/A ^B	1.5/2.5
Iron	0.40 max	0.35/1.0	0.40 max	0.35/1.0
Copper	N/A ^B	0.35/1.0	N/A ^B	0.35/1.0
Oxygen, max	0.30	0.30	0.30	0.30
Hydrogen, max	0.015	0.015	0.015	0.015
Nitrogen, max	0.04	0.04	0.04	0.04
Carbon, max	0.10	0.10	0.10	0.10
Sodium, max	0.20	0.20	TBD ^C	TBD ^C
Chlorine, max	0.20	0.20	TBD ^C	TBD ^C
Silicon, max	0.10	0.10	0.10	0.10
Residual elements each, max	0.10	0.10	0.10	0.10
Residual elements total, max	0.40	0.40	0.40	0.40
Titanium	remainder	remainder	remainder	remainder

^AFor the purpose of determining conformance with this specification, measured values shall be rounded “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding method of Practice E 29.

^BNot applicable.

^CVarious chloride levels may be available between the standard 0.20 max and the wrought equivalent of 0.001 max. The acceptable level for specific product applications shall be agreed upon between the purchaser and supplier and specified on the purchase order.

2. Referenced Documents

2.1 ASTM Standards:²

B 243 Terminology of Powder Metallurgy

B 311 Test Method for Density Determination for Powder Metallurgy (P/M) Materials Containing Less Than Two Percent Porosity

B 328 Test Method for Density, Oil Content, and Interconnected Porosity of Sintered Metal Structural Parts and Oil-Impregnated Bearings

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 2 Density Requirements

Class	Density Ratio min, %
A	94
B	99

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

3. Terminology

3.1 *Definitions*—Definitions of powder metallurgy terms can be found in Terminology **B 243**.

3.2 *Descriptions of Terms Specific to This Standard*—Additional descriptive information is available in the Related Material section of Volume 02.05 of the *Annual Book of ASTM Standards*.

4. Ordering Information

4.1 Orders for components under this specification shall include the following information:

4.1.1 Dimensions (see Section 9),

4.1.2 Chemical composition (see Section 6 and Table 1),

4.1.3 Density (see 7.1 and Table 2),

4.1.4 Mechanical properties (see Section 8 and Table X1.1), and

4.1.5 Certification (see Section 13).

5. Materials and Manufacture

5.1 Structural components shall be fabricated by cold compacting a mixture of CP titanium, master alloy, and other elemental powders into suitable shapes. The compacts shall be vacuum sintered and hot isostatically pressed, if necessary, to provide parts conforming to the requirements of this specification.

6. Chemical Composition

6.1 Chemical composition shall conform to the requirements of Table 1.

6.2 Chemical analysis shall be made in accordance with methods prescribed in Volume 03.05 of the *Annual Book of ASTM Standards*, or any other standard method mutually agreed upon between the manufacturer and the purchaser.

7. Physical Properties

7.1 *Density*:

7.1.1 Density ratio shall exceed minimum limits prescribed in Table 2. The purchaser and the producer shall mutually agree on pore-free density values.

7.1.2 Density shall be determined in accordance with Test Method **B 328** for Class A materials.

7.1.3 Density shall be determined in accordance with Test Method **B 311** for Class B materials.

8. Mechanical Properties

8.1 Whenever feasible tests shall be performed on material removed from actual components. The test requirements shall be determined after consideration of actual component function.

8.2 The required mechanical properties and a sampling plan shall be agreed upon between the manufacturer and the purchaser. All shipments of components subsequent to the establishment of testing conditions shall conform to the agreed limits.

9. Dimensions and Tolerances

9.1 Dimensions and tolerances of the structural components shall be indicated on drawings accompanying the purchase order or contract.

10. Sampling

10.1 *Lot*—Unless otherwise specified, a lot shall consist of components fabricated from powder of the same mix lot; compacted, sintered (and hot isostatically pressed, if required) under the same conditions.

10.2 *Chemical Analysis*—If required by purchase agreement, at least one sample for chemical analysis shall be taken from each lot. A representative sample of chips may be obtained by dry-milling, drilling or crushing at least two pieces without lubrication using clean, dry tools.

10.3 *Mechanical Testing*—If required by purchase agreement, the manufacturer and purchaser shall mutually agree on the representative number of specimens for mechanical testing, from each lot.

11. Inspection

11.1 Unless otherwise specified, inspection of components supplied on contract shall be made by the purchaser.

12. Rejection and Rehearing

12.1 Components that fail to conform to the requirements of this specification may be rejected. Rejection shall be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with test results, the producer or supplier may make a claim for a rehearing.

13. Certification

13.1 When specified in the purchase order or contract, a producer's certification of compliance document shall be furnished to the purchaser, verifying that the components manufactured were sampled, tested and inspected in accordance with this specification and have met the requirements. When specified in the purchase order or contract, a report of test results shall be furnished.

13.2 Certification by an independent, third party indicating conformance to the requirements of this specification may be considered upon the request of the purchaser.

13.3 The purchase order or contract must specify whether or not the certification includes a report of chemical analysis.

14. Keywords

14.1 compaction; cold isostatic pressing (CIP); ELCL titanium; HDH titanium powder; hot isostatic pressing (HIP); powder metallurgy; "sponge fines" titanium powder; structural components; Ti-6Al-4V; Ti-6Al-6V-2Sn; titanium; titanium alloys; vacuum sinter

TABLE X1.1 Typical Properties

Type	Grade	Class	0.2 % Offset				Elongation in 1 in. (25 mm) %	Reduction in Area, %
			Tensile Strength		Yield Strength			
			10 ³ psi	(MPa)	10 ³ psi	(MPa)		
I	1	A	111	(765)	101	(696)	4	5
I	1	B	123	(848)	108	(745)	8	14
II	1	A	131	(903)	113	(779)	3	4
II	1	B	139	(958)	131	(903)	6	8
I	2	A	131	(903)	118	(814)	8	18
I	2	B	139	(958)	125	(862)	13	29
II	2	A
II	2	B	139	(958)	128	(883)	13	13

APPENDIX

(Nonmandatory Information)

X1. MECHANICAL PROPERTY DATA

X1.1 Typical data for the mechanical properties of elementally mixed titanium alloy specimens are given in **Table X1.1**. These data do not constitute a part of this specification. They indicate, to the purchaser, the mechanical properties that may be expected from tension specimens conforming to the specified density and chemical requirements.

NOTE X1.1—Refer to Refs. **(1-10)**³ for supplemental material property information.

³ The boldface numbers in parentheses refer to a list of references at the end of the text.

REFERENCES

- (1) Froes, F. H. and Williams, J. C., "Titanium Alloys: Powder Metallurgy," *Encyclopedia of Materials Science and Engineering*, Vol 7, T-Z MIT Press, 1986, pp. 5089–5094.
- (2) *Titanium and Titanium Alloys Source Book*, "Powder Metallurgy," ASM, 1982, pp. 280–288.
- (3) *Metals Handbook Ninth Edition Volume 7 Powder Metallurgy*, "Titanium Alloys," ASM 1984, pp. 254, 512–513, 435, 437, 468–469, 449, 752, 41, 44, and 394.
- (4) Kubel, E. J., Jr., "Titanium NNS Technology Shaping Up," *Advanced Materials and Processes Inc. Metal Progress*, February 1987, pp. 46–50.
- (5) Abkowitz, S. and Weihrauch, P., "Trimming the Cost of MMC's," *Advanced Materials and Processes*, July 1989, pp. 31–34.
- (6) Abkowitz, S., Churrus, G. J., Fujishiro, S., Froes, F. H., and Eylon, D., "Titanium Alloy Shapes from Elemental Blend Powder and Tensile and Fatigue Properties of Low Chloride Compositions," *Conference Proceedings Titanium Net Shape Technologies*, The Metallurgical Society of AIME, Los Angeles, CA, February 1984, pp. 107–120.
- (7) Thellmann, E. L. "Great Potential for Titanium Powder Metallurgy," *Metal Powder Report*, Vol 34, No. 6, June 1980, AIME. Annual Meeting, February 1980, pp. 260–261.
- (8) Brosius, E. S., Malek, J. C., Peter, N. K., and Trzcinski, M. J., "Blended Elemental Powder Titanium for Automotive Applications," *Metal Powder Report*, Vol 42, No. 11, November 1987, pp. 768–773.
- (9) Will, R. H. and Paul, O., "Potential Titanium Airframe Applications," *Powder Metallurgy for High Performance Applications*, Syracuse University Press, 1972, pp. 333–349.
- (10) Hanson, A. D., Runkle, J., Widmer, R., and Hebeisen, J., "Titanium Shapes from Elemental Blends," *International Journal of Powder Metallurgy*, Vol 26, No. 2, 1990, pp. 157–164.

SUMMARY OF CHANGES

Committee B09 has identified the location of selected changes to this standard since the last issue B817–03 that may impact the use of this standard.

- (1) Changed P/M to PM throughout the document.
- (2) Section 1.1 changed “chemistries” to “chemical compositions”.
- (3) In Section 2 added reference to Practice E 29.
- (4) **Table 1** – added a footnote indicating that the rounding method in Practice E 29 shall be used for the purpose of determining conformance with this specification.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).