



Designation: B824 – 17

Standard Specification for General Requirements for Copper Alloy Castings¹

This standard is issued under the fixed designation B824; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes general requirements common to ASTM copper alloy casting specifications B22/B22M, B61, B62, B66, B67, B148, B176, B271/B271M, B369, B427, B505/B505M, B584, B763/B763M, B770, and B806. These requirements apply to the casting specifications to the extent referenced therein.

1.1.1 In the event of conflict between this specification and a casting specification, the requirements of the casting specification shall take precedence.

1.2 The chemical composition and other requirements not included in this specification shall be prescribed in the casting product specifications.

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 No precise quantitative relationship can be stated between the properties of the metal in various locations of the same casting or between the properties of castings and those of a test bar casting from the same metal. (See [Appendix X1](#).)²

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents, of the issue in effect on date of casting purchase, form, part of this specification to the extent referenced herein:

2.2 ASTM Standards:³

- B22/B22M Specification for Bronze Castings for Bridges and Turntables
- B61 Specification for Steam or Valve Bronze Castings
- B62 Specification for Composition Bronze or Ounce Metal Castings
- B66 Specification for Bronze Castings for Steam Locomotive Wearing Parts
- B67 Specification for Car and Tender Journal Bearings, Lined
- B148 Specification for Aluminum-Bronze Sand Castings
- B176 Specification for Copper-Alloy Die Castings
- B193 Test Method for Resistivity of Electrical Conductor Materials
- B194 Specification for Copper-Beryllium Alloy Plate, Sheet, Strip, and Rolled Bar
- B208 Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and Continuous Castings
- B271/B271M Specification for Copper-Base Alloy Centrifugal Castings
- B369 Specification for Copper-Nickel Alloy Castings
- B427 Specification for Gear Bronze Alloy Castings
- B505/B505M Specification for Copper Alloy Continuous Castings
- B584 Specification for Copper Alloy Sand Castings for General Applications
- B763/B763M Specification for Copper Alloy Sand Castings for Valve Applications
- B770 Specification for Copper-Beryllium Alloy Sand Castings for General Applications
- B806 Specification for Copper Alloy Permanent Mold Castings for General Applications
- B846 Terminology for Copper and Copper Alloys
- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E10 Test Method for Brinell Hardness of Metallic Materials

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved April 1, 2017. Published May 2017. Originally approved in 1992. Last previous edition approved in 2016 as B824-16. DOI: 10.1520/B0824-17.

² For ASME Boiler and Pressure Vessel Code application, see related specification in Section II of that code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

E18 Test Methods for Rockwell Hardness of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E54 Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)⁴

E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)⁴

E76 Test Methods for Chemical Analysis of Nickel-Copper Alloys (Withdrawn 2003)⁴

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E478 Test Methods for Chemical Analysis of Copper Alloys

E581 Test Methods for Chemical Analysis of Manganese-Copper Alloys

2.3 *JIS Standard*:⁵

JIS H 1068:2005 Methods for Determination of Bismuth in Copper and Copper Alloys (Japanese Industrial Standards)

3. Terminology

3.1 For definitions of terms related to copper and copper alloys, refer to Terminology **B846**.

3.2 *Definitions of Terms Specific to this Standard*:

3.2.1 *lot*—a collection of like final product (same alloy, temper, dimensions, as applicable) produced under the same or identical conditions from which samples were drawn for inspection or testing, or both.

4. Materials and Manufacture

4.1 *Manufacture*—Mechanical properties of Copper Alloy UNS Nos. C94700, C95300, C95400, C95410, C95500, C95520, and C96800 can be changed by heat treatment. Suggested heat treatments are given in the casting specifications containing these alloys.

5. Chemical Composition

5.1 The casting material shall conform to the chemical requirements of the casting product specification involved.

5.2 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer and the purchaser.

6. Mechanical Property Requirements

6.1 When tension testing is required by the casting product specification, the results shall conform to the requirements of that specification, when tested in accordance with Test Methods **E8/E8M**.

6.2 When Brinell Hardness testing is required by the casting product specification, the results shall conform to the requirements of that specification, when tested in accordance with the Test Method **E10**.

6.3 When Rockwell Hardness testing is required by the casting product specification, the results shall conform to the requirements of that specification, when tested in accordance with the Test Methods **E18**.

7. Other Requirements

7.1 *Hydrostatic Test*—When specified in the purchase order, a hydrostatic test shall be performed on the castings. The details of the test and acceptance criteria shall be established by agreement between the manufacturer and the purchaser.

7.2 *Soundness*—When specified in the purchase order, castings shall meet soundness requirements furnished or referenced by the purchaser. In the absence of standards for soundness, the requirement shall be as agreed upon between the manufacturer and the purchaser.

7.3 When Electrical Resistivity testing is required by the casting product specification, the results shall conform to the requirements of that specification, when tested in accordance with the Test Method **B193**.

8. Dimensions, Mass, and Permissible Variations

8.1 The manufacturer shall be responsible for conforming to the dimensional requirements of the castings as related to the drawing when the pattern equipment is produced by the manufacturer.

8.2 When the pattern equipment is provided by the purchaser, the manufacturer shall be responsible for conforming to the dimensional requirements of the castings, but with any mutually agreed to exceptions relating to the provided pattern equipment.

8.3 Where thick and thin sections of the casting adjoin, the manufacturer shall be permitted to add fillets of adequate size, where not previously provided, subject to approval of the purchaser.

9. Workmanship, Finish, and Appearance

9.1 The surface of the casting shall be free of adhering sand, cracks, and hot tears. Other surface discontinuities shall meet visual acceptance standards agreed upon between the manufacturer and the purchaser.

10. Sampling

10.1 *Lot Size*—A lot shall consist of: (1) all of the metal poured from a single furnace or crucible melt, or (2) all of the metal poured from two or more furnaces into a single ladle, or (3) all of the metal poured from a continuous melting furnace between charges, or (4) all of the metal poured from an individual melting furnace or group of melting furnaces having similar charges and the charge calculation shall be similar for all furnaces, operating during the course of one-half shift, not to exceed 5 h.

10.2 *Chemical Analysis*:

10.2.1 The sample for chemical analysis shall be taken in accordance with Practice **E255** for product in the final form from the pieces selected in **10.1** and combined into one composite sample. The minimum weight of the composite sample shall be 150 g.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from Japanese Standards Association (JSA), Mita MT Bldg., 3-13-12 Mita, Minato-ku, Tokyo 108-0073, Japan, <http://www.jsa.or.jp>.

10.2.2 Instead of sampling as directed in 10.2.1, the manufacturer shall have the option of sampling at the time castings are poured or from the semifinished product. When samples are taken during the course of manufacture, sampling of the finished product by the manufacturer is not required. The number of samples taken for the determination of composition shall be as follows:

10.2.2.1 When samples are taken at the time the castings are poured, at least one sample shall be taken for each group of castings poured from the same source of molten metal.

10.3 Tension-test bars used in meeting the requirements of 6.1 shall be separately cast for the sand, permanent mold, and centrifugal casting processes. The results represent the properties of the metal going into castings poured from the same heat. The mechanical properties may not be the same as the properties of the corresponding castings because of the solidification effects of varying size, section, and design. Test bars for continuous castings are taken from the castings and therefore represent the properties of the casting.

10.3.1 When the requirements of 6.1 have been complied with using separately cast test bars, additional tests may be performed using test bars removed from the casting with test bar location and mechanical properties agreed upon between the manufacturer and the purchaser. It should be noted that the minimum requirements, listed in applicable specifications, were obtained using data from separately cast coupons. Test specimens machined from castings may not achieve these results.

11. Number of Tests and Retests

11.1 Tests:

11.1.1 A chemical analysis of each element with a specified limiting value shall be made on each lot. Chemical analysis for residual elements is not required unless specified in the purchase order.

11.1.2 One tension test shall be performed on each lot.

11.1.3 Should the percent elongation of any tensile-test specimen be less than that specified and any part of the fracture is outside the middle two-thirds of the gage length or in a punched or scribed mark within the reduced section, the specimen may be discarded and replaced by another from the same lot.

11.1.4 If the result of any test fails to conform to the specified requirements, two retests shall be performed. If either retest fails to meet the specified requirements, the lot shall be rejected.

11.1.5 Should any of the properties be less than that specified and there is a discontinuity in the cross-sectional area of the fracture, the specimen may be discarded and replaced by another of the same lot.

11.2 Retests:

11.2.1 When requested by the manufacturer, a retest shall be permitted when test results obtained by the purchaser fail to conform to the casting specification requirements.

11.2.2 Retesting shall be as prescribed in the casting specification for the initial test, except the number of test specimens shall be twice that normally required for the test. Test results

for all specimens shall comply with the casting specification requirements. Failure to comply shall be cause for rejection.

11.2.3 *Chemical Analysis*—If one or more of the elements with specified limits fail to meet the compositional requirement of the product specification when determined from the sample prepared in accordance with Practice E255, one retest cycle shall be permitted with a second composite sample prepared in accordance with Practice E255.

12. Specimen Preparation

12.1 The specimen for chemical analysis shall be taken from the lot in such a manner as to avoid contamination and be representative of the molten metal. Sample preparation shall be in accordance with Practice E255. Analytical specimen preparation shall be the responsibility of the reporting laboratory.

12.2 Tension-test specimens shall be prepared in accordance with Practice B208.

12.2.1 If any specimen is machined improperly or if flaws are revealed by machining or during testing, the specimen shall be discarded and replaced by another from the same lot.

13. Test Methods

13.1 Chemical Composition:

13.1.1 The chemical analysis methods used for the routine determination of specification compliance and preparation of test reports shall be at the discretion of the laboratory performing the analysis.

13.1.2 In case of disagreement on chemical composition, referee analytical methods for copper alloys other than copper-beryllium alloys (Specification B770) are given in Table 1. Referee analytical methods for copper-beryllium alloys are given in the Annex of Specification B194.

TABLE 1 Referee Chemical Analytical Methods

Element	Range or % max	Test Methods
Aluminum (Al)	0.005–13.5	E478
Antimony (Sb)	0.05–0.70	E62
Arsenic (As)	0.0–0.50	E62
Bismuth (Bi)	0.1–6	JIS H 1068
Carbon (C)	0.0–0.50	E76
Copper (Cu)	50.0–99.75	E478
Iron (Fe)	0.003–1.25 0.0–5.0	E478 E54
Lead (Pb)	0.002–15.0 2.0–30.0	E478; Atomic Absorption E478; Titrimetric
Manganese (Mn)	0.10–12.0 12.0–23.0	E62 E581
Nickel (Ni) (incl Cobalt (Co))	0.0–5.0	E478; Photometric
Phosphorus (P)	0.01–1.0	E62
Silicon (Si)	0.005–5.50	E54; Perchloric Acid Dehydration
Sulfur (S)	0.05–0.08	E76; Direct Combustion
Tin (Sn)	0.01–1.0 0.50–20.0	E478; Photometric E478; Titrimetric
Zinc (Zn)	0.02–2.0 2.0–40.0	E478; Atomic Absorption E478; Titrimetric

13.1.3 The determination of magnesium, niobium, zirconium, and titanium, for which no recognized test method is known to be published, shall be subject to agreement between the manufacturer and the purchaser.

13.1.4 Analytical methods for elements with ranges beyond those given in **Table 1** shall be subject to agreement between the manufacturer and the purchaser.

13.1.5 Analytical methods for the determination of elements required by the purchase order agreement shall be as agreed upon between the manufacturer and the purchaser.

13.2 *Mechanical Properties:*

13.2.1 Tension testing shall be performed in accordance with Test Methods **E8/E8M**.

14. Significance of Numerical Limits

14.1 For the purpose of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value or a calculated value shall be rounded as indicated in accordance with the rounding method of Practice **E29**.

Property	Rounded Limit for Observed or Calculated Value
Chemical Composition	nearest unit in the last right-hand significance digit used in expressing the limiting value
Hardness	
Electrical Resistivity	
Electrical Conductivity	
Tensile Strength	nearest ksi (5 MPa)
Yield Strength	
Elongation	nearest 1 %
Grain Size:	nearest multiple of 0.005 mm nearest 0.01 mm
Under 0.060 mm	
0.060 mm and over	

15. Inspection

15.1 The manufacturer shall inspect and make tests necessary to verify that the product furnished conforms to the specified requirements.

15.2 The purchaser may have a representative inspect or witness the inspection and testing of the material prior to shipment. Such an arrangement shall be made by the purchaser and the manufacturer as part of the purchase order. When such inspection or witness of inspection and testing is agreed upon, the manufacturer shall afford the purchaser's representative all reasonable facilities necessary to confirm that the product meets the requirements of the purchase order. The purchaser's inspection and tests shall be conducted in such a manner that they will not interfere unnecessarily with the manufacturer's operation.

16. Rejection and Rehearing

16.1 *Rejection:*

16.1.1 Castings that fail to comply with the requirements of the casting product specification, when tested by the purchaser, may be rejected.

16.1.2 Rejection shall be reported to the manufacturer promptly and in writing.

16.1.3 In case of disagreement or dissatisfaction with the results of the test upon which rejection was based, the manufacturer or supplier may make claim for a rehearing.

16.2 *Rehearing:*

16.2.1 As a result of casting rejection, the manufacturer or supplier may make claim for retesting to be conducted by the manufacturer or supplier and the purchaser. Samples of the rejected castings shall be taken in accordance with the casting specification and Practice **E255** and tested by both parties in accordance with the casting specification, or alternatively, upon agreement between the manufacturer or supplier and the purchaser, an independent laboratory may be selected to perform the test prescribed in the casting specification. The number of specimens to be retested shall be as given in **11.2**.

17. Certification

17.1 When specified in the purchase order, a manufacturer's certificate of compliance shall be furnished to the purchaser stating that samples representing each lot have been tested and inspected in accordance with the material specification and that the requirements have been met.

18. Test Report

18.1 When specified in the purchase order, the manufacturer or supplier shall furnish to the purchaser a manufacturer's test report showing the results of the required tests, including chemical analysis.

19. Product Marking

19.1 Castings shall be marked as shown on the drawing or as prescribed in the purchase order.

19.2 When specified in the purchase order, the castings shall be marked with the manufacturer's name or identifying mark and pattern number or mark at a location on the casting where it will not be removed in machining to finished dimensions.

19.3 The marking of lot identification numbers shall be agreed upon between the manufacturer and the purchaser.

19.4 Castings containing bismuth or bismuth-selenium additives shall be marked with the identification BI or B depending on available space. Castings containing silicon additives shall be marked with the identification Si. This marking shall be at a location on the casting so as not to affect the usefulness of the casting and where it will not be removed during machining while concurrently enabling scrap castings to be segregated and prevented from entering the unregulated scrap metal stream.

20. Packaging and Package Marking

20.1 The material shall be separated by size, composition, and temper, and prepared for shipment in such a manner as to ensure acceptance by common carrier for transportation.

20.2 Each shipping unit shall be legibly marked with the purchase order number, metal or alloy designation, temper, size, gross and net weight, and name of supplier. The specification number shall be shown, when specified in the purchase order.

21. Keywords

21.1 copper alloy castings; copper-base alloy castings; UNS No. C94700; UNS No. C95300; UNS No. C95400; UNS No. C95410; UNS No. C95500; UNS No. C95520; UNS No. C96800

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements S1 to S4 shall apply only when specified by the purchaser in the inquiry, contract, or order, for agencies of the U.S. government.

S1. Referenced Documents

S1.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

S1.1.1 *ASTM Standard*.³

B900 Practice for Packaging of Copper and Copper Alloy Mill Products for U.S. Government Agencies

S1.1.2 *Federal Standards*.⁶

Fed. Std. No. 102 Preservation, Packaging, and Packaging Levels

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

Fed. Std. No. 185 Identification Marking of Copper and Copper-Base Alloy Mill Products

S1.1.3 *Military Standard*.⁶

MIL-STD-129 Marking for Shipment and Storage

S1.1.4 *Military Specification*.⁶

S2. Quality Assurance

S2.1 *Responsibility for Inspection*:

S2.1.1 Unless otherwise specified in the contract or purchase order, the manufacturer is responsible for the performance of all inspection and test requirements specified. Except as otherwise specified in the contract or purchase order, the manufacturer may use his own or any other suitable facilities for the performance of the inspection and test requirements

⁶ Available from DLA Document Services, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil/>.

unless disapproved by the purchaser at the time the order is placed. The purchaser shall have the right to perform any of the inspections or tests set forth when such inspections and tests are deemed necessary to ensure that the material conforms to prescribed requirements.

S3. Identification Marking

S3.1 All material shall be properly marked for identification in accordance with Fed. Std. No. 185 except that the ASTM specification and the alloy number shall be used.

S4. Preparation for Delivery

S4.1 *Preservation, Packaging, Packing*:

S4.1.1 *Military Agencies*—The material shall be separated by size, composition, grade, or class and shall be preserved and packaged, Level A or C, packed Level A, B or C, as specified in the contract or purchase order, in accordance with the requirements of Practice B900.

S4.1.2 *Civil Agencies*—The requirements of Fed. Std. No. 102 shall be referenced for definitions of the various levels of packaging protection.

S4.2 *Marking*:

S4.2.1 *Military Agencies*—In addition to any special marking required by the contract or purchase order, marking for shipment shall be in accordance with MIL-STD-129.

S4.2.2 *Civil Agencies*—In addition to any special marking required by the contract or purchase order, marking for shipment shall be in accordance with Fed. Std. No. 123.

APPENDIXES

(Nonmandatory Information)

X1. MECHANICAL PROPERTIES OF COPPER ALLOY CASTINGS

X1.1 The mechanical properties of copper alloy castings are influenced by the cooling rate during and after solidification, by chemical composition, by heat treatment, by the design and nature of the mold, by the location and effectiveness of gates and risers, and by certain other factors.

X1.2 The cooling rate in the mold and, therefore, the properties developed in any particular casting section are influenced by the presence of cores, chills, and chaplets;

changes in section thickness; and the existence of bosses, projections, and intersections, such as junctions of ribs and bosses. Because of the interactions of these factors, no precise quantitative relationship can be stated between the properties of the metal in various locations of the same casting or between the properties of a casting and those of a separately cast test bar.

X2. METRIC EQUIVALENTS

X2.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force which, when applied to a body having a mass of one kilogram, gives it an acceleration of one metre per second squared ($N = \text{kg}\cdot\text{m}/\text{s}^2$). The derived SI unit for pressure or

stress is the newton per square metre (N/m^2), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$, the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m^2 and N/mm^2 .

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B824 – 16) that may impact the use of this standard. (Approved April 1, 2017.)

(1) Revised 10.1 (4).

Committee B05 has identified the location of selected changes to this standard since the last issue (B824 – 14) that may impact the use of this standard. (Approved Oct. 15, 2016.)

(1) Added Brinell Hardness Test Method E10, Rockwell Hardness Test Methods E18, and Electrical Resistivity Test Method B193.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/