



Standard Practice for De-Agglomeration of Refractory Metal Powders and Their Compounds Prior to Particle Size Analysis¹

This standard is issued under the fixed designation B859; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice covers the de-agglomeration of refractory metal powders and their compounds in preparation for particle size analysis.

1.2 Experience has shown that this practice is satisfactory for the de-agglomeration of elemental tungsten, molybdenum, rhenium, and tantalum metal powders, and tungsten carbide. Other metal powders (for example, elemental metals, carbides, and nitrides) may be prepared for particle size analysis using this practice with caution as to effectiveness until actual satisfactory experience is developed.

1.3 With the exception of the values for mass, for which the use of the gram (g) unit is the long-standing industry practice, the values stated in SI are to be regarded as standard. No other units of measure are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific precautionary statements, see [Note 2](#).

2. Referenced Documents

2.1 *ASTM Standards*:²

[B243 Terminology of Powder Metallurgy](#)

[B330 Test Methods for Estimating Average Particle Size of Metal Powders and Related Compounds Using Air Permeability](#)

[B761 Test Method for Particle Size Distribution of Metal](#)

¹ This practice is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.03 on Refractory Metal Powders.

Current edition approved Oct. 1, 2013. Published October 2013. Originally approved in 1995. Last previous edition approved in 2003 as B859 – 03(2008) ^{ϵ 1}. DOI: 10.1520/B0859-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[Powders and Related Compounds by X-Ray Monitoring of Gravity Sedimentation](#)

[B821 Guide for Liquid Dispersion of Metal Powders and Related Compounds for Particle Size Analysis](#)

[B822 Test Method for Particle Size Distribution of Metal Powders and Related Compounds by Light Scattering](#)

2.2 *ASTM Adjunct*:

[ADJB0859 Detailed Drawings of Alternative Steel Milling Bottles](#)³

3. Terminology

3.1 *Definitions*—Definitions of powder metallurgy terms can be found in Terminology [B243](#).

4. Significance and Use

4.1 Refractory metal powders, such as tungsten and molybdenum, are usually produced by hydrogen reduction at high temperatures. Thus, they usually contain numerous large, strongly-sintered agglomerates. Many of the manufacturing processes using these powders involve a milling step or some similar treatment or depend on the individual particulate size, not on the agglomerate size.⁴ Thus, a knowledge of the individual particulate size distribution, not the agglomerate size distribution, is usually desired from a particle size analysis of these powders. This practice provides a procedure for breaking down agglomerates into their constituent particles (de-agglomeration), without excessive fracture of the individual particles. The procedure is often referred to as *laboratory milling* or *rod milling*.

4.2 The laboratory milling conditions specified in this guide have been in use since 1965, initially as part of a particle size analysis test method. This guide was first published as a separate, stand-alone standard in 1995 because of its applicability in preparing powder samples for analysis by other

³ Available from ASTM International Headquarters. Order Adjunct No. [ADJB0859](#).

⁴ Michaels, A. I., "Turbidimetric Particle Size Distribution Theory: Application to Refractory Metal and Oxide Powders," *1958 Symposium on Particle Size Measurement, ASTM STP 234*, ASTM, 1959, pp. 207–244.

*A Summary of Changes section appears at the end of this standard

methods as well (for example, Test Methods **B761** and **B822**). Information on the development and establishment of the milling conditions here specified can be found in the footnoted reference.⁵

4.3 The milling procedure described in this practice does not necessarily break down only agglomerates without fracturing individual particles; some particle fracture may occur in certain powders. However, use of this practice *does* provide consistent particle size analysis results that have been found to relate well to powder behavior in numerous manufacturing processes.

4.4 This practice shall be used for the de-agglomeration of the refractory metal powders and compounds listed in **1.2**, when an evaluation of the individual particulate size distribution is required from the subsequent particle size analysis. It shall not be used when the *agglomerate* (as-is or as-supplied) size distribution is desired.

4.5 This practice may be used in preparing samples for Test Methods **B330**, **B761**, **B822**, and other particle size analysis methods, prior to the dispersion procedure of Guide **B821**, if used.

5. Apparatus

5.1 *Milling Bottle*—There are two alternative materials for the milling container:

5.1.1 *Glass Bottle*—Round laboratory solution bottle, 250-mL capacity, or a 250-mL, 140-mm high, 60-mm diameter, wide-mouth, flat-bottom centrifuge bottle, with cap or stopper, or

5.1.2 *Stainless Steel Bottle*—Fabricated according to the detailed drawings in Adjunct No. **ADJB0859**³.

5.2 *Tungsten Rods*—Fifty rods 75 ± 3 mm long by 4.0 ± 0.3 mm in diameter, ground surface.

5.3 *Laboratory Jar Roll Mill*, capable of rotating the milling bottle at 145 rpm.

NOTE 1—If a jar roll mill is not available to give a bottle rpm of 145, the bottle can be either (1) set up on a lathe, or (2) built up in diameter and used on a faster rpm mill.

⁵ Buerkel, W. A., “Turbidimetric Particle Size Analysis as Applied to Tungsten Powder and the Carbide Industry,” *Handbook of Metal Powders*, A. Poster, ed., Reinhold Publishing Corp., New York, NY, 1966, pp. 20–37.

5.4 *Screen, No. 20 (850- μ m), and Bottom Pan.*

6. Procedure

6.1 Place 30 ± 0.1 g of tungsten, molybdenum, rhenium, or tantalum metal, or 50 ± 0.1 g of tungsten carbide powder in the milling bottle containing the 50 tungsten milling rods.

6.2 Seal the milling bottle and rotate on the jar roll mill for $60 \text{ min} \pm 15 \text{ s}$ at a bottle speed of 145 ± 5 rpm. After the first 5 min, check to be sure the rods are cascading inside the bottle by listening for the fast-paced, repeated “clinking” sound that the cascading rods make. If the rods are not cascading, stop the mill, set the bottle upright momentarily, then replace the bottle on the mill and continue milling for the remaining 55 min (if the rods are now cascading; if not, repeat setting the bottle upright and restarting until they are).

6.3 After milling, immediately screen the powder through a No. 20 (850- μ m) screen to remove the milling rods. Dislodge any milled powder that might remain in the bottle by placing a couple of screened rods in the bottle and “whipping” for a few turns.

NOTE 2—**Warning:** The fresh metal surfaces produced during milling may have a tendency to rapidly oxidize when the milling bottle is opened. Use caution when opening the bottle to avoid fire or explosion.

6.4 Remove all the milled powder from the bottom pan and place in a sample container.

7. Particle Size Analysis

7.1 If necessary, disperse the milled powder according to Guide **B821**.

7.2 Immediately perform the desired particle size analysis.

NOTE 3—Since milled powder has a greater tendency than as-supplied powder to pick up moisture and oxidize, the analysis procedure should be initiated immediately after milling is completed. For all practical purposes, however, two runs can be made in succession on each milled powder. If more than two runs on the same milled powder are desired, provisions may be taken to lessen (elimination is not possible) the effect of humidity on the milled powder, such as immediate splitting of the sample and storage under dry nitrogen or in a desiccator.

8. Keywords

8.1 de-agglomeration; laboratory-milled; laboratory milling; molybdenum; particle size analysis; powders; refractory metals; rhenium; rod-milled; rod milling; tantalum; tungsten; tungsten carbide

SUMMARY OF CHANGES

Committee B09 has identified the location of selected changes made to this standard since the last issue, B859–03(2008)^{e1}, that may impact the use of this standard.

- (1) A units statement was added, as Section 1.3.
- (2) References to now-obsolete Test Method B430 were deleted.
- (3) Inch-pound units were removed.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT).