



Standard Method for Pinhole Determination in Aluminum and Aluminum Alloy Plain Foil by Means of a Light Table¹

This standard is issued under the fixed designation B926; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This method covers the identification and counting of pinholes, including roll holes, in plain foil using a light table, and inspector with normal 20/20 or corrected 20/20 vision, and a darkened inspection area.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This method may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

B881 Terminology Relating to Aluminum- and Magnesium-Alloy Products

3. Terminology

3.1 *Definitions*—Refer to Terminology **B881** for definitions of product terms used in this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *calibration*—determination of the values of the significant parameter(s) by comparison with a value(s) indicated by a reference instrument or by a set of reference standards.

3.2.2 *pinhole*—any small void in the foil that will permit the transmission of light. Classification criteria for pinholes limits these voids to those that are too small in size to be clearly visible to the unaided eye (1 \times visual inspection).

¹ This test method is under the jurisdiction of ASTM Committee **B07** on Light Metals and Alloys and is the direct responsibility of Subcommittee **B07.03** on Aluminum Alloy Wrought Products.

Current edition approved Dec. 1, 2009. Published January 2010. Originally approved in 2003. Last previous edition approved in 2003 as B926–03. DOI: 10.1520/B0926-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.3 *roll hole*—the producer's classification of a pinhole caused by an imperfection on any type of roll the foil contacts during production. The distinguishing feature of a roll hole(s) is the repeatability of this void on a regular interval. This interval is directly proportional to the circumference of the roll causing the void (this interval will also increase proportionally to subsequent thickness reductions).

4. Summary of Method

4.1 This method contains guidelines for determining the number of pinholes present in the area with the highest pinhole concentration in a sample of foil.

4.2 A full width sample is placed on the light table, and the pinholes are counted in a sample of known area (five or more square feet).

5. Significance and Use

5.1 Foil in thickness of about 0.002 in. (0.05 mm) and heavier is virtually free of pinholes. With decrease in thickness, the number of pinholes may increase.

5.2 This method is provided to develop and maintain uniformity in the methods of evaluating pinholes in aluminum foil. The pinhole data provides assessments of process capability and quality levels of the foil as well.

6. Apparatus

6.1 A light table which provides illumination between 1500 and 1800 lux light intensity with a smooth and uniform inspection surface on which the foil is examined. The light table must be in a black booth or in an area where the lights are turned off to provide darkness of less than 50 lux. The light table should be able to accommodate the widest width of foil to be examined. The usual construction of the light table consists of a shallow box painted white on the inside with rows of fluorescent lights and with a frosted or milk glass covering to provide uniform light diffusion.

6.2 One or more counting frames (grids) that have openings of one square foot (one square decimeter for SI counts).

6.3 Sheet of foil to be tested.

6.4 Calibration of the necessary light intensities can be accomplished using a standard light meter.

*A Summary of Changes section appears at the end of this standard

7. Procedure

7.1 Test a full-width representative sample with a minimum of five square feet. Examine the full width of the sheet. The foil gage should be within tolerance.

7.2 Place the foil sample on the light table carefully to avoid wrinkling/creasing with the long direction of the bulbs perpendicular to the rolling direction of the foil and turn the lights on in the light table and off in the booth or area. Allow a reasonable time for eyes to adjust to darkened conditions.

7.3 If necessary, move the foil on the light table until the entire width has been examined. (Move the foil carefully and as little as possible because moving the sample may create voids in the sample.)

7.4 If a counting frame is used, place it over the area and count the holes. The person should be approximately 18 in. from the sample when counting.

7.5 Record the count.

8. Report

8.1 The report shall include the following:

8.1.1 Identification of the roll from which the sample was taken,

8.1.2 The average number of pinholes per square foot of sample,

8.1.3 Gage of the foil sample, and

8.1.4 Sample lot identification.

9. Precision and Bias

9.1 *Precision*—It is not practicable to specify the precision of the procedure in Method B926 for counting pinholes because as the gage decreases, their variability and number increase.

9.2 *Bias*—Since the vision of the inspector(s) are the most significant aspect of bias in counting pinholes, it is recommended that samples of known counts be used routinely to verify if bias exists. Operating outside of the range of light intensities stated will also cause biased counts.

SUMMARY OF CHANGES

Committee B07 has identified the location of selected changes to this standard since the last issue (B926 – 03) that may impact the use of this standard. (Approved Dec. 1, 2009.)

(1) ASTM references B373, B479 and E252 are not referenced in this document and were removed from Section 2.

(2) ASTM B881 was added to Section 2 and referenced in Section 3.

(3) Foil was removed from Section 3.2, because it is included in ASTM B881.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).