



Standard Test Method for Effect of Water on Compressive Strength of Compacted Bituminous Mixtures¹

This standard is issued under the fixed designation D1075; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers measurement of the loss of compressive strength resulting from the action of water on compacted bituminous mixtures containing asphalt cement. A numerical index of reduced compressive strength is obtained by comparing the compressive strength of freshly molded and cured specimens with the compressive strength of duplicate specimens that have been immersed in water under prescribed conditions.

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

- [C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)
- [D1074 Test Method for Compressive Strength of Bituminous Mixtures](#)
- [D2726 Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Bituminous Mixtures](#)
- [D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials](#)

¹ This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.22 on Effect of Water and Other Elements on Bituminous Coated Aggregates.

Current edition approved Aug. 15, 2011. Published August 2011. Originally approved in 1949. Last previous edition approved in 2007 as D1075 – 07. DOI: 10.1520/D1075-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D6752 Test Method for Bulk Specific Gravity and Density of Compacted Bituminous Mixtures Using Automatic Vacuum Sealing Method](#)

[E2251 Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids](#)

3. Significance and Use

3.1 This test method is useful as an indicator of the susceptibility to moisture of compacted bitumen-aggregate mixtures.

NOTE 1—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Standard Practice D3666 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with D3666 alone does not completely assure reliable results. Reliable results depend on many factors; following the suggestions of D3666 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

4. Apparatus

4.1 One or more automatically controlled water baths shall be provided for immersing the specimens. The baths shall be of sufficient size to permit total immersion of the test specimens. They shall be so designed and equipped as to permit accurate and uniform control of the immersion temperature within $\pm 1.8^\circ\text{F}$ (1°C). They shall be constructed of or lined with copper, stainless steel, or other nonreactive material. The water used for the wet storage of the specimens shall be either distilled or otherwise treated to eliminate electrolytes and the bath shall be emptied, cleaned, and refilled with fresh water for each series of tests.

4.2 A manually or automatically controlled water bath also shall be provided for bringing the immersed specimens to the temperature of $77 \pm 1.8^\circ\text{F}$ ($25 \pm 1^\circ\text{C}$) for the compression test. Any convenient pan or tank may be used provided it is of sufficient size to permit total immersion of the specimens.

4.3 A balance and a water bath with suitable accessory equipment will be required for weighing the test specimens in air and in water in order to determine their densities, the

amount of absorption, and any changes in specimen volume resulting from the immersion test.

4.4 A supply of flat transfer plates of glass or other non-reactive material will be required. One of these plates shall be kept under each of the specimens during the immersion period and during subsequent handling, except when weighing and testing, in order to prevent breakage or distortion of the specimens.

4.5 *Thermometers*—It is recommended the use of Calibrated liquid-in-glass thermometers of suitable range with a readability of 1°F (0.5°C) that conform to the requirements of specification E2251, but can be use also mercury thermometers. Alternatively, electronic thermometers, for example resistance thermometers (RTD, PRT, IPRT) of equal or better accuracy, may be used

4.6 *Air Bath*—The air bath shall be capable of either manual or automatic control for storing the specimen a $77 \pm 1.8^\circ\text{F}$ ($25 \pm 1^\circ\text{C}$) immediately prior to making the compression test.

5. Test Specimens

5.1 At least six 4 by 4-in (101.6 by 101.6-mm) cylindrical specimens shall be made for each test. The procedures described in Test Method D1074 shall be followed in preparing the loose mixtures and in molding and curing the test specimens.

NOTE 2—This test method was developed to measure the loss of compressive strength due to water for specimens designed at approximately 6% air voids by the compaction procedures of Test Method D1074. When used with mixtures designed by other test methods, it is possible that the specimens will be compacted to some other void level which may influence the results. Some agencies have established an air void or percent density target to which the specimens should be compacted. This is accomplished by adjusting the loading in the Molding and Curing Test Specimens Section of Test Method D1074.

6. Determination of Bulk Specific Gravity of Test Specimens

6.1 Allow each set of six test specimens to cool for at least 2 h after removal from the curing oven described in Test Method D1074. Determine the bulk specific gravity of each specimen in accordance with the procedure (thoroughly dry specimens) and calculation (bulk specific gravity) sections of Test Method D2726 or Test Method D6752.

NOTE 3—The calculation of air voids may be dependent on the test method used to determine the bulk specific gravity of the compacted sample.

7. Procedure

7.1 Sort each set of six test specimens into two groups of three specimens each so that the average bulk specific gravity

of the specimens in Group 1 is essentially the same as for Group 2. Test the specimens in Group 1 as described in 7.1.1. Test the specimens in Group 2 as described in 7.1.2 unless the alternative procedure described in 7.1.3 is specified.

7.1.1 *Group 1*—Bring the test specimens to the test temperature $77 \pm 1.8^\circ\text{F}$ ($25 \pm 1^\circ\text{C}$), by storing them in an air bath maintained at the test temperature for not less than 4 h and determine their compressive strengths in accordance with Test Method D1074.

7.1.2 *Group 2*—Immerse the test specimens in water for 24 h at $140 \pm 1.8^\circ\text{F}$ ($60 \pm 1^\circ\text{C}$). Transfer them to the second water bath maintained at $77 \pm 1.8^\circ\text{F}$ ($25 \pm 1^\circ\text{C}$) and store them there for 2 h. Determine the compressive strength of the specimens in accordance with Test Method D1074.

7.1.3 *Group 2, Alternative Procedure*—Immerse the test specimens in water for four days at $120.2 \pm 1.8^\circ\text{F}$ ($49 \pm 1^\circ\text{C}$). Transfer them to the second water bath maintained at $77 \pm 1.8^\circ\text{F}$ ($25 \pm 1^\circ\text{C}$) and store them there for 2 h. Determine the compressive strength of the specimens in accordance with Test Method D1074.

8. Calculation

8.1 Calculate the numerical index of resistance of bituminous mixtures to the detrimental effect of water as the percentage of the original strength that is retained after the immersion period as follows:

$$\text{Index of retained strength, \%} = (S_2/S_1) \times 100 \quad (1)$$

where:

S_1 = compressive strength of dry specimens (Group 1), and
 S_2 = compressive strength of immersed specimens (Group 2).

9. Precision and Bias

9.1 *Single-Operator Precision*—The single-operator standard deviation has been found to be 6% (see Note 4). Therefore, results of two properly conducted tests by the same operator on the same material should not differ by more than 18% (see Note 4).

NOTE 4—These numbers represent, respectively, the (1s) and (d2s) limits as described in ASTM Practice C670.

9.2 *Multilaboratory Precision*—The multilaboratory standard deviation has been found to be 18% (see Note 4). Therefore, results of two properly conducted tests from two different laboratories on identical samples of the same material should not differ by more than 50% (see Note 4).

10. Keywords

10.1 bituminous paving mixtures; compression testing; moisture; water

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).