



Standard Specification for Ammoniacal Copper Arsenate and Ammoniacal Copper Zinc Arsenate^{1,2}

This standard is issued under the fixed designation D 1325; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers ammoniacal copper arsenate solution for use in the preservative treatment of wood.

2. Referenced Documents

2.1 *ASTM Standards:*

D 1326 Test Method for Chemical Analysis of Ammoniacal Copper Zinc Arsenate³

2.2 *AWPA Standard:*

AWPA P5 Standards for Waterborne Preservatives⁴

3. Composition and Properties

3.1 The ingredients of ammoniacal copper arsenate solution (ACA) shall be present in the following proportions:

	Minimum	Nominal
Copper, calculated as CuO, %	47.7	49.8

Arsenic, calculated as As ₂ O ₅ , %	47.6	50.2
---	------	------

3.2 The ingredients of ammoniacal copper zinc arsenate (ACZA) solution shall be present in the following proportions:

Copper, calculated as CuO, %	45.0	50.0
Arsenic, calculated as As ₂ O ₅ , %	22.5	25.0
Zinc, calculated as ZnO, %	22.5	25.0

3.3 The ingredients listed in 3.1 for ACA shall be dissolved in an aqueous solution of ammonia of a strength such that the ammonia content of the solution will be 1.38 times the copper content when copper is calculated as CuO. To aid in solution, not over 1.7 % of the total active ingredients (CuO + As₂O₅) of glacial acetic acid may be added.

3.4 The ingredients listed in 3.2 for ACZA shall be dissolved in a solution of ammonia to copper oxide ratio of 1.38:1 (wt. basis). It is necessary to add ammonium bicarbonate (NH₄HCO₃) at least equal to 0.92 times the weight of copper oxide.

3.5 The solid preservative or treating solution shall be made up of water soluble compounds selected from the following groups each in excess of 95% purity on an anhydrous basis:

- Bivalent copper (for example, cupric hydroxide)
- Pentavalent arsenic (for example, arsenic acid)
- Zinc oxide (for example, zinc oxide)

4. Chemical Analysis

4.1 The material shall be analyzed in accordance with Methods D 1326.

5. Keywords

5.1 ammoniacal copper arsenate

¹ This specification is under the jurisdiction of the ASTM Committee D-7 on Wood and is the direct responsibility of Subcommittee D07.06 on Treatments for Wood Products.

Current edition approved July 15, 1994. Published September 1994. Originally published as D 1325-54T. Last previous edition D 1325-76 (1992)^{ε1}.

² This specification is identical with the Standards for Ammoniacal Copper Arsenate (ACA) in Section 2 and Ammoniacal Copper Zinc Arsenate (ACZA) in Section 3 of the American Wood-Preservers' Assn. Standards for Waterborne Preservatives (P5-92). Acknowledgment is made to the American Wood-Preservers' Association for its development of the subject matter covered in this specification.

³ *Annual Book of ASTM Standards*, Vol 04.10.

⁴ Available from American Wood-Preservers' Association, P.O. Box 286, Woodstock, MD 21163-0286.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).