



Standard Test Method for Saponification Number (Empirical) of Synthetic and Natural Waxes¹

This standard is issued under the fixed designation D1387; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the saponification number of synthetic waxes and natural waxes.

1.2 This test method is applicable to Fischer Tropsche, microcrystalline, polyethylene, and Montan Ester waxes.

1.3 Certain synthetic waxes, notably copolymers of ethylene, exhibit poor reproducibility when running saponification values. Reproducibility can be improved if cooking time in 7.2 is extended from 3 h to 18–20 h.

1.4 Some oxidized polyethylene and other waxes with a melt temperature above 100°C may give poor reproducibility.

1.5 Some dark-colored (Gardner Color 14) waxes may obscure the color change of the indicator, resulting in poor reproducibility.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

E200 Practice for Preparation, Standardization, and Storage of Standard and Reagent Solutions for Chemical Analysis

3. Terminology

3.1 *Definitions*:

3.1.1 *saponification number*—the number of milligrams of potassium hydroxide required to hydrolyze 1 g of the sample and is a measure of the amount of saponifiable matter present.

4. Significance and Use

4.1 This test method is used to determine the property of ester functionality. Ester functionality determines the utility of the wax as well as being a significant quality control test.

5. Apparatus

5.1 *Analytical Balance.*

5.2 *Boiling Chips*, chemically resistant glass.

5.3 *Burets*, two 50-mL capacity with 0.1-mL graduations.

5.4 *Erlenmeyer Flasks*, 250-mL, alkali-resistant.

5.5 *Hot Plate.*

5.6 *Reflux Condenser.*

6. Reagents and Materials

6.1 *Purity of Reagents*—Reagent-grade chemicals or equivalent as specified in Practice **E200** shall be used in all tests.

6.2 *Hydrochloric Acid Standard (0.5 N).*

6.3 *Phenolphthalein Indicator Solution (10 g/litre)*—Dissolve 1 g of phenolphthalein in 100 mL of USSD3A denatured ethanol or 95 % ethanol.

6.4 *Potassium Hydroxide, Alcoholic Solution (6.6 g/litre)*—Dissolve 6.6 g of potassium hydroxide (KOH) in USSD3A denatured ethanol or 95 % ethanol. Dilute to 1 L with the ethanol.

6.5 *Xylene.*

7. Procedure

7.1 Transfer approximately 1 g of the sample, weighed to the nearest 0.001 g to a 250-mL Erlenmeyer flask.

7.2 Add 40 mL of xylene and a few boiling chips to the flask. Dissolve by heating on the hot plate to the boiling point of xylene. As soon as the wax dissolves, remove from the hot

¹ This test method is under the jurisdiction of ASTM Committee **D21** on Polishes and is the direct responsibility of Subcommittee **D21.02** on Raw Materials.

Current edition approved Oct. 1, 2012. Published October 2012. Originally approved in 1955. Last previous edition approved in 2007 as D1387–89(2007). DOI: 10.1520/D1387-89R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

plate and add 50.0 mL of 0.1 *N* ethanolic KOH solution from the buret. Fit the flask with a reflux condenser and reflux for 3 h using the hot plate.

7.3 Remove the condenser from the flask, add 5 drops of the phenolphthalein solution and titrate the sample with 0.5 *N* HCl until the pink color disappears. Reheat the sample to the boiling point, and if it turns pink, resume titration until the color once again disappears. Repeat this procedure until the pink color does not reappear on heating. Saponified waxes usually require two repetitions of heating and additional titration until the pink color does not reappear.

8. Calculation

8.1 Calculate the saponification number as follows:

$$\text{Saponification number} = \frac{(B - A)N \times 56.1}{C} \quad (1)$$

where:

- A* = millilitres of HCl solution required for titration of the sample,
B = millilitres of HCl solution required for titration of the blank,

- C* = grams of sample used, and
N = normality of the HCl solution.

9. Precision and Bias

9.1 Precision and bias have been established only for light-colored waxes melting below 100°C.

9.1.1 Duplicate results by the same operator shall not be considered suspect unless they differ by more than ± 1.3 saponification numbers (95 % confidence limits for average).

9.1.2 Results reported by two laboratories shall not be considered suspect unless they differ by more than ± 3.2 saponification numbers (95 % confidence limits for average).

9.2 Dark-colored waxes or wax melting above 100°C, or polyethylene copolymer waxes may exhibit poorer reproducibility when running saponification values. See Section 1.

9.3 *Bias*—This test has no bias because the values produced are defined only in terms of this test method.

10. Keywords

10.1 natural wax; polish; polyethylene wax; saponification number; synthetic wax; titration; wax

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).