



Standard Test Method for Micronaire Reading of Cotton Fibers¹

This standard is issued under the fixed designation D1448; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the micronaire reading of loose cotton fibers by measuring the resistance of a specific mass (plug) of cotton fibers to air flow under prescribed conditions.

NOTE 1—For other methods for determining the fineness of fibers based on the air-flow principle, refer to Test Method D1449, Test Method for Specific Area and Immaturity Ratio of Cotton Fibers (Arealometer Method),² and to Test Method D1282, Test Method for Resistance to Air Flow as an Indication of Average Fiber Diameter of Wool Top, Card Sliver, and Scoured Wool.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D123 Terminology Relating to Textiles

D1282 Test Method for Resistance to Airflow as an Indication of Average Fiber Diameter of Wool Top, Card Sliver, and Scoured Wool

D1441 Practice for Sampling Cotton Fibers for Testing

D1449 Method of Test for Specific Area and Immaturity Ratio of Cotton Fibers (Arealometer Method) (Withdrawn 1977)³

D1776 Practice for Conditioning and Testing Textiles

D5867 Test Methods for Measurement of Physical Properties of Raw Cotton by Cotton Classification Instruments

D7139 Terminology for Cotton Fibers

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.11 on Cotton Fibers.

Current edition approved Jan. 1, 2011. Published January 2011. Originally approved in 1954 to replace portions of D414. Last previous edition approved in 2005 as D1448–05. DOI: 10.1520/D1448-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3. Terminology

3.1 For all terminology related to D13.11, refer to Terminology D7139.

3.1.1 The following terms are relevant to this standard: calibration cotton standards, fineness, micronaire reading.

3.2 For all other terminology related to textiles, refer to Terminology D123.

4. Summary of Test Method

4.1 The resistance a specific mass (plug) of cotton fibers offers to the flow of air is measured as an approximate indication of the fineness of fiber. A predetermined mass of loose cotton fibers is placed in the specimen holder and compressed to a fixed volume. The resistance to air flow is measured and expressed as a micronaire reading.

5. Significance and Use

5.1 This test method is considered satisfactory for acceptance testing when the levels of the laboratories are controlled by the use of the same reference standard cotton samples because the current estimates of between-laboratory precision are acceptable under these conditions. If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is a statistical bias between them, using competent statistical assistance. As a minimum, ensure the test samples to be used are as homogeneous as possible, are drawn from the material from which the disparate test results were obtained, and are randomly assigned in equal numbers to each laboratory for testing. The test from the two laboratories should be compared using a statistical test for unpaired data, at a probability level chosen prior to the testing series. If a bias is found, either its cause must be found and corrected, or future test results for that material must be adjusted in consideration of the known bias.

5.2 The micronaire reading of cotton fibers is a function of both fineness and maturity and is related to mill processing performance and to the quality of the end products. Factors correlated with micronaire reading include cleaning efficiency, nepiness, and the strength and uniformity of the yarn.

NOTE 2—A modification of this test method is used in commercial trading to select bales which will conform to contract guarantees for

specified micronaire readings (refer to **D5867**). For this purpose, it is usual practice to test only one specimen per sample.

6. Apparatus and Materials

6.1 *Air-Flow Instrument*, calibrated in micronaire readings or yielding numerical readings from which micronaire readings can be computed.⁴

NOTE 3—Instruments available to measure resistance to air flow use compressed air or vacuum and are constructed to measure air flow under constant pressure drop across the plug, to measure pressure drop when a constant flow of air is maintained, or to indicate resistance to air flow from both a balanced and unbalanced wheatstone bridge.

6.2 *Micronaire Scale*, appropriate for instrument.

NOTE 4—The air instrument scale is calibrated for a specific air regulator and tube. The model number on the scale should correspond to the model number of the instrument. If a regulator or tube is replaced, and the same scale is to be used, the new parts must be of the same make and model as those originally furnished with the instrument (**1**).⁵

6.3 *Balance*, having a capacity suitable for mass of the specimen to be used and a sensitivity of at least 0.2 % of the mass.

6.4 *Air Supply*, to furnish the required pressure or vacuum to operate the instrument in accordance with the manufacturer's instructions.

6.5 *International Calibration Cotton Standards*, with assigned micronaire readings.

7. Sampling and Selection of Specimens

7.1 Take the test specimen by random sampling from the laboratory sample prepared as directed in Practice **D1441**.

NOTE 5—In commercial testing consider the classer's sample that represents both sides of the bale as the laboratory sample. Take portions for each specimen from the end of the classer's sample, to be representative of all layers, or take two test specimens, one from each side of the bale.

8. Conditioning

8.1 Bring the laboratory sample from the prevailing atmosphere to moisture equilibrium in the standard atmosphere for textile testing as directed in Practice **D1776**. Preconditioning is not necessary.

NOTE 6—The effect of conditioning is small for cottons having micronaire readings below 3.5 but is appreciable for readings of 5.0 and above (**2, 3**).

9. Procedure

9.1 Set up and verify the instrument as directed in the manufacturer's instructions. Adjust the instrument if necessary to secure values assigned to the International Calibration Cotton Standards at the beginning of each testing period. Perform test on two specimens from each of the standard cottons. If the average of the two results is not within ± 0.1 unit of the established micronaire reading, recheck the instrument and the technique used by the operator. Check the instrument against the standards again at the end of each testing period. If

incorrect readings on the standards are obtained at the end of a testing period, discard the test results, recheck the instrument, and repeat the tests.

NOTE 7—Built-in calibration devices and calibration plugs alone give only approximate results.

9.2 Test the conditioned specimens in the atmosphere for testing textiles.

9.3 Remove obvious, large pieces of nonfibrous materials. Weigh out a test specimen having the mass specified for the instrument. Place the weighed specimen in the fiber compression cylinder, fluffing it with the fingers as it is packed into the cylinder to eliminate knotty balls, and being careful to place all the fibers inside the cylinder. Insert or activate the fiber compression plunger. Turn on or activate the air flow, and read the value to the nearest 0.1 unit reading.

9.4 Test two specimens.

10. Calculation

10.1 If the instrument readings are not in micronaire readings, compute micronaire readings from instrument readings in accordance with manufacturer's instructions.

10.2 Calculate the average for the two specimens tested to the nearest 0.1 micronaire reading.

11. Report

11.1 State that the test was carried out as directed in ASTM Test Method D1448.

11.2 Report the following information:

11.2.1 Type of material used and identification of the samples by shipment, mark, lot numbers or bale numbers, whichever is applicable.

11.2.2 Average readings to the nearest 0.1 micronaire reading.

11.2.3 Make, type, and model of the instrument used.

12. Precision and Bias

12.1 *Interlaboratory Test Data*⁶—An interlaboratory test is carried out semi-annually in connection with the International Calibration Cotton Standards Program (**4**). The data obtained by the five laboratories designated to establish standard values for check test numbers 29, 30, and 31 in 1971 and 1972 were used as the basis for the precision and accuracy statements. One operator at each of the five laboratories tested three specimens from each of six subsamples representing six different cottons. The subsamples for these tests were extracted from cotton which had been hand blended and processed into picker laps to obtain uniform material. The components of variance calculated from the results of these tests and expressed as standard deviations of micronaire reading are 0.0628 for the single-operator component and 0.0230 for the between-laboratory component.

12.2 *Precision*—For the components of variance in **12.1**, the averages of observed values should be considered significantly

⁴ Instruments commercially available.

⁵ The boldface numbers in parentheses refer to the list of references appended to this test method.

⁶ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report No. RR:D13-1029.

different at the 95 % probability level if the differences exceed the critical differences listed below for various number of specimens in the test:

Critical Differences, Micronaire Readings, for the Conditions Noted⁴

Number of Specimens in Each Average	Single-Operator Precision	Between-Laboratory Precision
1	0.17	0.19
2	0.12	0.14
3	0.10	0.12
4	0.09	0.11
5	0.08	0.10
10	0.05	0.08

⁴ The critical differences were calculated using $t = 1.960$ which is based on infinite degrees of freedom.

NOTE 8—The tabulated values of the critical differences should be considered to be a general statement particularly with respect to between-laboratory precision. Before a meaningful statement can be made about

two specific laboratories, the amount of statistical bias, if any, between them must be established with each comparison being based on recent data obtained on randomized specimens from one sample of the material being tested.

12.3 *Bias*—This method for the testing of the fiber fineness of cotton is accepted internationally for commercial trading and has no known bias when the results are controlled at the standard level by the use of International Calibration Cotton Standards.

13. Keywords

13.1 cotton; fineness; micronaire reading

REFERENCES

- (1) “Revised Micronaire Fiber-Fineness Scale for Use in Testing American Upland Cottons,” Cotton Branch, PMA, U.S. Dept. of Agriculture, Washington, D. C., October, 1950.
- (2) Gates, F. R., and Jennings, E. J., “The Effect of Relative Humidity on Micronaire Readings,” *Texas Research Journal*, TRJOA, Vol 23, 1953, pp. 942–944.
- (3) “Effect of Atmospheric Conditions on Testing Certain Cotton Fiber Properties,” Cotton Branch, PMA, U. S. Dept. of Agriculture, Washington, D.C., October, 1953.
- (4) *International Calibration Cotton Standards*, United States Department of Agriculture, Washington, D.C., Revised January 1966.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).