



# Standard Test Method for Carbon Black—Sieve Residue<sup>1</sup>

This standard is issued under the fixed designation D1514; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the water wash sieve residue in regular untreated carbon blacks. It may not be applicable to oil-treated carbon blacks because the oil would prevent proper wetting of the black by water.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. For specific precautionary statements, see Section 6.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D1799 Practice for Carbon Black—Sampling Packaged Shipments](#)

[D1900 Practice for Carbon Black—Sampling Bulk Shipments](#)

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

## 3. Summary of Test Method

3.1 A sample of carbon black is washed with water through a wire-mesh screen of a specified size until all that remains is a non-carbon black residue. This residue is dried, weighed, and the amount of residue is expressed as mg/kg (ppm) of the original sample.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.31 on Non-Carbon Black Components of Carbon Black.

Current edition approved June 15, 2015. Published August 2015. Originally approved in 1957. Last previous edition approved in 2011 as D1514 – 04 (2011). DOI: 10.1520/D1514-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 4. Significance and Use

4.1 The quantity of sieve residue of carbon black is important in some molded or extruded products as it may relate to the surface appearance of those products. The maximum residue in each application is normally determined and agreed to between the user and the producer.

## 5. Apparatus

5.1 *Sieve and Filtering Apparatus*,<sup>3,4</sup> as shown in Fig. 1.

5.2 *Balance*, with a sensitivity of 0.01 g.

5.3 *Analytical Balance*, with a sensitivity of 0.1 mg.

5.4 *Oven*, gravity-convection type, capable of temperature regulation within  $\pm 1^\circ\text{C}$  at  $125^\circ\text{C}$  and temperature uniformity within  $\pm 5^\circ\text{C}$ .

5.5 *Sieves*, of either phosphor bronze or stainless steel. The sieve shall be in accordance with Specification E11. The sieve to be used shall be agreed upon between the purchaser and the seller.

5.6 *Weighing Dishes*.

## 6. Precautions

6.1 Keep the apparatus clean at all times to prevent contamination.

6.2 Examine the sieves each time they are used to make sure that no cracks or holes have developed.


6.3 Examine the strainer periodically to ascertain that the filter screen is in good condition.

## 7. Sampling

7.1 Samples shall be taken in accordance with Practice D1799 or Practice D1900.

<sup>3</sup> Sieve and filtering apparatus, available from Titan Specialties, Inc., P.O. Box 2316, Pampa, TX 70066-2316, has been found suitable. The A2000 Test Set from Krahn IQS, GmbH, Paffrather Str. 13–15, D-51069 Koeln, Germany, has been found suitable. An ASTM specified apparatus modified with an enlarged funnel leg ID (5.080 cm or 2.0 in.) and sieve screen OD (6.032 cm or 2.375 in.) has also been found suitable.

<sup>4</sup> The sole source of supply of housing No. 20 and cartridge No. 30 known to the committee at this time is Amtek, Plymouth Products Division, 562 Indiana Ave., Sheboygan, WI 53081. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.



NOTE 1—Industrial/O.E.M. filter and pleated polyester fabric reusable cartridges have been found to be a satisfactory strainer.<sup>4</sup>

NOTE 2—Corrosion-free piping must be used.

NOTE 3—Detailed drawings can be obtained from Test Method D1514 – 88a.

NOTE 4—Spray nozzle: Part No. 460.746.30 BE available from Lechler Inc., 445 Kautz Rd., St. Charles, IL 60174, or Titan Specialties Inc., P.O. Box 2316, Pampa, TX 70066-2316.

**FIG. 1 Schematic Diagram of Apparatus for Sieve Residue Determination**

## 8. Calibration

8.1 Calculate the sieve residue to the nearest mg/kg (ppm) as follows:

$$R = (W/S) \times 10^6 \quad (1)$$

where:

$R$  = sieve residue, mg/kg (ppm),  
 $W$  = mass of sieve residue, g, and  
 $S$  = mass of sample, g.

## 9. Procedure

9.1 Prior to making a test, clean the strainer by opening valves *A* and *B* and closing valve *C* as shown in Fig. 1. Allow the strainer to wash for 2 min.

9.2 Close valve *B* and open valve *C*. With valves *A* and *C* completely open, regulate the water pressure by means of a reducing valve. The recommended water pressure is  $207 \pm 34$  kPa ( $30 \pm 5$  lbf/in.<sup>2</sup>).

9.3 After the water pressure has been regulated, attach the sieve holder with a 50-mm (2-in.) diameter sieve to the funnel and allow the water to run through it for 3 min. Stop the water flow by closing valves *A* and *C*. Examine the sieve for particles; if none are observed, the apparatus is ready for use.

9.4 Weigh 100.0 g of the carbon black on the balance.

9.5 Attach the proper sieve to the funnel and start the water flow by opening valves *A* and *C*.

9.6 Add the carbon black slowly to the funnel to prevent plugging of the sieve.

NOTE 1—If desired it is permissible to utilize wetting agents to facilitate dispersion. Care must be taken to ensure that all of the solid material is transferred from the vessel used for dispersing the black into the funnel of the washing apparatus.

9.7 Use a gentle stream of water from the hose attached to valve *D* to wash down any carbon black on the sides of the funnel.

9.8 Continue washing until the wash water coming through the sieve is clear.

9.9 Remove the sieve holder and sieve from the funnel and rub the residue lightly with the finger to disaggregate any hard carbon black lumps which may not have been thoroughly wet by the water.

9.10 Replace the sieve holder and sieve and wash for an additional 2 min.

9.11 Remove the sieve holder and sieve and dry for 1 h at 125°C.

9.12 Transfer the dried residue to a piece of smooth white bond paper and rub gently to remove any carbon black remaining on the residue. Rub until the white paper no longer shows any smears.

NOTE 2—The purpose of gently rubbing the residue is to remove any black that may be clinging to the gritty residue. Do not apply excessive force when rubbing, as this action may fracture the residue allowing it to escape, or may trap the residue in the paper causing a low grit determination. Similarly, do not wear gloves when performing this step, as the residue may be trapped in the glove material, giving a low result.

9.13 Brush all the loose residue to a tared weighing dish and weigh to the nearest 0.1 mg using the analytical balance.

## 10. Report

10.1 Report the following information:

10.1.1 Proper identification of the sample,

10.1.2 Identification of the sieve number, and

10.1.3 Result of the determinations reported to the nearest mg/kg (ppm).

## 11. Precision and Bias

11.1 These precision statements have been prepared in accordance with Practice D4483. Refer to this practice for terminology and other statistical details.

11.2 The precision results in this precision and bias section give an estimate of the precision of this test method with the materials used in the particular interlaboratory program described below. The precision parameters should not be used for acceptance or rejection testing of any group of materials without documentation that they are applicable to those particular materials and the specific testing protocols of the test method. Any appropriate value may be used from Table 1. A type 1 interlaboratory precision program was conducted as detailed in Table 2. Both repeatability and reproducibility represent short-term (daily) testing conditions. The testing was performed using two operators in each laboratory performing the test once on each of two days (total of four tests). A test result is the value obtained from a single determination. Acceptable difference values were not measured. The between

**TABLE 1 Precision Parameters for D1514 Sieve Residue, (Type 1 (No. 325 Sieve) Precision)**

Units	mg/kg (ppm)				
Material	Mean Level	<i>Sr</i>	<i>(r)</i>	<i>SR</i>	<i>(R)</i>
IRB#6 (N330)	18.3	6.0	93.3	13.1	203
N762	18.3	7.4	114	9.7	150
SRB A5 (N135)	20.8	5.1	69.5	9.7	132
N550	64.3	10.4	45.9	24.7	109
N650	75.7	20.2	75.6	46.7	174
Average	39.5				
Pooled Values		11.3	80.8	25.1	180

**TABLE 2 Interlaboratory Precision Program**

Nominal Test Period	Material	Number of Laboratories
March 1996	N650	49
October 1996	IRB#6 (N330)	41
March 1997	N762	45
September 1997	SRB A5 (N135)	42
March 1998	N550	47

operator component of variation is included in the calculated values for *(r)* and *(R)*.

11.3 The results of the precision calculations for this test are given in **Table 1**. The materials are arranged in ascending “mean level” order.

11.4 *Repeatability*—The pooled relative repeatability, *(r)*, of this test method has been established as 80.8 %. Any other value in **Table 1** may be used as an estimate of repeatability, as appropriate. The difference between two single test results (or determinations) found on identical test material under the repeatability conditions prescribed for this test will exceed the repeatability on an average of not more than once in 20 cases

in the normal and correct operation of the method. Two single test results that differ by more than the appropriate value from **Table 1** must be suspected of being from different populations and some appropriate action taken.

NOTE 3—Appropriate action may be an investigation of the test method procedure or apparatus for faulty operation or the declaration of a significant difference in the two materials, samples, and so forth, which generated the two test results.

11.5 *Reproducibility*—The pooled relative reproducibility, *(R)*, of this test method has been established as 180 %. Any other value in **Table 1** may be used as an estimate of reproducibility, as appropriate. The difference between two single and independent test results found by two operators working under the prescribed reproducibility conditions in different laboratories on identical test material will exceed the reproducibility on an average of not more than once in 20 cases in the normal and correct operation of the method. Two single test results produced in different laboratories that differ by more than the appropriate value from **Table 1** must be suspected of being from different populations and some appropriate investigative or technical/commercial action taken.

11.6 *Bias*—In test method terminology, bias is the difference between an average test value and the reference (true) test property value. Reference values do not exist for this test method, since the value or level of the test property is exclusively defined by the test method. Bias, therefore, cannot be determined.

## 12. Keywords

12.1 carbon black; non-carbon black residue; sieve residue; water wash sieve residue

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*