



# Standard Classification System and Basis for Specification for Cellulose Acetate Propionate Molding and Extrusion Compounds (CAP)<sup>1</sup>

This standard is issued under the fixed designation D1562; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This classification system covers requirements for plasticized cellulose acetate propionate thermoplastic compounds suitable for injection molding and extrusion. These compounds have a propionyl content less than 48 % and an acetyl content less than 3 % and can contain dyes and pigments. Cellulosic plastic materials, being thermoplastic, are reprocessable and recyclable. This classification system allows for the use of those cellulosic materials, provided that all specific requirements of this classification system are met.

1.2 The properties included in this classification system are those required to identify the compositions covered. Other requirements necessary to identify particular characteristics important to specialized applications are specified by using the suffixes as given in Section 5.

1.3 This classification system and subsequent line call out specification are intended to provide a means of calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection can be made by those having expertise in the plastic field only after careful consideration of the design and performance required of the part, environment to which it will be exposed, fabrication process to be employed, costs involved, and inherent properties of the material other than those covered by this classification system.

1.4 The values stated in SI units are to be regarded as standard.

1.5 The following safety hazards caveat pertains only to the test method portion, Section 11, of this classification system. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

<sup>1</sup> This classification system is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved May 1, 2015. Published June 2015. Originally approved in 1958. Last previous edition approved in 2009 as D1562 - 09. DOI: 10.1520/D1562-15.

NOTE 1—There is no known ISO equivalent to this standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics
- D257 Test Methods for DC Resistance or Conductance of Insulating Materials
- D570 Test Method for Water Absorption of Plastics
- D618 Practice for Conditioning Plastics for Testing
- D635 Test Method for Rate of Burning and/or Extent and Time of Burning of Plastics in a Horizontal Position
- D638 Test Method for Tensile Properties of Plastics
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D883 Terminology Relating to Plastics
- D1003 Test Method for Haze and Luminous Transmittance of Transparent Plastics
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials
- D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials
- D3892 Practice for Packaging/Packing of Plastics
- D4000 Classification System for Specifying Plastic Materials
- D5740 Guide for Writing Material Standards in the Classification Format
- D7209 Guide for Waste Reduction, Resource Recovery, and

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

Use of Recycled Polymeric Materials and Products (Withdrawn 2015)<sup>3</sup>

E308 Practice for Computing the Colors of Objects by Using the CIE System

### 3. Terminology

3.1 *Definitions*—The terminology used in this classification system is in accordance with Terminologies **D883** and **D1600**.

### 4. Classification

4.1 This classification system covers the following groups, classes, and grades (see Table CAP):

4.1.1 *Group 01*—High impact strength.

4.1.2 *Group 02*—High tensile strength.

4.1.3 *Class*—According to plasticizer content and properties specified in Table CAP.

4.1.4 *Grade 1*—For injection molding (general purpose).

4.1.5 *Grade 2*—For extrusion.

### 5. Suffixes

5.1 When requirements are needed that are not covered in Table CAP, they shall be indicated through the use of suffixes.

5.2 A list of suffixes can be found in Classification System **D4000** (Table 3) and can be used for additional requirements as appropriate. Additional suffixes will be added to that classification system as test methods and requirements are developed and requested.

5.3 Color and opacity shall be within the limits defined in **6.3**

5.4 Some of the more commonly used suffixes for cellulose acetate propionate are shown as follows:

E = electrical requirements (see Table 1) as designated by the following digits:

*First Digit*

1 = volume resistivity—Test Methods **D257**.

dielectric strength—Test Method **D149** (short-time/ step-by-step).

*Second Digit*

1 = volume resistivity and dielectric strength meet property requirements as shown in Table 1.

T = transmittance requirements as designed designated by the following digits:

*First Digit*

1 = total luminous transmittance Procedure A of Test Method **D1003**.

*Second Digit*

1 = total luminous transmittance, 80 % min.

5.5 An example of this classification system for a high-impact cellulose acetate propionate formulation would be as follows:

CAP0122FA053 (1)

CAP = Table CAP property requirements

- 01 = Group 1—High impact strength
- 2 = Class 2—Plasticizer range from 8 to 20 % (see Table CAP, Footnote 1)
- 2 = Grade 2—Extrusion application
- FA053 = Flammability requirement from Classification System **D4000**—Burn rate maximum of 50 mm/min with 3 mm minimum thickness, when tested in accordance with Test Method **D635**

NOTE 2—CAP0122 corresponds to the following physical property requirements in Table CAP:

Specific gravity: 1.19-1.20.

Tensile stress at yield: 19 MPa min.

Flexural modulus: 1 000 MPa min.

Izod impact strength: 200 J/m min.

Water absorption: 2.0 % max.

Weight loss on heating: 2.0 % max.

### 6. Materials and Manufacture

6.1 Materials supplied shall be as uniform in composition and size, and as free of contamination, as can be achieved by good manufacturing practice.

6.2 If these materials contain colorants in the nominal amounts ordinarily employed, such additives shall not alter the ability of the materials to meet the specified properties.

6.3 The color of material supplied shall be comparable, within commercial match tolerances, to the color of standard samples prepared by the manufacturer.

### 7. Physical Requirements

7.1 Test specimens of the material shall conform to the requirements prescribed in Table CAP.

7.2 Molded specimens, for those tests requiring them, shall be prepared in accordance with Section **10**.

7.3 Conformance to the requirements of this classification system shall be determined in accordance with Section **11**.

### 8. Sampling

8.1 Sampling shall be statistically adequate to satisfy the requirements of **12.4**

8.2 A batch or lot shall be constituted as a unit of manufacture as prepared for shipment and can consist of a blend of two or more “production runs.”

### 9. Number of Tests

9.1 Routine testing of each batch or lot shall be limited to properties designated in Table CAP of this classification system.

9.2 One set of samples for those tests that are designated (Section **12**) shall be considered sufficient for testing the batch or lot. The average results from those samples shall comply with the requirements prescribed in this classification system.

### 10. Specimen Preparation

10.1 Physical property requirements in Table CAP are based on injection molded specimens 3.2 mm thick. Specimens machined from compression-molded blanks or extruded strips can be used, provided it can be shown that the results are comparable.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

10.2 Prior to molding cellulose acetate propionate, dry the material to a moisture content of 0.2 % or less. The primary reason for drying the material is to eliminate visual defects such as surface imperfections and bubbles. Material spread in a tray to a maximum depth of 50 mm and exposed in a circulating-air oven at 75 to 90°C for 3 h is recommended. Formulations containing either very low or very high levels of plasticizer can require slightly higher or lower drying temperatures respectively. Control the injection molding cycles in accordance with Practice **D3641**, using a melt temperature 25 to 35°C above the “cold point.” (The “cold point” is the lowest melt temperature at which it is possible to obtain a full shot when all other operating variables are held constant within the normal operating range.) Mold temperatures between 35 and 60°C have been found desirable. As a rule, thin-section moldings and higher hardness materials (lower plasticizer content) require higher mold temperatures.

10.3 Test specimens injection molded from cellulosic materials are subject to “overpacking” if the gate size is too large, and this can result in brittleness in the gate area as well as throughout the entire specimen. A gate size 1.5 mm square has been found to produce satisfactory test specimens.

## 11. Test Methods

11.1 Determine the properties defined by this classification system in accordance with the following methods:

11.1.1 All tests shall be performed in the standard laboratory atmosphere as defined by Practice **D618**.

11.1.2 Test specimens shall be conditioned in accordance with Procedure A of Practice **D618**.

11.1.3 *Color Visual*—Practice **D1729**.

11.1.4 *Color-Quantitative*—Practice **E308**.

11.1.5 *Plasticizer Content*—The method for plasticizer content shall be specified.

11.1.6 *Specific Gravity*—Test Methods **D792**.

11.1.7 *Tensile Stress at Yield*—Test Method **D638**, Type I test specimen, 50-mm/min testing speed.

11.1.8 *Flexural Modulus*—Test Methods **D790**, 1.27-mm/min testing speed.

11.1.9 *Impact Strength (Izod)*—Test Method A of Test Method **D256**. Specimen size: 63.5 mm long by 12.7 mm wide by 3.2 mm thick.

11.1.10 *Water Absorption*—Test Method **D570**, 24-h immersion.

NOTE 3—The ungated “tab end” (75 mm long) of a Test Method **D638**, Type I tensile bar will give comparable results and can be used if the primary specimen type is not available. Condition in accordance with Test Method **D570**.

11.1.11 *Weight Loss on Heating*—Condition test specimens, 50.8 mm in diameter or 50.8 mm wide by 63.5 mm long by 3.2 mm thick, for 48 h over anhydrous calcium chloride at 23 ± 2°C or 4 h at 70 ± 2°C.

NOTE 4—The ungated “tab end” (75 mm long) of a Test Method **D638**,

Type I tensile bar will give comparable results and can be used if the primary specimen type is not available. Weigh three specimens and place them in a circulating-air oven for 72 h at 82 ± 2°C. Support the specimens flatwise on a screen in the oven. Upon removal from the oven, cool the specimens in a desiccator over anhydrous calcium chloride to 23 ± 2°C. Weigh the specimens and calculate the weight loss on heating as a percentage of the conditioned weight as follows:

$$\text{weight loss on heating, \%} = \frac{(W_1 - W_2)}{W_1} \times 100 \quad (2)$$

where:

$W_1$  = original weight, g, after initial conditioning, and

$W_2$  = weight, g, after 72 h in oven at 82°C.

## 12. Inspection and Certification

12.1 Inspection and certification of the material supplied with reference to a specification based on this classification system shall be for conformance to the requirements specified herein.

12.2 Lot-acceptance inspection shall be the basis on which acceptance or rejection of the lot is made. The lot-acceptance inspection shall consist of plasticizer content determination and color (see Table CAP, Footnote 1, and **11.1.3**) as specified in **6.3**.

12.3 Periodic check inspection with reference to a specification based on this classification system shall consist of the tests for all requirements of the material under the specification. Inspection frequency shall be adequate to ensure that the material is certifiable in accordance with **12.4**.

12.4 Certification shall be that the material was manufactured by a process in statistical control, sampled, tested, and inspected in accordance with this classification system and that the average values for the lot meet the requirements of the classification system (line call out).

12.5 A report of test results shall be furnished when requested. The report shall consist of results of the lot acceptance inspection for the shipment, the results of the most recent periodic-check inspection, and the percent by weight of recycled plastic, as defined in Guide **D7209**, if requested.

NOTE 5—The ASTM publication *Manual on Presentation of Data and Control Chart Analysis*, 8th Edition, stock number: MNL7-8TH-EB, provides detailed information about statistical process control.

## 13. Rejection

13.1 Material that fails to conform to all the requirements of this classification system is not to be certified.

## 14. Packaging, Packing, and Marking

14.1 The provisions of Practice **D3892** apply to packaging, packing, and marking of containers for plastic materials.

## 15. Keywords

15.1 cellulose acetate propionate; classification system; line callout; plastic; recycled; specification

**TABLE CAP Detailed Physical Property Requirements**

Material: CAP (Cellulose Acetate Propionate)						Specific Gravity, Test Methods <b>D792</b>	Tensile Stress at Yield, Test Method <b>D638</b> , min, MPa	Flexural Modulus, Test Methods <b>D790</b> , min, MPa	Izod Impact Strength, Test Method <b>D256</b> , min, J/m	Water Absorption, Test Method <b>D570</b> , max, %		Weight Loss on Heating, Paragraph <b>11.1.11</b> , max, %
Group	Description	Class	Plasticizer Content <sup>A</sup> , %	Grade	Description					Weight Gain <sup>B</sup>	Soluble Loss	
01	high impact strength	1	10-25	1	injection	1.18-1.20	15	830	230	1.8	0.2	2.2
				2	extrusion	1.18-1.20	15	830	230	1.8	0.2	2.2
				0	other							
		2	8-20	1	injection	1.19-1.20	19	1000	200	2.0	0.2	2.0
				2	extrusion	1.19-1.20	19	1000	200	2.0	0.2	2.0
				0	other							
		3	6-16	1	injection	1.19-1.21	23	1170	160	2.1	0.2	1.8
				2	extrusion	1.19-1.21	23	1170	160	2.1	0.2	1.8
				0	other							
		0	other			0	other					
0	other											
02	high tensile strength	1	4-13	1	injection	1.20-1.22	29	1310	105	2.2	0.1	1.2
				2	extrusion	1.20-1.22	29	1310	105	2.2	0.1	1.2
				0	other							
		2	2-10	1	injection	1.21-1.22	34	1520	80	2.3	0.1	0.8
				2	extrusion	1.21-1.22	34	1520	80	2.3	0.1	0.8
				0	other							
00	other	0	other	0	other							
				0	other							

<sup>A</sup>The method for plasticizer content shall be specified. Limits of ±2 % shall be maintained unless a closer tolerance is practical.

<sup>B</sup>Weight gain includes soluble matter loss.

**TABLE 1 Electrical Requirements**

Property	Units	Requirements	ASTM Test Method	Practice <b>D618</b> Condition Procedure
Volume resistivity	ohm-cm	10 <sup>13</sup> min	<b>D257</b>	condition 96/23/50
		10 <sup>11</sup> min	<b>D257</b>	condition 96/23/50 + 48/50/water + 1/23/water <sup>A</sup>
Dielectric strength, short-time test	V/mm	12 800 min	<b>D149</b>	condition 96/23/50
		11 800 min	<b>D149</b>	condition 96/23/50 + 48/50/water + 1/23/water <sup>A</sup>
Dielectric strength, step-by-step test	V/mm	12 800 min	<b>D149</b>	condition 96/23/50
		11 800 min	<b>D149</b>	condition 96/23/50 + 48/50/water + 1.23/water <sup>A</sup>

<sup>A</sup>Remove from water, wipe with damp cloth, and dry with dry cloth immediately before testing.

## SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue, D1562 - 09, that may impact the use of this standard. (May 1, 2015)

(1) Added abbreviated term CAP to the title and updated **Note 5**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*