



# Standard Test Method for Oxidative Aging of Electrical Insulating Petroleum Oils by Open-Beaker Method<sup>1</sup>

This standard is issued under the fixed designation D1934; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers two procedures for subjecting electrical insulating oils to oxidative aging:

- 1.1.1 *Procedure A*, without a metal catalyst, and
- 1.1.2 *Procedure B*, with a metal catalyst.

1.2 This test method is applicable to oils used as impregnating or pressure media in electrical power transmission cables if less than 10 % of the oil evaporates during the aging procedures. It applies and is generally useful primarily in the evaluation and quality control of unused oils, either inhibited or uninhibited.

1.3 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

- [D664 Test Method for Acid Number of Petroleum Products by Potentiometric Titration](#)
- [D923 Practices for Sampling Electrical Insulating Liquids](#)
- [D924 Test Method for Dissipation Factor \(or Power Factor\) and Relative Permittivity \(Dielectric Constant\) of Electrical Insulating Liquids](#)
- [D1169 Test Method for Specific Resistance \(Resistivity\) of Electrical Insulating Liquids](#)
- [E145 Specification for Gravity-Convection and Forced-Ventilation Ovens](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.06 on Chemical Test.

Current edition approved Feb. 1, 2012. Published February 2012. Originally approved in 1962. Last previous edition approved in 2005 as D1934 – 95 (2005). DOI: 10.1520/D1934-95R12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *metal catalyst*—any metal (for example, copper) that either increases the rate of oxidation of the oil or reacts with the oxidation products to increase oil dielectric loss.

3.1.2 *oxidative aging*—exposure of oil to oxygen under certain specified conditions.

## 4. Summary of Test Method

4.1 A 300 mL volume of oil, contained in 400 mL beaker is aged for 96 h in a circulating-air oven controlled at 115°C, either with or without the presence of catalyst.

## 5. Significance and Use

5.1 Open-beaker oxidative aging methods have been used for many years in laboratories of oil companies, electrical equipment manufacturers, and electric utility companies interested in the stability of electrical insulating oils under oxidative conditions. They are particularly useful as a check on the continuity of production and shipment of insulating oils. They are also useful as process and product checks for applicable type oils.

5.2 Specification limits for oils subjected to open-beaker oxidative aging by this method are established by agreement between individual producers and consumers of applicable type oils. These properties of the oil involved in specification limits for aging stability may be measured after the oxidative aging (and sometimes before aging) by appropriate test methods such as Test Method D924, Test Method D1169, and Test Method D664.

## 6. Apparatus

6.1 *Oven*, electrically heated, thermostatically controlled, capable of maintaining a constant temperature of  $115 \pm 1^\circ\text{C}$  ( $239 \pm 2^\circ\text{F}$ ). Use an oven with a testing chamber large enough to test the anticipated number of test specimens at one time. A uniformity of temperature within  $\pm 1\%$  of the differential between oven and ambient temperatures is required. (See [Note 1](#).) Circulate air in the chamber with a low velocity fan during

the aging period. The volume and condition of the circulated air is not considered to be critical. It is recommended that the oven provide several air changes per hour, and that vapors and fumes be removed if present.

NOTE 1—Refer to Specification E145 for the measurement of the temperature uniformity of the oven.

6.1.1 *Procedure A*—For test specimens aged in the absence of a metal catalyst the choice of a suitable oven design is not critical. Either fixed- or rotating-shelf stage ovens of satisfactory thermal quality may be used, although a rotating-shelf oven is preferred. If a fixed-shelf oven is used, it is recommended that test specimen positions within the oven be changed periodically (for example, at daily intervals) to minimize the effects of any temperature differentials that may exist.

6.1.2 *Procedure B*—When a metal catalyst, such as copper, is used, the rate of oxidation usually is increased, and the procedure becomes sensitive to movement of the oil past the metal surface. An aging oven equipped with a slowly rotating shelf has been adopted for uniformity when a metal catalyst is used.<sup>3</sup> Other oven designs having satisfactory thermal quality and a rotating shelf may be used.

6.2 *Beaker*, borosilicate glass, low-form, of 400-mL capacity. The approximate dimensions of a suitable beaker are 100 mm in depth and 70 mm inside diameter. Clean the beakers used in the aging test, and thoroughly dry before use. One recommended cleaning procedure is as follows: Remove residual oil from the beaker by rinsing in mineral spirits or equivalent. Rinse thoroughly with an acid cleaning solution consisting of 3 parts nitric acid (HNO<sub>3</sub>) to 1 part sulfuric acid (H<sub>2</sub>SO<sub>4</sub>). Remove traces of cleaning solution by carefully rinsing with distilled water followed by rinsing in acetone and air drying. (Ammonium persulfate is also a suitable cleaning reagent.)<sup>4</sup>

## 7. Reagents and Materials

7.1 *Purity of Reagents*—Use reagent grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>5</sup>

7.2 *Hydrochloric Acid*, 10 % volume solution from concentrated hydrochloric acid.

7.3 *Nitric Acid*—Concentrated nitric acid (HNO<sub>3</sub>).

7.4 *Sulfuric Acid*—Concentrated sulfuric acid (H<sub>2</sub>SO<sub>4</sub>).

<sup>3</sup> A suitable type oven is described in "Life Test for Transformer Oils," Appendix to Report of Committee D09 on Electrical and Electronic Insulating Materials, *Proceedings*, ASTM, Vol 27, Part I, 1927 pp. 541–549.

<sup>4</sup> The sole source of supply of ammonium persulfate (available as Nochromix) known to the committee at this time is Interox Corp., 3 Strathmore Rd., Natick, MA 01760. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

<sup>5</sup> *Reagent Chemicals*, American Chemical Society Specifications, American Chemical Society, Washington, DC. For Suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

7.5 *Metal Catalyst* with 15 cm<sup>2</sup> of clean surface available for exposure to the oil for use in Procedure B. If the metal catalyst is copper wire, it is convenient to wind an appropriate length into a loose hank which is then cleaned to remove oil, oxide, and the other extraneous matter. The metal catalyst may also be used in the form of strips, but the strips require special attention to maintain the desired amount of exposed surface. One good method of cleaning copper hanks is to immerse the hank for 30 s in a 10 % solution of hydrochloric acid (HCl), after which the hank is rinsed three times in distilled water then in acetone and air dried. The cleaned hank should be handled with clean tongs.

## 8. Procedure A—Aging Without a Metal Catalyst

8.1 Obtain the oil sample in accordance with Practices D923.

8.2 Adjust the oven temperature to 115 ± 1°C.

8.3 Pour without preheating 300 mL of the test specimen to be tested into a clean dry 400-mL beaker. Oil depth in the beaker will be approximately 75 mm. Measure the mass of the oil before test.

8.4 Place the beaker containing the test specimen in the preheated oven. To minimize temperature fluctuation it is desirable to place all test specimens in the oven at the same time.

8.5 Start the oven shelf into rotation if the oven is so equipped.

8.6 Remove the test specimen from the oven at the end of the 96-h aging period and measure the mass of the oil.

8.7 Determine the condition of the aged test specimen by means of appropriate test methods. The condition of an unaged test specimen usually should also be determined at the same time for comparison.

## 9. Procedure B—Aging with a Metal Catalyst

9.1 Proceed exactly as in Procedure A (Section 8) except before placing the beaker in the oven add the metal catalyst to the oil specimen in the beaker, with the specified amount of surface exposed to the oil.

9.2 Measure the mass of the oil plus catalyst before and after the test.

## 10. Report

10.1 Report the following information:

10.1.1 Designation of this test method (D1934),

10.1.2 Whether or not a metal catalyst was used (Procedure A or B) and the nature and form of the metal catalyst, if used,

10.1.3 Test specimen identification,

10.1.4 Values of the property or properties measured on the aged (and unaged) test specimens, and

10.1.5 Designations of the test methods used to determine the condition of the oil test specimens.

10.1.6 The measured change in mass percent of the oil to validate the test (less than 10 % evaporation).

## 11. Precision and Bias<sup>6</sup>

11.1 *Precision*—The precision of the open-beaker oxidative aging defined by this test method has not yet been adequately defined in accordance with Practice E177. However, precision estimates for both single-laboratory repeatability and multi-laboratory reproducibility of changes in oil dissipation factor (power factor) due to open-beaker oxidative aging are available from a 1958–59 round robin with ten participating laboratories.

11.2 In the case of four naphthenic insulating oils with different viscosities (55, 100, 760, and 2200 SUS at 100°F, and 38, 39, 60, and 105 SUS, respectively, at 210°F) with and without 2.8 cm<sup>2</sup> of copper wire catalyst, random errors were proportional to the ratio,  $Q$ :

$$Q = \frac{\text{dissipation factor after aging}}{\text{dissipation factor before aging}}$$

11.2.1 The data were normalized by a logarithmic transformation.

---

<sup>6</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D27-1007.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*

11.3 *Repeatability*—The standard deviation of the quantity  $\log Q$  has been estimated to be 0.07 (coefficient of variation of  $Q = 18\%$ ) for duplicate aging tests run at the same time in a given oven in the same laboratory. The standard deviation of  $\log Q$  has been estimated to be 0 (coefficient of variation of  $Q = 60\%$ ) for duplicate aging tests run at different times in the same laboratory.

11.4 *Reproducibility*—The standard deviation of the quantity  $\log Q$  has been found to be 0.37 (coefficient of variation of  $Q = 135\%$ ) for duplicate aging tests run in different laboratories.

11.5 *Bias*—Since there is no accepted reference material suitable for determining the bias for the procedure in this test method for measuring the true value of the property involved, no statement on bias is being made.

## 12. Keywords

12.1 aging; electrical insulating oil; open beaker test; oxidative; petroleum