



# Standard Test Method for Acetaldehyde Content of Vinyl Acetate<sup>1</sup>

This standard is issued under the fixed designation D2191; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This test method covers the determination of trace quantities of acetaldehyde, in the range from 0.00 to 0.05 %, contained in 99 % grade vinyl acetate.

1.2 For purposes of determining conformance of an observed or a calculated value using this test method to relevant specifications, test result(s) shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E29.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 For hazard information and guidance, see the supplier’s Material Safety Data Sheet.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements see Section 8.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D1193 Specification for Reagent Water

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

## 3. Summary of Test Method

3.1 The acetaldehyde present in the specimen is reacted with a measured excess of sodium bisulfite. The amount of sodium bisulfite consumed, determined by titrating the excess

with a standard iodine solution, is a measure of the acetaldehyde present in the vinyl acetate.

## 4. Significance and Use

4.1 This test method provides a measurement of acetaldehyde content in vinyl acetate. The results of these measurements can be used for specification acceptance.

## 5. Interference

5.1 Ketones and other aldehydes, if present, cause a positive interference.

## 6. Apparatus

6.1 *Buret*, 50-mL capacity, graduated in 0.1-mL subdivisions, with a funnel or flared top and a ground-glass stopcock.

6.2 *Erlenmeyer Flask*, 500-mL capacity, glass-stoppered.

6.3 *Pipet*, 50-mL capacity.

6.4 *Pipet*, 100-mL capacity.

## 7. Reagents

7.1 *Purity of Reagents*—Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>3</sup> Other grades may be used provided that it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV of Specification D1193.

7.3 *Iodine, Standard Solution (0.1 N)*—Dissolve 35.0 g of potassium iodide (KI) and 13.0 g of resublimed iodine in water, and dilute to 1 L with water. Store this solution in a dark bottle and standardize each day, as required, against a standard 0.1 N sodium thiosulfate ( $\text{Na}_2\text{S}_2\text{O}_3$ ) solution. (See standardization procedure, 9.3 and 9.4.)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved June 1, 2012. Published July 2012. Originally approved in 1963. Last previous edition approved in 2006 as D2191–06. DOI: 10.1520/D2191-06R12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>3</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

\*A Summary of Changes section appears at the end of this standard

7.4 *Potassium Iodate* ( $\text{KIO}_3$ ), primary standard.

7.5 *Sodium Bisulfite Solution (0.44 %)*—Dissolve 4.4 g of sodium metabisulfite ( $\text{Na}_2\text{S}_2\text{O}_5$ ) in 1 L of water. This solution should be prepared fresh daily or just before using.

7.6 *Sodium Thiosulfate, Standard Solution (0.1 N)*—Weigh to 0.1 g 24.8 g of sodium thiosulfate ( $\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$ ) crystals and dissolve in 500 mL of water. Dilute this solution to 1 L with water. Add 0.5 mL of chloroform per litre of solution as a preservative, and store in a clean dark bottle. This solution should be standardized weekly, as required, against potassium iodate ( $\text{KIO}_3$ ). (See standardization procedure, 9.1 and 9.2.)

7.7 *Starch Indicator*—Make a paste of 6 g of powdered soluble starch in water, and dilute to 1 L with water, stirring to produce a suspension. While stirring, add 20 g of potassium hydroxide (KOH) pellets, and continue stirring until the KOH is dissolved. Let stand for 2 h and add 27.5 mL of hydrochloric acid (HCl). Adjust the mixture to a pH of  $6.0 \pm 0.1$  by adding small increments of HCl or KOH as required. Add 6 mL of glacial acetic acid as a preservative.

7.8 *Sulfuric Acid (1 N)*—Place approximately 700 to 800 mL of water in a 1-L volumetric flask. Add slowly and with constant stirring 27.2 mL of concentrated sulfuric acid ( $\text{H}_2\text{SO}_4$ , sp gr 1.84). Allow the solution to cool to room temperature, and adjust the volume to the 1-L mark with additional water.

## 8. Hazards

8.1 Vinyl acetate is flammable and hazardous; use special precautions when handling it. Avoid eye and skin contact and the inhalation of its vapors.

## 9. Standardization

9.1 To standardize the 0.1 N  $\text{Na}_2\text{S}_2\text{O}_3$  solution, first dry for 6 h approximately 3 g of the  $\text{KIO}_3$  primary standard in a drying oven maintained at a temperature of  $110 \pm 5^\circ\text{C}$ . Place the dried  $\text{KIO}_3$  in a desiccator until cool. Weigh 0.14 to 0.15 g of the dried  $\text{KIO}_3$  to 0.1 mg, and transfer to a 250-mL Erlenmeyer flask. Add 25 mL of water to the flask to dissolve the  $\text{KIO}_3$ . To this solution, add 2 g of KI crystals and 10 mL of the 1 N  $\text{H}_2\text{SO}_4$ , and thoroughly mix. Fill a 50-mL buret with the  $\text{Na}_2\text{S}_2\text{O}_3$  solution to be standardized and titrate the  $\text{KIO}_3$  solution until the brown color of the iodine has been reduced to a pale yellow color. At this point, add 0.5 mL of the starch indicator, and continue the titration until the color changes sharply from blue to colorless.

NOTE 1—When titrating excess iodine with sodium thiosulfate, the starch indicator should be added only when near the end point as noted by the fading of the brown color of the iodine. Starch reacts with iodine in the presence of iodide to form an intensely blue color absorption complex, and if added to a solution containing free iodine, a stable complex is formed, that would give erroneous results.

9.2 Calculate the normality  $N$  of the  $\text{Na}_2\text{S}_2\text{O}_3$  solution as follows:

$$N = (W \times P) / (V \times 0.035669)$$

where:

$W$  = weight of  $\text{KIO}_3$  used, g

$P$  = correction for purity of  $\text{KIO}_3$  standard, and

$V$  = volume of  $\text{Na}_2\text{S}_2\text{O}_3$  required for titration of the  $\text{KIO}_3$ , mL.

9.3 Fill the funnel-topped 50-mL buret with the 0.1 N iodine solution to be standardized. Measure approximately 40 mL of the iodine solution into a 250-mL Erlenmeyer flask, and read the buret to the nearest 0.1 mL. Add approximately 50 mL of water to the flask containing the iodine solution, and titrate with the standardized 0.1 N  $\text{Na}_2\text{S}_2\text{O}_3$  solution as described in 9.1.

9.4 Calculate the normality  $N_1$  of the iodine solution as follows:

$$N_1 = (V \times N) / V_1 \quad (1)$$

where:

$V$  = volume of  $\text{Na}_2\text{S}_2\text{O}_3$  required for titration of the iodine solution, mL,

$N$  = normality of the  $\text{Na}_2\text{S}_2\text{O}_3$  solution, and

$V_1$  = volume of iodine solution used for standardization, mL.

## 10. Procedure

10.1 Pipet 50 mL of  $\text{Na}_2\text{S}_2\text{O}_5$  solution (7.5) into each of two glass-stoppered 500-mL Erlenmeyer flasks. Add approximately 25 g of clean chipped ice to each flask and into one of the flasks pipet 100 mL of the sample. Grease the stoppers and place the flasks on a mechanical shaker, allowing them to shake for  $10 \pm 1$  min.

10.2 At the end of the 10-min reaction period, add 0.5 mL of starch indicator to the blank and specimen. Titrate the excess sodium bisulfite with the standard iodine solution. The end point is when the first permanent blue color is obtained.

NOTE 2—In order to maintain good drainage of the iodine solution, care should be taken to always use a clean buret which should be filled with the iodine solution just before beginning each series of titrations.

## 11. Calculation

11.1 Calculate the weight percent aldehyde content of the vinyl acetate, as acetaldehyde,  $A$ , as follows:

$$A = [((B - V_2) \times N_1 \times 0.02202) / (D \times M)] \times 100 \quad (2)$$

where:

$B$  = volume of iodine required for the titration of the blank, mL,

$V_2$  = volume of iodine required for titration of the specimen, mL,

$N_1$  = normality of the iodine solution,

$D$  = specific gravity of the sample, and

$M$  = volume of sample used, mL.

## 12. Report

12.1 Report the following information: weight percent acetaldehyde to the nearest 0.001 %. Duplicate runs that agree within 0.003 % are acceptable for averaging (95 % confidence level).

## 13. Precision and Bias

13.1 *Precision*—The following criteria should be used for judging the acceptability of results at the 95 % confidence level:

13.1.1 *Repeatability*—Two results, each the mean of duplicate determinations, obtained by the same analyst should be considered suspect if they differ by more than 0.006 % absolute.

13.1.2 *Reproducibility*—Two results, each the mean of duplicate determinations, obtained by analysts in different laboratories should be considered suspect if they differ by more than 0.008 % absolute.

NOTE 3—The above precision estimates are based upon an interlaboratory study on four samples of vinyl acetate containing 0.01, 0.02, 0.03,

and 0.05 % acetaldehyde. Two analysts in each of three different laboratories performed duplicate determinations on each sample on two successive days making a total of 96 determinations.

13.2 *Bias*—Bias has not been determined for this test method because there is no appropriate standard available.

#### 14. Keywords

14.1 acetaldehyde ; vinyl acetate

### SUMMARY OF CHANGES

Committee D01.35 has identified the location of selected changes to this standard since the last issue (D2191 – 97 (2001)) that may impact the use of this standard. (Approved April 1, 2006.)

(1) Added reference to Practice E29 in the scope section.

(2) Added Practice E29 to list of Referenced Documents.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*