



Designation: D2219 – 17

Standard Specification for Poly(Vinyl Chloride) Insulation for Wire and Cable, 60°C Operation¹

This standard is issued under the fixed designation D2219; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers a thermoplastic insulation of poly(vinyl chloride) or the copolymer of vinyl chloride and vinyl acetate.

1.2 This insulation is recommended for use at conductor temperatures not in excess of 60°C in wet or dry locations at a maximum voltage rating of 600 V for power and control circuits.

1.3 In many instances, the insulation material cannot be tested unless it has been formed around a conductor or cable. Therefore, tests are done on insulated wire or cable in this specification solely to determine the relevant property of the insulation material and not to test the conductor or completed cable.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4.1 In some cases (including the title), temperatures are described in degrees Celsius only.

2. Referenced Documents

2.1 ASTM Standards:²

- [D1711 Terminology Relating to Electrical Insulation](#)
- [D2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable](#)
- [D2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable](#)
- [G153 Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials](#)
- [G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials](#)

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Electrical Insulating Materials.

Current edition approved March 1, 2017. Published March 2017. Originally approved in 1963. Last previous edition approved in 2011 as D2219 – 11. DOI: 10.1520/D2219-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology [D1711](#).

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *aging (act of), n*—exposure of materials to air or oil at a temperature and a time as specified in [Table 1](#).

4. Physical Properties

4.1 The insulation shall conform to the requirements for physical properties prescribed in [Table 1](#).

5. Electrical Requirements

5.1 Perform the ac voltage, insulation resistance, and dc voltage tests in that order when any of these tests are required. The sequence for other testing is not specified.

5.2 *AC Voltage Test*—Test the insulated conductor at the ac withstand voltage as specified in [Table 2](#). Unless otherwise specified, omit this test if the dc withstand voltage test described in [5.4](#) is performed.

5.2.1 For cables or conditions of service where mechanical stresses govern, such as in vertical risers, it is possible that the minimum conductor sizes in [Table 2](#) are not strong enough.

5.2.2 The thicknesses given in [Table 2](#) apply to aerial cables and to single conductors installed in conduits above ground and to the individual conductors of all multiple-conductor cables having a common jacket metallic sheath or protective covering over the assembly, except as shown in [5.2.2.1](#).

5.2.2.1 For single-conductor cables for installation in underground ducts or direct earth burial, add 15 mils (0.38 mm) to the insulation thicknesses given in [Table 2](#) when such cables do not have a thermoplastic jacket or metallic sheath over the assembly.

5.2.3 Where the thickness of the insulation is increased for mechanical reasons or for special service conditions, determine the test voltage in [Table 2](#) by the size of the conductor and the rated voltage.

5.3 Insulation Resistance:

5.3.1 Insulated conductors in sizes AWG 26 (0.13 mm²) and larger shall have an insulation resistance of at least that corresponding to a constant of 500 M Ω -1000 ft at 60°F (15.6°C).

*A Summary of Changes section appears at the end of this standard

TABLE 1 Physical Properties Requirements

Unaged Requirements:	
Tensile strength, min, psi (MPa)	1500 (10.3)
Elongation at rupture, min, %	100
Aged Requirements:	
After air oven test at 100± 1°C for 168 h:	
Tubular Specimens—up to size AWG 6 (13.3 mm ²)	
Tensile strength, min, % of unaged value	65
Elongation, min, % of unaged value	65
Buffed die-cut Specimens—sizes AWG 6 and larger	
Tensile strength, min, % of unaged value	65
Elongation, min, % of unaged value	45
Heat shock, 121 ± 1°C	no cracks
Heat distortion, 121 ± 1°C, max, %	50
Vertical flame test, after five 15-s applications	passes
Oil resistance test:	
After oil immersion at 70 ± 1°C for 4 h:	
Tubular Specimens—up to size AWG 6 (13.3 mm ²)	
Tensile strength, min, % of unaged value	85
Elongation, min, % of unaged value	85
Buffed die-cut Specimens—sizes AWG 6 and larger	
Tensile strength, min, % of unaged value	80
Elongation, min, % of unaged value	60
Cold bend test, -10 ± 1°C for 1 h	no cracks

TABLE 2 Conductor Sizes, Insulation Thicknesses, and Test Voltages for Poly(Vinyl Chloride)-Insulated Control and Power Cables

Rated Circuit Voltage, Phase-to-Phase, V	Power and Control Cable:		AC Test Voltage, kV
	Conductor Size, AWG or cmil (mm ²)	Insulation Thickness, mils (mm)	
0 to 300	26 to 16 (0.13 to 1.31)	15 (0.38)	1.0
0 to 600	18 to 16 (0.82 to 1.31)	30 (0.76)	1.5
	14 to 9 (2.08 to 6.63)	45 (1.14)	3.0
	8 to 2 (8.37 to 33.6)	60 (1.52)	3.5
	1 to 0000 (42.4 to 10.7)	80 (2.03)	4.0
	225 000 to 500 000 (140 to 253)	95 (2.41)	5.0
	501 000 to 1 000 000 (254 to 507)	110 (2.79)	6.0
	Over 1 000 000 (507)	125 (3.18)	7.0

5.3.2 If the temperature at the time measurement was made differs from 60°F (15.6°C), correct the insulation resistance to 60°F by multiplying the measured value by the proper correction factor from Table 1, Temperature Correction Factors for Insulation Resistance at 60°F, of Methods D2633.

5.4 DC Voltage Test—Upon completion of the insulation resistance test, test each non-shielded insulated conductor for 5 min at a dc withstand voltage which is three times the ac test

voltage specified in Table 2. Unless otherwise specified, omit this test if the ac withstand voltage test described in 5.2 is performed.

5.5 Accelerated Water Absorption—The insulation shall meet the requirements in Table 3.

5.6 Dielectric Strength Retention— The insulation shall be capable of meeting a dielectric strength retention of at least 50 % of the original dielectric strength when tested at a temperature of 50 ± 1°C.

6. Thickness of Insulation

6.1 The average thickness of the insulation shall be at least that prescribed in Table 2. The minimum thickness shall be at least 90 % of the thickness prescribed in Table 2.

7. Workmanship, Finish, and Appearance

7.1 Apply the insulation directly to the surface of the conductor or conductor covering and obtain a tight fit to that surface.

7.2 Repairs and Joints—When making repairs or joints in the insulation, do the work in such a manner that the repaired part of the joint, and all parts affected by the process, meet the same electrical tests as the remainder of the insulation and maintain the limitations on the thickness specified in Section 6.

8. Sampling

8.1 Sample the insulation in accordance with Methods D2633.

9. Test Methods

9.1 Test the insulation in accordance with Methods D2633.

10. Keywords

10.1 accelerated water absorption; ac voltage test; dc voltage test; insulation resistance; poly (vinyl chloride) insulation; 60°C poly (vinyl chloride) insulation; thickness

TABLE 3 Accelerated Water Absorption Requirements

Electrical method 60 Hz at 50 ± 1°C:	
Permittivity after 24 h, max	10.0
Increase in capacitance, max, %:	
1 to 14 days	10.0
7 to 14 days	5.0

APPENDIX
X1. Optional Weatherometer Test
(Nonmandatory Information)

X1.1 The optional weather resistance shall be in accordance with Practice **G153**, using cycle 1 for Carbon Arc testing, or in accordance with ASTM Practice **G155** using cycle 1 for Xenon arc testing.

X1.2 Sample the insulation in accordance with Test Methods **D2633**.

X1.3 The insulation shall conform to the requirements for physical properties prescribed in **Table X1.1**, below.

TABLE X1.1 Weatherometer Physical Properties Requirements

Weather Resistance Test (Optional) After 720 H in Either Xenon or Carbon Arc Exposure	
Tubular Specimens—up to size AWG 6 (13.3 mm ²)	
Tensile strength, min, % of unaged value	80
Elongation, min, % of unaged value	80
Buffed die-cut Specimens—sizes AWG 6 and larger	
Tensile strength, min, % of unaged value	80
Elongation, min, % of unaged value	80

SUMMARY OF CHANGES

Committee **D09** has identified the location of selected changes to this standard since the last issue (D2219 – 11) that may impact the use of this standard. (Approved March 1, 2017.)

- (1) Added Practices **G153** and **G155** to Referenced Documents (Section 2). (2) Added **Appendix X1**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/