



# Standard Specification for Sulfur Hexafluoride<sup>1</sup>

This standard is issued under the fixed designation D2472; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This specification applies to sulfur hexafluoride for use as an electrical insulating gas.

NOTE 1—This specification is intended to apply only to gas as purchased. However, the test methods referred to in this standard may be useful in the evaluation of in-service or used gas. Test Method D2284 may be particularly helpful since many sulfur hexafluoride decomposition products are acidic. Test Method D2284 should not be used to evaluate the total amount of sulfur hexafluoride decomposition nor to identify contaminant species. This can only be done by gas chromatography and similar instrumental techniques.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D2029 Test Methods for Water Vapor Content of Electrical Insulating Gases by Measurement of Dew Point

D2284 Test Method for Acidity of Sulfur Hexafluoride

D2685 Test Method for Air and Carbon Tetrafluoride in Sulfur Hexafluoride by Gas Chromatography

## 3. Detail Requirements

3.1 Sulfur hexafluoride for use as an electrical insulation material shall conform to the requirements prescribed in Table 1.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.02 on Gases and Non-Mineral Oil Liquids.

Current edition approved Oct. 1, 2015. Published November 2015. Originally approved in 1966. Last previous edition approved in 2014 as D2472 – 00(2014). DOI: 10.1520/D2472-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 4. Sampling

4.1 Withdraw a sample of sulfur hexafluoride from either the vapor space or liquid phase of the container.

4.2 For samples collected from the liquid phase the user must ascertain whether or not the cylinder valve is attached to a dip tube. Sample cylinders equipped with a dip tube in an upright position. Invert cylinders not equipped with a dip tube for sampling to ensure that the sample is obtained from the liquid phase of the cylinder.

4.3 Analyses may be performed on vapor space samples for routine or preliminary testing. If the vapor phase analysis indicates that impurities are not within specification, a liquid phase sample should be obtained and analysed. The liquid phase comprises most of the material in the container and is more representative of the overall composition of the SF<sub>6</sub> in the container. When a discrepancy exists between vapor and liquid phase analyses, the liquid phase analysis shall govern, unless otherwise agreed to by purchaser-seller agreement.

## 5. Precautions

5.1 Refer to the section titled Interferences in Test Method D2029.

## 6. Test Methods

6.1 *Water Content*— Test Method D2029.

6.2 *Hydrolyzable Fluorides*—Determine the acidity, expressed as HF, in accordance with Test Method D2284.

6.3 *Air*—Determine the amount of noncondensable gases, expressed as nitrogen, by gas chromatographic analysis in accordance with Test Method D2685.

6.4 *Carbon Tetrafluoride*—Determine the amount of carbon tetrafluoride by gas chromatographic analysis in accordance with Test Method D2685.

6.5 *Assay*—Assay shall be by difference, after impurity content has been determined.

## 7. Keywords

7.1 electrical insulating gas; sulfur hexafluoride

**TABLE 1 Detail Requirements for Sulfur Hexafluoride <sup>A</sup>**

Requirements	Property
Water content, max dew point, °C	-62 <sup>B</sup>
Hydrolyzable fluorides, expressed as HF acidity, max, mL/kg	0.3
Air, expressed as N <sub>2</sub> , max, weight %	0.05
Carbon tetrafluoride, max, weight %	0.05
Assay, min, weight %	99.8

<sup>A</sup> By agreement between the purchaser and the manufacturer, analysis may be required and limits established for properties, elements, or compounds not specified in the table of requirements.

<sup>B</sup> Corresponds to a water content of 0.0083 mg/L (0.0008 % by volume) at 1.01325 × 10<sup>5</sup> Pa.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*