



Designation: D2527 – 83 (Reapproved 2017)

Standard Specification for Rubber Seals—Splice Strength¹

This standard is issued under the fixed designation D2527; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the strength and appearance of the splice in vulcanized rubber-seal material of any size, type, or cross-sectional shape.

1.2 Many types and varieties of seals are used in services of all degrees of severity. In some instances, hollow tubing is spliced and used as a seal. It is also possible to have seals of irregular cross sections, or made of polymers which, due to their nature, or not conducive to a high-strength splice, although they will perform satisfactorily in their intended application.

1.3 Seals are exposed in service to a wide variety of media at various temperatures. The effect of such media on the spliced area must be considered. Details of the test procedures to evaluate the effect of the media shall be agreed upon by the purchaser and seller as part of the purchase contract.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee D11 on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee D11.37 on Coated Fabrics, Rubber Threads and Seals.

Current edition approved May 1, 2017. Published July 2017. Originally approved in 1966. Last previous edition approved in 2011 as D2527 – 83 (2011). DOI: 10.1520/D2527-83R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension](#)

3. Classification

3.1 In order to provide for the various types of seals and requirements, three classes of splices have been established:

3.1.1 *Class 1* covers splices in seals not having a solid cross section but an irregular cross section, of a polymer not conducive to a high-strength splice, or for moderate service requirements.

3.1.2 *Class 2* covers splices in solid seals of a shape and composition conducive to high-strength splices. This class covers applications requiring high-splice strength or service requirements.

3.1.3 *Class 3* covers splices in round solid seals of a composition conducive to extra-high-strength splices. This class covers applications requiring extra-high-splice tensile and bend strength due to difficult service requirements. Class 3 tests of seals in other than round shapes shall be agreed upon by the purchaser and manufacturer using this specification as a guide.

3.2 In the event that an application requires special consideration and values, these values can be indicated on the part print, using this specification as a guide.

4. Workmanship

4.1 Upon visual inspection, the splice shall not show any signs of separation.

5. Physical Requirements

5.1 When tested in accordance with the procedure outlined in Section 7, the splice shall meet the following requirements:

	Class 1	Class 2	Class 3 ^A
Ultimate elongation for the seal area, %	20	50	100

^AIn qualitative nondestructive test, Class 3 seals shall also meet the requirements in 7.2.3 and 7.2.4.

6. Significance and Use

6.1 These tests are used quantitatively, for evaluation, approval, and as a referee method. Also these tests are used qualitatively for quality control purposes.

7. Test Methods

7.1 *Quantitative Destructive Test:*

7.1.1 The method described herein is for a quantitative-type destructive test to be used for relative evaluation, approval, and as a referee method in the event of a dispute.

7.1.2 When the dimensions of the seal permit it, prepare elongation specimens in accordance with Test Methods **D412** in such a manner that the splice area shall fall within the test area (Dimension L of Fig. 2, Test Methods **D412**). When a bias-cut splice is made, cut the elongation specimen from the seal in such a manner that the “line of splice” shall run straight across the test specimen and perpendicular to the edges of the width of the test specimen (Dimension L of Fig. 2, Test Methods **D412**).

7.1.3 In the event that the seal cross section is too small to prepare a suitable standard specimen, employ the same method normally used to establish the ultimate tensile and elongation of the seal to establish the elongation of the splice.

7.2 *Qualitative Nondestructive Test:*

7.2.1 For a nondestructive type test such as used for production quality control, stretch the spliced area of the seal itself. Determine the elongation of the joints by measuring the separation of two marks placed 75 mm (3 in.) apart with the splice in the center of the marked area.

7.2.2 The minimum required elongation for the nondestructive seal test shall be as indicated in Section 5, or on the part print.

7.2.3 Class 3 seals while elongated 100 % shall be rotated in the splice area for a minimum of 180° in each direction.

7.2.4 Class 3 seals in the unstretched splice area shall be subjected to bend test—a maximum of 270° and a minimum of 180°. The rod diameter used to bend the gasket shall be equal to the cross-sectional diameter of the gasket.

8. Precision and Bias

8.1 A precision and bias statement is not necessary for this specification as it is a listing of material quality criteria.

9. Keywords

9.1 rubber seals; splice strength

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>