



Standard Test Method for Ignition Loss of Cured Reinforced Resins¹

This standard is issued under the fixed designation D2584; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the ignition loss of cured reinforced resins. This ignition loss can be considered to be the resin content within the limitations of 4.2.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard is used to measure and describe the response of composite material to heat under controlled conditions, but does not by itself incorporate all of the factors required for fire hazard or fire assessments of the composite materials under actual fire conditions.*

1.4 *Fire testing is inherently hazardous. Adequate safeguards for personnel and property shall be employed in conducting these tests.*

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of whoever uses this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

D618 Practice for Conditioning Plastics for Testing

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Summary of Test Method

3.1 The specimen contained in a crucible is ignited and allowed to burn until only ash and carbon remain. The

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.18 on Reinforced Thermosetting Plastics.

Current edition approved Oct. 15, 2011. Published November 2011. Originally approved in 1967. Last previous edition approved in 2008 as D2584 - 08. DOI: 10.1520/D2584-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

carbonaceous residue is reduced to an ash by heating in a muffle furnace at 565°C (1050°F), cooled in a desiccator, and weighed.

4. Significance and Use

4.1 This test method can be used to obtain the ignition loss of a cured reinforced resin sample. This test method can also be used to examine the fiber architecture of pultruded structural shapes.

4.2 If only glass fabric or filament is used as the reinforcement of an organic resin that is completely decomposed to volatile materials under the conditions of this test and the small amount of volatiles (water, residual solvent) that are potentially present are ignored, the ignition loss can be considered to be the resin content of the sample.

4.2.1 This test method does not provide a measure of resin content for samples containing reinforcing materials that lose weight under the conditions of the test or containing resins or fillers that do not decompose to volatile materials released by ignition.

5. Apparatus

5.1 *Crucible*, platinum or porcelain, approximately 30-mL capacity.

5.2 *Electric Muffle Furnace*, capable of maintaining a temperature of 565 ± 28°C (1050 ± 50°F).

6. Test Specimen

6.1 A minimum of three specimens shall be tested for each sample.

NOTE 2—It is often convenient to use samples obtained from specimens that have been tested for mechanical properties such as flexural or tensile strength. Specimens obtained from these samples must be dry and the fractured areas removed, leaving square, unfrayed faces, before being weighed and ignited.

6.2 The specimen shall weigh approximately 5 g with a maximum size of 2.5 by 2.5 cm by thickness (1 by 1 in. by thickness).

NOTE 3—Materials that have gross differences in the ratio of resin to reinforcement within an area as small as 2.5 by 2.5 cm (1 by 1 in.) may require a larger specimen area than that listed in 6.2. If larger specimens

*A Summary of Changes section appears at the end of this standard

are utilized, it will be necessary to cut into approximately 2.5 by 2.5-cm (1 by 1-in.) pieces and place in a crucible of sufficient size to contain the specimen.

7. Conditioning

7.1 *Conditioning*—Condition the test specimens at $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 10\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618 for those tests where conditioning is required. In cases of disagreement, the tolerances shall be $\pm 1^\circ\text{C}$ ($\pm 1.8^\circ\text{F}$) and $\pm 5\%$ relative humidity. The conditioning is not required if the test is only performed to examine the fiber architecture.

7.2 *Test Conditions*—Conduct tests in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 10\%$ relative humidity, unless otherwise specified in the test methods or in the specification. In cases of disagreement, the tolerances shall be $\pm 1^\circ\text{C}$ ($\pm 1.8^\circ\text{F}$) and $\pm 10\%$ relative humidity.

8. Procedure

8.1 Heat a crucible at 500 to 600°C for 10 min or more. Cool to room temperature in a desiccator and weigh to the nearest 1.0 mg. The desiccator is not required if the test is performed only to examine the fiber architecture.

8.2 Place the specimen in the crucible and weigh to the nearest 1.0 mg. Heat the crucible and specimen in a bunsen flame until the contents ignite. Maintain such a temperature that the specimen burns at a uniform and moderate rate until only ash and carbon remain when the burning ceases.

NOTE 4—It is not absolutely necessary to ignite the specimen in a bunsen flame. Instead the crucible and contents can be placed in a muffle furnace at a temperature lower than 565°C and ignited. Care must be taken that the ignition does not proceed so rapidly that there will be a mechanical loss of the noncombustible residue.

8.3 Heat the crucible and residue in the muffle furnace at $565 \pm 28^\circ\text{C}$ ($1050 \pm 50^\circ\text{F}$) until all carbonaceous material has disappeared (Note 5). Cool the crucible to room temperature in a desiccator and weight to the nearest 1.0 mg.

NOTE 5—The time for the carbonaceous residue to disappear is dependent largely on the specimen geometry. It can be up to 6 h but is usually much less.

8.4 Bring the crucible and residue to constant weight within 1.0 mg.

9. Calculations

9.1 Calculate the ignition loss of the specimen in weight percent as follows:

$$\text{Ignition loss, weight \%} = [(W_1 - W_2)/W_1] \times 100 \quad (1)$$

where:

W_1 = weight of specimen, g, and
 W_2 = weight of residue, g.

9.2 Average the 3 specimen values to obtain the sample average.

$$s = \sqrt{[\sum X^2 - n(\bar{X})^2]/(n - 1)} \quad (2)$$

where:

s = estimated standard deviation,
 X = value of a single observation,
 n = number of observations,
 \bar{X} = arithmetic mean of the set of observations.

9.3 Subtract the lowest specimen ignition loss from the highest specimen ignition loss for the sample and report as the ignition loss range.

10. Report

10.1 Report the following information:

10.1.1 Complete identification of the material.

10.1.2 The ignition loss, weight percent of the sample, and standard deviation. If only glass reinforcement and organic resin were present, the ignition loss can be considered to be the resin content.

10.1.3 Observations in regard to any irregularities noted in the physical properties of the residue, such as melting.

11. Precision and Bias

11.1 Table 1 is based on a round robin conducted in 2001 in accordance with Practice E691, involving two materials tested by seven laboratories (six for pultruded rod). For each material, all the samples were prepared at one source, but the individual specimens were prepared at the laboratories which tested them. Each test result was the average of three individual determinations. Each laboratory obtained two test results for each material. (Warning—The explanation of “r” and “R” in 11.2 and 11.3 are only intended to present a meaningful way of considering the approximate precision of this test method. The data in Table 1 should not be applied to acceptance or rejection of materials, as these data apply only to the materials tested in the round robin and are unlikely to be rigorously representative of other lots, formulations, conditions, materials, or laboratories. Users of this test method should apply the principles outlined in Practice E691 to generate data specific to their materials and laboratory (or between specific laboratories). The principles of 11.2-11.2.3 would then be valid for such data.)

11.2 *Concept of “r” and “R” in Table 1*—If S_r and S_R have been calculated from a large enough body of data, and for test results that were averages from testing two specimens for each test result, then:

TABLE 1 Ignition Loss of Cured Reinforced Resin

Material	Values expressed in % loss				
	Average	S_r^A	S_r^B	R^C	R^D
Glass Reinforced Laminate	36.30	2.57	2.57	7.21	7.21
Pultruded Rod	21.36	0.289	0.940	0.0808	0.2632

^A S_r = within laboratory standard deviation for the indicated material. It is obtained by pooling the within-laboratory standard deviations of the test results for all of the participating laboratories:

$$S_r = [[(S_1)^2 + (S_2)^2 \dots + (S_n)^2]/n]^{1/2}$$

^B S_R = between-laboratories reproducibility, expressed as standard deviation:

$$S_R = [S_r^2 + S_L^2]^{1/2}$$

where S_L = standard deviation of laboratory means.

^C r = within-laboratory critical interval between tow test results = $2.8 \times S_r$.

^D R = between-laboratories critical interval between tow test results = $2.8 \times S_R$.

11.2.1 *Repeatability*: Two results obtained within one laboratory shall be judged not equivalent if they differ by more than the “r” value for that material. “r” is the interval representing the critical difference between two test results for the same material, obtained by the same operator using the same equipment on the same day in the same laboratory.

11.2.2 *Reproducibility*: Two test results obtained by different laboratories shall be judged not equivalent if they differ by more than the “R” value for that material. “R” is the interval

representing the critical difference between two test results for the same material, obtained by different operators using different equipment in different laboratories.

11.2.3 Any judgement in accordance with 11.2.1 or 11.2.2 would have an approximate 95% (0.95) probability of being correct.

11.3 There are no recognized standards by which to estimate bias of this method.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).