



# Standard Specification for Diethylene Glycol<sup>1,2</sup>

This standard is issued under the fixed designation D2694; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers diethylene glycol for use in the preparation of surface coatings.

1.2 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit of Practice E29.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 For specific hazard information and guidance, consult the supplier’s Material Safety Data Sheet.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

D1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)

D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter

D5386 Test Method for Color of Liquids Using Tristimulus Colorimetry

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E202 Test Methods for Analysis of Ethylene Glycols and Propylene Glycols

E300 Practice for Sampling Industrial Chemicals

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved Feb. 1, 2011. Published February 2011. Originally approved in 1968. Last previous edition approved in 2005 as D2694 – 05. DOI: 10.1520/D2694-05R11.

<sup>2</sup> This compound is also known as 2,2’oxydiethanol.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

2.2 *U.S. Federal Specification:*

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>4</sup>

## 3. Properties

3.1 Diethylene glycol shall conform to the following requirements:

Apparent specific gravity 20/20°C	1.1170 to 1.1200
or 25/25°C	1.1147 to 1.1177
Color, Pt-Co units, max <sup>A</sup>	15
Distillation range, 760 mm Hg	
Initial boiling point, °C, min	240
Dry point, °C, max	250
Water, wt %, max	0.2
Acidity as acetic acid, wt %, max	0.01
Ethylene glycol, wt %, max	0.5
Triethylene glycol, wt %, max	1.0
Iron, ppm, max	1.0

<sup>A</sup> Instrumental Pt-Co color determined by Test Method D5386 have been shown to have no statistically significant difference from Pt-Co color determined by Test Method D1209. However, it is not known whether diethylene glycol was part of the sample set included in the interlaboratory study.

## 4. Sampling

4.1 The material shall be sampled in accordance with Practice E300.

## 5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with Test Methods E202.

5.2 The apparent specific gravity can also be determined in accordance with Test Method D4052.

## 6. Packaging and Package Marking

6.1 Package size shall be agreed upon by the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

<sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://dodssp.daps.dla.mil.

\*A Summary of Changes section appears at the end of this standard

## 7. Keywords

7.1 diethylene glycol

### SUMMARY OF CHANGES

Committee D01.35 has identified the location of selected changes to this standard since the last issue (D2694 – 91 (2000)) that may impact the use of this standard.

- (1) Added reference to Practice **E29** in Scope section.                      (3) Changed specs limits for apparent specific gravity in **3.1**.  
(2) Added Practice **E29** and Test Methods **D1209** and **D5386** to                      (4) Added new Note A to **3.1**.  
list of referenced documents.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT).*