



Standard Test Method for Cashmere Coarse-Hair Content in Cashmere¹

This standard is issued under the fixed designation D2816; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a sequential procedure for determining whether or not the cashmere coarse-hair content of a sample exceeds a specified value.

NOTE 1—For the maximum allowable cashmere coarse-hair content in cashmere, refer to Specification [D2817](#).

NOTE 2—For the quantitative analysis of cashmere hair and blends of cashmere hair and other fibers, refer to Test Methods [D629](#).

1.2 This test method is applicable only to cashmere hair in the form of roving, yarn, or fabric, and to the cashmere hair content of blends with other fibers, where the expected cashmere coarse-hair content is not more than five mass percent (see Footnote C of [Table 1](#)). For greater expected mass percentages of cashmere coarse-hair, see Test Methods [D629](#).

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D123 Terminology Relating to Textiles](#)

[D629 Test Methods for Quantitative Analysis of Textiles](#)

[D2130 Test Method for Diameter of Wool and Other Animal Fibers by Microprojection](#)

[D2817 Specification for Maximum Cashmere Coarse-Hair Content in Cashmere](#)

[D4845 Terminology Relating to Wool](#)

3. Terminology

3.1 For all terminology relating to [D13.13](#), [Wool and Wool Felt](#), refer to Terminology [D4845](#).

¹ This test method is under the jurisdiction of ASTM Committee [D13](#) on Textiles and is the direct responsibility of Subcommittee [D13.13](#) on Wool and Felt.

Current edition approved July 1, 2009. Published August 2009. Originally approved in 1969. Last previous edition approved in 2005 as [D2816 – 05](#). DOI: 10.1520/D2816-05R09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.1 The following terms are relevant to this test method: cashmere, cashmere coarse hair, cashmere coarse hair content, cashmere down, cashmere hair.

3.2 For all other terminology related to textiles, see Terminology [D123](#).

4. Summary of Test Method

4.1 One thousand (or more) individual fibers of cashmere hair are examined microscopically and classified either as cashmere down or cashmere coarse-hair on the basis of fiber width.

4.2 The procedure ([7.1](#) and [7.2](#)) for classifying a fiber as cashmere coarse-hair or cashmere requires microscopic examination of fiber segments of fixed length. The number of fiber segments of each width category is proportional to the total length of the fibers in each category. Hence, the percentage by length of cashmere coarse-hair in cashmere hair is equal to the percentage by number of cashmere coarse-hair segments as determined by this procedure.

4.3 The observed number of cashmere coarse-hair fibers is compared with the numbers in [Table 1](#) and a decision is made (1) to accept the lot as conforming, (2) to reject the lot as nonconforming, or (3) to continue testing. The counting, classification, and comparison process is continued until a decision can be made as to whether the lot does or does not conform to the specification. [Table 1](#) is based on stated levels of confidence.

5. Significance and Use

5.1 This test method may be used for determining compliance with a specification for maximum cashmere coarse-hair content and is required to be used for determining compliance with Specification [D2817](#).

5.1.1 In case of a dispute arising from differences in reported test results when using Test Method [D2816](#) for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between their laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens that are as homogeneous as possible and that are from a lot of material of the type in question. The test specimens should then be randomly assigned in equal numbers

TABLE 1 Sequential Accept-Reject Numbers for Selected Specifications^A

Number of Fibers Counted	Specification, Length % ^B																	
	0.2		0.3		0.4		0.5		0.6		0.7		0.8		0.9		1.0	
	A	R	A	R	A	R	A	R	A	R	A	R	A	R	A	R	A	R
1 000	... ^C	17	...	18	...	19	...	20	...	21	...	22	...	23	...	24	...	25
2 000	...	19	...	21	...	23	...	25	...	27	...	29	...	31	...	33	...	35
3 000	...	21	...	24	...	27	0	30	3	33	6	36	9	39	12	42	15	45
4 000	...	23	...	27	1	31	5	35	9	39	13	43	17	47	21	51	25	55
5 000	...	25	0	30	5	35	10	40	15	45	20	50	25	55	30	60	35	65
6 000	...	27	3	33	9	39	15	45	21	51	27	57	33	63	39	69	45	75
7 000	...	29	6	36	13	43	20	50	27	57	34	64	41	71	48	77	55	85
8 000	1	31	9	39	17	47	25	55	33	63	41	71	49	79	57	86	65	95
9 000	3	33	12	42	21	51	30	60	39	69	48	78	57	87	66	95	75	105
10 000	5	35	15	45	25	55	35	65	45	75	55	85	65	95	75	104	85	115

^A These accept-reject numbers are based on the following conditions:

(1) The probability of accepting a lot that exceeds the specifications by 10 % or more of the specification percent is 0.05.

(2) The probability of rejecting a lot that is 10 % or more of the specification percent below the specification is also 0.05.

^B Extensive interlaboratory tests have shown that, for the concentration of cashmere coarse-hair covered in **Table 1**, the relationship between “Specification, Length Percent” and mass percent of cashmere coarse-hair is approximately linear, as shown in (Eq 1):

$$M = 3S + 0.9 \quad (1)$$

where:

M = mass percent of cashmere coarse-hair, and

S = specified maximum coarse-hair content in length percent ($0.2 \leq S \leq 1.0$).

The data from these studies are on file with the Secretary of Subcommittee D13.13, Committee D13 of ASTM.

^C Blanks correspond to a theoretical number less than zero. No decision to accept can be made until a number of fibers corresponding to the first nonblank entry has been classified.

to each laboratory for testing. The average results from the two laboratories should be compared using Student’s t -test for unpaired data and an acceptable probability level chosen by the two parties before the testing is begun. If a bias is found, either its cause must be found and corrected or the purchaser and the supplier must agree to interpret future test results in the light of the known bias.

5.2 When the product being tested has a cashmere coarse-hair content that departs significantly either way from the specified amount, the sequential test procedure described herein will result in a substantial reduction in the number of observations required for a decision at the stated level of confidence. On the other hand, when the product being tested has a cashmere coarse-hair content that approaches the specified amount, the sequential procedure ensures that the necessary increased number of observations shall be made to secure a correct decision at the stated level of confidence.

6. Apparatus

6.1 Apparatus is as specified in Test Method **D2130**.

7. Procedure

7.1 Proceed as directed in Test Method **D2130** with respect to apparatus and materials, sampling and selection of specimens, test specimen, calibration of microprojector, and preparation of slides, positioning and traversing the slide, focusing, and selecting the fibers to be observed and, if necessary, measured.

7.2 Examine 1000 fibers and record the number of fibers the width of which exceeds 30 μm (classified as cashmere coarse-

hair). Measure fibers having widths close to 30 μm with particular care so as to assure correct classification.

7.3 In **Table 1**, refer to the appropriate column for the agreed upon specification. In the row labeled 1000, two numbers are given. The number of cashmere coarse-hair fibers counted in **7.2** is either (1) equal to or greater than the larger number, (2) equal to or smaller than the smaller number, or (3) lies between the two numbers.

7.3.1 If the observed number is equal to or greater than the larger number, terminate the test and report that the sample exceeds the specification for cashmere coarse-hair content.

7.3.2 If the observed number is equal to or smaller than the smaller number, terminate the test and report that all the sample conforms to the specification for cashmere coarse-hair content.

7.3.3 If the observed number lies between the two numbers in the table, examine an additional 1000 fibers as in **7.2** and record the number of fibers classified as cashmere coarse-hair.

7.4 Compare the number of cashmere coarse-hair fibers observed in 2000 observations with the second row of the table, labeled 2000, in the column for the applicable specification. Use the table as directed in **7.3**, and continue the examination of the fibers in groups of 1000 as long as necessary to reach a decision with respect to conformance or nonconformance to the prescribed specification.

7.5 If, after 10 000 fibers have been examined, the total number of cashmere coarse-hair fibers found remains between the limiting numbers, terminate the test. Calculate the percentage of cashmere coarse-hair fibers and report that the sample conforms or does not conform to the prescribed cashmere coarse-hair content specification according to whether this

calculated percentage is, respectively, less than or more than the prescribed cashmere coarse-hair specification.

NOTE 3—A decision based on a test terminated as directed in 7.5 has a lower level of confidence than that corresponding to the level of confidence on which the calculations of Table 1 are based.

8. Report

8.1 State that the samples (or specimens) were tested as directed in Test Method D2816. Describe the material or product sampled and the method of sampling used.

8.2 Report the following information:

8.2.1 Number of fibers examined,

8.2.2 Number of cashmere coarse-hair fibers observed,

8.2.3 Maximum cashmere coarse-hair content specified, and

8.2.4 Whether the lot conforms or does not conform to the cashmere coarse-hair content specification.

9. Precision and Bias

9.1 The critical values in Table 1 (Note 4) are based on a probability of 0.05 of accepting a lot having a cashmere coarse-hair content exceeding the specification by 10 % or more and a probability of 0.05 of rejecting a lot having a cashmere coarse-hair content 10 % or more below the specification. That is, the total probability of making either a Type I error or a Type II error is 0.10.

NOTE 4—The table entries were calculated by the procedure given by Mood, A. F., *Introduction to the Theory of Statistics*, McGraw-Hill Book Co., New York, 1950, pp. 366–369, with $P_0 = 0.9$, $P_1 = 1.1$, $\alpha = \beta = 0.05$, $P =$ specification for which the table is calculated.

9.2 *Bias*—Test Method D2816 for testing the cashmere coarse-hair content in cashmere has no known bias and is accepted as a referee method.

10. Keywords

10.1 animal fibers (except wool); content

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).