



Designation: D3023 – 98 (Reapproved 2017)

Standard Practice for Determination of Resistance of Factory-Applied Coatings on Wood Products to Stains and Reagents¹

This standard is issued under the fixed designation D3023; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers evaluation of clear factory-applied coating systems on wood substrates.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D235 Specification for Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)

D333 Guide for Clear and Pigmented Lacquers

D2571 Guide for Testing Wood Furniture Lacquers (Withdrawn 2003)³

3. Significance and Use

3.1 When used in conjunction with Guide D333, this practice will provide a comprehensive evaluation of resistance to stains caused by chemical reagents and household chemicals.

¹ This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.52 on Factory Coated Wood Products.

Current edition approved July 1, 2017. Published July 2017. Originally approved in 1972. Last previous edition approved in 2011 as D3023 – 98 (2011). DOI: 10.1520/D3023-98R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3.2 This practice applies only to coatings applied in sufficient quantity to form a continuous film. It is recommended that the dry film thickness of the coating under test be reported.

3.3 Results from stain tests conducted in accordance with this practice distinguish differences between coatings.

4. Reagents

4.1 *Code for Applicability of Reagents*—V = Vertical, any surface that may be vertical as on a dresser front. H = Horizontal, any surface that may be horizontal as on a table top. L = Laboratory, any surface that may be used for laboratory furniture (Section 9).

4.2 *Water:*

4.2.1 *Tap Water:* V, H, L

4.2.2 *Boiling Water* (test in accordance with the Boiling Water Resistance section of Guide D2571): H, L

4.3 *Alcohol:*

4.3.1 *Ethyl Alcohol* (test in accordance with the Alcohol Resistance section of Guide D2571): V, H, L

4.4 *Aliphatic:*

4.4.1 *Mineral Spirits:* L (Specification, Type III)

4.4.2 *Perchloroethylene:* V, H, L

4.5 *Ketone:*

4.5.1 *Methyl Ethyl Ketone:* L

4.6 *Acetate:*

4.6.1 *Amyl Acetate:* H, L

4.7 *Inorganic Acid:*

4.7.1 *Hydrochloric Acid (3 N)*—Dilute 258 mL of 12 N (36 %) HCl to 1 L: L

4.8 *Organic Acid:*

4.8.1 *Acetic Acid (3 N)*—Dilute 172 mL of 99 % acetic acid to 1 L: V, H, L

4.8.2 *Grape Juice* (unsweetened): V, H

4.8.3 *Lactic Acid (5 % solution):* V, H

4.9 *Bases:*

4.9.1 *Unscented Mild Soap* (saturated solution): V, H, L

4.9.2 *Potassium Tripolyphosphate* (saturated solution containing 0.5 % sodium *N*-methyl-*N*-oleyl laurate (Igepon T-73)): V, H, L

- 4.9.3 *Ammonium Hydroxide* (3 % solution): L
 4.9.4 *Trisodium Phosphate* (saturated solution): V, H, L
 4.9.5 *Urea* (6.6 % solution): V, H, L

4.10 *Disinfectant*:

- 4.10.1 *Cresols* (5 % solution): V, H, L

4.11 *Ink*:

- 4.11.1 *Washable Ink*: V, H, L
 4.11.2 *Permanent Ink*: V, H, L
 4.11.3 *Ball-Point Ink*: V, H, L

4.12 *Dye*:

- 4.12.1 *Coffee* (test in accordance with the Coffee Stain Resistance section of Guide **D2571**): V, H

4.13 *Wax*:

- 4.13.1 *Wax Crayons, Red, Blue, and Yellow*: V, H
 4.13.2 *Lipstick* (test in accordance with the Cosmetic Stain section of Guide **D2571**): V, H

4.14 *Shoe Polish*:

- 4.14.1 *Liquid Shoe Polish, tan*: V, H

4.15 *Oil*:

- 4.15.1 *Corn Oil* or equivalent: V, H
 4.15.2 *Hair Oil*: V, H

4.16 *Miscellaneous*:

- 4.16.1 *Mustard*: V, H
 4.16.2 *Tincture of Merthiolate* (1 + 1000): V, H (see Section 5)
 4.16.3 *Sodium Hypochlorite* (6 % solution): V, H, L
 4.16.4 *Tincture of Iodine*—Wet 50 g of potassium iodide (KI) with water, weigh into the wet KI 70 g of iodine, let stand 1 h to dissolve the iodine, and make up to 1 L with alcohol: V, H, L

4.17 *Staining Solutions*, unless otherwise specified, are water solutions.

5. Selection of Staining Agents for Testing Stain Resistance of Coatings

5.1 The producer and the user shall select staining agents from the reagents in Section 4. Selection of staining agents should depend on end use, such as wall, ceiling, horizontal surface, or floor.

5.2 In the absence of agreement between the producer and the user, the suggested staining reagents for each intended use are indicated in Section 4 by V, H and L.

5.3 It is not necessary that all finishes pass all tests.

6. Test Specimen

6.1 Test panels shall be of regular production finish.

6.2 If regular production finished panels are not available, the producer and the user shall agree upon the following variables: face veneer or wood surface, filler or filler stain, primer coat, topcoat, and dry film thickness for each coating material.

7. Panel Conditioning

7.1 Before testing, panels must be aged for a time and by a method agreed upon between the producer and the user.

8. Procedure

8.1 Conduct the test with panel surfaces horizontal at room temperature unless a different temperature is specified.

8.2 Place 0.5 mL (0.017 oz) of each staining agent on the finish surface and allow to stand uncovered for 18 h (or a time agreeable to the producer and the user) except for staining agents 4.3 to 4.6. On these put a 25-mm (1-in.) square of double-acid-washed quantitative filter paper. The purpose of the filter paper is to maintain a longer wet contact of volatile reagents with the surface of the finish.

8.3 After 18 h exposure, or other time period agreed to by the producer and the user, wash the surface with water, rinse with ethanol (1 + 1), or other reagent as agreed upon between the producer and user, and dry with a paper towel. Place the panel in a vertical position with a diffuse light source and view (**Note 1**) from a distance of 0.6 to 0.9 m (2 to 3 ft). Examine the surface for graying, spotting, wrinkling, discoloration, or other film defects and report.

NOTE 1—This method of viewing panels gives the best correlation of staining damage between laboratories. However, the following information should be noted: (1) When viewing panels across the grain at a low angle that is being varied, many more stains will appear visible than would appear visible perpendicular to the surface. These additional stains are superficial stains only. (2) When viewing with and against the grain, there appears to be an even greater number of superficial stains than would appear when viewing perpendicular to the surface or across the grain.

9. Interpretation of Results

9.1 Each product finish differs greatly in stain resistance requirements. The key, in general, is that the resistance to staining must be adequate for that finish's end use when first used in place and throughout the expected life span of the specific product.

9.2 The end use choice of resistance to staining should be agreed upon between the producer and the user.

10. Report

10.1 Report the following information:

- 10.1.1 Reagents and concentrations used,
- 10.1.2 Substrate tested,
- 10.1.3 Coating tested,
- 10.1.4 Rinsing reagent,
- 10.1.5 Film thickness of coating and thickness method, and
- 10.1.6 Stain or film defect observations.

11. Precision and Bias

11.1 *Precision*—Agreement between laboratories by visual comparison varied according to how samples were viewed.

11.1.1 Stains viewed perpendicular with a diffused light source at a distance of 0.6 to 0.9 m (2 to 3 ft) for graying, spotting, wrinkling, discoloration, or other film defects gave complete agreement between laboratories.

11.1.2 The same test stains viewed both with and across the grain at a low angle resulted in many more superficial stains being evident, depending upon the eyesight and judgment of the observer.

11.2 *Bias*—Bias cannot be determined since there is no accepted reference material.

12. Keywords

12.1 coating, factory-applied; coating, wood; household chemicals; stain tests

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>