



Standard Test Methods for Rubber—Evaluation of SBR (Styrene-Butadiene Rubber) Including Mixtures With Oil¹

This standard is issued under the fixed designation D3185; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the standard materials, test formulas, mixing procedures, and test methods for the evaluation of emulsion polybutadiene (EBR) and styrene-butadiene rubbers (SBR) including the emulsion polybutadiene oil masterbatch rubbers, SBR oil masterbatches, and partially cross-linked and high Mooney rubbers.

1.2 These test methods are also applicable to certain types of solution SBR and solution SBR oil masterbatches that are used in applications requiring vulcanization.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension](#)

[D1646 Test Methods for Rubber—Viscosity, Stress Relaxation, and Pre-Vulcanization Characteristics \(Mooney Viscometer\)](#)

[D2084 Test Method for Rubber Property—Vulcanization Using Oscillating Disk Cure Meter](#)

[D3182 Practice for Rubber—Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets](#)

¹ These test methods are under the jurisdiction of ASTM Committee D11 on Rubber and are the direct responsibility of Subcommittee D11.23 on Synthetic Rubbers.

Current edition approved June 1, 2016. Published July 2016. Originally approved in 1973. Last previous edition approved in 2010 as D3185–06 (2010). DOI: 10.1520/D3185-06R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D3896 Practice for Rubber From Synthetic Sources—Sampling](#)

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

[D5289 Test Method for Rubber Property—Vulcanization Using Rotorless Cure Meters](#)

[D6204 Test Method for Rubber—Measurement of Unvulcanized Rheological Properties Using Rotorless Shear Rheometers](#)

2.2 *ISO Standard:*

[ISO 2322 Rubber, Styrene-Butadiene \(SBR\)—Emulsion-Polymerized General-Purpose Type—Test Recipe and Evaluation of Vulcanization Characteristics](#)³

3. Summary of Test Methods

3.1 These test methods include the standard test formulas, mixing procedures, and test methods for evaluating the following types of synthetic rubbers:

3.1.1 *Non-Oil-Extended Types*, mill and Miniature Internal Mixer (MIM) mixing procedures.

3.1.2 *Oil Masterbatch Types*, mill and Miniature Internal Mixer (MIM) mixing procedures.

3.2 No correlation between results for mill and MIM mixing procedures is implied.

4. Significance and Use

4.1 These test methods are mainly intended for referee purposes but may be used for quality control of synthetic rubber production. They may also be used in research and development work and for comparison of different rubber samples in a standard formula.

4.2 These test methods may also be used to obtain values for customer acceptance of rubber.

5. Standard Test Formulas

5.1 *Standard Formulas for Non-Oil-Extended Types*—See [Table 1](#).

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

TABLE 1 Standard Non-Oil Extended SBR Test Formulas

Material	IRM-SRM No.	Quantity, Parts by Mass	
		1A	2A
SBR or masterbatch	...	100.00	100.00
Zinc oxide	^A	3.00	3.00
Sulfur	^A	1.75	1.75
Stearic acid	^A	1.00	1.00
Oil furnace black ^B	^A	50.00	35.00
TBBS ^C	^A	1.00	1.00
Total		156.75	141.75
Batch factor for mill mix ^D		3.0	3.3
Batch factor for MIM mix ^E :			
Cam head		0.47	0.49
Banbury head		0.41	0.46

^A Use Current IRM/SRM.

^B The current Industry Reference Black (IRB), which has been dried for 1 h at 125 ± 3°C.

^C *N-tert-butyl-2-benzothiazolesulfenamide*.

^D For mill batches, weigh the rubber and carbon black to the nearest 1.0 g, the sulfur and accelerator to the nearest 0.02 g, and the other compounding materials to the nearest 0.1 g.

^E For MIM batches, weigh the rubber and carbon black to the nearest 0.1 g, the compounding material blend to the nearest 0.01 g, and the individual compounding materials, if used, to the nearest 0.001 g.

5.1.1 For the MIM procedure it is recommended that a blend of compounding materials, excluding carbon black, be prepared to improve accuracy in the weighing of these materials. The compounding material blend is prepared by blending a proportional mass of each material in a dry powder blender such as a biconical blender or vee blender. A mortar and pestle may be used for blending small quantities.

5.1.2 Formula 1A shall apply to the general-purpose nonpigmented, non-oil-extended rubber types. It is also specified in International Standard [ISO 2322](#) for evaluation of general purpose, nonpigmented, non-oil-extended rubbers. Formula 2A shall apply to the partially crosslinked and

high-Mooney rubber (>90 ML 1 + 4 at 100°C) for example, SBR 1009, 1018, and 1012 types.

5.2 *Standard Formulas for Oil Masterbatch Types*—See [Table 2](#).

5.2.1 Formulas 1B to 6B shall apply to the general purpose nonpigmented oil-extended rubber types according to the oil content of the rubber. Formula 1A may be used as an alternative to Formulas 1B to 6B. International Standard ISO 2322 specifies Formula 1A for evaluation of general purpose, nonpigmented, oil-extended SBR.

5.2.2 For the MIM procedure it is recommended that a blend of compounding materials, excluding carbon black, be prepared to improve accuracy in the weighing of these materials. The pigment blend is prepared by blending a proportional mass of each material in a dry powder blender such as a biconical blender or vee blender. A mortar and pestle may be used for blending small quantities.

6. Sample Preparation

6.1 Obtain the test samples in accordance with Practice [D3896](#).

7. Mixing Procedures

7.1 Three mixing procedures are provided:

7.1.1 *Method A*—Mill mix ([7.2](#)).

7.1.2 *Method B*—Miniature internal mixer (MIM) mix ([7.3](#)).

7.1.3 *Method C*—Internal mixer mix ([7.4](#)).

NOTE 1—These mixing methods may not obtain comparable results.

7.2 *Method A—Mill Mix Procedure:*

7.2.1 For general mixing procedures refer to Practice [D3182](#).

7.2.2 Mix with the mill roll temperature maintained at 50 ± 5°C (122 ± 9°F). The indicated mill openings are desired and

TABLE 2 Standard Oil Masterbatch Type SBR Test Formulas

Material	IRM-SRM No.	Quantity, Parts by Mass					
		1B	2B	3B	4B	5B	6B
Formula No.		25	37.5	50	62.5	75	Base
Parts Oil							
Masterbatch		125.00	137.50	150.00	162.50	175.00	100 + Y ^A
Zinc oxide	^B	3.00	3.00	3.00	3.00	3.00	3.00
Sulfur	^B	1.75	1.75	1.75	1.75	1.75	1.75
Stearic acid	^B	1.00	1.00	1.00	1.00	1.00	1.00
Oil furnace black ^C	^B	62.50	68.75	75.00	81.25	87.50	50 (100 + Y)0.01
TBBS ^D	384	1.25	1.38	1.50	1.63	1.75	1
Total		194.50	213.38	232.25	251.13	270.00	1 (100 + Y)0.01
Batch factor for mill mix ^E		2.4	2.2	2.0	1.9	1.7	1
Batch factor for MIM mix:							
Cam head ^D		0.37	0.34	0.31	0.29	0.27	
Banbury head ^F		0.328	0.298	0.273	0.252	0.234	

^A Y = parts oil by mass per 100 parts base polymer in masterbatch.

^B Use Current IRM/SRM.

^C The current Industry Reference Black (IRB) which has been dried for 1 h at 125 ± 3°C.

^D *N-tert-butyl-2-benzothiazolesulfenamide*.

^E For mill batches, weigh the rubber and carbon black to the nearest 1.0 g, the sulfur and accelerator to the nearest 0.02 g, and the other compounding materials to the nearest 0.1 g.

^F For MIM batches, weigh the rubber and carbon black to the nearest 0.1 g, the compounding material blend to the nearest 0.01 g and the individual compounding materials, if used, to the nearest 0.001 g.

should be maintained insofar as possible to provide uniformity in the breakdown of the rubber due to milling.

7.2.3 *Mixing Cycle*—See [Table 3](#).

7.2.3.1 After mixing according to [Table 3](#), measure and record the batch mass. If it differs from the theoretical value by more than 0.5 %, discard the batch.

7.2.3.2 If required, cut samples from the batch to allow testing of compound viscosity and processability in accordance with Test Methods [D1646](#) or [D6204](#), and vulcanization characteristics in accordance with Test Methods [D2084](#) or [D5289](#).

7.2.3.3 If tensile stress strain tests are required, sheet off to a finished thickness of approximately 2.2 mm (0.087 in.) and condition the compound according to Practice [D3182](#).

7.3 *Method B—Miniature Internal Mixer Procedure:*

7.3.1 For general mixing procedures refer to Practice [D3182](#). Mix with the head temperature of the miniature internal mixer maintained at $60 \pm 3^\circ\text{C}$ ($140 \pm 5^\circ\text{F}$) and the unloaded rotor speed at 6.3 to 6.6 rad/s (60 to 63 rpm).

7.3.2 Prepare the rubber by passing it through a mill one time with the temperature set at $50 \pm 5^\circ\text{C}$ ($122 \pm 9^\circ\text{F}$) and an opening of 0.5 mm (0.02 in.). Cut the sheet into strips that are approximately 25 mm (1 in.) wide, if desired.

7.3.3 *Mixing Cycle*—See [Table 4](#).

7.3.3.1 After mixing according to [Table 4](#), turn off the motor, raise the ram, remove the mixing chamber, and discharge the batch. Record the maximum batch temperature indicated, if desired.

7.3.3.2 Immediately pass the discharge from the mixer twice through a standard mill maintained at $50 \pm 5^\circ\text{C}$ ($122 \pm 9^\circ\text{F}$) with a roll separation of 0.5 mm (0.020 in.) once, then twice at a separation of 3 mm (0.12 in.) in order to dissipate heat. Pass the rolled batch endwise through the mill six times with an opening of 0.8 mm (0.31 in.) to enhance the dispersion.

7.3.3.3 Measure and record the batch mass. If it differs from the theoretical value by more than 0.5 %, discard the batch.

7.3.3.4 If required, cut samples from the batch to allow testing of compound viscosity and processability in accordance with Test Methods [D1646](#) or [D6204](#), and vulcanization characteristics in accordance with Test Methods [D2084](#) or [D5289](#).

7.3.3.5 If tensile stress strain tests are required, sheet off to a finished thickness of approximately 2.2 mm (0.087 in.) and condition the compound according to Practice [D3182](#).

7.4 *Method C—Internal Mixer:*

7.4.1 For general mixing procedure refer to Practice [D3182](#).

7.4.2 *Mixing Cycle-Initial Mix*—See [Table 5](#).

7.4.2.1 After mixing according to [Table 5](#), measure and record the batch mass. If it differs from the theoretical value by more than 0.5 %, discard the batch.

7.4.2.2 Pass the batch immediately through the standard laboratory mill three times, set at 6.0 mm (0.25 in.) and $40 \pm 5^\circ\text{C}$ ($104 \pm 9^\circ\text{F}$).

7.4.2.3 Allow the batch to rest for 1 to 24 h.

7.4.3 *Final Mix*—See [Table 6](#).

7.4.3.1 After mixing according to [Table 6](#), measure and record the batch mass. If it differs from the theoretical value by more than 0.5 %, discard the batch.

7.4.3.2 If required, cut samples from the batch to allow testing of compound viscosity and processability in accordance with Test Methods [D1646](#) or [D6204](#), and vulcanization characteristics in accordance with Test Methods [D2084](#) or [D5289](#).

7.4.3.3 If tensile stress strain tests are required, sheet off to a finished thickness of approximately 2.2 mm (0.087 in.) and condition the compound according to Practice [D3182](#).

8. Testing Procedures

8.1 For stress-strain testing, prepare the test sheets and vulcanize them in accordance with Practice [D3182](#).

8.1.1 The recommended standard vulcanization times for the mill mixed compound are 25, 35, and 50 min at 145°C

TABLE 3 Mill Mixing Cycle

NOTE 1—Do not cut any stock while free carbon black is evident in the bank or on the milling surface. Be certain to return to the milling stock any ingredients that drop through the mill.

	Duration, min	Accumulative, min
Set the mill opening at 1.15 mm (0.045 in.) and band the rubber on the slow roll. Make $\frac{3}{4}$ cuts every $\frac{1}{2}$ min from alternate sides.	7	7
Add the sulfur slowly and evenly across the mill at a uniform rate.	2	9
Add the stearic acid. Make one $\frac{3}{4}$ cut from each side after the stearic acid has been incorporated.	2	11
Add the carbon black evenly across the mill at a uniform rate. When about half the black is incorporated, open the mill to 1.25 mm (0.050 in.) and make one $\frac{3}{4}$ cut from each side. Then add the remainder of the carbon black. When all the black has been incorporated, open the mill to 1.40 mm (0.055 in.) and make one $\frac{3}{4}$ cut from each side.	10	21
Add the other materials at the 1.40-mm (0.055-in.) setting.	3	24
Make three $\frac{3}{4}$ cuts from each side and cut the batch from the mill.	2	26
Set the rolls at 0.8 mm (0.032 in.). Pass the rolled batch endwise through the mill six times.	2	28
Open the mill to give a minimum batch thickness of 6 mm (0.25 in.) and pass the stock through the mill four times, folding it back on itself each time.	1	29

TABLE 4 Miniature Internal Mixer Cycle

	Duration, min	Accumulative, min
Charge the mixing chamber with the rubber strips, lower the ram, and start the timer.	0	0
Masticate the rubber.	1.0	1.0
Raise the ram and add all the zinc oxide, sulfur, stearic acid, and TBBS that have been previously blended, taking care to avoid any loss. Then add the carbon black, sweep the orifice, and lower the ram.	1.0	2.0
Allow the batch to mix.	7.0	9.0

TABLE 5 Internal Mixer—Initial Cycle

	Duration, min	Accumulative, min
Adjust the internal mixer temperature to achieve the discharge conditions outlined below. Close the discharge gate, start the rotor at 8.1 rad/s (77 rpm) and raise the ram.	0.5	0.5
Charge one half the rubber, all of the zinc oxide, carbon black, stearic acid, and then the other one half of the rubber. Lower the ram.	3.0	3.5
Allow the batch to mix.	0.5	4.0
Raise the ram and clean the mixer throat and the top of the ram. Lower the ram.	2.0	6.0
Allow the batch to mix until a temperature of 170°C (338°F) or a total mixing time of 6 min is reached, whichever occurs first. Discharge the batch.	2.0	6.0

TABLE 6 Internal Mixer—Final Cycle

	Duration, min	Accumulative, min
Adjust the internal mixer temperature to 40 ± 5°C (104 ± 9°F), turn off steam and turn on full cooling water to the rotors, at 8.1 rad/s (77 rpm), and raise the ram.	0	0
Charge ½ the batch, with all the sulfur and accelerator rolled into this portion of the batch before feeding to the mixer. Add the remaining portion of the batch. Lower the ram.	5.0	5.0
Allow the batch to mix until a temperature of 110 ± 5°C (230 ± 9°F) or a total mixing time of 3 min is reached, whichever occurs first. Discharge the batch.	2.5	3.0
With the rolls of a standard laboratory mill maintained at 40 ± 5°C (104 ± 9°F) and set at 0.8 mm (0.0032 in.) opening, pass the rolled batch endwise through the rolls six times.	2.0	5.0
Open the rolls to give a minimum thickness of 6 mm (0.25 in.) and pass the compound through four times, folding it back itself each time.	1.0	6.0

(293°F). The recommended standard vulcanization time for the miniature internal mixer compound is 35 min at 145°C.

8.1.2 Condition the cured sheets for 16 to 96 h at a temperature of 23 ± 3°C (73 ± 5°F).

NOTE 2—Quality control of rubber production may require testing

within 1 to 6 h to provide close surveillance of the plant operations; however, slightly different results may be obtained.

8.1.3 Prepare test specimens and obtain tensile stress, tensile strength, and elongation in accordance with Test Methods **D412**.

8.2 An alternative to measuring vulcanization characteristics by means of tensile stress measurement on vulcanizates is the measurement of vulcanization characteristics in accordance with Test Method D2084 (Oscillating Disk Cure Meter Method) or Test Method D5289 (Rotorless Cure Meter Method). These methods will not produce equal results.

8.2.1 The recommended Test Method D2084 test conditions are 1.67 Hz (100 cpm) oscillation frequency, 1° oscillation amplitude, 160°C die temperature, 30-min test time, and no preheating. The recommended Test Method D5289 test conditions are 1.67 Hz (100 cpm) oscillation frequency, 0.5° oscillation amplitude, 160°C die temperature, 30-min test time, and no preheating. Test condition tolerances are specified by the test methods.

8.2.2 The recommended standard test parameters are M_L , M_H , t_{s1} , $t'50$, and $t'90$.

9. Precision and Bias

9.1 These precision statements have been prepared in accordance with Practice D4483. Please refer to this practice for terminology and other testing and statistical concept explanations. The precision results in this precision and bias section give an estimate of the precision of the test method with the materials used in the particular interlaboratory program as described below. The precision parameters should not be used for acceptance/rejection testing of any group of materials without documentation that they are applicable to those particular materials and the specific testing protocols that include these test methods.

9.2 The Type 2 precision of these test methods was determined from an interlaboratory study of 2 rubbers, Type 1712 and Type 1502. Seven laboratories mixed and tested each rubber by the miniature internal mixer method on 2 days.

9.3 Table 7 gives the Basic Precision (BT) data as obtained in the interlaboratory program. The cure meter testing was conducted in accordance with Test Method D2084. In Practice

D4483 terminology, Type 2 Precision includes as components of variation the mixing and curing operations within each laboratory.

9.4 A test result for cure meter testing (Test Method D2084) represents one measurement with a cure meter.

9.5 A test result for tension testing (Test Methods D412) is the median of 3 dumbbell specimens.

9.6 A test result for viscosity testing (Test Method D1646) represents one measurement with a viscometer.

9.7 The precision of these test methods may be expressed in the format of the following statements which use what is called an “appropriate value” of r , R , (r), or (R), that is, that value to be used in decisions about test results (obtained with the test method). The appropriate value is that value of r or R associated with a mean level in Table 7 closest to the mean level under consideration at any given time, for any given material in routine testing operations.

9.8 Repeatability—The repeatability, r , of these test methods has been established as the appropriate value tabulated in Table 7. Two single test results, obtained under normal test method procedures, that differ by more than this tabulated r (for any given level) must be considered as derived from different or nonidentical sample populations.

9.9 Reproducibility—The reproducibility, R , of these test methods has been established as the appropriate value tabulated in Table 7. Two single test results obtained in two different laboratories, under normal test method procedures, that differ by more than the tabulated R (for any given level) must be considered to have come from different or nonidentical sample populations.

9.10 Repeatability and reproducibility expressed as a percentage of the mean level, (r) and (R), have equivalent application statements for r and R . For the (r) and (R)

TABLE 7 Type 2 Test Precision

NOTE 1—Symbols are defined as follows:
 Sr = within laboratory standard deviation.
 r = repeatability (in measured units).
 (r) = repeatability (in percent).
 SR = between laboratory standard deviation.
 R = reproducibility (in measurements units).
 (R) = reproducibility (in percent).

Property	Units	Range of Values	Within Laboratories			Among (Between) Laboratories		
			Sr	r	$(r)^A$	SR	R	$(R)^A$
Precision estimates for Test Method D2084 at 160°C, 1.7 Hz, and 1° amplitude are:								
M_L	dN·m	9.7–9.8	0.21	0.594	6.1	0.52	1.47	15.2
M_H	dN·m	32.5–43.8	0.77	2.18	5.7	2.21	6.25	16.4
t_{s1}	min	3.5–4.9	0.13	0.368	8.8	0.67	1.90	45.2
$t'50$	min	8.2–8.3	0.20	0.566	6.9	0.74	2.09	25.3
$t'90$	min	13.6–16.4	0.48	1.36	9.1	1.12	3.17	21.1
Precision estimates for Test Methods D412 at 145°C for 35 min are:								
300 % modulus, MPa		8.7–13.8	0.62	1.75	15.6	1.55	4.39	39.0
Tensile strength, MPa		21.9–25.9	0.83	2.35	9.8	1.40	3.96	16.6
Elongation, %		504–599	16.2	45.8	8.3	67.7	191.0	34.7
Precision estimates for Test Method D1646 are:								
M_L 1 + 4 at 100°C		63.8–70.3	1.51	4.27	6.4	6.61	18.7	27.9

^A Mid-point of range used to calculate (r) and (R).

statements, the difference in the two single test results is expressed as a percentage of the arithmetic mean of the two test results.

9.11 *Bias*—In test method terminology, bias is the difference between an average test value and the reference (or true) test property value. Reference values do not exist for these test methods since the value (of the test property) is exclusively defined by the test methods. Bias, therefore, cannot be determined.

10. Keywords

10.1 butadiene rubber; EBR; evaluation of emulsion polybutadiene; evaluation of SBR oil masterbatches; evaluation of solution SBR; SBR

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>