



Designation: D3203/D3203M – 17

# Standard Test Method for Percent Air Voids in Compacted Asphalt Mixtures<sup>1</sup>

This standard is issued under the fixed designation D3203/D3203M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers determination of the percent air voids in compacted asphalt mixtures.

1.2 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

- D1188 Test Method for Bulk Specific Gravity and Density of Compacted Bituminous Mixtures Using Coated Samples
- D2041 Test Method for Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures
- D2726 Test Method for Bulk Specific Gravity and Density of Non-Absorptive Compacted Bituminous Mixtures
- D3549 Test Method for Thickness or Height of Compacted Bituminous Paving Mixture Specimens
- D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials
- D4460 Practice for Calculating Precision Limits Where Values are Calculated from Other Test Methods
- D6752 Test Method for Bulk Specific Gravity and Density

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.21 on Specific Gravity and Density of Asphalt Mixtures.

Current edition approved April 1, 2017. Published April 2017. Originally approved in 1973. Last previous edition approved in 2011 as D3203/D3203M – 11. DOI: 10.1520/D3203\_D3203M-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

of Compacted Bituminous Mixtures Using Automatic Vacuum Sealing Method  
D6857 Test Method for Maximum Specific Gravity and Density of Bituminous Paving Mixtures Using Automatic Vacuum Sealing Method

## 3. Terminology

3.1 *Definitions:*

3.1.1 *air voids*—the pockets of air between the bitumen-coated aggregate particles in a compacted asphalt mixture.

3.1.2 *dense asphalt mixtures*—asphalt mixtures in which the air voids are less than 10 % when compacted.

3.1.3 *open asphalt mixtures*—asphalt mixtures in which the air voids are 10 % or more when compacted.

3.1.3.1 *Discussion*—For borderline cases, an asphalt mixture shall be designated an open asphalt mixture if the calculated percent air voids, based on either 6.1 or 6.2, is 10 % or more.

## 4. Significance and Use

4.1 The percent of air voids in an asphalt mixture is used as one of the criteria in the design methods and for evaluation of the compaction imparted in asphalt paving projects.

NOTE 1—The text of this test method references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the test method.

NOTE 2—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Specification D3666 are generally considered capable of competent and objective testing/sampling/inspection, etc. Users of this standard are cautioned that compliance with Specification D3666 alone does not completely ensure reliable results. Reliable results depend on many factors; following the suggestions of Specification D3666 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors.

## 5. Sampling

5.1 Samples for testing shall consist of specimens from laboratory-molded mixtures or cores from field-compacted mixtures.

## 6. Procedure

6.1 For dense asphalt mixtures, determine the bulk specific gravity of the compacted mixture by Test Method **D1188**, by Test Method **D2726**, or by Test Method **D6752**.

6.2 For open asphalt mixtures, determine the density of a regularly shaped specimen of compacted mixture from its dry mass (in grams) and its volume (in cubic centimetres).

6.2.1 Obtain the height of the specimens by Test Method **D3549**.

6.2.2 Measure the diameter of the specimen at four locations and determine the average.

6.2.3 Calculate the volume of the specimen based on the average height and diameter measurement.

6.2.4 Convert the density to bulk specific gravity by dividing by 0.99707 g/cm<sup>3</sup> or 997 kg/m<sup>3</sup>, the density of water at 25 °C.

NOTE 3—The density measurements should be converted to the appropriate SI units before performing the calculation in 6.2.4.

6.3 Determine the theoretical maximum specific gravity by Test Method **D2041** or by Test Method **D6857** on a comparable asphalt mixture to avoid the influence of differences in gradation, asphalt content, etc.

6.4 For referee purposes, determine both the bulk specific gravity and the theoretical maximum specific gravity on approximately equal portions of the same sample of compacted asphalt mixture.

## 7. Calculation

7.1 Calculate the percent air voids in a compacted asphalt mixture as follows:

$$\text{Percent air voids} = 100(1 - (\text{bulk sp gr} / \text{theoretical maximum sp gr})) \quad (1)$$

7.2 If the percent air voids of a specimen tested according to 6.1 equals or exceeds 10 %, the specimen shall be retested according to 6.2 as an open asphalt mixture.

## 8. Precision and Bias

8.1 The precision of this test method depends on the precision of test methods for bulk specific gravity and theoretical maximum specific gravity. It is computed by a procedure described in Practice **D4460**. Since the computation for percent air voids in 7.1 involves the quotient of bulk specific gravity divided by the theoretical maximum specific gravity, the quotient formula is used:

$$\sigma_{x/y} = \sqrt{\frac{\bar{y}^2 \sigma_x^2 + \bar{x}^2 \sigma_y^2}{\bar{y}^4}} \quad (2)$$

where:

$\sigma_{x/y}$  = standard deviation for determining precision limits of test results based on the quotient of test results from Test Method **D1188**, **D2726**, or **D6752**, and Test Method **D2041** or **D6857**,

$\bar{x}$  = mean (average) of  $x$  standard test results (bulk specific gravity, Test Method **D1188**, **D2726**, or **D6752**),

$\bar{y}$  = mean (average) of  $y$  standard test results (theoretical maximum specific gravity, Test Method **D2041** or **D6857**),

$\sigma_x$  = standard deviation from the precision statement of  $x$  standard test results (bulk specific gravity, Test Method **D1188**, **D2726**, or **D6752**), and

$\sigma_y$  = standard deviation from precision statement of  $y$  standard test results (maximum theoretical specific gravity, Test Method **D2041** or **D6857**).

8.2 Criteria for judging the acceptability of percent air voids test results would be presented in the form:

Operator Precision	Standard Deviation $\sigma_{x/y}$	Acceptable Range of Two Results 2.8 $\sigma_{x/y}$
--------------------	--------------------------------------	---

## APPENDIX

### (Nonmandatory Information)

#### X1. EXAMPLE CALCULATION OF PRECISION

X1.1 Assume the following precision data:

Bulk specific gravity,  $x$

Average	Standard Deviation
2.423	0.007

Theoretical maximum specific gravity,  $y$

Average	Standard Deviation
2.523	0.004

Then using the equation in 8.1:

$$\sigma_{x/y} = \sqrt{\frac{(2.523)^2 (0.007)^2 + (2.423)^2 (0.004)^2}{(2.523)^4}} \quad (X1.1)$$

$$= 0.00316$$

This value is in terms of air voids; therefore it should be multiplied by 100 to convert it into a percentage. Therefore:

$$\sigma_{x/y} = 0.00316(100) = 0.32 \% \quad (X1.2)$$



*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*