



Standard Specification for PTFE Tubing, Miniature Beading and Spiral Cut Tubing¹

This standard is issued under the fixed designation D3295; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers PTFE tubing, miniature beading and spiral cut tubing—manufactured from PTFE resin produced from dispersion specified in Specification [D4895](#).

NOTE 1—PTFE tube and rod manufactured from resin specified in Specification [D4894](#) are covered in Specification [D1710](#).

1.2 The values stated in SI units are to be regarded as standard. The inch-pound units given in parentheses are for information only.

1.3 The following hazard caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 As PTFE resin produced from dispersion is not a true thermoplastic material, any reuse for the specification referenced above is impossible. However, markets do exist for non-virgin PTFE as additives and fillers.

NOTE 2—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 ASTM Standards:²

- [D618 Practice for Conditioning Plastics for Testing](#)
- [D638 Test Method for Tensile Properties of Plastics](#)
- [D792 Test Methods for Density and Specific Gravity \(Relative Density\) of Plastics by Displacement](#)
- [D883 Terminology Relating to Plastics](#)
- [D1600 Terminology for Abbreviated Terms Relating to Plastics](#)
- [D1675 Test Methods for Polytetrafluoroethylene Tubing](#)

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.15.12).

Current edition approved Sept. 1, 2015. Published September 2015. Originally approved in 1974. Last previous edition approved in 2011 as D3295 - 06(2011). DOI: 10.1520/D3295-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens](#)
- [D1710 Specification for Extruded Polytetrafluoroethylene \(PTFE\) Rod, Heavy Walled Tubing and Basic Shapes](#)
- [D3892 Practice for Packaging/Packing of Plastics](#)
- [D4894 Specification for Polytetrafluoroethylene \(PTFE\) Granular Molding and Ram Extrusion Materials](#)
- [D4895 Specification for Polytetrafluoroethylene \(PTFE\) Resin Produced From Dispersion](#)

3. Terminology

3.1 *Definitions*—The terminology given in Terminologies [D883](#) and [D1600](#) is applicable to this specification.

3.2 *Description of Term Specific to This Standard:*

3.2.1 *lot*—a single production run, or a uniform blend of two or more production runs.

4. Classification

4.1 This specification provides for five groups of PTFE tubing, miniature beading and spiral cut tubing, differentiated by size and type. The groups are further subdivided into classes based on wall thickness.

4.1.1 *Group 01*—Tubing based upon the American Wire Gage (AWG) sizes.

4.1.2 *Group 02*—Tubing based upon fractional inch sizes.

4.1.3 *Group 03*—Tubing specified by inner diameter and wall thickness in [Table 6](#) referred to as “Custom or Metric.”

4.1.4 *Group 04*—Tubing cut to form spiral wrap as in [Table 7](#).

4.1.5 *Group 05*—Miniature beading having diameters as listed in [Table 8](#).

4.2 The types are further differentiated in accordance with increasing wall thickness as follows:

4.2.1 *Class 1*—Tubing having walls tabulated in [Table 1](#) listed as light wall.

4.2.2 *Class 2*—Tubing having walls of greater thickness than Class 1 listed as thin wall.

4.2.3 *Class 3*—Tubing having walls tabulated in [Table 2](#) listed as standard wall.

4.2.4 *Class 4*—Tubing having walls tabulated in [Table 3](#) listed as chemical tubing.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Dimensions and Tolerances for Group 01 PTFE Tubing, mm (in.) (Classes 1 and 2)

AWG Size Grade	Inside Diameter			Class 1	
				Light Wall	
	min	max	nom	min	max
30	0.25 (0.010)	0.38 (0.015)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
28	0.33 (0.013)	0.46 (0.018)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
26	0.41 (0.016)	0.53 (0.021)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
24	0.51 (0.020)	0.66 (0.026)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
22	0.64 (0.025)	0.81 (0.032)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
20	0.81 (0.032)	1.01 (0.040)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
19	0.91 (0.036)	1.12 (0.044)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
18	1.02 (0.040)	1.25 (0.049)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
17	1.14 (0.045)	1.37 (0.054)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
16	1.30 (0.051)	1.55 (0.061)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
15	1.45 (0.057)	1.70 (0.067)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)
14	1.65 (0.064)	1.88 (0.074)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
13	1.83 (0.072)	2.08 (0.082)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
12	2.06 (0.081)	2.31 (0.091)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
11	2.31 (0.091)	2.57 (0.101)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
10	2.59 (0.102)	2.85 (0.112)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
9	2.90 (0.114)	3.15 (0.124)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
8	3.28 (0.129)	3.58 (0.141)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)
7	3.66 (0.144)	4.01 (0.158)	0.20 (0.008)	0.15 (0.005)	0.25 (0.011)
6	4.12 (0.162)	4.52 (0.178)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
5	4.62 (0.182)	5.03 (0.198)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
4	5.18 (0.204)	5.69 (0.224)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
3	5.82 (0.229)	6.33 (0.249)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
2	6.55 (0.258)	7.06 (0.278)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
1	7.34 (0.289)	7.90 (0.311)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
0	8.26 (0.325)	8.81 (0.347)	0.25 (0.012)	0.22 (0.009)	0.38 (0.015)

AWG Size Grade	Inside Diameter			Class 2	
				Thin Wall	
	min	max	nom	min	max
30	0.25 (0.010)	0.38 (0.015)	0.23 (0.009)	0.19 (0.007)	0.28 (0.011)
28	0.33 (0.013)	0.48 (0.019)	0.23 (0.009)	0.18 (0.007)	0.28 (0.011)
26	0.41 (0.016)	0.56 (0.022)	0.23 (0.009)	0.18 (0.007)	0.28 (0.011)
24	0.51 (0.020)	0.69 (0.027)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
22	0.64 (0.025)	0.81 (0.032)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)
20	0.81 (0.032)	1.01 (0.040)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
19	0.91 (0.036)	1.11 (0.044)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
18	1.02 (0.040)	1.25 (0.049)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
17	1.14 (0.045)	1.38 (0.054)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
16	1.30 (0.051)	1.55 (0.061)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
15	1.45 (0.057)	1.70 (0.067)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
14	1.63 (0.064)	1.88 (0.074)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
13	1.83 (0.072)	2.08 (0.082)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
12	2.06 (0.081)	2.31 (0.091)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
11	2.31 (0.091)	2.57 (0.101)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
10	2.59 (0.102)	2.85 (0.112)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)
9	2.90 (0.114)	3.15 (0.124)	0.38 (0.015)	0.31 (0.012)	0.46 (0.018)
8	3.28 (0.129)	3.58 (0.141)	0.38 (0.015)	0.31 (0.012)	0.46 (0.018)
7	3.66 (0.144)	4.01 (0.158)	0.38 (0.015)	0.31 (0.012)	0.46 (0.018)
6	4.12 (0.162)	4.52 (0.178)	0.38 (0.015)	0.31 (0.012)	0.46 (0.018)
5	4.62 (0.182)	5.03 (0.198)	0.38 (0.015)	0.35 (0.012)	0.46 (0.018)
4	5.18 (0.204)	5.69 (0.224)	0.38 (0.015)	0.35 (0.012)	0.46 (0.018)
3	5.82 (0.229)	6.33 (0.249)	0.38 (0.015)	0.35 (0.012)	0.46 (0.018)
2	6.55 (0.258)	7.06 (0.278)	0.38 (0.015)	0.35 (0.012)	0.46 (0.018)
1	7.34 (0.289)	7.90 (0.311)	0.38 (0.015)	0.35 (0.012)	0.46 (0.018)
0	8.26 (0.325)	8.81 (0.347)	0.38 (0.015)	0.35 (0.012)	0.46 (0.018)

4.2.5 *Class 5*—Tubing having walls tabulated in **Table 2** and **Table 3** listed as heavy wall.

4.3 A one-line system may be used to specify materials covered by this specification. The system uses predefined cells to refer to specific aspects of this specification, as illustrated below.

Specification				
Standard Number:	Class:	Grade:	Special Notes	
Block	Group:			
Example: Specification D3295 – 01	01	1	24	

For this example, the line callout would be Specification D3295 – 01, 01124 and would specify tubing having walls

TABLE 2 Dimensions and Tolerances for Group 01 PTFE Tubing, mm (in.) (Classes 3 and 4)

AWG Size Grade	Inside Diameter		Class 3		
			Standard Wall		
	min	max	nom	min	max
30	0.25 (0.010)	0.38 (0.015)	0.23 (0.009)	0.18 (0.007)	0.28 (0.011)
28	0.33 (0.013)	0.48 (0.019)	0.23 (0.009)	0.18 (0.007)	0.28 (0.011)
26	0.41 (0.016)	0.56 (0.022)	0.23 (0.009)	0.18 (0.007)	0.28 (0.011)
24	0.51 (0.020)	0.67 (0.027)	0.31 (0.012)	0.25 (0.010)	0.36 (0.014)
22	0.64 (0.025)	0.81 (0.032)	0.31 (0.012)	0.25 (0.010)	0.36 (0.014)
20	0.81 (0.032)	1.02 (0.040)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
19	0.91 (0.036)	1.11 (0.044)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
18	1.02 (0.040)	1.25 (0.049)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
17	1.14 (0.045)	1.37 (0.054)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
16	1.30 (0.051)	1.55 (0.061)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
15	1.45 (0.057)	1.70 (0.067)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
14	1.63 (0.064)	1.88 (0.074)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
13	1.83 (0.072)	2.08 (0.082)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
12	2.06 (0.081)	2.31 (0.091)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
11	2.31 (0.091)	2.57 (0.101)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
10	2.59 (0.102)	2.85 (0.112)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
9	2.90 (0.114)	3.15 (0.124)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
8	3.28 (0.129)	3.58 (0.141)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
7	3.66 (0.144)	4.01 (0.158)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
6	4.12 (0.162)	4.52 (0.178)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
5	4.62 (0.182)	5.03 (0.198)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
4	5.18 (0.204)	5.69 (0.224)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
3	5.82 (0.229)	6.33 (0.249)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
2	6.55 (0.258)	7.06 (0.278)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
1	7.34 (0.289)	7.90 (0.311)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
0	8.26 (0.325)	8.81 (0.347)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)

AWG Size Grade	Inside Diameter		Class 5		
			Heavy Wall		
	min	max	nom	min	max
24	0.51 (0.020)	0.69 (0.027)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
22	0.64 (0.025)	0.81 (0.032)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
20	0.81 (0.032)	1.02 (0.040)	0.46 (0.018)	0.38 (0.015)	0.53 (0.021)
19	0.91 (0.036)	1.12 (0.044)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
18	1.02 (0.040)	1.25 (0.049)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
17	1.14 (0.045)	1.37 (0.054)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
16	1.30 (0.051)	1.55 (0.061)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
15	1.45 (0.057)	1.70 (0.067)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
14	1.63 (0.064)	1.88 (0.074)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
13	1.83 (0.072)	2.08 (0.082)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
12	2.06 (0.081)	2.31 (0.091)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
11	2.31 (0.091)	2.57 (0.101)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)
10	2.59 (0.102)	2.85 (0.112)	0.64 (0.025)	0.51 (0.020)	0.76 (0.030)
9	2.90 (0.114)	3.15 (0.124)	0.64 (0.025)	0.51 (0.020)	0.76 (0.030)
8	3.28 (0.129)	3.58 (0.141)	0.76 (0.030)	0.64 (0.025)	0.89 (0.035)
7	3.65 (0.144)	4.01 (0.158)	0.76 (0.030)	0.64 (0.025)	0.89 (0.035)
6	4.12 (0.162)	4.52 (0.178)	0.76 (0.030)	0.64 (0.025)	0.89 (0.035)
5	4.62 (0.182)	5.03 (0.198)	0.81 (0.032)	0.69 (0.027)	0.94 (0.037)

listed as light wall that has all the properties listed for that group, class and grade in the appropriate specified properties, tables, or both, in the specification identified. These shall be based on AWG size within the group and class. Grade will be the AWG size designation. Only Groups 01 and 02 shall have requirements for Class and no separator is needed.

5. Physical Properties

5.1 The tubing and miniature beading shall be made of PTFE meeting the requirements of Specification **D4895** and may contain a maximum of two mass percentage of additive.

5.2 The melting point for all Groups of tubing, and miniature beading shall be $327 \pm 10^\circ\text{C}$ ($621 \pm 18^\circ\text{F}$) when measured in accordance with **8.1.4**.

5.3 The inside diameter, wall thickness, pitch and tolerances of the tubing, miniature beading and spiral cut tubing shall be as shown in **Tables 1-3** and **Tables 6-8** when determined in accordance with **8.1.3.1** and **8.1.3.2**.

5.4 The specific gravity of the tubing and miniature beading shall be as specified in **Table 4** when determined in accordance with **8.1.5**.

5.5 The weight loss of the tubing and miniature beading shall not exceed 0.05 % when determined in accordance with **8.1.6**.

5.6 The tubing and miniature beading shall have tensile properties as specified in **Table 4** and a minimum elongation of 200 % when determined in accordance with **8.1.7**.

TABLE 3 Dimensions and Tolerances for Group 02 PTFE Tubing, mm (in.)

Fractional Sizes	Inside Diameter						Wall Thickness					
	Class 1, 2, 3			Class 1			Class 2			Class 3		
	nom	min	max	nom	min	max	nom	min	max	nom	min	max
0.79 (1/32)	0.79 (0.031)	0.74 (0.031)	0.84 (0.033)	0.15 (0.006)	0.10 (0.004)	0.20 (0.008)	0.25 (0.010)	0.20 (0.008)	0.31 (0.012)	0.31 (0.012)	0.25 (0.010)	0.36 (0.014)
1.6 (1/16)	1.7 (0.066)	1.6 (0.063)	1.85 (0.072)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
2.4 (3/32)	2.4 (0.094)	2.3 (0.091)	2.5 (0.099)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)	0.41 (0.016)	0.33 (0.013)	0.48 (0.019)
3.2 (1/8)	3.2 (0.126)	3.1 (0.122)	3.3 (0.130)	0.20 (0.008)	0.15 (0.006)	0.25 (0.010)	0.38 (0.015)	0.28 (0.011)	0.48 (0.019)	0.51 (0.020)	0.40 (0.016)	0.61 (0.024)
4.8 (3/16)	4.7 (0.185)	4.6 (0.181)	5.0 (0.198)	0.25 (0.010)	0.18 (0.007)	0.33 (0.013)	0.38 (0.015)	0.28 (0.011)	0.48 (0.019)	0.51 (0.020)	0.40 (0.016)	0.61 (0.024)
6.4 (1/4)	6.5 (0.255)	6.4 (0.252)	6.6 (0.260)	0.24 (0.009)	0.18 (0.007)	0.33 (0.013)	0.38 (0.015)	0.28 (0.011)	0.48 (0.019)	0.51 (0.020)	0.40 (0.016)	0.61 (0.024)
7.9 (5/16)	8.1 (0.319)	8.0 (0.315)	8.2 (0.332)	0.31 (0.012)	0.23 (0.009)	0.38 (0.015)	0.38 (0.015)	0.28 (0.011)	0.48 (0.019)	0.51 (0.020)	0.40 (0.016)	0.61 (0.024)
9.5 (3/8)	9.7 (0.381)	9.5 (0.374)	9.8 (0.385)	0.38 (0.015)	0.31 (0.012)	0.46 (0.018)	0.38 (0.015)	0.30 (0.012)	0.46 (0.018)	0.64 (0.025)	0.48 (0.019)	0.79 (0.031)
11.1 (7/16)	11.3 (0.445)	11.1 (0.437)	11.7 (0.460)	0.46 (0.018)	0.38 (0.015)	0.53 (0.021)	0.46 (0.018)	0.36 (0.014)	0.56 (0.022)	0.64 (0.025)	0.48 (0.019)	0.79 (0.031)
12.7 (1/2)	12.9 (0.508)	12.7 (0.500)	13.3 (0.523)	0.46 (0.018)	0.38 (0.015)	0.53 (0.021)	0.46 (0.018)	0.36 (0.014)	0.56 (0.022)	0.64 (0.025)	0.48 (0.019)	0.79 (0.031)
15.9 (5/8)	15.2 (0.598)	15.9 (0.624)	16.6 (0.653)	0.07 (0.002)	0.38 (0.015)	0.64 (0.025)	0.51 (0.020)	0.41 (0.016)	0.61 (0.024)	0.76 (0.030)	0.60 (0.024)	0.91 (0.036)
19.0 (3/4)	19.3 (0.760)	19.0 (0.748)	20.0 (0.787)	0.51 (0.020)	0.38 (0.015)	0.64 (0.025)	0.64 (0.025)	0.51 (0.020)	0.76 (0.030)	0.89 (0.035)	0.68 (0.027)	1.09 (0.043)
22.2 (7/8)	22.4 (0.881)	22.2 (0.874)	23.1 (0.909)	0.89 (0.035)	0.68 (0.027)	1.09 (0.043)
25.4 (1)	25.6 (1.08)	25.4 (1.000)	26.3 (1.035)	0.89 (0.035)	0.68 (0.027)	1.09 (0.043)
31.8 (1 1/4)	32.1 (1.264)	31.8 (1.250)	32.7 (1.287)	1.02 (0.040)	0.81 (0.032)	1.22 (0.048)
38.1 (1 1/2)	38.6 (1.552)	38.1 (1.500)	39.4 (1.551)	1.02 (0.045)	0.81 (0.038)	1.22 (0.048)

Fractional Sizes	Inside Diameter		Wall Dimensions	
	Class 4		Class 4	
	max	min	Thickness	Tolerance
3.2 (1/8)	3.3 (0.130)	3.05 (0.120)	0.762 (0.030)	±0.127 (±0.005)
4.8 (3/16)	4.9 (0.193)	4.65 (0.183)	0.762 (0.030)	±0.127 (±0.005)
6.4 (1/4)	6.5 (0.257)	6.17 (0.243)	0.762 (0.030)	±0.127 (±0.005)
9.5 (5/16)	8.13 (0.320)	7.72 (0.304)	0.762 (0.030)	±0.127 (±0.005)
11.1 (3/8)	9.73 (0.383)	9.32 (0.367)	0.762 (0.030)	±0.127 (±0.005)
(7/16)	11.4 (0.448)	10.9 (0.428)	0.762 (0.030)	±0.127 (±0.005)
(1/2)	(0.510)	(0.490)	(0.030)	(±0.006)
(9/16)	(0.572)	(0.552)	(0.030)	(±0.006)
(5/8)	(0.637)	(0.613)	(0.030)	(±0.006)
(1 1/16)	(0.700)	(0.676)	(0.032)	(±0.006)
(3/4)	(0.764)	(0.736)	(0.040)	(±0.007)
(7/8)	(0.891)	(0.859)	(0.045)	(±0.007)
(1)	(1.020)	(0.980)	(0.050)	(±0.008)
(1 1/4)	(1.270)	(1.230)	(0.040)	(±0.008)
(1 1/2)	(1.525)	(1.475)	(0.040)	(±0.008)

Fractional Sizes	Inside Diameter		Wall Dimensions	
	Class 5		Class 5	
	max	min	Thickness	Tolerance
3.2 (1/8)	3.2 (0.125)	2.79 (0.110)	1.57 (0.062)	±0.250 (±0.005)
6.35 (1/4)	6.35 (0.250)	5.84 (0.230)	1.5 (0.062)	±0.250 (±0.005)
9.5 (3/8)	9.53 (0.375)	8.85 (0.350)	1.5 (0.062)	±0.250 (±0.005)

5.7 The tubing shall be a minimum dielectric breakdown as shown in **Table 5** when determined in accordance with **8.1.8**.

5.8 The inside diameter of the tubing shall be within the applicable tolerance limits after subjection to the thermal treatment of **8.1.9**.

5.9 The color of the tubing shall be as agreed upon between the purchaser and the seller. The tubing shall exhibit no significant change in color after heat-aging in accordance with **8.1.10**.

TABLE 4 Physical Requirements for PTFE Tubing

Classification	Melting Point	Specific Gravity	Tensile Strength, min		Elongation, min, %
			MPa	psi	
Group 01	327 ± 10°C (621 ± 18°F)	2.13 to 2.20	20.7	3000	200
Group 02	327 ± 10°C (621 ± 18°F)	over 2.13	13.8	2000	200

TABLE 5 Minimum Dielectric Breakdown Voltage for PTFE Tubing

Nominal Wall Thickness		Dielectric Breakdown Volts, min, V
mm	in.	
0.15 to 0.17	0.006 to 0.0069	9 000
0.18 to 0.23	0.007 to 0.0089	10 000
0.23 to 0.25	0.009 to 0.0099	11 500
0.25 to 0.30	0.010 to 0.0119	12 500
0.30 to 0.38	0.012 to 0.0149	14 600
0.38 to 0.40	0.015 to 0.0159	15 000
0.41 to 0.51	0.016 to 0.0199	16 300
over 0.51	over 0.020	17 000

6. Sampling

6.1 Sampling shall be statistically adequate to satisfy the requirements of 9.4.

7. Number of Tests

7.1 One set of test specimens shall be considered sufficient for testing each lot. The average result of the specimens tested shall conform to the requirements of this specification.

8. Test Methods

8.1 Determine the properties enumerated in this specification in accordance with the following test methods.

8.1.1 *Conditioning*—Conditioning is not required except in referee cases. When conditioning is required, condition the test specimens at 23°C for a period of at least 4 h prior to test. If the test material has been exposed to temperatures below 20°C within 24 h prior to test, the conditioning shall be for at least 24 h. (See Practice D618)

8.1.2 *Test Conditions*—Conduct tests at the standard laboratory temperature of 23 ± 2°C (73.4 ± 3.6°F). The maintenance of constant humidity is not necessary; in referee cases the standard laboratory atmosphere including 50 ± 5 % relative humidity shall apply.

8.1.3 *Dimensions and Tolerances:*

8.1.3.1 *Inside Diameter*—Determine the inside diameter in accordance with Test Method D1675.

8.1.3.2 *Wall Thickness*—Determine the wall thickness in accordance with the procedures described in Test Method D1675, except that no individual measurements shall be allowed to exceed the tolerances specified in Tables 1-3, Tables 6 and 7.

8.1.3.3 *Pitch*—Determine the pitch by measuring across the cut as depicted in Fig. 2.

8.1.3.4 *Outer Diameter of Miniature Beading*—Determine the outer diameter in accordance with the procedures described in Test Method D1675.

8.1.4 *Melting Point*—The melting point shall be determined in accordance with Specification D4895, using a shaving from the tubing rather than a molded disk.

8.1.5 *Specific Gravity*—Determine the specific gravity in accordance with Method A of Test Methods D792. Add two drops of wetting agent (liquid detergent) to the water in order to reduce the surface tension and ensure complete wetting of the specimen.

8.1.6 *Weight Loss*—Determine the loss in weight in accordance with Test Method D1675, except that the minimum weight of the test specimens shall be 50 g and they shall be heated in a forced-draft oven for 3 h at 300 ± 5°C (572 ± 9°F).

8.1.7 *Tensile Strength and Elongation*—Determine the tensile strength and elongation as specified in 8.1.7.1 – 8.1.7.3. Average the test results for the longitudinal and the transverse specimens separately. Determine the tensile properties in accordance with Test Method D638 with the following exceptions. Use the test specimen and die identified in Test Method D1708 and Fig. 1. The initial jaw separation shall be 22.2 ± 0.13 mm (0.875 ± 0.005 in.), and the speed of testing shall be 51 mm/min (2 in./min). Clamp the specimens with essentially equal lengths in each jaw. Determine the elongation from the chart, expressing it as a percentage of the initial jaw separation.

8.1.7.1 *Tubing Having an Inside Diameter of 15.9 mm (0.625 in.) and Over*—Determine the tensile strength and elongation in both the longitudinal and transverse directions. To prepare specimens, slit the tubing parallel to the axis and flatten out, prior to punching out specimens.

8.1.7.2 *Tubing Having an Inside Diameter Less Than 15.9 mm (0.625 in.) to 4.8 mm (0.189 in.) Inclusive*—Determine the tensile strength and elongation in the longitudinal direction. For longitudinal specimens, slit the tubing parallel to the axis and flatten out, prior to punching out specimens.

8.1.7.3 *Tubing Having an Inside Diameter Less Than 4.8 mm (0.189 in.)*—Test specimens as filaments. Make nonslip-type loop knots in each end of the specimen so that there are 34.9 mm (1.37 in.) between the knots of the loops (see Fig. 1). Place loops over the drum of a standard wire specimen holder in the tension testing machine and pull in this position.

8.1.8 *Dielectric Breakdown Voltage*—Determine the dielectric breakdown voltage of the tubing in accordance with Test Method D1675. Testing may be in air or oil, the latter being the referee method.

8.1.9 *Dimensional Stability*—Cut three specimens each 305 mm (12 in.) long, measured to the nearest 1.6 mm (1/16 in.). Place the specimen on steel mandrels having a diameter 5 to 10 % less than the inside diameter of the specimen, then in a circulating-air oven at 260 ± 5°C (500 ± 9°F) for 3 h. Determine the inner diameter and maximum and minimum wall thickness in accordance with 7.1.3.1 and 7.1.3.2. Then remove the specimens from the oven and allow to cool to 23 ± 2°C (73.4 ± 3.6°F). Again measure the length to the nearest 1.6 mm (1/16 in.) and the diameter and the wall thickness.

TABLE 6 Dimensions and Tolerances for Group 03 “Custom or Metric PTFE-Tubing

Inside Diameter		Wall Thickness	
Nominal Inside Diameter, mm (in.)	Inside Diameter Tolerance, mm (in.)	Nominal Thickness, mm (in.)	Thickness Tolerance, mm (in.)
0 to 0.25 (0.000 to 0.010)	±0.03 (0.001)	0 to 0.13 (0.000 to 0.005)	±0.030 (0.001)
0.26 to 0.50 (0.011 to 0.020)	±0.05 (0.002)	0.14 to 0.30 (0.006 to 0.012)	±0.050 (0.002)
0.51 to 0.75 (0.021 to 0.030)	±0.08 (0.003)	0.31 to 0.48 (0.013 to 0.019)	±0.080 (0.003)
0.76 to 2.54 (0.031 to 0.100)	±0.10 (0.004)	0.49 to 0.74 (0.020 to 0.029)	±0.100 (0.004)
2.55 to 4.32 (0.101 to 0.170)	±0.13 (0.005)	0.75 and > (0.030 and >)	±0.130 (0.005)
4.33 to 6.35 (0.171 to 0.250)	±0.15 (0.006)		
6.36 to 19.05 (0.251 to 0.750)	±0.18 (0.007)		
19.06 to 25.39 (0.751 to 0.999)	±0.25 (0.010)		
25.4 and (1.000 and >)	±0.38 (0.015)		

TABLE 7 Dimensions and Tolerances for Group 04 Spiral Cut PTFE-Tubing, mm (in.)

Size	OD	OD Tolerance	Wall	Wall Tolerance	Pitch	Pitch Tolerance
1/8	3.18 (.125)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	5.54 (.218)	±.76 (±.030)
3/16	4.78 (.188)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	7.92 (.312)	±.76 (±.030)
1/4	6.35 (.250)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	9.53 (.375)	±.76 (±.030)
5/16	7.94 (.313)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	9.53 (.375)	±.76 (±.030)
3/8	9.53 (.375)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	11.10 (.437)	±.76 (±.030)
1/2	12.70 (.500)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	14.27 (.562)	±.76 (±.030)
5/8	15.88 (.625)	±0.13 (±.005)	0.76 (.030)	±0.13 (±.005)	15.88 (.625)	±.76 (±.030)
3/4	19.05 (.750)	±0.13 (±.005)	0.89 (.035)	±0.13 (±.005)	22.23 (.875)	±.76 (±.030)
1	25.40 (1.000)	±0.13 (±.005)	1.02 (.040)	±0.13 (±.005)	25.40 (1.000)	±.76 (±.030)

TABLE 8 Dimensions and Tolerances for Group 05 PTFE Miniature Beading, mm (in.)

Diameter	Diameter Tolerance
Nominal Diameter mm (in.)	
0 to 0.25 (0.000 to 0.010)	±0.03 (0.001)
0.26 to 0.50 (0.011 to 0.020)	±0.05 (0.002)
0.51 to 0.75 (0.021 to 0.030)	±0.08 (0.003)
0.76 to 3.81 (0.031 to 0.150)	±0.10 (0.004)




FIG. 1 Tension Specimen for Tubing Less Than 2.29 mm (0.090 in.)

Calculate the change in length as a percentage of the original length and the change in diameter and wall thickness as a percentage of the original length and the change in diameter and wall thickness as a percentage of the original.

8.1.10 *Heat Resistance*—Place three specimens, each 305 mm (12 in.) long, in a circulating-air oven at 260 ± 5°C (500 ± 9°F) for 5 h.

9. Inspection and Certification

9.1 Inspection and certification of the material supplied with reference to a specification based on this specification shall be for conformance to the requirements specified herein.

9.2 Lot-acceptance shall be based on acceptance or rejection of the lot as a whole.

9.3 Lot-acceptance inspection shall consist of measurements for inside diameter and wall thickness.

9.4 Certification shall be that the material was manufactured by a process in statistical control, sampled, tested, and inspected in accordance with this specification, and that the average values for the lot meet the requirements of the specification (line callout).

9.5 A report of test results shall be furnished when requested. The report shall consist of results of the lot-acceptance inspection for the shipment and the results of the most recent periodic-check inspection.

10. Packaging and Package Marking

10.1 *Packaging*—The material shall be packaged in standard commercial containers so constructed as to ensure acceptance by common or other carrier for safe transportation at the lowest rate to the point of delivery, unless otherwise specified in the contract or order.

10.2 *Marking*—Shipping containers can be marked with the name of the material, type, class, size, and quantity contained therein.

10.3 All packing, packaging, and marking provisions of Practice D3892 shall apply to this specification.

11. Keywords

11.1 coagulated dispersion PTFE; fluorocarbon polymer; fluoropolymers; miniature beading; polytetrafluoroethylene; PTFE; PTFE extruded tubing; spiral cut tubing; thin-walled tubing



FIG. 2 Specification for Measuring the Pitch of Spiral Cut Tubing

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D3295-06(2011)) that may impact the use of this standard. (September 1, 2015)

- (1) Fixed multiple conversion errors in **Table 3**.
- (2) Fixed conversion errors in **Fig. 1**.
- (3) Fixed conversion errors in **8.1.7.2** and **8.1.7.3**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/