



Standard Specification for Coilable High Density Polyethylene (HDPE) Cable in Conduit (CIC)¹

This standard is issued under the fixed designation D3485; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers cable in conduit (CIC), which is a smooth-walled, coilable, high-density polyethylene (HDPE) conduit (duct) that contains preassembled wires and cables. The outside diameter of the conduit is controlled and the wire or cable encased within may be comprised of single or multiple configurations consisting of electrical/power wires or cables, fiber optic, traditional copper communication, coaxial cable, or any combination thereof. CIC configurations are preassembled into the conduit during the extrusion process and in industry-specific designs for use in commercial, industrial, transportation, government, and utility applications

1.2 This specification does not attempt to identify every possible preassembled conduit/cable configuration but is intended to identify material and minimum assembled product properties for optimizing reliability and service life.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—Whenever two sets of values are presented, in different units, the imperial units are the standard, while those in the parentheses (metric units) are provided for informational purposes.

NOTE 2—End users may elect to field install single or multiple wire or cable configurations into field-installed conduit. In the case where polyethylene conduit is to have the wire or cable configurations field installed, then the more appropriate specifications to select for establishing the conduit's material, dimensional, workmanship, and property tests would be Specification F2160 or NEMA TC-7.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.26 on Olefin Based Pipe.

Current edition approved March 1, 2015. Published May 2015. Originally approved in 1976. Last previous edition approved in 2008 as D3485–02 which was withdrawn in July 2011 and reinstated in March 2014. DOI:10.1520/D3485-15.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer
- D1505 Test Method for Density of Plastics by the Density-Gradient Technique
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics
- D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings
- D2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading
- D2444 Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)
- D3350 Specification for Polyethylene Plastics Pipe and Fittings Materials
- D4883 Test Method for Density of Polyethylene by the Ultrasound Technique
- F2160 Specification for Solid Wall High Density Polyethylene (HDPE) Conduit Based on Controlled Outside Diameter (OD)
- F412 Terminology Relating to Plastic Piping Systems

2.2 Other References:

- NFPA 70 National Electrical Code³

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from the National Fire Protection Assn., 470 Atlantic Ave., Boston, MA 02210.

NEMA TC 7-2013 Smooth-Wall Coilable Electrical Polyethylene Conduit⁴

Underwriter Laboratories, Inc – UL 1990, Nonmetallic Underground Conduit with Conductors.

IEEE Standard 1210 Standard Tests for Determining Compatibility of Cable-Pulling Lubricants with Wire and Cable

2.3 Plastic Pipe Institute Standards:

Handbook of Polyethylene Pipe

TR-46 (2009) Technical Reference, Guidelines for Use of Mini-Horizontal Directional Drilling for Placement of High Density Polyethylene Pipe (2009)

TR-47/2011 Pipe Stiffness and Flattening Tests in Coilable HDPE conduit; and Its Relationship to burial Depth in Conduit Applications

3.1 Definitions—General terms used in this specification are as defined in Terminology F412 and abbreviations are in accordance with Terminology D1600, unless otherwise specified.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 continuous runs—buried sections of coilable CIC comprised of long lengths having no joints between access structures as opposed to the assembling short sections such as 20 foot lengths of conduit and field installation of the cable or cables.

3.2.2 delaminate, *v*—coextruded layers such as, a color layer on the outside of the conduit, shall be permanently bonded and homogeneous to the conduit wall.

3.2.3 obstructions, *n*—Anything that crosses the path or interrupts a continuous run of conduit or power cable such as, other utilities and road crossings.

3.2.4 termination points—end points of continuous runs of CIC that provide access to the conduit and cable within structures such as vaults, hand holes and manholes for connecting cable to a device or splicing of the cable ends.

3.3 Acronyms:

CIC = Cable in Conduit

HDPE = High Density Polyethylene

4. Application and Installation

4.1 General—This specification covers conduit made from non-pressure rated HDPE resins available in five wall types that are outside diameter controlled.

4.2 HDPE conduit for underground electrical distribution systems utilizing insulations suitable for use with power and electrical conductors not exceeding 194°F (90°C) for normal allowable cable operating temperature. The minimum recommended installation temperature for the HDPE duct is -13°F (-25°C), but in no case should be lower than the minimum installation temperature of the cable.

4.3 CIC is ideally suited for underground or buried installations that allow it to be placed in continuous runs between

termination points with a limited number of obstructions in the route. CIC can be installed using any of the following installation methods; in a trench, plowed or horizontal directionally drilled.

4.4 Concrete encasement of CIC made from HDPE for providing added mechanical protection is an acceptable option.

4.5 CIC may be required by local, state or federal agencies or other governing bodies or codes to be approved for use. For example, CIC with electrical cables may need to be installed in accordance with the NFPA 70 National Electric Code (NEC) and have third party testing, be properly labeled and listed by a certified testing laboratory.

5. Materials and Manufacture

5.1 Polyethylene Plastics—the high-density polyethylene (HDPE) materials used to make the conduit under this specification shall meet or exceed the following requirements:

5.1.1 Compound—PE resin compounds shall be classified in accordance with Specification D3350, Table 1.

5.1.2 Rework Material—Clean polyethylene compound from the manufacturer’s internal production may be compounded into the conduit, either alone or blended with virgin compound. Conduit containing the rework material must meet all the material and property requirements of this specification.

5.1.3 Material Physical Properties:

5.1.3.1 Density—Density values shall be determined by Test Methods D792, D1505 or D4883.

5.1.3.2 Melt Index—Melt index of up to 0.55 grams/10 minutes as per Test Method D1238 condition 190/2.16 is allowable provided that all other material requirements specified in Table 1 are met.

5.1.3.3 Slow Crack Growth—The minimum requirement as per Test method D1693, Condition B, 10% Igepal solution, with a requirement of F10 > 96 hours as defined per cell classification 8 in D3350.

5.1.3.4 The tests listed in this section, shall be confirmed for the PE compound by the resin or conduit manufacturer. In addition, the CIC manufacturer shall conduct the quality control tests listed in Section 7.

5.1.3.5 Minimum resin properties for cell classification 334480C/E (select C for black or E for color) Table 1:

TABLE 1 Minimum Resin Properties Based on Cell Classification per Specification D3350

Properties	ASTM Test Method	Minimum Acceptable Cell / Value
Density	D1505, D792, or D4883	3 / > 0.940 grams/cm ³
Melt Index, (190/2.16)	D1238	3 / <0.40 or 2 see Note 2
Flexural Modulus	D790	4 / ≥ 80,000 psi
Tensile Strength	D638	4 / ≥ 3,000 psi
Slow Crack Growth Resistance	D1693	8 / as defined in 5.1.3.3
Hydrostatic Design Basis	No test required	0 / Not pressure rated
Color and UV resistance	D3350	C or E as defined in 5.4.1

Cell class 2 allows for a higher melt index up to 1.00 but for this standard the maximum allowed is 0.55 provided all of the conditions of 5.1.3.2 are met.

⁴ Available from National Electrical Manufacturers Association (NEMA), 1300 N. 17th St., Suite 1752, Rosslyn, VA 22209, http://www.nema.org.

5.2 *Coextruded Layer*—Any material used as a coextruded layer on the inside or outside surfaces for lubrication or color-coding of the conduit shall adhere to the surface of the PE and shall not delaminate during normal use. Further, coextruded materials shall not degrade or lower the performance of the PE conduit.

5.3 *Above Grade Applications*—PE material installed in above ground application that will be subjected to long term UV exposure, such as aerial suspension, shall have UV stabilization additives compounded into the HDPE. The UV stabilization additives shall be compounded to create homogeneous dispersion for assuring long-term product protection. For example, UV stabilization of black conduit shall have a minimum of 2% by weight of carbon black having an average particle size less than or equal to 45 nanometers and be thoroughly dispersed throughout the conduit wall.

5.3.1 Using smaller particle sizing than 45 nanometers is not recommended due to processing complexities in dispersion and mixing that may adversely impact the conduit’s final homogeneity resulting in reduced performance properties. When using the smaller particle size as specified for above ground applications, the end-user should receive assurance of processing capability from the manufacturer.

5.3.2 Where conduit that is to be extruded with colors other than black and is intended for above grade installation with UV exposure during its service life, the end user should consult with the manufacturer for assurance that the colorant used in extruding the conduit has sufficient UV stabilizer additives that will achieve the service life requirements for the application.

5.4 *Outdoor Storage Stability:*

5.4.1 Both black and color conduits, shall have sufficient formulations of carbon black (2% minimum as defined in Specification D3350) or UV color additives that are properly dispersed either by pre-compounding or compounding during extrusion of the conduit. The additive levels shall be sufficient to protect the conduit from UV degradation during shipping and storage outdoors uncovered for a minimum of 1 year.

6. Requirements

6.1 *Workmanship*—Each conduit layer shall be homogeneous throughout and essentially uniform in color, opacity, density and other properties. The inside and outside surfaces shall be free of visible; cracks, holes, blisters, voids, foreign materials or other surface defects.

6.2 *Dimensions and Tolerances:*

6.2.1 *Outside Diameters*—The outside diameters and tolerances shall be as shown in Table 2 for SDR and Schedule sizes covered by this specification, when measured in accordance with Test Method D2122.

6.2.2 *Wall Thickness*—The wall thicknesses and tolerances shall be as shown in Fig. 3 and Table 4 for the SDR and Schedule sizes respectively, and shall be measured in accordance with Test Method D2122.

6.2.3 *Special Sizes*—When mutually agreed to between the manufacturer and the purchaser, other trade sizes and wall types shall be acceptable provided they adhere to the dimensional tolerances. The tolerance for outside diameter shall be ±

TABLE 2 Outside Diameter and Tolerance for PE Conduit, SDR and Schedule Diameters

Nominal Size in.	Outside Diameter		Tolerance	
	in.	mm	in.	mm
½ (12.7)	0.840	(21.3)	±0.004	(± 0.1)
¾ (19.1)	1.050	(26.7)	±0.005	(± 0.1)
1 (25.4)	1.315	(33.4)	±0.007	(±0.2)
1¼ (31.8)	1.660	(42.2)	±0.008	(±0.2)
1½ (38.1)	1.900	(48.3)	±0.010	(±0.2)
2 (50.8)	2.375	(60.3)	±0.012	(±0.3)
2½ (63.5)	2.875	(73.0)	±0.014	(±0.4)
3 (76.2)	3.500	(88.9)	±0.018	(±0.4)

5% of the nominal outside diameter. The lowest minimum wall thickness for any conduit diameter shall be 0.062 in. (1.57 mm). Tolerances for wall thicknesses shall be a set minimum of +12% or less but not less than 0.020 in.

6.3 *Out-of-Roundness*—is a measurement of variations in wall thickness commonly called out-of-roundness shall not exceed 12% and shall be tested in accordance with Section 7.

6.4 *Ovality:*

6.4.1 There are different causes of ovality for HDPE conduit, the first is processing which can be controlled and shall be less than 5% and measured as follows:

6.4.1.1 *Apparatus*—A micrometer or vernier caliper accurate to within ±0.001 in (± 0.02 mm).

6.4.1.2 *Procedure*—take a series of outside diameter (OD) measurements at closely spaced intervals around the circumference, prior to coiling, to ensure that the minimum and maximum diameters have been determined for the following calculation.

6.4.1.3 *Calculation*—Calculate the percent Ovality as follows:

$$\% \text{ovality} = \frac{(\text{max i m u m O D} - \text{min i m u m O D})}{(\text{max i m u m O D} + \text{min i m u m O D})} \times 200 \tag{1}$$

6.4.2 The second factor influencing ovality is the result of bending the conduit as it is coiled onto reels or as coils. This condition can be minimized by properly cooling the conduit to ambient temperature prior to coiling and by selecting the proper reel drum size. The suggested minimum drum size shall be 18 times the OD of the conduit, rounded to the nearest in. (mm) as shown in Table 5.

6.4.2.1 A third cause of ovality is deformations due to packaging requirements, as such the end sections, when within five (5) ft. of either end of coiled conduit should not be used.

6.4.2.2 Ovality is a packaging condition that occurs when a HDPE conduit is wound into a coil configuration causing the conduit to flatten as it is coiled. The amount of ovality is largely influenced by diameter and bending radius, becoming more oval as the diameter increases or radius decreases. Ovality can be corrected either when clamps designed for rounding are applied, like those used in butt fusion equipment, or by pulling the conduit through re-rounding equipment during installation.

6.5 *Friction Reduction and Prevention of Cable Adhesion:*

TABLE 3 SDR's 15.5, 13.5 and 11 Minimum Walls and Nominal ID's

Nominal Size in. (mm)	SDR 15.5		SDR 13.5		SDR 11	
	Minimum Wall ^A	Nominal ID ^B	Minimum Wall ^A	Nominal ID ^B	Minimum Wall ^A	Nominal ID ^B
½ (12.7)	0.062 (1.6)	0.696 (17.7)	0.062 (1.6)	0.696 (18.0)	0.076 (1.9)	0.679 (17.3)
¾ (19.1)	0.068 (1.7)	0.894 (22.7)	0.078 (1.9)	0.885 (22.5)	0.095 (2.4)	0.849 (21.6)
1 (25.4)	0.085 (2.2)	1.125 (28.6)	0.097 (2.5)	1.109 (28.2)	0.120 (3.1)	1.061 (27.0)
1¼ (31.8)	0.107 (2.7)	1.426 (36.2)	0.123 (3.1)	1.399 (35.5)	0.151 (3.8)	1.340 (34.0)
1½ (38.1)	0.123 (3.1)	1.634 (41.5)	0.141 (3.6)	1.601 (40.7)	0.173 (4.4)	1.533 (38.9)
2 (50.8)	0.153 (3.9)	2.051 (52.1)	0.176 (4.5)	2.002 (50.9)	0.216 (5.5)	1.917 (48.7)
2½ (63.5)	0.185 (4.7)	2.483 (63.1)	0.213 (5.4)	2.423 (61.5)	0.261 (6.6)	2.322 (59.0)
3 (76.2)	0.226 (5.7)	3.021 (76.7)	0.259 (6.6)	2.951 (75.0)	0.318 (8.1)	2.826 (71.8)

^A Minimum wall is calculated by dividing the average OD by the standard dimension ratio (SDR) but shall not be less than 0.062 in. and the maximum wall is determined by adding the allowable wall tolerance of +0.020 in. or +12% of the wall thickness, whichever is greater.

^B The nominal inside diameter is calculated by the following method, (average OD) – ((min wall + ½ Tolerance)*2).

TABLE 4 Schedules 40 and 80 Minimum Walls and Nominal ID's

Nominal Size in. in. (mm)	Schedule 40		Schedule 80	
	Minimum Wall ^A	Nominal ID ^B	Minimum Wall ^A	Nominal ID ^B
½ (12.7)	0.109 (2.8)	0.602 (15.3)	0.147 (3.7)	0.526 (13.4)
¾ (19.1)	0.113 (2.9)	0.804 (20.4)	0.154 (3.9)	0.722 (18.3)
1 (25.4)	0.133 (3.4)	1.029 (26.1)	0.179 (4.6)	0.936 (23.8)
1¼ (31.8)	0.140 (3.6)	1.360 (34.5)	0.191 (4.9)	1.255 (31.9)
1½ (38.1)	0.145 (3.7)	1.590 (40.4)	0.200 (5.1)	1.476 (37.5)
2 (50.8)	0.154 (3.9)	2.047 (52.0)	0.218 (5.5)	1.913 (48.6)
2½ (63.5)	0.203 (5.2)	2.445 (62.1)	0.276 (7.0)	2.290 (58.2)
3 (76.2)	0.216 (5.5)	3.042 (77.3)	0.300 (7.6)	2.864 (72.8)

^A Minimum wall is replicated from F2160, Table 9.

^B Nominal inside diameter is calculated by the following method, (average OD) – ((min wall + ½ Tolerance)*2)

TABLE 5 Suggested Reel Drum, Coil ID Sizes

Nominal Size	Outside Diameter		Minimum Reel Drum/Coil ID	
	in.	(mm)	in.	(mm)
½ (12.7)	0.840	(21.3)	15	(384.0)
¾ (19.1)	1.050	(26.7)	19	(480.6)
1 (25.4)	1.315	(33.4)	24	(601.6)
1¼ (31.8)	1.660	(42.2)	30	(759.0)
1½ (38.1)	1.900	(48.3)	35	(869.0)
2 (50.8)	2.375	(60.3)	43	(1086.2)
2½ (63.5)	2.875	(73.0)	52	(1315.8)
3 (76.2)	3.500	(88.9)	64	(1600.6)

6.5.1 The manufacturer shall implement process controls to assure the cable(s) being installed shall not adhere to the conduit during extrusion and shall move freely within the conduit.

6.5.2 Internal lubrication or a coextruded lubrication layer on the inner wall of the conduit for reducing friction and preventing cable bonding during extrusion shall be permitted.

6.5.3 Liquid type lubricants, that are to be applied during extrusion, shall be tested as specified in 9.4.

6.5.4 Lubrication applied during manufacture of the CIC shall not adversely affect the removal or replacement of cables in the future.

7. Physical Properties

7.1 *Pipe Stiffness*—is the force per unit length of the test specimen, extruded from resin having a minimum flexural modulus of 80,000 psi, loaded at a prescribed rate of 0.5 in./min, at a prescribed percentage deflection of 5%. The test measures the conduit's resistance to ring deflection as it is being compressed between two steel plates. More details describing pipe stiffness as a quality test can be found in Test Method D2412.

7.2 The parallel plate method described above, empirically determines pipe stiffness where as an alternative “calculated” method uses the materials modulus and SDR (Standard Dimension Ratio).

7.2.1 Table 6 below, provides the minimum calculated loads based on the flexural modulus and relative dimension ratios for each wall type listed in this specification.

7.3 *Conduit Size Selection*—this section is provided as a guideline. Actual conduit size must be agreed to between the seller and the purchaser.

7.3.1 *Percent Fill Electrical/Power Cables*—Article 347 of the NFPA 70, the National Electric Code limits the maximum percentage fill of electrical wires or cables. Percentage fill is the ratio of the cross sectional area of the wire(s)/cable(s) installed to the cross sectional area of the conduits ID expressed as a maximum allowable percentage.

7.3.1.1 *Calculations of Conduit Size:*

$$\text{MinimumDuctArea} = 100 \times (A / B) \quad (2)$$

TABLE 6 Minimum Force for Pipe Stiffness at 5% Deflection

Nominal Size	SDR-15.5		SDR 13.5		SDR 11		Schedule 40		Schedule 80	
	Lbs/in/in	kPa	Lbs/in/in	kPa	Lbs/in/in	kPa	Lbs/in/in	kPa	Lbs/in/in	kPa
½ (12.7)	160	1120	180	1260	360	2470	1190	8180	3420	23560
¾ (19.1)	120	810	180	1260	360	2470	630	4330	1820	12530
1 (25.4)	120	810	180	1260	360	2470	510	3520	1400	9960
1¼ (31.8)	120	810	180	1260	360	2470	280	1930	790	5420
1½ (38.1)	120	810	180	1260	360	2470	200	1390	580	4020
2 (50.8)	120	810	180	1260	360	2470	120	820	370	2550
2½ (63.5)	120	810	180	1260	360	2470	160	1080	430	2960
3 (76.2)	120	810	180	1260	360	2470	100	700	300	2060

where:

A = cross-sectional area of cable to be installed, in.² (mm²),
and

B = percent fill from **Table 7**.

7.3.1.2 Maximum percent fill **Table 7** for electrical/power wires/cables:

7.3.1.3 **Table 8** shows the cross-sectional area for the conduit, calculated from the conduits nominal ID: gives cross-sectional area for the various duct sizes.

7.3.2 Communication type cables like fiber optic, copper twisted pair and coaxial cables will follow the same conventions for conduit size selection as described for above in sections 7.3.1.1 through 7.3.1.3.

8. Performance Requirements

8.1 *Toe-In*—When measured in accordance with 6.2.1 the outside diameter at the cut end of the conduit shall not be more than 1.5% smaller than the outside diameter per **Table 2**. Outside diameter measurement shall be made no closer than 1.5 pipe diameters or 11.8 in (300 mm), whichever distance is less, from the cut end of the conduit.

9. Qualification Test Methods

9.1 *Conditioning*—Condition the test specimens at the test temperature for not less than 40 h prior to test in accordance with procedure A of Practice **D618**, for those tests where conditioning is required. Requirements for humidity are excluded.

NOTE 3—These conditioning requirements are only for product qualification or certification testing, not for manufacturing quality assurance purposes.

9.2 *Elongation at Break*—Specimens shall be die cut or machined from the wall of the conduit parallel to the extrusion direction. Testing shall be performed in accordance with Specification **D3350** for tensile properties (that is, in accordance with Test Method **D638** at a strain rate or cross-head separation rate of 2 in/min). If the sample thickness of the specimen must be reduced by milling in order to meet test specimen dimensional requirements, the inside surface of the conduit shall be left unaltered.

9.3 *Impact*—test specimens at a temperature of -4°F (-20°C).

9.3.1 *Low Temperature Test*—Test three specimens of each Nominal Size conduit listed in **Table 12**. The specimens shall be equal in length to the nominal outside diameter but not less than 6 in (152 mm) in length. Condition the specimens at a temperature of $-4 \pm 3.6^\circ\text{F}$ ($-20 \pm 2^\circ\text{C}$) for 5 h. Conduct the test in a room maintained at a temperature of $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$), within 30 s after removal from the cold chamber or if the test is made in an atmosphere or at a temperature other than that at which the specimens are conditioned, conduct the tests

as soon as possible after removal from the cold chamber and test within 30 s. In a case of disagreement, conduct the tests in a room maintained at $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) within 30 s. using the test apparatus and method are described in 9.3.2.

9.3.2 *Test Method*—Using the apparatus as described in Test Method **D2444**, test each specimen separately while it is resting on a solid flat plate as specified in 4.2 of Test Method **D2444**. It is recommended that a protective cage surround the plates and specimen to prevent injury from a failed sample.

9.3.3 Allow a Type B tup as described in Test Method **D2444** to fall freely through a vertical guide so that the minimum impact energies in **Table 9** are attained. Allow the face of the tup to strike the center of the specimen once (provide safeguards as necessary to prevent the tup from striking the specimen more than once). Failure is determined by a crack or tear longer than 0.031 in (0.8 mm) appearing on the inner or outer surface of the conduit.

NOTE 4—The impact test cited in this specification is a product quality control test. The test is known to be affected by the condition of the outside surface of the specimens and by any preexisting cracks in the specimens. The impact requirement included in this specification should not be applied to results obtained on specimens whose surfaces are not representative of the product lot(s) being evaluated. Results on impact specimens, which fail at flaws induced after manufacture, do not indicate inadequate impact resistance as manufactured.

9.4 *Lubrication*—Liquid type cable lubricants shall not diminish the physical properties of the conduit and the jacket or insulating materials of the cables to be installed.

9.4.1 Each type of electric or power wire/cable shall be tested in accordance with IEEE/ICC 1210, Standard Tests for Determining Compatibility of Cable-Pulling Lubricants with Wire and Cable. This qualification test is to assure the lubricant being applied during extrusion of the CIC does not adversely impact the physical properties of the cable jacket/insulating materials on power or electrical cables.

9.4.2 The temperature for testing in accordance with IEEE/ICC Standard 1210 will be reduced to 50°C for all data and communication type cables.

9.4.3 The test is a qualification test for cable compatibility and shall be conducted whenever a new insulation type is added which has not previously been tested and is to be processed as CIC by the manufacturer. Tests shall be conducted for each formulation of lubricant to be used in the manufacture of the CIC or retested any time a formulation is modified by the CIC manufacturer.

10. Retest and Rejection

10.1 If the results of any of the required tests fail to meet the requirements of this specification, the test(s) may be conducted again in accordance with an agreement between the purchaser and the manufacturer. There shall be no agreement to lower the minimum requirement of the specification or eliminate any of the required tests. In retesting, the product requirements of this specification shall be met and the test methods designated in the specification shall be followed. If, upon retest failure to meet the requirements occurs, that quantity of product represented by the test(s) does not meet the requirements of this specification.

TABLE 7 Maximum Percentage Fill (A)

Conductor Type	Number of Conductors				
	1	2	3	4	>4
All (except lead-covered)	53	31	40	40	40
Lead-covered	55	30	40	38	35

TABLE 8 Cross-Sectional areas for Conduit Nominal ID's

Nominal Size, in. (cm)	SDR 15.5		SDR 13.5		SDR 11		Schedule 40		Schedule 80	
	in ²	(cm ²)	in ²	(cm ²)	in ²	(cm ²)	in ²	(cm ²)	in ²	(cm ²)
½ (1.3)	0.413	(2.7)	0.395	(2.5)	0.362	(2.3)	0.285	(1.8)	0.217	(1.4)
¾ (1.9)	0.645	(4.2)	0.615	(4.0)	0.566	(3.7)	0.508	(3.3)	0.409	(2.6)
1 (2.5)	1.012	(6.5)	0.966	(6.2)	0.884	(5.7)	0.832	(5.4)	0.688	(4.4)
1¼ (3.2)	1.613	(10.4)	1.537	(9.9)	1.410	(9.1)	1.453	(9.4)	1.237	(8.0)
1½ (3.8)	2.112	(13.6)	2.013	(13.0)	1.846	(11.9)	1.986	(12.8)	1.711	(11.0)
2 (5.1)	3.301	(21.3)	3.148	(20.3)	2.886	(18.6)	3.291	(21.2)	2.874	(18.5)
2½ (6.4)	4.838	(31.2)	4.611	(29.7)	4.235	(27.3)	4.695	(30.3)	4.119	(26.6)
3 (7.6)	7.168	(46.2)	6.840	(44.1)	6.272	(40.5)	7.268	(46.9)	6.442	(41.6)

TABLE 9 Impact Energy for Impact Testing

Nominal Size In.	Impact Energy Ft-lb	Impact Energy J
½ (12.7)	50	68.0
¾ (19.1)	80	108.8
1 (25.4)	100	136.0
1 ¼ (31.8)	120	163.2
1 ½ (38.1)	150	204.0
2 (50.8)	190	258.4
2 ½ (63.5)	210	285.6
3 (76.2)	220	299.2

11. Certification

11.1 When specified in the purchase order or contract, a manufacturer's certification shall be furnished to the purchaser confirming that the conduit was manufactured, sampled, tested and inspected in accordance with this specification, and has been found to meet the requirements.

11.2 Standard sampling for purposes of certification shall be based at minimum on a given production run or material lot number unless otherwise specified by the purchaser in the purchase order or contract.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/

12. Marking

12.1 Marking on the conduit shall be legible and of a color that contrasts with the color of the conduit. The marking on the conduit shall include at minimum, the following information at intervals not exceeding 3 ft. (1.5 m).

12.1.1 The letters ASTM followed by the designation letter and numbers of this specification (D3485).

12.1.2 The letters HDPE.

12.1.3 Conduit Trade Size (that is, 2.0" IPS, etc).

12.1.4 The wall type, (that is, SDR 13.5 or Schedule 40, etc.)

12.1.5 Name or Trademark, or both, of the manufacturer.

12.1.6 Production code will include the means to identify location and date of manufacture.

12.1.7 Sequential footage (meter) marks shall be accurate to $\pm 2\%$ of the marking interval.

12.1.8 Optional markings may be added as agreed to between the buyer and seller.

13. Keywords

13.1 cable; conduit; high-density polyethylene