



# Standard Performance Specification for Woven Drycleanable Coat Fabrics<sup>1</sup>

This standard is issued under the fixed designation D3562; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This performance specification covers woven drycleanable topcoats, overcoats, and dress coat outer fabrics composed of any textile fiber or mixture of textile fibers.

1.2 This performance specification is not applicable to woven fabrics used for linings, interlinings, rainwear garments, and all-purpose, water-repellent garments nor is this performance specification applicable to bonded or laminated fabrics.

1.3 These requirements apply to both the length and width directions for those properties where each fabric direction is pertinent.

1.4 When a fabric requires special treatment, specific methods will be described as they are developed for that material, and such special tests will have precedence over these general requirements.

1.5 The following precautionary caveat pertains only to the test method portion, Section 7, of this performance specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D123 Terminology Relating to Textiles

D434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam (Withdrawn 2003)<sup>3</sup>

D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus

D2262 Test Method for Tearing Strength of Woven Fabrics

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel.

Current edition approved Feb. 1, 2014. Published March 2014. Originally approved in 1977. Last previous edition approved in 2012 as D3562 – 99(2012). DOI: 10.1520/D3562-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

by the Tongue (Single Rip) Method (Constant-Rate-of-  
Traverse Tensile Testing Machine) (Withdrawn 1995)<sup>3</sup>

D2724 Test Methods for Bonded, Fused, and Laminated  
Apparel Fabrics

D5034 Test Method for Breaking Strength and Elongation of  
Textile Fabrics (Grab Test)

2.2 AATCC Test Methods:<sup>4</sup>

8 Colorfastness to Crocking: AATCC Crockmeter Method

15 Colorfastness to Perspiration

16 Colorfastness to Light

23 Colorfastness to Burnt Gas Fumes

116 Colorfastness to Crocking: Rotary Vertical Crockmeter  
Method

124 Appearance of Durable Press Fabrics after Repeated  
Home Launderings

132 Colorfastness to Drycleaning

135 Dimensional Changes in Automatic Home Laundering  
of Durable Press Woven or Knit Fabrics

Evaluation Procedure 1: Gray Scale for Color Change

Evaluation Procedure 2: Gray Scale for Staining

Evaluation Procedure 3: AATCC Chromatic Transference  
Scale

2.3 Federal Standard:<sup>5</sup>

16 CFR 1610 Chapter II—Consumer Product Safety  
Commission, Subchapter D—Flammable Fabrics Act  
Regulations

2.4 ASQ Standard:

ASQ Z1.4 Sampling Procedures and Tables for Inspection  
by Attributes<sup>6</sup>

NOTE 1—Reference to test methods in this specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

## 3. Terminology

3.1 *Definitions*—For definitions of textile terms used in this specification, refer to the individual ASTM and AATCC test methods and to Terminology D123.

<sup>4</sup> AATCC Technical Manual, available from American Association of Textile Chemists and Colorists (AATCC), One Davis Dr., P.O. Box 12215, Research Triangle Park, NC 27709-2215.

<sup>5</sup> Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401.

<sup>6</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

3.1.1 *pressing and finishing, n*—this term takes into account all of the industrial pressing and finishing treatments used in garment production.

NOTE 2—No standard method is available for reproducing on a laboratory level the results of industrial pressing or finishing treatments used in the manufacture of garments.

4. Significance and Use

4.1 Upon mutual agreement between the purchaser and the seller, woven fabrics intended for this end use should meet all of the requirements listed in Table 1 of this specification.

4.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in Table 1; therefore, one or more of the requirements may be modified by mutual agreement between the purchaser and the seller.

4.2.1 In such cases, any references to the specification shall specify that: This fabric meets Performance Specification D3562 except for the following characteristic(s).

4.3 Where no prepurchase agreement has been reached between the purchaser and the seller, and in case of controversy, the requirements listed in Table 1 are intended to be used as a guide only. As noted in 4.2, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

4.4 The significance and uses of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

5. Sampling

5.1 *Acceptance Testing Lot*—Unless there is prior agreement consider as a lot for acceptance testing all material of a single item received as a single shipment.

5.2 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable specification or other agreement between the purchaser and the seller, such as an agreement to use ASQ Z1.4.

5.3 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric and at least 375 mm (15 in.) along the selvage.

5.4 *Test Specimens*—Take the number of specimens directed in each of the applicable test methods. Perform the tests on the fabric as it will reach the consumer. Any “partially-finished” or “post-finished” fabrics should be processed in accordance with the fabric manufacturer’s instructions.

5.5 If the applicable test method does not specify per laboratory sampling unit. Use a reliable estimate of the variability of individual observations on similar materials in the user’s laboratory, a 95 % probability level, and an allowable difference of 5 % of the average between the test results on laboratory sampling units and the average for the laboratory sampling unit. The average for a laboratory sampling unit is the average that would be obtained by applying the test to all of the potential specimens from that laboratory sampling unit.

6. Specification Requirements

6.1 The properties of fabrics for woven drycleanable coats shall conform to the specification requirements in Table 1.

TABLE 1 Specification Requirements for Woven Drycleanable Coat Fabrics

Characteristic	Requirements		Section
	Men's & Boy's	Women's & Girl's	
Breaking strength (load) (CRT)	133 N (30 lbf), min	133 N (30 lbf), min	7.1
Napped fabrics:			
Length	—	111 N (25 lbf), min	
Width	—	89 N (20 lbf), min	
Resistance to yarn slippage:			7.2
All fabrics, ¼ in. (6 mm) separation	111 N (25 lbf), min	—	
Cross-dyed fabrics,	—	89 N (20 lbf), min	
½ in. (3 mm) separation	—	89 N (20 lbf), min	
Solid shades, ¼ in. (6 mm) separation	—	89 N (20 lbf), min	
Tongue tear strength	13 N (3 lbf), min	13 N (3 lbf), min	7.3
Dimensional change (each direction):			
Pressing	2 % max shrinkage & 0 % growth		7.4.1
After 3 dry cleanings	2 % max shrinkage & 0 % growth		7.4.2
Colorfastness to:			
Burnt gas fumes			
Alteration in shade: 1 cycle each on original & after 1 cleaning	Class 4, min	Grade 4, min	7.5.1
Dry cleaning			7.5.2
Shade change	Grade 4, min	Grade 4, min	
Crocking <sup>A</sup>			7.5.3
Dry	Grade 4, min	Grade 4, min	
Wet	Grade 3.5, min	Grade 3, min	
Perspiration <sup>A</sup>			7.5.4
Shade change	Grade 4, min	Grade 4, min	
Staining	Grade 3.5, min	Grade 3, min	
Light (xenon-arc)			7.5.5
20 AATCC fading units	Grade 4, min	Grade 4, min	
Fabric appearance (see 7.6.1.1)	SA 4, min	See 7.6.1	7.6
Flammability (16 CFR 1610)	Class I	Class I	7.7

<sup>A</sup>See Note 7.

## 7. Test Methods (Note 1)

7.1 *Breaking Force*—Determine the dry breaking force in the standard atmosphere for testing textiles, as directed in Test Method **D5034**, using a constant rate of traverse (CRT) tensile testing machine with the speed of the pulling jaw at  $0 \pm 10$  mm ( $12 \pm 0.5$  in.)/min.

NOTE 3—If preferred, the use of a constant-rate-of-extension (CRE) tensile testing machine is permitted. The crosshead speed should be as agreed between the purchaser and the seller. There may be no overall correlation between the results obtained with the CRT machine and CRE machine. Consequently, these two breaking load testers cannot be used interchangeably. In the case of controversy, the CRT method, Test Method **D1682**, shall prevail.

7.2 *Resistance to Yarn Slippage*—Determine the resistance to yarn slippage as directed in Test Method **D434**.

NOTE 4—The precision of Test Method **D434** is being established and it may not be suitable for fabrics with low yarn counts (see **4.2**) in terms of ends and picks per inch.

7.3 *Tongue Tear Strength*—Determine the tongue tear strength as directed in Test Method **D2262**.

NOTE 5—If preferred, use of Test Method **D1424** is permitted with existing requirements as given in this specification. There may be no overall correlation between the results obtained with the tongue tear machine and the Elmendorf machine. Consequently, these two tongue tear testers cannot be used interchangeably. In the case of controversy, Test Method **D2262** shall prevail.

### 7.4 *Dimensional Change:*

7.4.1 *Pressing and Finishing During Garments Manufacturing*—Mark specimens as directed in 4.3.1 of AATCC Method 135. Press and finish specimens as agreed by the purchaser and the seller with respect to time cycles, temperature, steam, vacuum, and mechanical pressure of the press head. Measure the specimens and calculate the dimensional change as directed in Sections 8 and 9 of AATCC Method 135 (see **Note 2**).

7.4.2 *Drycleaning*—Press the specimen as agreed by the purchaser and the seller prior to drycleaning. Determine the maximum dimensional change after three drycleanings as directed in 10.1.1 through 10.1.6 of Test Method **D2724**.

NOTE 6—Specimens prepared for **7.4.1** may be used for **7.4.2** if desired. When this is done, subtract the pressing dimensional change from the total

dimensional change to obtain that portion due to dry-cleaning.

### 7.5 *Colorfastness:*

7.5.1 *Burnt Gas Fumes*—Determine the colorfastness to burnt gas fumes on the original fabric and after one drycleaning as directed in AATCC Test Method 23.

7.5.2 *Drycleaning*—Determine the colorfastness to drycleaning as directed in AATCC Test Method 132.

7.5.3 *Crocking*—Determine the colorfastness to dry and wet crocking as directed in AATCC Test Method 8 for solid shades or AATCC Test Method 116 for prints, or as agreed between the purchaser and the seller.

NOTE 7—It has been reported that the results for staining, obtained by standard AATCC Test Methods, on fabrics dyed to dark shades that contain a combination of polyester and spandex, or their blends, may not show the full staining propensity of such fabrics in consumer use. It is, therefore, recommended that the staining results obtained by these tests not be used for acceptance testing of such fabrics.

7.5.4 *Perspiration*—Determine the colorfastness to perspiration as directed in AATCC Test Method 15 (acid phase) (see **Note 7**).

7.5.5 *Light*—Determine the colorfastness to light as directed in AATCC Test Method 16A or 16E.

NOTE 8—There is a distinct difference in spectral distribution between the xenon fading lamp apparatus and the enclosed carbon-arc (not sunshine-carbon arc). Consequently, these two fading lamp apparatus cannot be used interchangeably since there is no overall correlation between them. In case of controversy, AATCC Test Method 16E shall prevail.

7.6 *Fabric Appearance*—Determine the fabric appearance as directed in AATCC Test Method 124, after drycleaning as specified in **7.4.2**.

7.6.1 For fabrics not intended for use in “Durable Press” garments, determine the fabric appearance after pressing as specified in 10.2.5 of Test Method **D2724**.

7.7 *Flammability*—The flammability requirements shall be as agreed between the purchaser and the seller, except when regulated by applicable government mandatory standards.

## 8. Keywords

8.1 drycleaning; fabric; overcoat; performance; specification

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*