



Standard Specification for Polychlorotrifluoroethylene (PCTFE) Extruded Plastic Sheet and Film¹

This standard is issued under the fixed designation D3595; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers extruded sheet and film in thicknesses from 0.015 to 0.25 mm (0.0006 to 0.01 in.).

1.2 The values stated in SI units shall be regarded as the standard.

1.3 The following precautionary statement pertains only to the test methods portion, Section 9 of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

- D618 Practice for Conditioning Plastics for Testing
- D882 Test Method for Tensile Properties of Thin Plastic Sheeting
- D883 Terminology Relating to Plastics
- D1204 Test Method for Linear Dimensional Changes of Nonrigid Thermoplastic Sheeting or Film at Elevated Temperature
- D1430 Classification System for Polychlorotrifluoroethylene (PCTFE) Plastics
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D3892 Practice for Packaging/Packing of Plastics
- F1249 Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved March 1, 2014. Published March 2014. Originally approved in 1977. Last previous edition approved in 2007 as D3595 - 02(2007). DOI: 10.1520/D3595-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

IEEE/ASTM SI 10 [Standard for Use of the International System of Units \(SI\): The Modern Metric System](#)³

3. Terminology

3.1 Definitions of terms used in this specification shall be in accordance with Terminology D883.

3.2 *lot, n*—one production run or a uniform blend of two or more production runs.

3.3 Abbreviations are in accordance with Terminology D1600. PCTFE is the abbreviation for polychlorotrifluoroethylene.

4. Classification

4.1 This specification covers four types of polychlorotrifluoroethylene sheet and film:⁴

4.1.1 *Type I*—Transparent film, with high and low moisture vapor transmission rate.

4.1.2 *Type II*—Dimensionally stable transparent sheet and film with low moisture vapor transmission rate.

4.1.3 *Type III*—Dimensionally stable transparent film with very low moisture vapor transmission rate.

4.1.4 *Type IV*—Low crystalline transparent film with high ductility and extremely low moisture vapor transmission.

4.2 A one-line system may be used to specify materials covered by this specification. The system uses predefined cells to refer to specific aspects of this specification, as illustrated below.

Specification				
Standard Number Block	Type	Grade	Class	Special Notes
-----	---	---	---	---
Example: Specification D3595 — 02,	I	6	C	

For this example, the line callout would be Specification D3595 – 02, I6C, and would specify a coagulated dispersion form of polytetrafluoro-ethylene that has all of the properties listed for that Type, Grade, and Class in the appropriate

³ Available from ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428–2959.

⁴ The basic polymer used to make these types of polymer does not correspond to the types given in Specification D1430.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Thickness Tolerance

Thickness		Tolerance, %	Type Availability
mm	in.		
0.015	0.0006	±20	IV
0.019	0.00075	±20	III
0.020	0.0008	±20	IV
0.0216	0.00085	±20	IV
0.023	0.0009	±20	IV
0.038	0.0015	±20	I,
0.051	0.002	±15	I, II, III, IV
0.064	0.0025	±20	IV
0.076	0.003	±15	II
0.102	0.004	±15	II
0.127	0.005	±15	II
0.140	0.0055	±15	IV
0.152	0.006	±15	IV
0.19	0.0075	±10	II
0.20	0.0078	±10	III
0.25	0.010	±10	II

specified properties, tables, or both, in the specification identified. A comma is used as the separator between the Standard Number and the Type. Separators are not needed between the Type, Grade, and Class.⁵ Provision for Special Notes is included so that other information can be provided when required. An example would be in Specification D3295 – 81a where dimensions and tolerances are specified for each AWG size within Type and Class. When Special Notes are used, they should be preceded by a comma.

5. Requirements

5.1 The sheet and film shall be manufactured from polychlorotrifluoroethylene (PCTFE) plastics that consist of at least 90 % chlorotrifluoroethylene. The remaining 10 % may include chemical modifications, such as co-monomers, but not colorants, fillers, plasticizers, or mechanical blends of other resins.

5.2 The length, width, roll core diameter, and maximum number of splices permitted shall be as agreed upon between the purchaser and the seller. The tolerance for roll width shall be 3 mm (1/8 in.). The tolerance for roll length shall be ± 10 % of the specified length.

5.3 Thickness tolerances shall be as specified in [Table 1](#).

5.4 The sheet and film shall conform to the property values specified in [Table 2](#), [Table 3](#), and [Table 4](#).

5.5 The material shall be essentially free from contamination, wrinkles, holes, scratches, and other imperfections unless otherwise agreed upon between the purchaser and the seller.

6. Sampling

6.1 Sampling shall be statistically adequate to satisfy the requirements of [10.4](#).

7. Number of Tests

7.1 One set of test specimens as prescribed in Section 8 shall be considered sufficient for testing each batch. The

TABLE 2 Tensile Strength and Elongation

Thickness, mm (in.)	Type	Tensile Strength, min		Elongation, min, %
		psi	MPa	
0.019 to 0.0075 (0.00075 to 0.0015)	I, II, III	2800	19.32	50
0.051 to 0.002 (0.020 to 0.01)	I, II, III	3100	21.40	50
0.015 to 0.191 (0.0006 to 0.0075)	IV	4000	27.60	70

TABLE 3 Dimensional Stability

Thickness, mm (in.)	Type	Shrinkage, ^A max, %
0.038 to 0.051	I	±15
0.0015 to 0.002		
0.019 to 0.051	II, III	±8
0.00075 to 0.002		
0.051 to 0.250	III	±5
0.002 to 0.010	II, III	±5
0.015 to 0.191 (0.0006 to 0.002)	IV	±15

^APositive sign means increase in length.

TABLE 4 Moisture Vapor Transmission Rate

Thickness		Type	Moisture Vapor Transmission Rate, max, g/m ² × 24 h
mm	in.		
0.038	0.0015	I	0.61
0.191	0.0075	II	0.07
0.0051	0.0002	III	0.14
0.016	0.0006	IV	0.48
0.051	0.002	IV	0.16

average result of the specimens tested shall conform to the requirements of this specification.

8. Specimen Preparation

8.1 *Conditioning*—For those tests where conditioning is required, condition the test specimens in accordance with Procedure A of Practice [D618](#) for a period of at least 24 h prior to test.

8.2 *Test Conditions*—Unless otherwise specified, conduct tests at the Standard Laboratory Temperature of 23 ± 2°C (70 to 77°F) and at 50 ± 10 % relative humidity.

8.3 *Preparation of Specimens*—Take test specimens across the width of the roll.

9. Test Methods

9.1 *Thickness*—Measure the sample across the web width at 25-mm (1-in.) increments. All readings shall be within the specified tolerances. Abnormal readings may occasionally result from spot imperfections. Discard such readings and take new readings in the same area (excluding the defect).

9.2 *Tensile Strength and Elongation*—Determine tensile strength and elongation of the sheet or film in accordance with Test Methods [D882](#), Method A. The specimen size shall be 25 by 127 mm (1 by 5 in.). Elongation rate shall be 508 mm (20 in.)/min. Separation between jaws shall be 51 mm (2 in.). Edges of the specimen shall be parallel within 2 % of the width.

⁵ See the ASTM *Form and Style Manual*. Available from ASTM Headquarters.

9.3 *Dimensional Stability*—Test dimensional stability of the sheet or film in accordance with Test Method **D1204** after exposure to 149°C (300°F) for 10 min.

9.4 *Moisture Vapor Transmission Rate*—Measure the moisture vapor transmission rate in accordance with Test Method **F1249** at 100 % relative humidity at 38°C (100°F).

10. Inspection and Certification

10.1 Inspection and certification of the material supplied with reference to a specification based on this specification shall be for conformance to the requirements specified herein.

10.2 Lot-acceptance shall be the basis on which acceptance or rejection of the lot is made. The lot acceptance inspection shall consist of thickness measurement.

10.3 Periodic check inspection with reference to this specification shall consist of the test for all requirements of the material in accordance with this specification.

10.4 Certification shall be that the material was manufactured by a process in statistical control, sampled, tested, and inspected in accordance with this specification, and that the average values for the lot meet the requirements of this specification.

10.5 A report of test results shall be furnished when requested. The report shall consist of results of the lot-acceptance inspection for the shipment and the results of the most recent periodic-check inspection.

11. Packaging and Package Marking

11.1 *Packaging*—The material shall be packaged in standard commercial containers so constructed as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery, unless otherwise specified in the contract or order.

11.2 *Marking*—Shipping containers shall be marked with the name of the material, type, size, and quantity contained therein. Each roll of tape shall be marked to designate type, grade, and lot number. The marking will be in the core and on the pallet.

11.3 All packing, packaging, and marking provisions of Practice **D3892** shall apply to this specification.

12. Keywords

12.1 chlorofluorocarbon plastics; copolymer; extruded PCTFE; fluorocarbon polymer; fluoropolymers; homopolymer; PCTFE; PCTFE film; PCTFE sheet; polychlorotrifluoroethylene

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D3595 - 02(2007)) that may impact the use of this standard. (March 1, 2014)

(1) Modified **Tables 1-4** to reflect correct conversion values.
 (2) Changed the humidity tolerance in **8.2** from $\pm 5\%$ to $\pm 10\%$.

(3) Removed “%” from **5.2**.
 (4) Removed Test Method **D374** from **2.1** since it is a withdrawn standard.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).