



# Standard Test Method for Acid Number of Styrene-Maleic Anhydride Resins<sup>1</sup>

This standard is issued under the fixed designation D3644; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the measurement of the free acidity present in styrene-maleic anhydride resins.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D329 Specification for Acetone

D1193 Specification for Reagent Water

## 3. Terminology

3.1 *Definitions:*

3.1.1 *acid number*—the number of milligrams of potassium hydroxide (KOH) required to neutralize the alkali-reactive groups in 1 g of material under the conditions of test.

## 4. Significance and Use

4.1 This test method is used to determine the property of styrene-maleic anhydride resins functionality. Acid functionality determines the utility of resin as well as being a significant quality control test.

4.2 Because some of the anhydride functionality has been hydrolyzed in the manufacturing process, direct titration with base will produce erroneous data on the total acid content of the fully hydrolyzed resin in use. This test method charges excess alkali to hydrolyze the anhydride functionality and neutralize the resulting acid. The remaining unreacted alkali is

then back titrated with a standardized acid solution and the acid content is determined by difference.

## 5. Reagents and Materials

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>3</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Specification D1193.

5.3 *Acetone*, conforming to the requirements described in Specification D329.

5.4 *Phenolphthalein Indicator Solution (20 g/L)*—Dissolve 10 g of phenolphthalein in 100 mL of acetone.

5.5 *Sodium Hydroxide, Standard Solution (0.1 N)*—Dissolve 7 g of sodium hydroxide (NaOH) in 7 mL of water, and filter the resulting solution through a glass mat in a Gooch crucible with the aid of suction. Do not wash the residue. Dilute two thirds of the clear filtrate to 1 L with freshly boiled water. Standardize against National Institute of Standards and Technology standard sample of acid potassium phthalate No. 84, using phenolphthalein as the indicator. Do not adjust the concentration of the solution, but calculate the normality.

5.6 *Sulfuric Acid, Standard Solution (0.1 N)*—Measure out 3 mL of concentrated sulfuric acid ( $H_2SO_4$ ) ( $d = 1.84$ ) and pour it slowly, and with constant stirring, into about 100 mL of water. Cool to room temperature, mix thoroughly, and dilute to 1 L. Standardize against 0.1 N NaOH solution, as prepared in 4.5, using phenolphthalein as the indicator. Do not adjust the concentration of the solution, but calculate the normality.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.02 on Raw Materials.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1983. Last previous edition approved in 2012 as D3644 – 06(2012). DOI: 10.1520/D3644-15.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

## 6. Procedure

6.1 Weigh 0.1 g of the sample to the nearest 0.0001 g into a 250-mL Erlenmeyer flask.

6.2 Add  $150 \pm 2$  mL of acetone to the flask, stopper it, and swirl it until the sample is dissolved. All 0.2 mL of phenolphthalein indicator solution and titrate with NaOH solution to the end point, a faint pink color which persists for 30 s. Then add 2.0 mL of additional NaOH solution, stopper the flask, and allow it to stand for exactly 10 min.

NOTE 1—If a precipitate forms during the titration, discard the sample and repeat the test using a smaller sample or a greater volume of acetone, or both. A slight haze can be tolerated and does not interfere with the test.

6.3 Back titrate with 0.1 N  $\text{H}_2\text{SO}_4$  to the end point, at which the sample turns colorless and remains so for 30 s.

6.4 Using the same procedure, titrate a blank composed of 150 mL of acetone and 5 mL of water.

## 7. Calculation

7.1 Calculate the acid number as follows:

$$\text{Blank} = (V_B N_B) - (V_A N_A)$$

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*

$$\text{Acid number} = \frac{(V_B N_B - (V_A N_A + \text{blank})) \times 56.1}{C}$$

$V_A$  = millilitres of  $\text{H}_2\text{SO}_4$ ,  
 $N_A$  = normality of  $\text{H}_2\text{SO}_4$ ,  
 $V_B$  = millilitres of NaOH solution,  
 $N_B$  = normality of NaOH solution, and  
 $C$  = weight of sample.

## 8. Report

8.1 Report the acid number of the resin tested, to the nearest whole number.

## 9. Precision and Bias

9.1 *Precision*—Duplicate results by the same operator shall not be considered suspect unless they differ by more than a standard deviation of 0.8.

9.2 *Bias*—This test has no bias because the values produced are defined only in terms of this test method.

## 10. Keywords

10.1 acid number; free acid; polish; resins; SMA resins; styrene-maleic anhydrid resin; titration