



Standard Specification for Emulsified Asphalt Adhesive for Adhering Roof Insulation¹

This standard is issued under the fixed designation D3747; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers emulsified asphalt adhesive for use in adhering preformed roof insulation to steel roof decks with inclines up to 33 %. When applied as a continuous film over an acceptable deck surface, the emulsion functions as both an adhesive and a vapor retarder.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 The following precautionary caveat pertains only to the test method portion, Section 5, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

- C208 Specification for Cellulosic Fiber Insulating Board
- D244 Test Methods and Practices for Emulsified Asphalts
- D312 Specification for Asphalt Used in Roofing
- D2939 Test Methods for Emulsified Bitumens Used as Protective Coatings
- E96/E96M Test Methods for Water Vapor Transmission of Materials

3. Classification

3.1 *Type I*—Suitable for use at temperatures above 4°C (40°F).

3.2 *Type II*—Suitable for use at temperatures above –7°C (20°F).

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.09 on Bituminous Emulsions.

Current edition approved May 1, 2007. Published May 2007. Originally approved in 1979. Last previous edition approved in 2000 as D3747 – 79 (2000) ^{ϵ 1}. DOI: 10.1520/D3747-79R07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Physical Requirements

4.1 The emulsion shall be homogeneous. There shall be no separation of water or coagulation of the asphalt base, and no settling or packing in the container that cannot be overcome by hand stirring at temperatures above 10°C (50°F).

4.2 The consistency of the emulsion shall permit application at a rate of 0.8 to 1.0 L/m² (2 to 2½ gal/100 ft²) with a brush, long-napped roller, or spray at the minimum temperature for each type. For the application of a continuous film, a spray application is recommended.

4.3 The material shall conform to the physical properties prescribed in Table 1.

5. Sampling and Test Methods

5.1 Sample the material and determine the properties enumerated in this specification in accordance with Test Methods D2939.

5.2 *Water Vapor Permeance*—Test Methods E96/E96M, Procedure E. Prepare specimen in accordance with Test Methods E96/E96M, except for the following modifications:

5.2.1 *Specimen Preparation*—On a silicone-treated sheet of aluminum foil,³ cast a film of the emulsified asphalt at the rate of 0.8 to 1.0 L/m² (2 to 2½ gal/100 ft²) using a draw bar and suitable template. Allow to dry at room temperature for 24 h. After drying, remove the specimen from the silicone-treated aluminum foil and trim to a suitable diameter to fit the test dish.

5.2.2 *Test Cell Assembly*—Fill the test dish with desiccant as prescribed and insert a circular wire grid of 1.18 to 2.00-mm (10 by 10 to 16 by 16-mesh) openings and equal to the size of the specimen under test. Lay the test specimen on the grid and seal as prescribed.

NOTE 1—The specimen may be dusted with talc to facilitate handling.

5.3 *Adhesive Strength:*

5.3.1 *Scope*—This method covers a simple procedure to determine if the cured adhesive strength is adequate.

5.3.2 *Apparatus and Materials:*

5.3.2.1 *Ring Stand*, 225 mm (9 in.) high with 125-mm (5-in.) diameter ring.

³ Available from Daubert Chemical Co., 4700 South Central Ave., Chicago, IL 60638.

TABLE 1 Physical Properties of Emulsified Asphalt Adhesives

Property	Type I		Type II	
	min	max	min	max
Density, kg/m ³ (lb/gal)	988 (8.25)	...	1000 (8.35)	...
Residue by evaporation, %	50	55	50	55
Ash content of residue, %	3.5	...	3.5	...
Heat test results	no blistering, sagging, or slipping			
Adhesive strength	no loss of bond		no loss of bond	
Water vapor permeance, ^A ng/Pa·s·m ² (grain/ft ² ·h·in. Hg)	...	57 (1.0)	...	57 (1.0)
Freezing resistance	remains homogeneous	

^A The requirement for water vapor permeance is pertinent only for those instances where the adhesive will also be used as a vapor retarder.

5.3.2.2 *Sheet Metal*, 1.27 mm (18 gage) thick cold-rolled steel, 150 by 150 mm (6 by 6 in.). Steel shall be clean and free of rust and oil.

5.3.2.3 *Metal Insulation Hanger*,⁴ with perforated plate 50 by 50 mm (2 by 2 in.) and wire spindle approximately 25 mm (1 in.) long.

5.3.2.4 *Mass*, 2.3 kg (5.0 lb).

5.3.2.5 *Preformed Roof Insulating Board*, conforming to the requirements of Specification **C208**, any thickness, 50 by 50 mm (2 by 2 in.).

5.3.2.6 *Asphalt*, conforming to the requirements of Specification **D312**, Type IV.

5.3.3 *Procedure*:

5.3.3.1 Form the metal pin of the metal insulation hanger⁴ into a hook that will position a suspended mass in the center of the sample. Adhere the metal insulation hanger to the top surface of the roof insulation with molten asphalt.

5.3.3.2 Mark off an area 50 by 50 mm (2 by 2 in.) in the center of the sheet metal square and apply 2.0 g of emulsion uniformly to this area.

5.3.3.3 Immediately bring the bottom surface of the roof insulation into intimate contact with the emulsion-coated surface of the sheet metal, using slight pressure to ensure

⁴ Gemco Insulation Hanger Model IH-F can be obtained from Goodloe E. Moore Inc., P.O. Box 846, Danville, IL 61832.

uniform embedment, and allow to cure for 24 h at room temperature (22 ± 2°C (72 ± 3°F)).

5.3.3.4 Turn the assembly upside down and place it on the ring stand so that the ring supports the sheet metal square, and the insulation and hanger are suspended below.

5.3.3.5 Attach the mass to the hanger and allow it to remain suspended in this manner for 2 h. Examine the sample for loss of bond.

5.4 *Freezing Resistance*—Test Methods **D244**, Freezing Test, shall be used for measuring this property.

6. Inspection

6.1 Inspection of the material shall be agreed upon between the purchaser and the supplier as part of the purchase contract.

7. Rejection and Rehearing

7.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

8. Packaging and Marking

8.1 Emulsion shall be packaged to permit acceptance by the carrier for transportation and to afford adequate protection from the normal hazards of handling and shipping.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT).