



Standard Test Method for Plastic-Coated Fabrics—Completeness of Fusion of PVC Dispersion Coatings¹

This standard is issued under the fixed designation D4005; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a simple procedure to determine the completeness of fusion of poly(vinyl chloride) (PVC) dispersion coatings on fabric. This test applies primarily to coatings with a mechanical bond and does not include tie coating.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Summary of Test Method

2.1 Specimens of the PVC-coated fabric are examined for surface cracks or breaks, followed by immersion in acetone. Subsequent appearance of additional cracking indicates that fusion is incomplete.

3. Significance and Use

3.1 Poly(vinyl chloride) (PVC) is applied to coated fabrics as a dispersion of PVC particles in a liquid vehicle. During the processing of the fabric the PVC is fused or melted to produce a uniform film on the fabric. This test measures whether the PVC is converted, fused, or melted to produce a homogeneous film.

3.2 This conversion process is a melting of the crystallite structures in the polymer particles followed by solution of the molten polymer in the plasticizing vehicle. Fusion is important in the production of PVC-coated fabrics.

4. Apparatus and Reagents

4.1 *Glass Beaker, 500-mL.*

4.2 *Acetone.*

4.3 *Glass Rods, 5-mm diameter.*

4.4 *Metal Clips.*

5. Sampling

5.1 Select a sample of coated fabric to adequately represent the roll or lot under consideration.

5.2 Cut three 20 by 40-mm test specimens to be tested, one in the middle and the others from the sides at least 200 mm from the edges of the roll of fabric.

5.3 Remove the PVC coating from the fabric of the test specimens by peeling carefully.

6. Procedure

6.1 Carefully examine each specimen for cracks on the surface or breaks (cracks completely through the film) and record size, frequency, and location.

6.2 Wrap each specimen around a glass rod with the coating under test outward. Secure the assembly with a metal clamp.

6.3 Immerse the test specimens in acetone at 23 ± 2 °C for 15 min. Remove and examine visually. Determine whether cracks or breaks have appeared.

7. Report

7.1 Report the following information:

7.1.1 Description of the material and date manufactured,

7.1.2 Date tested,

7.1.3 If any cracks or breaks have appeared, report that fusion is incomplete, and

7.1.4 Report the observation of each test specimen separately.

8. Precision and Bias

8.1 This test is essentially a “pass-fail” test and does not assess a quantitatively measured test characteristic. Due to this no precision and bias data are reported.

9. Keywords

9.1 coated fabrics; fusion; PVC

¹ This test method is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.37 on Coated Fabrics, Rubber Threads and Seals.

Current edition approved June 1, 2015. Published September 2015. Originally approved in 1981. Last previous edition approved in 2010 as D4005 – 92 (2010). DOI: 10.1520/D4005-92R15.

 **D4005 – 92 (2015)**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>