



Standard Classification System for Nylon Injection and Extrusion Materials (PA)¹

This standard is issued under the fixed designation D4066; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

This standard is maintained in order to support products that must utilize ASTM D4066 in the product definition. This is necessary because there are some differences between the material property test requirements of ASTM D4066 and ASTM D6779, Standard Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA). There are also differences between the two specifications in some of the Group/Class/Grade callouts. Designers of new products are urged to use ASTM D6779 rather than ASTM D4066.

1. Scope*

1.1 This classification system covers nylon materials suitable for injection molding and extrusion. Some of these compositions are also suitable for compression molding and application from solution.

1.2 The properties included in this classification system are those required to identify the compositions covered. There may be other requirements necessary to identify particular characteristics important to specialized applications. These may be specified by using the suffixes as given in Section 5.

1.3 This classification system and subsequent line call-out (specification) are intended to provide a means of calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastic field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this classification system.

1.4 The values stated in SI units are to be regarded as the standard.

1.5 The following precautionary caveat pertains only to the test methods portion, Section 11, of this classification system. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and*

health practices and determine the applicability of regulatory limitations prior to use.

NOTE 1—There is no known ISO equivalent to this standard.

NOTE 2—This classification system is being revised to include international 4-mm specimens and test procedures as the standard for compliance. The 3.2-mm specimens; test methods; and Tables PA, A, and B are included in Appendix X3 as a reference for those wishing to use them. It is recommended that the material manufacturer be consulted on all call-outs against this classification system.

2. Referenced Documents

2.1 ASTM Standards:²

- D149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation
- D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics
- D257 Test Methods for DC Resistance or Conductance of Insulating Materials
- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics
- D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
- D789 Test Methods for Determination of Solution Viscosities of Polyamide (PA)
- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

¹ This classification system is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved July 1, 2013. Published July 2013. Originally approved in 1982. Last previous edition approved in 2008 as D4066-01a(2008), which was withdrawn November 2012 and reinstated in July 2013. DOI: 10.1520/D4066-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D883 Terminology Relating to Plastics
- D1600 Terminology for Abbreviated Terms Relating to Plastics
- D3418 Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry
- D3641 Practice for Injection Molding Test Specimens of Thermoplastic Molding and Extrusion Materials
- D3892 Practice for Packaging/Packing of Plastics
- D4000 Classification System for Specifying Plastic Materials
- D5630 Test Method for Ash Content in Plastics
- D6260 Test Method for Gravimetric Determination of Carbon Black in Nylon Materials (PA) (Withdrawn 2004)³
- D6779 Classification System for and Basis of Specification for Polyamide Molding and Extrusion Materials (PA)
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- 2.2 *Military and Federal Specifications and Standards:*⁴
 - L-P-410 Plastic, Polyamide (Nylon) Rigid: Rods, Tubes, Flats, Molded and Cast Parts
 - VV-I-530 Insulating Oil, Electrical (for Transformers, Switches, and Circuit Breakers)
- 2.3 *ISO Standards:*⁵
 - ISO 75-1:1993 Plastics—Determination of Temperature of Deflection Under Load—Part 1: General Test Methods
 - ISO 75-2:1993 Plastics—Determination of Temperature of Deflection Under Load—Part 2: Plastic and Ebonite
 - ISO 178:1993 Plastics—Determination of Flexural Properties
 - ISO 180:1993 Plastics—Determination of Izod Impact Strength
 - ISO/DIS 294-1:1995 Plastics—Injection Moulding of Test Specimens of Thermoplastic Materials—Part 1: General Principles, Multipurpose-Test Specimens (ISO Mould Type A) and Bars (ISO Mould Type B)
 - ISO 307 Determination of Viscosity Number of Polyamides In Dilute Solutions
 - ISO 527-1:1993 Plastics—Determination of Tensile Properties—Part 1: General Principles
 - ISO 527-2:1993 Plastics—Determination of Tensile Properties—Part 2: Testing Conditions
 - ISO 960:1969 Plastics—Determination of the Water Content in Polyamides
 - ISO 1183:1987 Plastics—Methods for Determining the Density and Relative Density of Non-Cellular Plastics
 - ISO/DIS 1874-2:1995 Plastics—Polyamide (PA) Homopolymers for Moulding and Extrusion—Part 2: Preparation of Test Specimens and Determination of Properties

- ISO 3146: Plastics—Determination of Melting Behaviour (Melting Temperature or Melting Range) of Semi-Crystalline Polymers
- ISO 3167 Plastics, Multipurpose Test Specimens
- ISO 3451-4:1994 Plastics—Determination of Ash—Part 4: Polyamides

3. Terminology

3.1 The terminology used in this classification system is in accordance with Terminologies D883 and D1600.

4. Classification

4.1 Nylon materials are classified into groups according to their composition. These groups are subdivided into classes and grades as shown in the Basic Property Table (Table PA).

NOTE 3—An example of this classification system for unreinforced nylon is given as follows: The designation PA0123 indicates the following:

- PA = polyamide (nylon) as found in Terminology D1600,
- 01 (group) = 66 nylon,
- 2 (class) = heat stabilized, and
- 3 (grade) = with a minimum viscosity number of 210 and the requirements given in Table PA.

NOTE 4—An example of this classification system for reinforced nylon is given as follows: The designation PA012G35 indicates the following:

- PA = polyamide (nylon) as found in Terminology D1600,
- 01 (group) = 66 nylon,
- 2 (class) = heat stabilized, and
- G35 (grade) = nominal 35 % glass with the requirements given in Table PA.

4.1.1 Grades of reinforced or filled versions, or both, of the basic materials are identified by a single letter that indicates the reinforcement or filler used and two digits, in multiples of 5, that indicate the nominal quantity in percent by weight. Thus, a letter designation G for glass reinforced and 35 for percent or reinforcement, G35, specifies a material with a nominal glass level of 35 %. The reinforcement letter designations and associated tolerance levels are shown as follows:

Symbol	Material	Tolerance (Based on the Total Mass)
C	carbon- and graphite-fiber-reinforced	±2 %
G	glass-reinforced	±2 %
L	lubricants (such as PTFE, graphite, silicone, and molybdenum disulfide)	Depends upon material and process—to be specified.
M	mineral-reinforced	±2 %
R	combinations of reinforcements or fillers, or both	±3 %

NOTE 5—This part of the classification system uses percent of reinforcements or additives, or both, in the call-out of the modified basic material. The types and percentages of reinforcements and additives should be shown on the supplier's technical data sheet unless they are proprietary in nature. If necessary, additional control of these reinforcements and additives can be accomplished by use of the suffix part of the system (see Section 5).

NOTE 6—Materials containing reinforcements or fillers, or both, at nominal levels not in multiples of 5 are included in the nearest PA grade designation. For example, a material with a nominal material level of 28 % is included with Grade M30.

NOTE 7—An example of this classification system for a 33 % glass-reinforced nylon is given as follows. The designation PA011G35 indicates the following:

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

PA = polyamide (nylon) as found in Terminology **D1600**,
 01 (group) = 66 nylon,
 1 (class) = general purpose, and

G35 (grade) = with requirements given in Table PA.

NOTE 8—Ash content of filled or reinforced materials may be determined using Test Method **D5630**.

TABLE PA Requirements for Nylons Dry-as-Molded^{A,B}

Group	Description	Class	Description	Grade	Description ^C	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm ³	Tensile Strength, ^D ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m ²	Deflection Temperature at 1.82 MPa, ^E ISO 75-1 and ISO 75-2 min, °C	
01	66 Nylon	1	General-purpose	1		135	1.13–1.15	70	2 300	3.3	60	
				2		165	1.13–1.15	70	2 300	3.3	60	
				3		210	1.13–1.15	70	2 300	3.3	60	
				4		270	1.13–1.15	70	2 300	3.3	60	
				5	recycled	115	1.13–1.15	70	2 300	3.3	60	
				6	recycled	135	1.13–1.15	70	2 300	3.3	60	
				0	other							
				G15	15 % glass	...	1.20–1.26	100	4 000	3.0	215	
				G20	20 % glass	...	1.25–1.33	115	5 000	4.0	220	
				G25	25 % glass	...	1.29–1.37	140	6 000	5.0	225	
		G35	35 % glass	...	1.35–1.45	170	8 000	7.0	235			
		G40	40 % glass	...	1.42–1.52	175	9 000	8.0	235			
		G45	45 % glass	...	1.45–1.55	180	10 000	9.0	240			
		M40	40 % mineral	...	1.45–1.55	80	5 000	2.0	150			
		2	Heat-stabilized	1		135	1.13–1.15	70	2 300	3.0	60	
				2		165	1.13–1.15	70	2 300	3.0	60	
				3		210	1.13–1.15	70	2 300	3.0	60	
				4		270	1.13–1.15	70	2 300	3.0	60	
				5	recycled	115	1.13–1.15	70	2 300	3.0	60	
				6	recycled	135	1.13–1.15	70	2 300	3.0	60	
0	other											
G15	15 % glass			...	1.20–1.26	100	4 000	3.0	220			
G25	25 % glass			...	1.29–1.37	140	6 000	5.0	225			
G30	30 % glass			...	1.32–1.42	160	7 000	6.0	230			
G35	35 % glass			...	1.35–1.45	170	8 000	7.0	235			
G40	40 % glass			...	1.43–1.53	175	9 000	8.0	235			
G45	45 % glass			...	1.45–1.55	180	10 000	9.0	240			
M40	40 % mineral			...	1.45–1.55	80	5 000	2.0	150			
R20	20 % filler			...	1.23–1.31	70	3 200	1.5	...			
R40	40 % filler	...	1.43–1.53	100	5 500	2.5	200					
3	Nucleated	1		135	1.13–1.15	80	2 500	2.8	60			
		2		165	1.13–1.15	80	2 500	2.8	60			
		3		210	1.13–1.15	80	2 500	2.8	60			
		4		270	1.13–1.15	80	2 500	2.8	60			
		5	recycled	115	1.13–1.15	80	2 500	2.8	60			
		6	recycled	135	1.13–1.15	80	2 500	2.8	60			
		0	other									
4	Nucleated, heat-stabilized	1										
		2										
		3										
		4										
		0	other									
5	Impact-modified	1		...	1.06–1.12	52	1 700	9.0	50			
		2	recycled	...	1.06–1.12	50	1 600	8.0	50			
		0	other									
		G15	15 % glass	...	1.15–1.23	85	3 000	6.0	210			
		G35	35 % glass	...	1.31–1.41	110	5 500	6.0	225			
6	Impact-modified, heat-stabilized	1		...	1.08–1.12	52	1 700	9.0	50			
		2	recycled	...	1.08–1.12	50	1 600	8.0	50			
		0	other									
		G15	15 % glass	...	1.15–1.23	85	3 000	6.0	210			
		G35	35 % glass	...	1.31–1.41	110	5 500	6.0	225			
		M40	40 % mineral	...	1.45–1.55	75	4 500	4.0	...			
R35	35 % filler	...	1.38–1.48	80	5 500	3.0	200					
7	Toughened	1		...	1.06–1.10	42	1 500	40	45			
		2	recycled	...	1.05–1.11	40	1 300	35	45			
		0	other									
		G15	15 % glass	...	1.15–1.23	70	2 800	9.0	180			
G35	35 % glass	...	1.28–1.38	110	5 500	11	220					
8	Toughened, heat-stabilized	1		...	1.06–1.10	42	1 500	40	45			
		2	recycled	...	1.05–1.11	40	1 300	35	45			

Requirements the same as corresponding grades under Group 01, Class 3.

TABLE PA Requirements for Nylons Dry-as-Molded^{A,B}

Group	Description	Class	Description	Grade	Description ^C	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm ³	Tensile Strength, ^D ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m ²	Deflection Temperature at 1.82 MPa, ^E ISO 75-1 and ISO 75-2 min, °C
					0 other						
					G15 15 % glass	...	1.15–1.23	70	2 800	9.0	180
					G35 35 % glass	...	1.28–1.38	110	5 500	11	220
					G45 45 % glass	...	1.39–1.49	130	8 000	10	230
					M35 35 % mineral	...	1.37–1.47	70	3 800	6.0	...
		9	Weather-stabilized ^F		1	135	1.13–1.17	80	2 400	2.5	60
					2 recycled	115	1.13–1.17	65	2 200	2.0	60
					0 other						
		0	Other		0 other						
02	6 Nylon	1	General-purpose		1	100	1.12–1.14	75	2 400	4	50
					2	135	1.12–1.14	70	2 200	3	50
					3	150	1.12–1.15	70	2 200	3	50
					4	200	1.12–1.15	70	2 200	3	50
					0 other						
					G15 15 % glass		1.20–1.28	110	4 200	4	170
					G25 25 % glass		1.28–1.36	135	5 000	6.5	180
					G30 30 % glass		1.32–1.40	150	7 000	7.5	180
					G35 35 % glass		1.38–1.44	155	7 500	8	180
					G00 other						
					M30 30 % mineral		1.30–1.40	70	3 200	2.4	50
					M40 40 % mineral		1.44–1.52	75	4 500	4	70
					M00 other						
					R40 40 % glass/ mineral		1.42–1.50	100	6 000	3	180
					R00 other						
		2	Heat-Stabilized		1	100	1.12–1.14	75	2 400	4	50
					2	135	1.12–1.14	70	2 200	3	50
					3	150	1.12–1.15	70	2 200	3	50
					4	200	1.12–1.15	70	2 200	3	50
					7 recycled	135	1.12–1.14	70	2 000	3	50
					0 other						
					G5 5 % glass		1.16–1.22	85	2 500	2.5	110
					G15 15 % glass		1.20–1.28	110	4 200	4	180
					G25 25 % glass		1.28–1.36	135	5 000	6.5	190
					G30 30 % glass		1.32–1.40	150	7 000	7.5	190
					G35 35 % glass		1.36–1.44	155	7 500	8	190
					G45 45 % glass		1.46–1.54	175	10 000	10	190
					G50 50 % glass		1.52–1.60	175	10 000	10	190
					G65 65 % glass		1.70–1.78	175	13 000	10	200
					G00 other						
					M30 30 % mineral		1.30–1.40	70	3 200	2.4	50
					M35 35 % mineral		1.39–1.47	70	3 500	3	60
					M40 40 % mineral		1.44–1.52	75	4 500	4	70
					M00 other						
					R20 20 % glass/ mineral		1.25–1.33	80	3 200	2.5	120
					R40 40 % glass/ mineral		1.42–1.50	100	6 000	3	180
					R00 other						
		3	Nucleated		1	100	1.12–1.14	70	2 300	2.5	50
					2	135	1.12–1.14	70	2 300	2.5	50
					3	150	1.12–1.15	75	2 300	2.5	50
					4	200	1.12–1.15	80	2 300	2.5	50
					0 other						
		4	Nucleated and Heat-Stabilized		1	100	1.12–1.14	70	2 300	2.5	50
					2	135	1.12–1.14	70	2 300	2.5	50
					3	150	1.12–1.15	75	2 300	2.5	50
					4	200	1.12–1.15	80	2 300	2.5	50
					7 recycled	135	1.12–1.14	70	2 100	2.5	50
					0 other						
		5	Impact-Modified		1		1.05–1.12	45	1 700	30	45
					2		1.05–1.18	55	2 000	6	45
					3		1.05–1.18	40	1 000	6	35
					0 other						
					G15 15 % glass		1.15–1.24	75	3 300	9	130
					G30 30 % glass		1.30–1.40	135	6 500	15	180
					G35 35 % glass		1.32–1.42	135	6 800	15	190
					G40 40 % glass		1.39–1.47	135	8 000	10	200
					G00 other						

TABLE PA Requirements for Nylons Dry-as-Molded^{A,B}

Group	Description	Class	Description	Grade	Description ^C	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm ³	Tensile Strength, ^D ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m ²	Deflection Temperature at 1.82 MPa, ^E ISO 75-1 and ISO 75-2 min, °C		
	Impact-Modified, Heat-Stabilized	6		1		1.05–1.12		45	1 700	30	45		
				2		1.05–1.18		55	2 000	6	45		
				3		1.05–1.18		40	1 000	6	35		
				4		1.05–1.18		25	1 000	30	30		
				0	other								
				G15	15 % glass			1.15–1.24		75	3 300	9	130
				G30	30 % glass			1.30–1.40		135	6 500	15	180
				G35	35 % glass			1.32–1.42		135	6 800	10	190
				G40	40 % glass			1.39–1.47		135	8 000	10	200
				G00	other								
				M35	35 % mineral			1.35–1.45		65	3 200	3	50
				M40	40 % mineral			1.37–1.47		65	3 200	3	50
				M00	other								
	Flexurally-Modified, Heat-Stabilized	8		2	injection molding	1.05–1.16		55	2 375 max	10	45		
				3	extrusion	1.05–1.16		30	2 000 max	7	25		
				4	blends	1.05–1.10		35	1 700 max	4.5	35		
				0	other								
03 ^G	11 Nylon	1	General purpose	0	other								
				1		221	1.03–1.06						
				2		234	1.03–1.06	45	1000	4.0	35		
				3		252	1.03–1.06						
				4		291	1.03–1.06						
				5	hydrolysis-resistant		1.03–1.06						
				0	other								
				2	Heat-stabilized	1		234	1.03–1.06				
						2		252	1.03–1.06	45	900	2.0	35
						3		291	1.03–1.06				
						4	hydrolysis-resistant		1.03–1.06				
						0	other						
					Highly plasticized	1			1.03–1.06				
2			1.03–1.06										
3			1.03–1.06										
4			1.03–1.06										
0	other												
4	Highly plasticized, heat stabilized	1			1.03–1.06								
		2			1.03–1.06								
		3			1.03–1.06								
		4			1.03–1.06								
		0	other										
5	Moderately plasticized	1			1.03–1.06								
		2			1.03–1.06								
		3			1.03–1.06								
		4			1.03–1.06								
		5			1.03–1.06								
		0	other										
6	Moderately plasticized, heat-stabilized	1			1.03–1.06								
		2			1.03–1.06								
		3			1.03–1.06								
		4			1.03–1.06								
		5			1.03–1.06								
		0	other										
04	12 Nylon	0	Other	0	other								
				General purpose	1		100–210	1.00–1.06	30	800	2.5	35	
					2		100–210	1.00–1.06	35	1 000	2.5	35	
					3		211–270	1.00–1.06	35	1 000	2.5	35	
					4		271–340	1.00–1.06	35	1 000	2.5	35	
					0	other							
				2	Heat-stabilized	1		100–150	1.00–1.06	35	800	2.5	35
						2		151–210	1.00–1.06	35	800	2.5	35
						3		211–280	1.00–1.06	35	1 000	2.5	35
						0	other						
						G15	15 % glass		1.10–1.20	75	3 000	10	160
						G25	25 % glass		1.10–1.25	90	3 000	15	160
						G30	30 % glass		1.15–1.30	95	4 000	15	160

TABLE PA Requirements for Nylons Dry-as-Molded^{A,B}

Group	Description	Class	Description	Grade	Description ^C	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm ³	Tensile Strength, ^D ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m ²	Deflection Temperature at 1.82 MPa, ^E ISO 75-1 and ISO 75-2 min, °C
				G40	40 % glass		1.30–1.45	100	4 500	15	160
				R30	30 % filler		1.22–1.28	55	3 500	5.0	100
		3	Nucleated	1		100–180	1.00–1.06	35	800	1.0	35
				2		181–250	1.00–1.06	35	800	1.0	35
				0	other						
		4	Plasticized	1		100–280	1.00–1.06	30	300–550	15	...
				2		100–280	1.00–1.06	30	450–750	10	...
				0	other						
		5	Plasticized, heat-stabilized	1		100–280	1.00–1.06	20	200–350	20	...
				2		100–280	1.00–1.06	30	300–550	15	...
				3		100–280	1.00–1.06	30	450–750	10	...
				4		100–280	1.00–1.06	35	550–950	5.0	...
		0	Other	0	other						
05	69 Nylon	1	General purpose	1			1.07–1.09				
				2			1.07–1.09				
				3			1.07–1.09				
				0	other						
		2	Heat-stabilized	1			1.07–1.09				
				2			1.07–1.09				
				3			1.07–1.09				
				0	other						
		0	Other	0	other						
06	612 Nylon	1	General purpose	1		100–139	1.05–1.07	50	1 800	2.0	45
				2		140–199	1.05–1.07	50	1 800	2.5	45
				3		200	1.05–1.07	50	1 800	3.0	45
				0	other						
				G35	35 % glass	...	1.28–1.38	140	7 000	9.0	175
				G45	45 % glass	...	1.38–1.48	150	8 500	11	180
		2	Heat-stabilized	1		140	1.05–1.07	50	1 800	2.0	45
				0	other						
				G30	30 % glass	...	1.25–1.33	120	5 500	5.0	170
				G35	35 % glass	...	1.28–1.38	140	7 000	9.0	175
		3	Weather-stabilized ^F	1		140	1.05–1.07	50	1 800	1.5	45
				0	other						
		0	Other	0	other						
07	610 Nylon	1	General purpose	1			1.05–1.09				
				2			1.05–1.09				
				3			1.05–1.09				
				0	other						
		2	Heat-stabilized	1			1.05–1.09				
				2			1.05–1.09				
				0	other						
		0	Other	0	other						
08	Special	1	n-alkoxy-alkyl 6:6	1			1.09–1.12				
				0	other						
		0	Other	0	other						
09	46 Nylon	1	General-purpose	1							
				2		170	1.16–1.20	85	2 300	6.0	140
				3		195	1.16–1.20	85	2 300	6.0	140
				0	other						
		2	Heat-stabilized	1							
				2		165	1.16–1.20	85	2 300	6.0	140
				3		195	1.16–1.20	85	2 300	6.0	140
				0	other						
				G15	15 % glass	...	1.25–1.31	125	5 000	3.6	240
				G30	30 % glass	...	1.38–1.42	175	8 000	7.5	280
				G40	40 % glass	...	1.48–1.53	195	10 000	10.0	280
				G50	50 % glass	...	1.58–1.63	210	12 000	12.0	280
				R50	50 % filler	...	1.60–1.67	140	9 000	4.0	280
		3	Flame-retardant, ^G heat-stabilized	1							
				2			1.32–1.36	45	2 250	4.0	140
				0	other						
				G15	15 % glass	...	1.55–1.59	115	6 000	4.5	270
				G30	30 % glass	...	1.63–1.69	155	10 000	7.5	280
				G40	40 % glass	...	1.76–1.80	145	11 000	8.0	280
				G45	45 % glass	...	1.75–1.79	165	12 000	8.0	280
		4	Impact-modified, heat-stabilized	1							

TABLE PA Requirements for Nylons Dry-as-Molded^{A,B}

Group	Description	Class	Description	Grade	Description ^C	Viscosity Number, ISO 307, min, mL/g	Density, ISO 1183, g/cm ³	Tensile Strength, ^D ISO 527-1 and ISO 527-2, min, MPa	Flexural Modulus, ISO 178, min, MPa	Izod Impact Resistance, ISO 180/1A, min, kJ/m ²	Deflection Temperature at 1.82 MPa, ^E ISO 75-1 and ISO 75-2 min, °C
				2		...	1.08–1.12	40	1 500	50	70
				0	other						
		5	Wear-resistant heat-stabilized	1							
				2		...	1.16–1.20	75	2 200	3.0	140
				0	other						
10	6T/MPMDT nylon	1	General-purpose	0	other						
		2	Heat-stabilized	G35	35 % glass	...	1.42–1.52	200	10 000	8.0	250
				G45	45 % glass	...	1.53–1.63	210	12 000	8.0	250
		0	Other	0	other						
11	66 nylon copoly-mers + blends	1	66/6	G15	15 % glass	...	1.20–1.26	90	3 500	3.0	180
			General-purpose	G35	35 % glass	...	1.35–1.45	160	7 500	8.0	190
				G45	45 % glass	...	1.45–1.55	180	8 500	10	200
		2	66/6	G15	15 % glass	...	1.20–1.26	90	3 500	3.0	180
			Heat-stabilized	G25	25 % glass	...	1.29–1.37	115	4 500	6.5	190
				G35	35 % glass	...	1.35–1.45	160	7 500	8.0	190
				G45	45 % glass	...	1.45–1.55	180	8 500	10	200
				M20	20 % mineral	...	1.25–1.33	70	3 000	4.0	...
				M30	30 % mineral	...	1.35–1.45	75	4 000	3.0	...
				M40	40 % mineral	...	1.45–1.55	75	4 000	3.0	...
		3	66 + 6	G15	15 % glass	...	1.20–1.26	100	4 000	3.0	200
			General purpose	G35	35 % glass	...	1.35–1.45	170	8 000	9.0	210
				G45	45 % glass	...	1.45–1.55	190	10 000	10	220
		4	66 + 6	M20	20 % mineral	...	1.25–1.33	70	3 000	3.0	...
			Heat-stabilized	M40	40 % mineral	...	1.45–1.55	75	4 500	3.0	...
		0	Other	0	other						
12	6 nylon co-polymer + blends	1	6 + polypropylene blend	1		...	1.00–1.05	50	2 000	7.0	50
				0	other						
			Heat-stabilized	G35	35 % glass	...	1.23–1.33	150	8 500	9.0	200
				R35	35 % filler	...	1.28–1.38	53	6 000	2.0	135
		0	Other	0	other						
13	6T/66 nylon	1	General-purpose	0	other						
		2	Heat-stabilized	G35		...	1.41–1.51	175	9 000	6.0	270
				0	other						
14	PA MXD6 + filters	1	General Purpose	G50	50 % glass	...	1.64–1.66	255	18 000	10	230
				G60	60 % glass	...	1.76–1.78	280	21 000	8	230
		0	Other	0	other						
00	Other	0	Other	0	other						

^AData on 4-mm test specimens may be limited, and the minimum values may be changed in a later revision after a statistical data base of sufficient size is generated.

^BRefer to 9.1 for source of test pieces.

^CNo descriptions are listed unless needed to describe a special grade under the class. All other grades are listed by requirements.

^DCrosshead speed shall be 50 mm/min ± 10 % unless the specimen exhibits brittle failure (no yield point) and strain at break of <10 % in which case crosshead speed shall be 5 mm/min ± 25 %.

^EDeflection temperature shall be determined with the specimen in the flatwise position (Method A₁).

^FWeatherable nylon typically contains 1.90 to 2.25 % carbon black as determined in accordance with methods found in Test Method D6260. It is possible that materials incorporating other pigments or soluble stabilizers, or both may prove adequate for particular applications.

^GRelative Viscosities for Group 03 were generated from a correlation with Test Method D789, utilizing an Ubbelohde viscometer, and m-Cresol as the solvent. Refer to Table X3.1, Note B for more specific information.

4.2 Variations of nylon materials that are not in Table PA are classified in accordance with Tables PA and A or B. Table PA is used to specify the group of nylon and Table A or B is used to specify property requirements.

4.2.1 Specific requirements for variations of nylon materials shall be shown by a six-character designator. The designation will consist of the letter “A” or “B” and the five digits comprising the cell numbers for the property requirements in the order as they appear in Tables A and B.

4.2.1.1 Although the values listed are necessary to include the range of properties available in existing material, users should not infer that every possible combination of the properties exists or can be obtained.

4.2.2 When the grade of the basic material is not known or is not important, the use of “0” grade classification shall be used for reinforced materials in this classification system.

NOTE 9—An example of this classification system for a reinforced nylon material is given as follows. The designation PA0110G30A22450

would indicate the following material requirements:

- PA0110 = 66 nylon, from Table PA,
- G30 = glass reinforced at 30 % nominal,
- A = Table A property requirements,
- 2 = 70-MPa tensile strength, min,
- 2 = 4 500-MPa flexural modulus, min,
- 4 = 10.0-kJ/m² Izod impact, min,
- 5 = 160°C deflection temperature at 1.82 MPa, min, and
- 0 = unspecified.

If no properties are specified, the designation would be PA0110G30A00000.

NOTE 10—When a grade of polyamide is not fully identified by a standard callout, it is possible to specify all table properties by the use of an addition of Classification D4000 suffixes. Suffix values will override the PA table values.

An example of an unreinforced nylon material is given as follows: PA0212UM023. This example is a general purpose, low viscosity nylon 6 material where U denotes flexural modulus. M denotes ISO 178 as the test method, and 023 denotes a value of 2300 MPa. This value for flexural modulus overrides the normal table value.

This example can be applied to replace all table values, that is, tensile stress, notched Izod impact, and heat deflection temperature.

4.3 To facilitate the specification of special materials where the basic property table does not reflect the properties required,

Table B has been incorporated into this classification system. This table will be used in a manner similar to Table A.

NOTE 11—Pigmented or colored nylons can differ significantly from the natural polymers in mechanical properties depending on the choice of colorants and concentrations. The main property affected is ductility, as illustrated by a reduction in Izod impact and elongation values. In a typical white pigmented nylon, elongation losses of up to 50 % and Izod impact losses of up to 30 % are common. If specific properties of pigmented materials are necessary, Table B may be employed to specify property requirements.

NOTE 12—An example of a special material using this classification system is as follows: The designation PA0220B54220 would indicate the following material requirements from Table B:

- PA0220 = 6 nylon, heat stabilized, from Table PA,
- B = Table B property requirements,
- 5 = 70-MPa tensile strength, min,
- 4 = 2400-MPa flexural modulus, min,
- 2 = 4.0-kJ/m² Izod impact, min,
- 2 = 55°C deflection temperature at 1.82 MPa, min, and
- 0 = unspecified.

TABLE A Detail Requirements^{A,B} Reinforced Nylons

Designation Order No.	Property	0	1	2	3	4	5	6	7	8	9
1	Tensile strength, ISO 527, min, MPa ^C	unspecified	35	70	105	140	175	210	245	280	specify ^D value
2	Flexural modulus, ISO 178, min, MPa	unspecified	1 500	4 500	7 500	10 500	13 500	16 500	19 500	22 500	specify ^D value
3	Izod impact, ISO 180/1A, min, kJ/m ²	unspecified	2.5	5.0	7.5	10.0	12.5	15.0	22.5	30.0	specify ^D value
4	Deflection temperature, ISO 75, Method A, 1.82 MPa, min, °C ^E	unspecified	50	85	110	135	160	185	200	235	specify ^D value
5	To be determined	unspecified

^AIt is recognized that detailed test values, particularly Izod impact, may not predict nor even correlate with performance of parts molded of these materials.

^BRefer to 9.1 for source of test specimens.

^CCrosshead speed shall be 50 mm/min ± 10 % unless the specimen exhibits brittle failure (no yield point) and a strain at break of <10 % in which case crosshead speed shall be 5 mm/min ± 25 %.

^DIf a specific value is required, it must appear on the drawing or contract, or both.

^EDeflection temperature shall be determined with the specimen in the flatwise position (Method A_T).

TABLE B Detail Requirements^{A,B} Unreinforced Nylons

Designation Order No.	Property	0	1	2	3	4	5	6	7	8	9
1	Tensile strength, ISO 527, min, MPa ^C	unspecified	10	25	40	55	70	85	100	115	specify ^D value
2	Flexural modulus, ISO 178, min, MPa	unspecified	300	1 000	1 700	2 400	3 100	3 800	4 500	5 200	specify ^D value
3	Izod impact, ISO 180/1A, min, kJ/m ²	unspecified	2.0	4.0	6.0	10.0	14.0	18.0	24.0	30.0	specify ^D value
4	Deflection temperature, ISO 75, Method A, 1.82 MPa, min, °C ^E	unspecified	40	55	70	85	100	115	130	145	specify ^D value
5	To be determined	unspecified

^AIt is recognized that detailed test values, particularly Izod impact, may not predict nor even correlate with performance of parts molded of these materials.

^BRefer to 9.1 for source of test specimens.

^CCrosshead speed shall be 50 mm/min ± 10 % unless the specimen exhibits brittle failure (no yield point) and a strain at break of <10 % in which case crosshead speed shall be 5 mm/min ± 25 %.

^DIf a specific value is required, it must appear on the drawing or contract, or both.

^EDeflection temperature shall be determined with the specimen in the flatwise position (Method A_T).

5. Suffixes

5.1 When additional requirements are needed that are not covered by the basic requirements or cell-table requirements, they shall be indicated through the use of suffixes.

5.1.1 When using the callout for the materials covered by this classification system, the following suffixes may be used for specific requirements for the material for the application intended. In general, the suffix letter gives the general requirements needed and the first number (digit) gives the test condition, with the second number (digit) giving the specific requirement.

Suffixes:

E = Electrical requirements as designated by the following digits:

First Digit

- 0 = to be specified by user.
- 1 = specimens tested dry-as-molded.
- 2 = specimens tested conditions 96 h at 23°C and 50 % relative humidity.

Second Digit

- 0 = to be specified by user.
- 1 = insulation resistance, dielectric strength, dielectric constant, and dissipation factor meet property limits as shown in Table 1. These are electrical limits applied to unreinforced nylons when control of their electrical properties is required.
- 2 = dielectric strength, dielectric constant, and dissipation factor meet property limits as shown in Table 2. These are electrical limits applied to reinforced nylons when control of their electrical properties is required.
- Z = Other special requirement characteristics, that is, color, not covered by existing call-out capabilities may be assigned by the user. These will be spelled out in detail and identified in sequence, that is, 01, 02, 03, etc.

NOTE 13—A further list of suffixes can be found in Classification D4000 and may be used for additional requirements as appropriate.

5.2 A list of suffixes can be found in Classification System D4000 (Table 3) and may be used for additional requirements as appropriate. Additional suffixes will be added to that classification system as test methods and requirements are developed and requested.

NOTE 14—As modified by the following: Electrodes shall be American Standard No. 3 tapered pins 3 in. (76.2 mm) long having a diameter at the large end of 5.56 mm and tapering 6.35 mm/305 mm. The specimen shall be of sufficient size so that two 4.75-mm diameter holes centrally located, 25.4 mm apart, center-to-center, and perpendicular to the faces of the

TABLE 1 Electrical Properties of Unreinforced Nylons

	ASTM Test Method	Requirement
Insulation resistance, min, MΩ	D257 (Note 13)	5 × 10 ⁶
Dielectric strength step-by-step test, min, kV/mm	D149 (Note 14)	14.8 (Note 20)
Dielectric constant at 1 MHz, max	D150 (Note 15)	4.0
Dissipation factor at 1 MHz, max	D150 (Note 15)	0.11

TABLE 2 Electrical Properties of Reinforced Nylons

	ASTM Test Method	Requirement
Dielectric strength step-by-step test, min, kV/mm	D149 (Note 14)	14.8 (Note 20)
Dielectric constant at 1 MHz, max	D150 (Note 15)	4.2
Dissipation factor at 1 MHz, max	D150 (Note 15)	0.025

specimen, may be drilled. The holes shall be drilled as above and then reamed, using a standard-tapered pin reamer, to a sufficient depth to allow the pins to extend approximately 31.75 mm beyond the small end of the hole. The electrodes shall be inserted after the specimens have been conditioned. These specimens shall be tested.

NOTE 15—As modified by the following: The test specimen shall be a disk 101.6 mm in diameter and 3.18 mm thick. Step-by-step testing shall be done after a short-time test where voltage is increased uniformly at the rate of 500 V/s. Voltage increments for the step-by-step test shall be determined from short-time test results as follows:

Breakdown by short-time test, kV	Increment for step-by-step test, kV
12.5 or less	0.5
Over 12.5 to 25, incl	1.0
Over 25 to 50, incl	2.5
Over 50 to 100, incl	5.0
Over 100	10.0

Dielectric strength testing shall be run under oil conforming to Federal Specification VV-I-530 at a frequency not exceeding 100 Hz. Step-by-step testing shall be carried out using five test specimens.

NOTE 16—As modified by the following: The test specimen is a disk 50.8 or 101.6 mm in diameter by 3.18 mm thick. The dissipation factor is the cotangent of the dielectric phase angle or the tangent of the dielectric loss angle. Five specimens shall be tested. After the humidity conditioning specified by the first digit following the E suffix, test specimens are immersed in distilled water at 50°C for 48 h followed by immersion in distilled water at 23°C for ½ h. Start the test within 2 min after removing the specimen and wiping with a dry cloth.

NOTE 17—kV/mm × 25.4 = V/mil.

6. General Requirements

6.1 Basic requirements from the property tables or cell tables are always in effect unless superseded by specific suffix requirements, which always take precedence.

6.2 The plastics composition shall be uniform and shall conform to the requirements specified herein.

7. Detail Requirements

7.1 The material shall conform to the requirements prescribed in Tables PA, A, and B, and suffix requirements as they apply.

7.2 For purposes of determining conformance, all specified limits for classification (line callout based on this classification system are absolute limits, as defined in Practice E29).

7.2.1 With the absolute method, an observed value or a calculated value is not rounded, but is to be compared directly with the specified limiting value. Conformance or nonconformance is based on this comparison.

8. Sampling

8.1 Sampling shall be statistically adequate to satisfy the requirements of 12.4.

8.2 A batch or lot shall be constituted as a unit of manufacture as prepared for shipment, and may consist of a blend of two or more “production runs.”

9. Specimen Preparation

9.1 Test pieces for relevant test methods shall be based on the injection molded ISO 3167 type multipurpose test specimen. All tests shall be conducted on as-molded (not annealed) specimens conditioned dry-as-molded. The following pieces are to be used for the listed relevant test methods:

Test Piece	Relevant Test Method
ISO 3167 Type 1A bar	tensile strength by ISO 527
80 ± 2 mm by 10 ± 9.2 mm by 4 ± 0.2 mm cut from the center portion of ISO 3167 Type 1A bar	flexural modulus by ISO 178. Izod impact resistance by ISO 180/1A deflection temperature by ISO 75/Method A _f
Specimen approximately 10 by 10 by 4 mm cut from center of ISO 3167 Type 1A bar	Density by ISO 1183

9.2 The test specimens shall be prepared by an injection molding process as specified in ISO 294 and Practice D3641. Recommended processing temperatures are shown in Table 3.

NOTE 18—Test specimens of PA 6 and PA 66 copolymers and blends may be prepared at the same process temperatures as specified for their homopolymers, without significant property loss. Selection of process temperature is made based on the major polymer component.

NOTE 19—Consult ISO 1874-2.2, Table 1, for a more comprehensive listing of the Conditions for Injection Moulding of Test Specimens.

9.3 Molding material-granules of the molding material used in preparation of test specimens shall contain no more than 0.2 % moisture, with the exception of PA 46 which will contain no more than 0.05 % moisture.

NOTE 20—If the moisture content exceeds the limits stated above, the material may be dried by a variety of methods such as, a temperature of 80 to 100°C in vacuum or a stream, or both, of dry nitrogen or a desiccant bed dryer, or both, until the moisture content is within stated limits.

10. Conditioning

10.1 *Conditioning*—Test data shall be obtained using dry-as-molded specimens, defined as those specimens that immediately upon removal from mold are sealed in containers that are impermeable to water vapor. Maximum moisture content of specimens shall be 0.2 %. No moisture shall be intentionally added to reach this level. Condition specimens a minimum of 24 h in sealed containers at 23 ± 2°C.

NOTE 21—Physical properties of most nylon resins are highly dependent upon the moisture content of the molded item. The user is referred to the manufacturer’s literature for details.

10.2 *Test Conditions*—Conduct tests, other than solution viscosity or those tests conducted at elevated temperature, in the standard laboratory atmosphere of 23 ± 2°C and 50 ± 5 % relative humidity. Individual specimens shall not be removed from sealed containers until immediately before testing.

11. Test Methods

11.1 Determine the properties enumerated in this classification system by means of the test methods referenced in Section 2.

11.1.1 The number of tests shall be consistent with the requirements of Section 8.18.2 and 12.4.

12. Inspection and Certification

12.1 Inspection and certification of the material supplied with reference to a specification based on this classification system shall be for conformance to the requirements specified herein.

12.2 Lot-acceptance inspection shall be the basis on which acceptance or rejection of the lot is made. The lot-acceptance inspection shall consist of the tests listed as they apply:

- (1) Relative viscosity, or viscosity number, or both,
- (2) Moisture content,
- (3) Reinforcement content,
- (4) Carbon black content (weather-stabilized materials), and
- (5) Heat stabilizer content (heat-stabilized materials, supplier’s test showing positive presence).

12.3 Periodic-check inspection with reference to a specific based upon this classification system shall consist of the tests specified for all requirements of the material under this classification system. Inspection frequency shall be adequate to ensure the material is certifiable in accordance with 12.4.

12.4 Certification shall be that the material was manufactured by a process in statistical control, sampled, tested, and inspected in accordance with this classification system and that the average values for the lot meet the requirements of the specification (line callout).

12.5 A report of the test results shall be furnished when requested. The report shall consist of results of the lot-acceptance inspection for the shipment and the results of the most recent periodic-check inspection.

13. Packing, Packaging, and Marking

13.1 The provisions of Practice D3892 apply to packaging, packing, and marking of containers for plastic materials.

14. Keywords

14.1 classification; classification system; line callout; plastic materials

TABLE 3 Process Temperatures for Injection Molding of Specimens

Polyamide		Plastic Melt Temperature, °C	Mold Surface Temperature, °C
PA 6	unfilled	260	80
	filled	290	80
PA 46	unfilled	305	80
	filled	305	80
PA 66	unfilled	290	80
	filled	290	80
PA 69, PA 610, PA 612, PA 11, PA 12	unfilled	270	80
	filled	230	80
PA 6T/MPMDT	filled	325	140

15. History of Modifications

15.1 D4066 – 01a:

(1) Added Group 14 (PA-MXD6) to Table PA. (2) Made revisions to Table PA for Nylon 6.

15.2 D4066 – 01:

(1) Revised Note F of Table PA.

15.3 D4066 – 00a:

(1) Added Group 13 (PA 6T/66) and Group 00 to Table PA. (2) Removed reinforcement Grades G00, M00, and R00 from Table PA.

15.4 D4066 – 00:

(1) Revised Nylon 46 data in Table PA.

15.5 D4066 – 99:

(1) Table PA was expanded to include Group 03 Nylon 11 data.

15.6 D4066 – 98:

(1) A new Note 10 was added to 4.2 to explain the use of Classification D4000 suffixes, and all subsequent notes were renumbered.

15.7 D4066 – 96a:

(1) This edition includes revised Nylon 6 data in Table PA. (2) Table X3.1 was corrected to reflect Table PA of Classification System D4066 – 94b.

15.8 D4066 – 96:

(1) This edition includes the addition of international test specimens and procedures, and additional grades to Table PA; the removal of melting point, specific gravity, elongation, and moisture content from Table PA; and the addition of melting point to the appendix.

APPENDIXES

(Nonmandatory Information)

X1. VISCOSITY CONVERSION: ASTM TEST METHODS D789 and ISO 307

X1.1 The relation between relative viscosity in 90 % HCOOH (test Methods D789) and viscosity number in 96 % H2SO₄ (ISO 307) was developed in an interlaboratory round-robin study by ISO TC-61 Subcommittee 9/Work Group 8 (Plastic Materials/Polyamides). Seven laboratories, including 3 U.S. laboratories (Allied, DuPont, and Monsanto), participated in the work. A95 ± 9 % between-laboratory confidence interval was predicted for the measurements.

where:

- VN = viscosity number (ISO 307),
- RV = relative viscosity (Test Methods D789),
- A = -206.52124, and
- B = 90.23355.

X1.2 For convenience, a conversion table and graph (Fig. X1.1) are provided using the following established relationship:

$$VN = A + B \times \ln(RV) \tag{X1.1}$$




FIG. X1.1 Nylon 6 and Nylon 66 Viscosity Correlation Relative Viscosity in 90 % HCOOH (Test Methods D789) versus Viscosity Number in 96 % H2SO₄ (ISO 307)

X2. MELTING POINT

X2.1 The melting point range of the various polyamide polymers shown in Table PA are listed as follows:

X2.2 The melting point shall be determined using ISO 3146, Method C2, with a heating rate of 10°C/min. The melting point, T_m, is obtained from the second melting curve.

Group	Description	T _m , °C
02	6 nylon	222
03	11 nylon	190
04	12 nylon	178
05	69 nylon	215
06	612 nylon	212
07	610 nylon	218
08	special	150
09	46 nylon	290
10	6T/MPMDT	300

X3. REFERENCE TO PREVIOUS EDITIONS

X3.1. Referenced Documents

X3.1.1 ASTM Standards:

- D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics
- D638 Test Method for Tensile Properties of Plastics
- D648 Test Method for Deflection Temperature of Plastics Under Flexural Load in the Edgewise Position
- D789 Test Methods for Determination of Solution Viscosities of Polyamide (PA)

- D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
- D3418 Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry

TABLE X3.1 Requirements for Nylons Dry-as-Molded (Table PA, Specification D4066–94b)

Group	Description	Class	Description	Grade	Description ^A	Relative Viscosity, ^B min, ASTM D789	Melt Point, °C, ASTM D3418, DTA or DSC ^{C,D}	Specific Gravity, ASTM D792	Tensile Strength, ^E ASTM D638, min, MPa	Elongation ^F (ultimate), ASTM D638, min, %	Flexural Modulus, ^F ASTM D790, min, MPa	Izod Impact Resistance, ^G ASTM D256, min, J/m	Deflection Temperature, ^H °C, min, ASTM D648 at 1.82 MPa	Moisture ^I "as received," ASTM D789, max, %		
01	66 Nylon	1	General-purpose	1		45	250–265	1.13–1.15	76	50	2 600	50	63	0.25		
				2		60	250–265	1.13–1.15	76	50	2 600	50	63	0.20		
				3		100	250–265	1.13–1.15	76	50	2 600	50	63	0.15		
				4		200	250–265	1.13–1.15	76	100	2 600	50	63	0.15		
				5	recycled	35	250–265	1.13–1.15	76	10	2 600	50	63	0.30		
				6	recycled	45	250–265	1.13–1.15	76	25	2 600	50	63	0.25		
				7	recycled	45	250–265	1.13–1.15	76	50	2 600	50	63	0.25		
				0	other											
				2	Heat-stabilized	1		45	250–265	1.13–1.15	76	40	2 600	40	63	0.25
						2		60	250–265	1.13–1.15	76	40	2 600	40	63	0.20
	3		100			250–265	1.13–1.15	76	40	2 600	40	63	0.15			
	4		200			250–265	1.13–1.15	76	100	2 600	40	63	0.15			
	5	recycled	35			250–265	1.13–1.15	76	10	2 600	40	63	0.30			
	6	recycled	45			250–265	1.13–1.15	76	20	2 600	40	63	0.25			
	7	recycled	45			250–265	1.13–1.15	76	40	2 600	40	63	0.25			
	0	other														
	3	Nucleated	1				45	250–265	1.13–1.15	83	20	2 800	40	63	0.25	
			2				60	250–265	1.13–1.15	83	20	2 800	40	63	0.20	
			3		100	250–265	1.13–1.15	83	20	2 800	40	63	0.15			
			4		200	250–265	1.13–1.15	83	20	2 800	40	63	0.15			
5			recycled	45	250–265	1.13–1.15	83	15	2 600	40	63	0.25				
6			recycled	45	250–265	1.13–1.15	83	20	2 600	40	63	0.25				
0			other													
4	Nucleated, heat-stabilized	1														
		2														
		3														
		4														
		0	other													
5	Highly nucleated	1		45	250–265	1.13–1.15	90	5	2 900	40	63	0.25				
		2		60	250–265	1.13–1.15	90	5	2 900	40	63	0.20				
		3		100	250–265	1.13–1.15	90	5	2 900	40	63	0.15				

Requirements the same as corresponding grades under Group 1 Class 3

TABLE X3.1 *Continued*

Group	Description	Class	Description	Grade	Description ^A	Relative Viscosity, ^B min, ASTM D789	Melt Point, °C, ASTM D3418, DTA or DSC ^{C,D}	Specific Gravity, ASTM D792	Tensile Strength, ^E ASTM D638, min, MPa	Elongation ^E (ultimate), ASTM D638, min, %	Flexural Modulus, ^F ASTM D790, min, MPa	Izod Impact Resistance, ^G ASTM D256, min, J/m	Deflection Temperature, ^H °C, ASTM D648 at 1.82 MPa	Moisture ^I "as received," ASTM D789, max, %	
02	6 Nylon	1	General-purpose	1		30	210–225	1.12–1.14	76	40	2 600	40	58	0.20	
				2		40	210–225	1.12–1.14	76	40	2 600	50	58	0.20	
				3		50	210–225	1.12–1.14	76	100	2 600	50	58	0.20	
				4		95	210–225	1.12–1.14	76	150	2 600	55	58	0.20	
				5		200	210–225	1.12–1.14	76	200	2 600	55	58	0.20	
				6	recycled	30	210–225	1.12–1.14	68	25	2 600	40	58	0.20	
		7	recycled	40	210–225	1.12–1.14	68	35	2 600	40	58	0.20			
		8	recycled	40	210–225	1.12–1.14	76	40	2 600	40	58	0.20			
		0	other												
		2	Heat-stabilized	1		30	210–225	1.12–1.14	76	40	2 600	40	58	0.20	
		2			40	210–225	1.12–1.14	76	40	2 600	50	58	0.20		
		3			50	210–225	1.12–1.14	76	100	2 600	50	58	0.20		
4		95		210–225	1.12–1.14	76	150	2 600	55	58	0.20				
5		200		210–225	1.12–1.14	68	25	2 600	40	58	0.20				
6	recycled	30		210–225	1.12–1.14	68	25	2 600	40	58	0.20				
7	recycled	40	210–225	1.12–1.14	68	35	2 600	40	58	0.20					
8	recycled	40	210–225	1.12–1.14	76	40	2 600	40	58	0.20					
0	other														
					G10	10 % glass	70	...	3 200	25	135	...	
					G15	15 % glass	105	...	4 500	40	185	...	
					G30	30 % glass	140	...	7 500	75	200	...	
					G45	45 % glass	175	...	10 500	100	200	...	
					G00	other									
					M35	35 % mineral	63	...	3 600	50	
					M40	40 % mineral	80	...	4 100	25	85	...	
					M00	other									
					R20	20 % filler	90	...	4 200	25	185	...	
					R40	40 % filler	105	...	6 200	25	185	...	
					R00	other									
	3	Nucleated		1		30	210–225	1.12–1.15	82	10	2 800	35	63	0.20	
				2		40	210–225	1.12–1.15	82	10	2 800	40	63	0.20	
				3		50	210–225	1.12–1.15	82	50	2 800	40	63	0.20	
				4		95	210–225	1.12–1.15	82	100	2 800	45	63	0.20	
				5		200	210–225	1.12–1.15	82	100	2 800	45	63	0.20	
				6	recycled	30	210–225	1.12–1.15	70	10	2 800	35	63	0.20	
				7	recycled	40	210–225	1.12–1.15	70	10	2 800	40	63	0.20	
				8	recycled	40	210–225	1.12–1.15	82	10	2 800	40	63	0.20	
				0	other										
					4	Nucleated, heat-stabilized		1							
2															
3															
4															
5															
6															

Requirements the same as corresponding grades under Group 2 Class 3

TABLE X3.1 *Continued*

Group	Description	Class	Description	Grade	Description ^A	Relative Viscosity, ^B min, ASTM D789	Melt Point, °C, ASTM D3418, DTA or DSC ^{C,D}	Specific Gravity, ASTM D792	Tensile Strength, ^E ASTM D638, min, MPa	Elongation ^E (ultimate), ASTM D638, min, %	Flexural Modulus, ^F ASTM D790, min, MPa	Izod Impact Resistance, ^G ASTM D256, min, J/m	Deflection Temperature, ^H °C, min, ASTM D648 at 1.82 MPa	Moisture ^I "as received," ASTM D789, max, %
				7										
				8										
				0	other									
		5	Flexural-modified	1		...	185–225	1.05–1.16	27	50	700 max	80	33	0.20
				2		...	185–225	1.05–1.16	34	50	1 400 max	80	35	0.20
				3		...	185–225	1.05–1.16	41	50	2 100 max	80	38	0.20
				4		...	185–225	1.05–1.16	55	50	2 800 max	80	44	0.20
				0	other									
		6	Flexural-modified, heat-stabilized	1										
				2										
				3										
				4										
				0	other									
				1										
				2										
				3										
				4										
				0	other									
				1		...	185–225	1.05–1.16	55	50	1 890	55	44	0.20
				2		...	185–225	1.05–1.16	27	50	690	105	33	0.20
				3		...	185–225	1.05–1.16	27	50	550	265	33	0.20
				4		...	185–225	1.05–1.16	27	50	275	425	33	0.20
				5	recycled	...	210–225	1.05–1.16	55	30	1 890	69	65	0.20
				0	other									
		8	Impact-modified, heat-stabilized	1										
				2										
				3										
				4										
				0	other									
				0	other									
		0	Other	0	other									
03	11	Nylon	General-purpose	1		1.53–1.58	185–195	1.03–1.06	41	200	900	55	35	0.15
				2		1.59–1.67	185–195	1.03–1.06	45	200	900	55	40	0.12
				3		1.67–1.82	185–195	1.03–1.06	45	200	900	55	40	0.10
				4		1.83–2.00	185–195	1.03–1.06	48	200	900	55	40	0.08
				5	hydrolysis-resistant ^K	1.83–2.00	185–195	1.03–1.06	48	200	900	55	40	0.08
				0	other									
				1		1.59–1.67	185–195	1.03–1.06	45	200	900	55	40	0.12
				2		1.67–1.82	185–195	1.03–1.06	45	200	900	55	40	0.10
				3		1.83–2.00	185–195	1.03–1.06	48	200	900	55	40	0.08
				4	hydrolysis-resistant	1.83–2.00	185–195	1.03–1.06	48	200	900	55	40	0.08
				0	other									
				1		1.59–1.67	185–195	1.03–1.06	45	250	300	80	35	0.10
				2		1.67–1.82	185–195	1.03–1.06	52	250	300	80	35	0.08
				3		1.83–2.00	185–195	1.03–1.06	52	250	300	80	35	0.08
				4		2.00 min	185–195	1.03–1.06	52	250	300	80	35	0.08
				0	other									
		4	Highly plasticized, heat-stabilized	1										
				2										
				3										
				4										
				0	other									
				1		1.59–1.67	185–195	1.03–1.06	45	250	350	80	35	0.10
				2		1.83–2.00	185–195	1.03–1.06	52	250	350	80	35	0.08
				3		1.59–1.67	185–195	1.03–1.06	45	225	450	80	35	0.08
				4		1.83–2.00	185–195	1.03–1.06	52	225	450	80	35	0.08
				5		1.83–2.00	185–195	1.03–1.06	52	225	600	80	35	0.08
				0	other									

TABLE X3.1 *Continued*

Group	Description	Class	Description	Grade	Description ^A	Relative Viscosity, ^B min, ASTM D789	Melt Point, °C, ASTM D3418, DTA or DSC ^{C,D}	Specific Gravity, ASTM D792	Tensile Strength, ^E ASTM D638, min, MPa	Elongation ^E (ultimate), ASTM D638, min, %	Flexural Modulus, ^F ASTM D790, min, MPa	Izod Impact Resistance, ^G ASTM D256, min, J/m	Deflection Temperature, ^H °C, ASTM D648 at 1.82 MPa	Moisture ^I "as received," ASTM D789, max, %
		6	Moderately plasticized, heat-stabilized	1										
				2										
				3										
				4										
				5										
				0	other									
		0	Other	0	other									
04	12 Nylon	1	General-purpose	1		1.50–2.05	170–185	1.01–1.06	30	140	800	25 ^L	35 ^M	0.10
				2		1.50–2.05	170–185	1.01–1.06	35	150	1 000	25	35	0.10
				3		2.06–2.35	170–185	1.01–1.06	35	150	1 000	25	35	0.10
				4		2.36–2.70	170–185	1.01–1.06	35	150	1 000	25	35	0.10
				0	other									
		2	Heat-stabilized	1		1.50–1.75	170–185	1.00–1.06	35	150	800	25 ^L	35 ^M	0.10
				2		1.76–2.05	170–185	1.00–1.06	35	150	800	25	35	0.10
				3		2.06–2.40	170–185	1.00–1.06	35	150	1 000	25	35	0.10
				0	other									
		3	Nucleated	1		1.50–1.90	170–185	1.00–1.06	35	100	800	10 ^L	35 ^M	0.10
				2		1.91–2.25	170–185	1.00–1.06	35	100	800	25	35	0.10
				0	other									
		4	Plasticized	1		1.50–2.40	165–180	1.00–1.06	30	180	300–550	200 ^L	...	0.10
				2		1.50–2.40	165–180	1.00–1.06	30	200	300–550	200	...	0.10
				3		1.50–2.40	170–185	1.00–1.06	30	200	450–750	100	...	0.10
				0	other									
		5	Plasticized, heat-stabilized	1		1.50–2.40	160–175	1.00–1.06	20	200	200–350	200 ^L	...	0.10
				2		1.50–2.40	165–180	1.00–1.06	30	180	300–550	200	...	0.10
				3		1.50–2.40	165–180	1.00–1.06	30	200	300–550	200	...	0.10
				4		1.50–2.40	170–185	1.00–1.06	30	200	450–750	100	...	0.10
				5		1.50–2.40	170–185	1.00–1.06	35	200	550–950	50	...	0.10
				0	other									
		0	Other	0	other									
05	69 Nylon	1	General-purpose	1		30	208–220	1.07–1.09	60	50	1 900	40	47	0.20
				2		45	208–220	1.07–1.09	60	50	1 900	40	47	0.20
				3		100	208–220	1.07–1.09	60	508	1 900	40	47	0.20
				0	other									
		2	Heat-stabilized	1		30	208–220	1.07–1.09	60	50	1 900	40	47	0.20
				2		45	208–220	1.07–1.09	60	50	1 900	40	47	0.20
				3		100	208–220	1.07–1.09	60	50	1 900	40	47	0.20
				0	other									
		0	Other	0	other									
06	612 Nylon	1	General-purpose	1		0.90 ^N	208–220	1.05–1.07	55	50	1 900	30	65	0.30
				2		1.1 ^N	208–220	1.05–1.07	55	100	1 900	40	65	0.25
				3		1.3 ^N	208–220	1.05–1.07	55	100	1 900	40	60	0.15
				0	other									
		2	Heat-stabilized	1		1.1 ^N	208–220	1.05–1.07	55	50	1 900	35	60	0.30
				0	other									
		3	Weather-stabilized ^J	1		1.1 ^N	208–220	1.05–1.07	40	60	0.30
				0	other									
		0	Other	0	other
07 ^O	610 Nylon	1	General-purpose	1		25	210–222	1.05–1.09	50	50	1 850	40	60	0.25
				2		40	210–222	1.05–1.09	60	70	1 850	45	60	0.22
				3		60	210–222	1.05–1.09	65	70	1 850	45	60	0.22
				0	other									
		2	Heat-stabilized	1		25	210–222	1.05–1.09	50	50	1 850	40	60	0.25
				2		40	210–222	1.05–1.09	60	70	1 850	45	60	0.22
				0	other									
		0	Other	0	other

TABLE X3.1 Continued

Group Description	Class	Description	Grade	Description ^A	Relative Viscosity, ^B min, ASTM D789	Melt Point, °C, ASTM D3418, DTA or DSC ^{C,D}	Specific Gravity, ASTM D792	Tensile Strength, ^E ASTM D638, min, MPa	Elongation ^E (ultimate), ASTM D638, min, %	Flexural Modulus, ^F ASTM D790, min, MPa	Izod Impact Resistance, ^G ASTM D256, min, J/m	Deflection Temperature, ^H °C, ASTM D648 at 1.82 MPa	Moisture ^I "as received," ASTM D789, max, %
08 Special	1	<i>n</i> -Alkoxy-alkyl 6:6	1		40	143–158	1.09–1.12	20	250	200	N/B ^G	...	0.20
			0	other
09 46 Nylon	1	General-purpose	1		45	285–295	1.16–1.20	90	25	2 600	50	140	0.05
			2		80	285–295	1.16–1.20	90	25	2 600	50	140	0.05
			3		125	285–295	1.16–1.20	90	25	2 600	50	140	0.05
			0	other
	2	Heat-stabilized	1		45	285–295	1.16–1.20	90	25	2 600	50	140	0.05
			2		80	285–295	1.16–1.20	90	25	2 600	50	140	0.05
			3		125	285–295	1.16–1.20	90	25	2 600	50	140	0.05
			0	other
	0	Other	0	other
	19 Reinforced/Filleted 46 Nylon ^P	2	Glass-reinforced, heat-stabilized	2	15 % glass	1.28 ^Q	145 ^R	...	4 500	35	275
5				30 % glass	1.41 ^Q	190 ^R	...	7 700	80	280	...
7				40 % glass	1.51 ^Q	210 ^R	...	9 000	85	280	...
9				50 % glass	1.62 ^Q	235 ^R	...	12 000	85	280	...
0				other
2		Glass-reinforced, heat-stabilized, flame-retardant ^S	2	15 % glass	1.53 ^Q	140 ^R	...	4 700	25	270	...
			5	30 % glass	1.68 ^Q	180 ^R	...	8 000	55	280	...
			0	other
3		Mineral-filled, heat-stabilized	7	40 % mineral	1.49 ^Q	100 ^R	...	5 000	25	240	...
			0	other
4	Mineral/glass-filled, heat-stabilized	5	30 % filler	1.40 ^Q	120 ^R	...	5 500	30	270	...	
		7	40 % filler	1.50 ^Q	140 ^R	...	6 000	30	270	...	
		0	other	
0	Other	0	Other	0	other	

^ANo descriptions are listed unless needed to describe a special grade under the class. All other grades are listed by requirements.
^BViscosities for Groups 03, 04, 06, and 08 are measured as described as follows. Refer to Specification D789 for general directions and for the calculation of relative viscosities. Relative viscosities of Groups 03 and 04 shall be measured on 0.5 g of polymer dissolved in 99.5 g of *m*-cresol at 25.0 ± 0.1°C in a Cannon-Fenske No. 200 viscometer. Inherent viscosity of Group 06 shall be measured on 0.5 g of polymer dissolved in 100 mL of *m*-cresol at 25.0 ± 0.1°C in a Cannon-Fenske No. 200 viscometer. The inherent viscosity is calculated as follows:

$$\text{Inherent viscosity} = \frac{\ln(t_s/t_c)}{C}$$

t_s = average efflux time for sample solution,
 t_c = average efflux time for solvent, and
 C = concentration, g/100 mL.

Relative viscosity of Group 08 shall be measured on 9.44 g of polymer dissolved in 100 mL of *m*-cresol at 25.0 ± 0.1°C in a Cannon-Fensky No. 450 viscometer. Details of these methods will be included in a future revision of Specification D789.

^CHeating rate—10°C/min.

^DThe results of an international round robin (ISO-USA, Germany, Japan, Poland, and Italy) showed DSC melt point to be the method having the best reproducibility of results when compared to other available methods (ref. ISO 3146).

^ETensile strength and elongation shall be determined on Test Method D638 test specimens 3.2 ± 0.4 mm thick. The speed of testing shall be 50 mm/min (±10 %) unless otherwise agreed upon.

^FFlexural modulus shall be determined on Test Method D790 test specimens 3.2 by 12.7 by 127 mm with a crosshead speed of 1.3 mm/min (±50 %), Procedure A.

^GIzod impact for these materials shall be conducted on specimens with a 12.7-mm depth and a notch radius of 0.25 mm. The specimens tested are 3.17 mm in width. N/B = No Break.

^HRequirements are based on unannealed test specimens 3.17 mm in width. Annealed specimens tend to give higher results because of the elimination of the effect of molding stresses when annealed in accordance with the supplier's recommendation.

^IGroups 03 and 04 materials use Specification D789 except sample to be immersed in a heat bath for 45 min at 180 ± 2°C.

^JCarbon black content and absorbance must be 1.90 to 2.25 % and 0.230 minimum, respectively, as determined in accordance with methods found in Federal Specification L-P-410a. It is possible, by agreement between the buyer and the seller, that materials incorporating other pigments or soluble stabilizers, or both, may prove adequate for particular applications.

^KHydrolysis-resistance test. To be agreed upon between the user and the supplier.

^LIzod impact requirements for Group 04 materials based on specimens with a 12.7-mm depth, 3.17-mm width, and a notch radius of 0.25 mm.

^MDeflection temperature requirements for Group 04 materials are based on unannealed test specimens 3.17 mm in width.

^NInherent viscosities (dL/g).

^OGroup 07 nylons are presently used commercially only as reinforced materials.

^PMoisture of material¹ as received² shall be 0.05 % max (Test Method **D789**).

^QFor general information (not a requirement).

^RTensile strength and elongation shall be determined on Test Method **D638** test specimens 3.2 ± 0.4 mm thick. The speed of testing shall be 5 mm/min (±10 %) unless otherwise agreed upon.

^SFor specific flammability requirement use the proper suffix from Classification **D4000**, for example, FL310 = (UL 94) VO at 0.8 mm.

TABLE X3.2 Detail Requirements^A Reinforced Nylons (Table A, Specification D4066–94b)

Designation Order No.	Property	0	1	2	3	4	5	6	7	8	9
1	Tensile strength, ASTM D638 , min, MPa ^{B,C}	unspecified	35	70	105	140	175	210	245	280	Specify ^D value
2	Flexural modulus, ASTM D790 , min, MPa ^{B,E}	unspecified	1 500	4 500	7 500	10 500	13 500	16 500	19 500	22 500	Specify ^D value
3	Izod impact, ASTM D256 , min, J/m ^F	unspecified	25	50	75	100	125	150	225	300	Specify ^D value
4	Deflection temperature, ASTM D648 , 1820 kPa, °C, min ^G	unspecified	50	85	110	135	160	185	200	235	Specify ^D value
5	To be determined	unspecified

^AIt is recognized that detailed test values, particularly Izod impact, may not predict nor even correlate with performance of parts molded of these materials.

^BMPa × 145 = psi.

^CTensile strength and elongation shall be determined on Test Method **D638** test specimens 3.2 ± 0.4 mm thick. The speed of testing shall be 5 mm/min (±25 %) unless otherwise agreed upon.

^DIf specific value is required, it must appear on drawing or contract, or both.

^EFlexural modulus shall be determined on Test Methods **D790** test specimens 6.4 by 13 by 130 mm with a crosshead speed of 2.8 mm/min (±50 %), Procedure A.

^FJ/m × 18.73 × 10⁻³ = ft · lbf/in.

^GRequirements are based on unannealed test specimens 3.17 mm in width. Annealed specimens tend to give higher results because of the elimination of the effect of molding stresses when annealed in accordance with the supplier's recommendation.

TABLE X3.3 Detail Requirements^A Unreinforced Nylons (Table B, Specification D4066–94b)

Designation Order No.	Property	0	1	2	3	4	5	6	7	8	9
1	Tensile strength, ASTM D638 , min, MPa ^{B,C}	unspecified	10	25	40	55	70	85	100	115	Specify ^D value
2	Flexural modulus, ASTM D790 , min, MPa ^{B,E}	unspecified	300	1 000	1 700	2 400	3 100	3 800	4 500	5 200	Specify ^D value
3	Izod impact, ASTM D256 , min, J/m ^{C,F}	unspecified	20	40	60	100	140	180	240	300	Specify ^D value
4	Deflection temperature, ASTM D648 , 1820 kPa, °C, min ^G	unspecified	40	55	70	85	100	115	130	145	Specify ^D value
5	To be determined	unspecified

^AIt is recognized that detailed test values, particularly Izod impact, may not predict nor even correlate with performance of parts molded of these materials.

^BMPa × 145 = psi.

^CTensile strength and elongation shall be determined on Test Method **D638** test specimens 3.2 ± 0.4 mm thick. The speed of testing shall be 50 mm/min (±25 %) unless otherwise agreed upon.

^DIf specific value is required, it must appear on drawing or contract, or both.

^EFlexural modulus shall be determined on Test Methods **D790** test specimens 6.4 by 13 by 130 mm with a crosshead speed of 2.8 mm/min (±50 %), Procedure A.

^FJ/m × 18.73 × 10⁻³ = ft · lbf/in.

^GRequirements are based on unannealed test specimens 3.17 mm in width. Annealed specimens tend to give higher results because of the elimination of the effect of molding stresses when annealed in accordance with the supplier's recommendation.

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D4066 - 01a(2008)) that may impact the use of this standard. (July 1, 2013)

(1) Reinstated D4066 with the addition of an introduction.

(3) Updated Note 1.

(2) Added section on History of Modifications.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>