



Standard Practice for Visual Evaluation of Metamerism¹

This standard is issued under the fixed designation D4086; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

Because perceived color involves the spectral characteristics of source, object, and eye, different combinations of spectral characteristics can evoke the same color sensation. For this reason, metamerism has been described as “invisible spectral differences.”

A pair of specimens is said to be metameric when the specimens match under one set of illuminating and viewing conditions and do not match under another set. For this condition to exist, there must be differences in spectral character of specimens and sources or specimens and observers. There may be more than one condition under which the specimens match, as well as more than one for which they are a mismatch. Similarly, two specimens may be a near-match under one set of conditions, and under another set the direction and magnitude of the color difference may change.

1. Scope

1.1 This practice describes visual methods for detecting metamerism and for estimating the magnitude of a metameric color difference.

1.2 The practice is limited to the consideration of illuminant metamerism and observer metamerism. It is not designed to cover so-called geometric metamerism, in which members of specimen pairs change relative appearance as the angles of illumination and viewing are changed, for example, because they incorporate flake metal or pearlescent colorants.

1.3 This practice does not provide for the computation of indices of metamerism based upon instrumental measurement of spectral characteristics.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

¹ This practice is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.11 on Visual Methods.

Current edition approved July 1, 2012. Published August 2012. Originally approved in 1982. Last previous edition approved in 2007 as D4086 – 92a (2007). DOI: 10.1520/D4086-92AR12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

D2616 Test Method for Evaluation of Visual Color Difference With a Gray Scale

E284 Terminology of Appearance

3. Terminology

3.1 Definitions of appearance terms used in this practice may be found in Terminology E284.

3.2 *Definitions:*

3.2.1 *metamerism, n*—property of two specimens that match under a specified illuminator and to a specified observer and whose spectral reflectances or transmittances differ in the visible wavelengths.

3.2.1.1 *Discussion*—As a consequence of the required difference, the two specimens may not match under a different illuminator or to a different observer. Similar considerations apply to two lights matching to a specified observer but not to other observers. (E284)

3.2.2 *paramerism, n*—phenomenon in which specimens having different spectrophotometric curves produce approximately the same color sensation under the same illuminating and viewing conditions. (E284)

4. Significance and Use

4.1 Metameric color matches result from the use of different colorants (pigments, dyes, and the like) in achieving the same color match. Usually, the purchaser requires that the color match be nonmetameric; this practice permits this requirement to be quickly tested in both field and laboratory. Where nonmetameric matches are not possible or practicable, for cost or other reasons, some limitation of metamerism may be required. The procedures for estimating the magnitude of

metamerism described in this practice provide methods for assessing the effectiveness of such limitation.

5. Test Specimens

5.1 This practice does not cover the preparation of test specimens. The method shall be agreed upon between the purchaser and the seller.

6. Procedure for Visual Detection of Metamerism

6.1 *Illuminant Metamerism*—After observing that a pair of specimens is a visual match under one light source, the observer should view the specimens under one or more sources having distinctly different spectral power distributions. Among the suggested sources are daylight, incandescent light, and fluorescent lamp light. The larger the differences in spectral character of the sources, the easier it is to detect small degrees of metamerism.

6.2 *Observer Metamerism*—Specimens that are a match to one observer under a given light source are then viewed by other normal observers under the same conditions. Typically, five to ten observers should be used so that the results are not biased by differences among observers within the range of normal color vision. Replicate judgments by each observer may also be useful. Observer metamerism is indicated when there is obvious disagreement among observers as to the magnitude and direction of the color difference.

7. Procedures for Estimating Degrees of Metamerism

7.1 When the existence of metamerism has been established by visual evaluation of a pair of specimens, as indicated in Section 6, the degree of metamerism for that combination of source and observer can be determined by a visual estimate of the color difference. Use is made of paired gray scales, as specified in Test Method **D2616**, that display increasingly larger color differences with each successive pair of grays in the scale. The metameric specimen pair is placed in juxtaposition with the edge of the gray scale and compared with various gray pairs. The total perceived color difference between the two members of the test pair is compared to the lightness differences of the pairs on the gray scale, and the gray scale pair is selected that is the best visual equivalent to the color difference of the test pair. It is assumed, as in the

Significance and Use section in Test Method **D2616**, that, the total color difference can be so evaluated in terms of an equivalent lightness difference. Observers can be expected to reproduce such evaluations within a half-step on the gray scale.

NOTE 1—Visual Evaluation of Spectral Reflectance Curves—When specimens that match under one set of circumstances are measured on a spectrophotometer that produces a reflectance curve in the visual region of the spectrum, direct comparison of such curves will disclose if there is metamerism. It is convenient to plot the spectral curves of the two members of a metameric pair on the same sheet. The curves must intersect a minimum of three times for specimens to be metameric. Specimens are not metameric when the curves intersect only one or two times in the visible wavelengths, or when the curves do not intersect, but are merely proportionally higher or lower in reflectance throughout the wavelength region. Judgment of the degree of metamerism by qualitative visual inspection of spectrophotometric curves requires considerable skill and experience.

8. Report

8.1 Report the following information:

8.1.1 Identification of the specimens,

8.1.2 Procedures employed,

8.1.3 Results observed in Section 6,

8.1.4 Matching gray scale pair in Section 7,

8.1.5 Observed qualitative differences in hue, saturation, and lightness in accordance with the Procedure section, see Evaluation of the Color Difference, of Test Method **D2616**,

8.1.6 Number of observers and whether or not they were tested for color vision anomalies, and

8.1.7 Description of light sources used as to type, size, color temperature, and spectral power distribution.

9. Precision and Bias

9.1 *Precision*—The only quantitative portion of this practice, for which consideration of precision is appropriate, is Section 7, where use is made of Test Method **D2616**. The precision statements of that test method should be consulted if **D2616** is used.

9.2 *Bias*—There are no recognized standards by which to assess the bias of this practice.

10. Keywords

10.1 metamerism; visual examination-color; visual examination-metamerism

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).