



Standard Performance Specification for Women's and Girls' Knitted and Woven Corset-Girdle-Combination Fabrics¹

This standard is issued under the fixed designation D4116; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers woven and knitted fabrics composed of any textile fiber or mixture of fibers used in corsets, girdles or a combination of the same.

1.2 This performance specification is not applicable to knitted or woven corset-girdle-combination fabrics, to knitted lace fabrics, and to fabrics used for interlinings.

1.3 These requirements apply to the length and width directions for those properties where each fabric direction is pertinent.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D123 Terminology Relating to Textiles

D434 Test Method for Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam (Withdrawn 2003)³

D2261 Test Method for Tearing Strength of Fabrics by the Tongue (Single Rip) Procedure (Constant-Rate-of-Extension Tensile Testing Machine)

D2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Traversal Tensile Testing Machine) (Withdrawn 1995)³

D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method

D3787 Test Method for Bursting Strength of Textiles—Constant-Rate-of-Traversal (CRT) Ball Burst Test

D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

D7022 Terminology Relating to Apparel

2.2 *AATCC Test Methods:*⁴

8 Colorfastness to Crocking: Crockmeter Method

15 Colorfastness to Perspiration

16.3 Colorfastness to Light: Xenon-Arc

23 Colorfastness to Burnt Gas Fumes

61 Colorfastness to Laundering: Accelerated

116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method

135 Dimensional Changes of Fabrics after Home Laundering

172 Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering

188 Colorfastness to Sodium Hypochlorite Bleach in Home Laundering

Evaluation Procedure No. 1 Gray Scale for Color Change

Evaluation Procedure No. 2 Gray Scale for Staining

Evaluation Procedure No. 8 AATCC 9-Step Chromatic Transference Scale

A Glossary of AATCC Standard Terminology

2.3 *Federal Standard:*⁵

16 CFR, Chapter II-Consumer Product Safety Commission Subchapter D-Flammable Fabrics Act Regulations

2.4 *Military Standard:*⁶

MIL-STD-105D Sampling Procedures and Tables for Inspection by Attributes

¹ This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel.

Current edition approved Feb. 1, 2014. Published March 2014. Originally approved in 1982. Last previous edition approved in 2008 as D4116 – 01(2008). DOI: 10.1520/D4116-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

NOTE 1—Reference to test methods in this standard give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

⁴ Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, <http://www.aatcc.org>.

⁵ Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

3. Terminology

3.1 For terminology related to Apparel, see Terminology **D7022**.

3.2 For definitions of all other textile terms, see Terminology **D123**.

3.3 For terms relating to chemical or colorfastness testing, refer to specific AATCC test methods, or the glossary of AATCC Standard Terminology, or both.

3.4 Definitions found in a dictionary of common terms are suitable for this performance specification.

4. Specification Requirements

4.1 The properties of knitted and woven fabrics for women's and girls' corset-girdle-combinations shall conform to the specification requirements in **Table 1**.

5. Significance and Use

5.1 Upon agreement between the purchaser and the supplier, fabrics intended for this end use should meet all the requirements listed in **Table 1** of this performance specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in **Table 1**. Therefore, one or more of the

requirements listed in **Table 1** may be modified upon agreement between the purchaser and the supplier.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D4116 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the supplier, and in case of controversy, the requirements listed in **Table 1** are intended to be used as a guide only. As noted in **5.2**, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The uses and significance of particular properties and methods are discussed in the appropriate sections of the specified methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable specification or other agreement between the purchaser and the supplier, such as an agreement to use MIL-STD-105D.

6.2 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric and at least 375 mm (15 in.) along the selvage.

TABLE 1 Specification Requirements

NOTE 1—Grade in colorfastness is based on a numerical scale of 5 for negligible color change or color transfer to 1 for very severe color change or color transfer.

Characteristic	Requirements		Section
	Knit	Woven	
Breaking strength (load)(CRT) ^A	...	301 N (70 lbf), min	7.1
Bursting strength (ball burst) ^A	222 N (50 lbf), min	...	7.2
Tongue-tear strength ^A	...	13 N (3 lbf), min	7.3
Yarn slippage	...	6 mm (¼ in.) separation @ 155 N (35 lbf), min	7.4
<i>Dimensional change:</i>			
Laundering			
Length	5 % max	5 % max	7.5.1
Width	5 % max	3 % max	
<i>Colorfastness:</i>			
Burnt gas fumes—1 cycle:			
Shade change, original fabric	Grade 4 ^B , min	Grade 4 ^B , min	7.6.1
Shade change, after one laundering	Grade 4 ^B , min	Grade 4 ^B , min	
Laundering: ^E			
Shade change	Grade 4 ^B , min	Grade 4 ^B , min	7.6.2
Staining	Grade 3 ^C , min	Grade 3 ^C , min	
Crocking: ^E			
Dry	Grade 4 ^D , min	Grade 4 ^D , min	7.6.3
Wet	Grade 3 ^D , min	Grade 3 ^D , min	
Perspiration: ^E			
Shade change	Grade 4 ^B , min	Grade 4 ^B , min	7.6.4
Staining	Grade 3 ^C , min	Grade 3 ^C , min	
Light (10 AATCC Fading Units) ^A (xenon-arc)	Grade 4 ^B , min	Grade 4 ^B , min	7.6.5
Sodium Hypochlorite Bleach	Grade 4 ^B , min	Grade 4 ^B , min	7.6.6
Powdered Non-chlorine Bleach	Grade 4 ^B , min	Grade 4 ^B , min	7.6.7
Flammability	pass	pass	7.7

^A There is more than one method that can be used to measure breaking strength (load).

^B AATCC Gray Scale for Color Change.

^C AATCC Gray Scale for Staining.

^D AATCC 9-Step Chromatic Transference Scale.

^E See **Note 8**.

7. Test Methods (See **Note 1**)

7.1 Breaking Force (woven fabrics only)—Determine the dry breaking force in the standard atmosphere for testing textiles, as directed in Test Method **D5034**, using a constant rate of traverse (CRT) tensile-testing machine with the speed of the pulling clamp at 300 ± 10 mm (12 ± 0.5 in.)/min.

NOTE 2—If preferred, a constant-rate-of-extension (CRE) tensile-testing machine may be used. The crosshead speed should be as agreed upon between the purchaser and the supplier. There may be no overall correlation between the results obtained with the CRT machine and with the CRE machine. Consequently, these two breaking load testers cannot be used interchangeably. In case of controversy, the CRT method shall prevail.

7.2 Bursting Strength (knit fabrics only)—Determine the bursting strength of knit fabrics as directed in Test Methods **D3786** or **D3787** as agreed upon between the purchaser and the supplier.

NOTE 3—Care should be taken to subtract the tare diaphragm pressure from the gross pressure to obtain actual bursting strength of fabric when using the diaphragm bursting tester. Calibrate the equipment according to manufacturer's instruction before use. Since there is no overall correlation between the results obtained with the CRT machine equipped with a bursting attachment and the diaphragm bursting tester, these two bursting testers cannot be used interchangeably. In case of controversy, the CRT machine equipped with a bursting attachment method shall prevail.

NOTE 4—The precision of the ball burst method using the CRT machine equipped with a bursting attachment and the precision of the diaphragm bursting tested method are being established by Subcommittee D13.59. The methods are accordingly not recommended for acceptance testing unless preceded by an interlaboratory check test in the laboratory of the purchaser and the laboratory of the supplier using randomized replicate specimens of the type of material to be evaluated.

7.3 Tongue-Tear Strength (woven fabrics only)—Determine the tear strength as directed in Test Method **D2262**.

NOTE 5—If preferred, the use of Test Methods **D1424** or **D2261** is permitted with existing requirements as given in this performance specification. There may be no overall correlation between the results obtained with the tongue-tear machines and with the Elmendorf machine. Consequently, these three testers cannot be used interchangeably. In case of controversy, Test Method **D2262** shall prevail.

7.4 Resistance to Yarn Slippage (woven fabrics only)—Determine the resistance to yarn slippage as directed in Test Method **D434**.

NOTE 6—The precision of Test Method **D434** is being established, and it may not be suitable for fabrics with a low number of warp (ends) and filling (picks) counts (see **5.2**).

7.5 Dimensional Change:

7.5.1 Laundering—Determine the maximum-dimensional change after five launderings, or as agreed upon between the purchaser and the supplier, as directed in the applicable procedure in AATCC Test Method 135.

7.6 Colorfastness:

7.6.1 Burnt Gas Fumes—Determine the colorfastness to burnt gas fumes on the original fabric and after one laundering or one drycleaning as directed in AATCC Test Method 23 after 1 cycle.

NOTE 7—Washing conditions shall be the same as those used in **7.5.1**.

7.6.2 Laundering—Determine the colorfastness to laundering as directed in the applicable procedure of AATCC Test Method 61. The test conditions shall be as specified by the seller.

NOTE 8—It has been reported that the results for staining, obtained by standard AATCC Test Methods, on fabrics dyed to dark shades that contain a combination of polyester and spandex, or their blends, may not show the full staining propensity of such fabrics in consumer use. It is, therefore, recommended that the staining results obtained by these tests not be used for acceptance testing of such fabrics.

7.6.3 Crocking—Determine colorfastness to dry and wet crocking as directed in AATCC Test Method 8 for solid shades and AATCC Test Method 116 for prints, or as agreed upon between the purchaser and the supplier (see **Note 8**).

7.6.4 Perspiration—Determine colorfastness to perspiration as directed in AATCC Test Method 15 (see **Note 8**).

7.6.5 Light—Determine colorfastness to light as directed in AATCC Test Method 16.3 Option 3.

7.6.6 Colorfastness to Sodium Hypochlorite Bleach—Determine colorfastness to light as directed in AATCC Test Method 188. The test conditions shall be as specified by the seller.

7.6.7 Colorfastness to Powdered Non-chlorine Bleach—Determine colorfastness to light as directed in AATCC Test Method 172. The test conditions shall be as specified by the seller.

7.7 Flammability—The flammability requirements shall be as agreed upon between the purchaser and the supplier, provided they meet or exceed those of Part 1610 of the Flammable Fabrics Act Regulations.

8. Keywords

8.1 fabric; foundation garment; performance; specification

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).