



Standard Test Method for Mechanically Tapped Packing Density of Formed Catalyst and Catalyst Carriers¹

This standard is issued under the fixed designation D4164; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the mechanically tapped density of formed catalyst and catalyst carriers. For the purpose of this test method, catalyst particles are defined as extrudates, spheres, or formed pellets of 0.8 to 4.8-mm ($1/32$ to $3/16$ -in.) nominal diameter.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D3766 Terminology Relating to Catalysts and Catalysis

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E456 Terminology Relating to Quality and Statistics

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E1272 Specification for Laboratory Glass Graduated Cylinders

3. Terminology

3.1 *Definitions*—See Terminology D3766.

4. Summary of Test Method

4.1 A preconditioned sample of formed catalyst or catalyst carrier is tapped in a graduated cylinder. The mechanically tapped packing density is determined from the known mass and tapped volume.

¹ This test method is under the jurisdiction of ASTM Committee D32 on Catalysts and is the direct responsibility of Subcommittee D32.02 on Physical-Mechanical Properties.

Current edition approved Dec. 1, 2013. Published December 2013. Originally approved in 1988. Last previous edition approved in 2008 as D4164 – 03 (2008). DOI: 10.1520/D4164-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Significance and Use

5.1 This test method is to be used for measuring the mechanically tapped packing density of formed particles that will not break up during sampling, filling, or tapping of the measuring cylinder under test conditions.

6. Apparatus

6.1 *Graduated Cylinder*, capacity 250 mL, conforming to Specification E1272, Class A, with a base designed to accommodate the cylinder holder.

6.2 *Cylinder Holder*, weighing approximately 1 lb (454 g).

6.3 *Tapping Device*, consisting of a base-plate with worm drive, reduction ratio 15:1, nominal cam shaft speed of 250 r/min, tapping stroke travel $1/8$ in. (3.2 mm).

6.4 *Four Digit Adjustable Counter*, which can be preset to deliver any number of taps between 1 and 9999.

6.5 *Desiccator*, with a desiccant grade molecular sieve such as No. 4A.

6.6 *Balance* having a sensitivity of 0.1 g.

6.7 *Drying Oven*.

7. Procedure

7.1 Heat an adequate sample(s) at $400 \pm 15^\circ\text{C}$ for not less than 3 h. Normally, this treatment can take place in air. However, in the case of materials that might react with air at elevated temperatures (such as prerduced catalysts) the heat treatment should take place in an inert atmosphere. After heating, cool the test sample(s) in a desiccator or other suitable container to eliminate the possibility of moisture adsorption prior to testing.

NOTE 1—These conditions may not be appropriate for all materials.

NOTE 2—Since many catalyst formulations are strong adsorbents, the use of No. 4A indicating (cobalt-treated) molecular sieves as a desiccating medium is suggested. The desiccant should be regenerated at 493 K (220°C) to 533 K (260°C), as required.

7.2 Pour between 240 and 250 mL of the test specimen carefully into the tared graduated cylinder using a funnel. To ensure proper level, rotate the funnel while pouring the test specimen. Weigh immediately to the nearest 0.1 g.

7.3 Preset the counter to 1000 taps.

7.4 Start the tapping device.

7.5 When tapping is completed, read the tapped volume, V , to the nearest 1 mL by estimating the average level of the catalyst or catalyst carrier surface in the cylinder.

8. Calculation

8.1 Calculate mechanically tapped packing density MTD as follows:

$$MTD = W/V \quad (1)$$

where:

W = mass of catalyst particles, g, and

V = volume occupied by particles in measuring cylinder, mL.

9. Precision and Bias³

9.1 *Test Program*—An interlaboratory study was conducted in which the named property was measured in two separate test

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D32-1017.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).

materials in three separate laboratories. Practice E691, modified for non-uniform data sets, was followed for the data reduction.

9.2 *Precision*—Pairs of test results obtained by a procedure similar to that described in the study are expected to differ in absolute value by less than 2.772 S , where 2.772 S is the 95 % probability interval limit on the difference between two test results, and S is the appropriate estimate of standard deviation. Definitions and usage are given in Terminology E456 and Practice E177, respectively.

Test Result (consensus mean), kg/L	95 % Repeatability Interval (within laboratory), kg/L (% of mean)	95 % Reproducibility Interval (between laboratories), kg/L (% of mean)
0.6391	0.007 (1.02)	0.023 (3.54)
1.5333	0.005 (0.47)	0.055 (4.73)

9.3 *Bias*—The procedure in this test method has no bias because the value of mechanically tapped packing density can be defined only in terms of a test method.

10. Keywords

10.1 carriers; catalyst; mechanically tapped; packing density