



Standard Terminology Related to Multicomponent Textile Fibers¹

This standard is issued under the fixed designation D4466; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 Man-made polymers can be combined during manufacture, or natural polymers can be formed during growth, to produce multicomponent fibers having special properties such as cross dyeability, differential shrinkage, or bulk. This standard contains terms which can be used to describe the physical arrangement of components of such fibers. The schematic diagram in [Annex A1](#) provides a guide for interpreting the terminology used in describing two- and three-component fibers, but is not intended to be limiting. Some examples of usage are given in [Annex A2](#), and a bibliography of related literature is given in [Appendix X1](#).

1.2 For definitions of other textile terms, refer to Terminology [D123](#).

2. Referenced Documents

- 2.1 *ASTM Standards*:²
[D123 Terminology Relating to Textiles](#)

Generic Class

3. Terminology

generic class, *n*—as used with textile fibers, a grouping having similar chemical compositions or specific chemical characteristics.

DISCUSSION—In the United States, the generic names and definitions of man-made fibers, such as nylon, polyester, and acrylic, are published by the Federal Trade Commission in “Rules and Regulations Under the Textile Fiber Products Identification Act.” Technically, fibers may be bigeneric, trigeneric, etc.

Components

polymer, *n*—a macromolecular material formed by the chemical combination of monomers having either the same or different chemical composition.

¹ This terminology is under the jurisdiction of ASTM Committee [D13](#) on Textiles and is the direct responsibility of Subcommittee [D13.58](#) on Yarns and Fibers.

Current edition approved July 1, 2012. Published August 2012. Originally approved in 1985^ε. Last previous edition approved in 2007 as D4466 – 02(2007). DOI: 10.1520/D4466-02R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

component, *n*—as used with textile fiber polymers, a polymer with distinguishable properties.

bicomponent fiber, *n*—a fiber consisting of two polymers which are chemically different or physically different, or both.

biconstituent fiber, *n*—deprecated term. Use the preferred term *bicomponent bigeneric fiber*.

DISCUSSION—As used in the Federal Trade Commission’s “Rules and Regulations Under the Textile Fiber Products Identification Act,” “biconstituent fiber” is “essentially a physical combination or mixture of two or more chemically distinct constituents or components combined at or prior to the time of extrusion, which if separately extruded, would fall within different ...” generic classes. In the preferred ASTM terminology, a biconstituent fiber is a bicomponent bigeneric fiber. It is not clear from the “Rules” whether a biconstituent fiber has a sheath-core, bilateral, or matrix configuration.

tricomponent fiber, *n*—a fiber consisting of three polymers which are chemically different, physically different, or any combination of such differences.

Physical Arrangement of Components

lateral, *adj*—a descriptive term for a textile fiber composed of two or more polymers at least two of which have a continuous longitudinal external surface.

sheath-core, *adj*—a descriptive term for a multicomponent textile fiber consisting of a continuous envelope which encases a continuous, central, internal region. (See also *component*.)

DISCUSSION—Both the sheath and the core can consist of more than one component arranged laterally, concentrically, or in matrix.

matrix, *adj*—a descriptive term for a textile fiber in which one or more polymeric fibrous material(s) is dispersed in another.

Order for Naming Multicomponent Fibers

1. Trademark.
2. Physical arrangement of components: bilateral, matrix, sheath-core.
3. Number of components: bicomponent, tricomponent, etc.
4. Number of generic classes: monogeneric, bigeneric, trigeneric, etc.
5. Subparts 1 through 4 to be separated by commas.
6. Generic class(es): polyester, nylon, spandex, etc.

7. Makeup of generic classes:
- (a) Generic class(es) in parentheses.
 - (b) For matrix structures—Generic classes to be separated by a hyphen.
 - (c) For lateral structures—Generic classes to be separated by a slash mark (/) (virgule).
 - (d) For sheath-core structures—Generic classes to be separated by a slash mark (/) (virgule).
 - (e) The generic class that is in the greatest quantity will be named first.

8. State the percentage of each generic class, based on percent of the total fiber weight, in square brackets following the generic class (optional).

9. Name the fiber in the form in which it is produced rather than after any subsequent treatment(s) that might separate the components.

5. Keywords


5.1 terminology; textile fibers

ANNEXES

(Mandatory Information)

A1. SCHEMATIC DIAGRAM

See Fig. A1.1




NOTE 1—Where X, X', and X'' represent polymer components of the same generic class, and Y and Z represent components of different generic classes.

FIG. A1.1 Schematic Diagram of Some Potential Fiber Configurations

A2. Nomenclature Usage

See Fig. A2.1



¹ Registered trademark of Du Pont Company
² Trademark of Allied Chemical Corp.
³ Trademark of Cordelan Fiber Industry Co. Ltd.
⁴ Registered trademark of Monsanto Textiles Co.

NOTE 1—Where A and A', NY and NY', and PE and PE' represent different polymeric components within three generic classes.

FIG. A2.1 Examples of Nomenclature Usage

APPENDIX

(Nonmandatory Information)

X1. BIBLIOGRAPHY

(1) Morton, W. E., and Hearle, J. W. S., *Physical Properties of Textile Fibers*, John Wiley, New York, NY, 1975, pp. 58–59.

(2) Onions, J. W., *Wool: An Introduction to its Properties, Varieties, Uses, and Production*, Interscience, New York, NY, 1962, p. 19.

(3) Paul, D. R., and Newman, Seymour, *Polymer Blends*, Academic Press, New York, NY, Vol 2, Chapter 16, 1978.

(4) Code of Federal Regulations, “Rules and Regulations Under the Textile Fiber Products Identification Act” (16 CFR 303.1–303.11).

(5) “Generic Names and Definitions for Manufactured Fibers,” Annex A1, ASTM Standard D123 “Terminology Relating to Textiles,” *Annual Book of ASTM Standards*, Vols 07.01 and 07.02.

(6) Farnfield, Carolyn A., and Alvey, P. J., Editors, *Textile Terms and Definitions*, Seventh Ed., The Textile Institute, Manchester, 1975.

(7) Placek, C., *Multicomponent Fibers*, Noyes Data Corp., Park Ridge, NJ, 1971.

(8) Jeffries, R., *Bicomponent Fibers*, Merrow Publishing Co., Ltd., Watford, 1971.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).