



Designation: D4528 – 88 (Reapproved 2017)

Standard Classification for Rubber Compounding Materials—Sulfur¹

This standard is issued under the fixed designation D4528; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This classification covers the variety of sulfur grades used in the rubber industry. Typical chemical and physical properties for sulfur are shown. Sulfur is principally used in unsaturated rubbers as a vulcanizing agent.

2. Referenced Documents

2.1 *ASTM Standards*:²

D4569 Test Method for Rubber Compounding Materials—Determination of Acidity in Sulfur

D4571 Test Methods for Rubber Compounding Materials—Determination of Volatile Material

D4572 Test Method for Rubber Chemicals—Wet Sieve Analysis of Sulfur

D4573 Test Method for Rubber Chemicals—Determination of Oil Content in Oil-Treated Sulfur

D4574 Test Methods for Rubber Compounding Materials—Determination of Ash Content

D4578 Test Methods for Rubber Chemicals—Determination of Percent Sulfur by Extraction

3. Significance and Use

3.1 Sulfur is one of the principal rubber vulcanizing agents. It is a critical additive. When chemically combined with rubber, sulfur develops basic performance properties in the vulcanized compound such as: tensile strength, elongation, modulus, and hardness. In soft or elastic rubber compounds, sulfur is an essential but minor additive. In semi-hard rubber and ebonite, sulfur becomes a major compounding material while retaining its role as a vulcanizing agent.

3.2 The most stable molecular form of sulfur at ambient conditions is a ring structure containing eight sulfur atoms. Depending on conditions these molecules orient into one of two crystalline structures. At room temperature the crystals are

rhombic and above 95°C they rearrange to monoclinic. Less than 1.5 % of either crystalline structure of sulfur is soluble in any rubber at room temperature.

3.3 The second common molecular form of sulfur is polymeric sulfur, made up of unbranched chains of sulfur atoms. It is commonly referred to in the rubber industry as insoluble sulfur. When this material is created by rapid heating to above 160°C and quenching to room temperature, the sulfur is amorphous. If formed under other conditions, the polymer chains may develop regions of pseudo crystallinity.

3.4 Insoluble sulfur is an important form of sulfur used only in the rubber industry. It is not soluble in any type of rubber hydrocarbon. When it is mixed in rubber, it disperses but remains undissolved in the rubber. The use of insoluble sulfur prevents the development of a supersaturated solution of sulfur in rubber that occurs when rhombic sulfur is used. No sulfur bloom will develop on the surface of uncured rubber pieces when the rubber cools after mixing or processing; therefore, building tack is preserved. At curing temperatures, insoluble sulfur rapidly transforms to a soluble species, dissolves in the rubber, and enters into the vulcanization process.

4. Basis of Classification of Sulfurs

4.1 *Rhombic Sulfur* (ordinary ground sulfur)—Rhombic sulfur, which is the ordinary form of sulfur under normal conditions, is ground and classified to meet specific particle size requirements. The various grades of this type of sulfur contain less than 1 % polymeric sulfur. The ground types of sulfur may also contain additives to enhance performance. Oil is added to sulfur to help control sulfur dust and improve dispersion in rubber. Finely ground solid minerals are also added to improve dispersion in rubber. Ordinarily the total additive level is 5 % or less of the sulfur formulation. Many of these types of sulfur may be added to rubber compounds as 100 % sulfur.

4.2 *Insoluble Sulfur* (polymeric) —There are two general types of insoluble sulfur and the general description of each is detailed as follows:

4.2.1 *Low Insoluble Content Sulfur or Flowers of Sulfur*—This product is made by vaporizing pure sulfur and quenching the vapors in an inert gaseous atmosphere. A select grade of this product contains between 30 and 40 % of polymeric sulfur. This level of insoluble sulfur is often insufficient to prevent

¹ This classification is under the jurisdiction of ASTM Committee D11 on Rubber and Rubber-like Materials and is the direct responsibility of Subcommittee D11.20 on Compounding Materials and Procedures.

Current edition approved Feb. 1, 2017. Published February 2017. Originally approved in 1988. Last previous edition approved in 2012 as D4528 – 88 (2012). DOI: 10.1520/D4528-88R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Typical Properties of Rhombic (Ordinary Ground) Sulfur

Typical Properties	ASTM Test Method	Sulfur Grade			
		General Purpose	Fine	Oiled	Conditioned
Sulfur, %	...	99.8	99.8	98 to 99.5	95.5 to 99
Rubber process oil, %	D4573	0.5 to 2	0 to 2.0
Additive, %	D4574	up to 2.5
Acidity, % as H ₂ SO ₄	D4569	0.01	0.01	0.01	0.01
Ash, %	D4574	0.02	0.02	0.02	depends on additive
Heat loss, %	D4571	0.04	0.04	0.10	0.10
Fineness,	D4572				
Residue on standard sieve					
180 μm, %		<0.3	<0.2	<0.3	<0.3
75 μm, %		5–15	0.5 to 1	variable ^A	variable ^A
45 μm, %		NA ^B	<2	variable	variable

^A Oils and conditioning agents may be added to any grind without changing the sieve residues. Refer to the values given for the untreated ground sulfur.

^B NA—not available.

TABLE 2 Typical Properties of Insoluble (Polymeric) Sulfurs

Typical Properties	ASTM Test Method	Flowers of Sulfur	60 % Insoluble	90 % Insoluble	
				Regular	Oiled
Sulfur, %	...	99.8	99.8	99.8	78.8
Insoluble sulfur, %	D4578	34.0	63.0	93.0	74.5
Rubber process oil, %	D4573	19.0 to 21.0
Acidity, % as H ₂ SO ₄	D4569	0.1	0.01	0.01	0.01
Ash, %	D4574	0.01	0.01	0.01	0.01
Heat loss, %	D4571	0.10	0.20	0.20	0.30
Fineness,	D4572				
Residue on standard sieve					
180 μm, %		0.2	0.2	0.2	0.2
150 μm, %		1.0	1.0	1.0	1.0

bloom, and its use is restricted to rubber compounds containing high levels of fillers or rubber compounds using modest amounts of sulfur. Historically, this was the first commercial insoluble sulfur available.

4.2.2 High Insoluble Content Sulfur—In this type of insoluble sulfur, the major constituent is polymeric sulfur. The polymeric sulfur level ranges from 60 to over 95 %. The product is made by heating sulfur to temperatures greater than 160°C with subsequent rapid quenching. The polymeric sulfur content is increased by extracting rhombic sulfur from the solid with an appropriate solvent. The amount extracted is determined by the particular insoluble sulfur specification.

4.2.3 Insoluble sulfur also contains added oil and occasionally finely ground minerals. These are added to aid dispersion in rubber and to limit sulfur dusting. However, the additive levels are usually much higher than those used with rhombic sulfur. Oil treatments may range as high as 35 % of the total material. Mineral additives may amount to as much as 25 % of the final sulfur formulation. The treatment levels are always significant enough to require adjustment in the formulation to provide the necessary sulfur for complete vulcanization .

5. Keywords

5.1 insoluble sulfur; rhombic sulfur; sulfur

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/