



# Standard Test Method for Rubber Chemicals—Determination of Oil Content in Oil-Treated Sulfur<sup>1</sup>

This standard is issued under the fixed designation D4573; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the amount of hydrocarbon oils added to oil-treated sulfurs. The test method is employed when the amount of oil added is 1 % or more of the total sample.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *lot sample*—a production sample representative of a standard production unit, normally referred to as “the sample.”

3.1.2 *specimen*—also known as the “test portion;” it is the actual material used in the analysis; it must be representative of the lot sample.

## 4. Significance and Use

4.1 This test method measures the hydrocarbon oils added to sulfur to help control dusting of the sulfur. It can be used for

research, development, and quality control to measure the level of oil added to the sulfur to help maintain the oil content at required levels.

## 5. Apparatus

5.1 *Filtering Crucible*, 30 cm<sup>3</sup>, medium porosity sintered glass.

5.2 *Vacuum Filter Flask*, 500 cm<sup>3</sup> and filter crucible holder.

5.3 *Circulating Air Oven*, capable of 70 ± 2°C explosion proof, vented.

5.4 *Desiccator*.

5.5 *Analytical Balance*, sensitive to 0.001 g.

5.6 *Conical (Erlenmeyer) Flask*, 250 cm<sup>3</sup>.

## 6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.<sup>3</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Fine Particle Size Pure Sulfur* (45 μm or smaller).

6.3 *Hexane Saturated With Sulfur:*

6.3.1 *Method of Preparation*—In a well-ventilated hood, in a suitable size container equipped with an air stirrer and external heater, mix hexane and sulfur for 2 h while heating to 40°C maximum. Continue to stir while the mixture cools to room temperature. Allow to settle for 12 h. Decant off the sulfur saturated hexane, and filter just prior to use in the test. Store in a capped bottle.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.11 on Chemical Analysis.

Current edition approved July 1, 2014. Published November 2014. Originally approved in 1986. Last previous edition approved in 2009 as D4573 – 03 (2009). DOI: 10.1520/D4573-03R14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

**TABLE 1 Type 1 Precision Results—Oil Content (Sulfur)**

Material	Average	Within Laboratory <sup>A</sup>			Between Laboratory <sup>A</sup>		
		$S_r$	$r$	( $\bar{r}$ )	$S_R$	$R$	( $\bar{R}$ )
Oil Treated, 90 % Insoluble Sulfur—B	17.84	0.175	0.496	2.78	1.081	3.060	17.1
Oil Treated, 90 % Insoluble Sulfur—A	20.32	0.247	0.699	3.44	0.360	1.020	5.0
Pooled Values <sup>B</sup>	18.97	0.211	0.597	3.14	0.806	2.281	12.0

<sup>A</sup> $S_r$  = repeatability standard deviation.

$r$  = reproducibility (as a percent of material average) = repeatability =  $2.83 \times$  the square root of the repeatability variance.

( $\bar{r}$ ) = repeatability (as a percent of material average).

$S_R$  = reproducibility standard deviation.

$R$  = reproducibility =  $2.83 \times$  the square root of the reproducibility variance.

( $\bar{R}$ ) = reproducibility (as a percent of material average).

<sup>B</sup> No values omitted.

## 7. Procedure

7.1 Tare a 30 cm<sup>3</sup> filter crucible (see 5.1) to the nearest 0.001 g.

7.2 Into a 250 cm<sup>3</sup> conical flask (see 5.6) weigh, to the nearest 0.001 g,  $5 \pm 0.5$  g ( $W_1$ ) of the oil-treated sulfur specimen.

7.3 In a well-ventilated hood, add 20 cm<sup>3</sup> of the freshly filtered sulfur-saturated hexane (see 6.3) to the flask. Gently swirl the flask to disperse the sulfur specimen.

7.4 Vacuum filter this mixture quantitatively through the previously tared filter crucible (see 5.1), contained in the filter crucible holder, into a 500 cm<sup>3</sup> vacuum filter flask (see 5.2) adjusting the suction to pull the filtrate through the filter crucible at a rate forming drops and not a steady stream of filtrate.

7.5 Wash the residue in the flask with three successive 50 cm<sup>3</sup> of sulfur-saturated hexane, quantitatively transferring each washing through the filter crucible.

NOTE 1—Filtration should take 8 to 15 min to complete. Do not allow the filter cake to dry or crack during filtration.

7.6 When filtration is complete, increase the suction to pull the last traces of filtrate through the filter cake, leaving the vacuum on for 30 s after the last drop of filtrate falls.

7.7 Remove the filter crucible from the holder and place it in an oven (see 5.3) at  $70 \pm 2^\circ\text{C}$  for 1 h. Then transfer the filter crucible to a desiccator for 0.5 to 1 h.

7.8 Remove the filter crucible from the desiccator and weigh it to the nearest 0.001 g ( $W_2$ ).

7.9 Repeat steps 7.1 – 7.8 on a  $5.0 \pm 0.5$  g sample of pure sulfur as a blank ( $B_1$ ). The weight of the “blank” residue is ( $B_2$ ).

## 8. Calculation

8.1 Calculate the percent oil extracted from the oil-treated sulfur sample as follows:

$$\% \text{ Oil} = [1 - (W_2/W_1 + C)] \times 100 \quad (1)$$

$$C_f = 1 - \frac{B_2}{B_1} \quad (2)$$

where:

$W_1$  = mass of oil treated sulfur sample (see 7.2) in g,

$W_2$  = mass of oil treated sulfur sample after filtration (see 7.8) in g,

$B_1$  = mass of pure sulfur “blank” in g,

$B_2$  = mass of pure sulfur “blank” after filtration in g, and

$C_f$  = correction factor for “blank.”

NOTE 2— $C_f$  may be positive or negative.

## 9. Report

9.1 Report the following information:

9.1.1 Proper identification of samples, and

9.1.2 Percent of extracted oil from two individual determinations and their average to the nearest 0.01 %.

## 10. Precision and Bias<sup>4</sup>

10.1 This precision and bias section has been prepared in accordance with Practice D4483. Refer to this practice for terminology and other statistical details.

10.2 The precision results in this precision and bias section give an estimate of the precision of this test method with the materials (rubbers) used in the particular interlaboratory programs as described below. The precision parameters should not be used for acceptance/rejection testing of any group of materials without documentation that they are applicable to those particular materials and the specific testing protocols that include this test method.

10.3 A Type 1 (interlaboratory) precision was evaluated in 1986. Both repeatability and reproducibility are short term; a period of a few days separates replicate test results. A test result is the mean value, as specified by this method, obtained on two determinations or measurements of the property or parameter in question.

10.4 Two different materials were used in the interlaboratory program. These were tested in six laboratories on two different days.

10.5 The results of the precision calculations for repeatability and reproducibility are given in Table 1, in ascending order of material average or level, for each of the materials evaluated.

<sup>4</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D11-1049.

10.6 The precision of this test method may be expressed in the format of the following statements which use an “appropriate value” of  $r$ ,  $R$ , ( $r$ ) or ( $R$ ), that is, that value to be used in decisions about test results (obtained with the test method). The *appropriate value* is that value of  $r$  or  $R$  associated with a mean level in **Table 1** closest to the mean level under consideration at any given time, for any given material in routine testing operations.

10.7 *Repeatability*—The repeatability,  $r$ , of this test method has been established as the *appropriate value* tabulated in the Precision Table. Two single test results, obtained under normal test method procedures, that differ by more than this tabulated  $r$  (for any given level) must be considered as derived from different or nonidentical sample populations.

10.8 *Reproducibility*—The reproducibility,  $R$ , of this test method has been established as the *appropriate value* tabulated in **Table 1**. Two single test results obtained in two different

laboratories, under normal test method procedures, that differ by more than the tabulated  $R$  (for any given level) must be considered to have come from different or nonidentical sample populations.

10.9 Repeatability and reproducibility expressed as a percent of the mean level, ( $r$ ) and ( $R$ ), have equivalent application statements as above for  $r$  and  $R$ . For the ( $r$ ) and ( $R$ ) statements, the difference in the two single test results is expressed as a percent of the arithmetic mean of the two test results.

10.10 *Bias*—In test method terminology, bias is the difference between an average test value and the reference (or true) test property value. Reference values have not been evaluated for this test method. Bias, therefore, cannot be determined.

## 11. Keywords

11.1 oil content; oil-treated sulfur; rubber chemicals; sulfur

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*