



Standard Practice for Carbon Black—Calculation of Process Indexes From an Analysis of Process Control Data¹

This standard is issued under the fixed designation D4583; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers (1) a statistical procedure for analyzing the test data generated in the statistical process control of a carbon black manufacturing process; (2) a format for reporting process capability determined from the analysis of control chart data of an individual production run, and (3) a format for reporting process performance determined from the analysis of control chart data of an individual production run.

1.2 This practice specifically applies to the analysis of pelleted carbon black samples taken during the manufacturing process prior to storage. This practice does not apply to shipment samples taken from hopper cars or other containers or packages.

1.3 This practice is specifically designed to be used for those test methods given in Classification D1765 which specify target values. However, these techniques are applicable to other test methods on carbon black.

1.4 This practice describes the calculation for two methods of determining capability factors from an analysis of process control data.

1.4.1 Process capability (C_p) is a measurement of variation calculated from the process control chart data with the use of an estimated standard deviation ($\hat{\sigma}$) from the mean value of the moving range (R) chart. The calculation of the process capability (C_p and C_{pk}) indexes can be used as historical information or to predict future performance of the process, but are only valid when the process is in a state of statistical control.

1.4.2 Process performance (P_p) is a measurement of variation calculated from the process control chart data using sample standard deviation(s). The calculation of the process performance (P_p and P_{pk}) indexes are used for a historical reference of a process' performance and does not require a state of statistical control.

¹ This practice is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.61 on Carbon Black Sampling and Statistical Analysis.

Current edition approved Jan. 1, 2015. Published February 2015. Originally approved in 1986. Last previous edition approved in 2009 as D4583 – 95 (2009). DOI: 10.1520/D4583-95R15.

2. Referenced Documents

2.1 *ASTM Standards*:²

D1765 Classification System for Carbon Blacks Used in Rubber Products

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:⁴

3.1.1 *average moving range* (\bar{R})—the arithmetic mean of n moving ranges, $\bar{R} = \sum R/n$.

3.1.2 *Cpk index*—an index that indicates how well the common cause process variability is actually contained within the specifications. (See 6.4.)

3.1.3 *moving range* (R)—the absolute difference between consecutive, individual test values.

3.1.4 *Ppk index*—indicates how well the common and special cause process variability is actually contained within the specifications. (See 6.6.)

3.1.5 *process capability index* (C_p)—an index that compares the magnitude of common cause process variability to the range of upper and lower specification limits (USL and LSL) without regard to where the process is centered; C_p index = $(USL - LSL)/(6\hat{\sigma})$. (See 6.3.)

3.1.6 *process performance index* (P_p)—an index that compares the magnitude of common and special cause process variability to the range of the upper and lower specification limits (USL and LSL) without regard to where the process is centered; P_p index = $(USL - LSL)/(6s)$. (See 6.5.)

4. Significance and Use

4.1 This practice will provide the following: (1) a statistical summary of individual production run data plotted on a control

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ *Manual on Presentation of Data and Control Chart Analysis, STP 15D*, ASTM International, 1976.

⁴ *Ford Motor Company Manual on "Process Capability and Continuing Process Control,"* Publication No. 80-01-251. Available in packs of five from Ford Motor Company, Statistical Methods Publications, P.O. Box 1000, Plymouth, MI 48170.

chart; (2) a statistical summary of data from multiple production runs; (3) a procedure to relate the average and variation of these data groups to specification limits, and (4) indexes for comparing different manufacturing units for projecting future capabilities or as historical reference.

5. Procedure

5.1 *Sampling:*

5.1.1 In order to provide uniformity and the ability to make valid comparisons of process capability and process performance indexes, all samples used for these calculations shall be collected in the same way. Samples that are to be tested for properties on which capability or performance indexes will be calculated shall be collected as follows:

5.1.1.1 All samples shall be taken from the process at the finished pellet discharge and tested individually. Compositing of samples is not permitted.

5.1.1.2 Samples normally shall be taken every 4 h. All results obtained on material that is put into finished product storage tanks shall be included.

5.1.1.3 Averaging of results is not permitted. Each result, as defined by the appropriate test method, is to be recorded and used in performing the calculations described in Section 6.

5.2 *Process Capability:*

5.2.1 A minimum of 30 test data generated during production periods in which the process is in statistical control are

recommended for estimating a process capability standard deviation. In that case, the number (*n*) of moving ranges averaged will be 29.

5.2.2 Calculate *C_p* and *C_{pk}* as shown in 6.3 and 6.4. The *C_p* index and the *C_{pk}* index must be greater than 1.00 in order to indicate the capability of the process to meet the established specifications. The *C_{pk}* index is inherently less than or equal to the *C_p* index (for one-sided specifications, only the *C_{pk}* index is applicable).

5.2.3 The *C_p* index indicates whether or not the process is capable of meeting a specification. Maximum performance is achieved when the process is perfectly centered and the *C_{pk}* is equal to the *C_p*.

5.2.4 In comparing one manufacturing unit to another, the larger *C_{pk}* index demonstrates a greater capability to conform to the specification range of the specified property.

5.2.5 A *process capability summary* can be used to evaluate a production unit over a period of time such as weekly, monthly, or quarterly. (See Fig. 1.) After each production run, or after 30 or so tests, the values of *n*, \bar{x} , \pm difference from target, *MR*, $3\hat{\sigma}$, *C_p*, and *C_{pk}* are recorded on the summary form. At the conclusion of the appropriate time interval, the grand average

($\bar{\bar{x}}$),
 average difference from target, average *C_p*, and average *C_{pk}* can be displayed at the foot of the appropriate column.

PROCESS CAPABILITY SUMMARY

PLANT: _____ UNIT: _____ GRADE: _____ PROPERTY: _____ AS OF DATE: _____

MATERIAL SPEC: _____

RANGE: _____

TARGET: _____

Production Period	n	\bar{x}	Difference +/- Target	\overline{MR}	3σ	<i>C_p</i>	<i>C_{pk}</i>

FIG. 1 Sample Process Capability Summary Sheet

These average values, especially the Cpk , can be used to compare the quality levels of different manufacturing units.

5.3 Process Performance:

5.3.1 A minimum of 30 test data are required, without regard to the process being in a state of statistical control, when calculating the standard deviation for process performance. In this case, extended production periods such as weeks or months can be represented.

5.3.2 Calculate Pp and Ppk as shown in 6.5 and 6.6. Both the Pp index and Ppk index must be greater than 1.0 in order to indicate that the process meets specifications. The Ppk index is inherently less than or equal to the Pp index (for one-sided specifications, only the Ppk is applicable).

5.3.3 A *process performance summary* can be used to summarize the data generated by the different production periods represented in a row of calculated values. (See Fig. 2.)

6. Calculation

6.1 Calculate estimated standard deviation ($\hat{\sigma}$) as follows:

$$(\hat{\sigma}) = \frac{R}{d_2} \tag{1}$$

where:

$d_2 = 1.128$ for $n = 2$.

6.2 Calculate sample standard deviation as follows:

$$s = \sqrt{\frac{\sum_{i=1}^n (X_i^2) - \bar{X} \left(\sum_{i=1}^n X_i \right)}{n - 1}} \tag{2}$$

where:

- s = sample standard deviation,
- n = number of tests,
- X_i = individual test results, and
- \bar{X} = average of all test results.

6.3 Calculate the Cp index as follows:

$$Cp \text{ index} = \frac{USL - LSL}{6\hat{\sigma}} \tag{3}$$

where:

- USL = the upper specification limit,
- LSL = the lower specification limit, and
- $\hat{\sigma}$ = the process capability estimated standard deviation.

6.4 Calculate the Cpk index as follows:

Cpk index = minimum ratio of: (4)

$$\frac{USL - \bar{X}}{3\hat{\sigma}} \text{ or } \frac{\bar{X} - LSL}{3\hat{\sigma}} \tag{5}$$

where:

- \bar{X} = the process average, and
- $\hat{\sigma}$ = the estimated standard deviation.

6.5 Calculate the Pp index as follows:

$$Pp \text{ index} = \frac{USL - LSL}{6s} \tag{6}$$

6.6 Calculate the Ppk index as follows:

Ppk index = minimum ratio of: (7)

$$\frac{USL - \bar{X}}{3s} \text{ or } \frac{\bar{X} - LSL}{3s} \tag{8}$$

where:

- \bar{X} = the process average, and
- s = the sample standard deviation.

7. Keywords

7.1 carbon black; Cp index; Cpk index; moving range; process capability; process capability from test data; process control

PROCESS PERFORMANCE SUMMARY

PLANT: _____ UNIT: _____ GRADE: _____ PROPERTY: _____ AS OF DATE: _____

MATERIAL SPEC: _____

RANGE: _____

TARGET: _____

Production Period	n	\bar{X}	Difference \pm Target	3s	Pp	Ppk

FIG. 2 Sample Process Performance Summary Sheet

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>