



Standard Test Method for Volatile Content in Phenolic Resins¹

This standard is issued under the fixed designation D 4639; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of matter in a solid phenolic resin that is volatile at 300°F (150°C).

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Summary of Test Method

2.1 A specified weight of resin is added to a tared aluminum dish and weighed. The resin is then heated for 2 h in an oven at 300°F (150°C) and reweighed.

3. Significance and Use

3.1 Volatile material causes problems when phenolic resins and varnishes are heated at temperatures above 300°F (150°C). Heating a specified weight of resin for 2 h at this temperature indicates the amount of volatile material emitted when molding or curing phenolic resins.

4. Apparatus

4.1 *Analytical Balance*, capable of weighing to 0.1 mg.

4.2 *Thermometer*, glass, having a range from 1 to 200°C and accurate to 1°C.

4.3 *Circulating Oven*, maintained at 300 ± 3.5°F (150 ± 2°C).

4.4 *Aluminum Drying Dishes*, 2½-in. (63 mm) diameter, ¾-in. (20 mm) depth or equivalent.

4.5 *Desiccator*.

¹ This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.33 on Polymers and Resins.

Current edition approved Nov. 28, 1986. Published January 1987.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

5. Procedure

5.1 Mark two aluminum dishes for identification of each resin being tested and weigh them on the analytical balance to 0.1 mg. Record as w_1 .

5.2 Weigh a 5-g specimen of resin to 0.1 mg into each aluminum dish. Record total weight as w_2 .

5.3 Place the dishes in the oven for 2 h at 300°F (150°C).

5.4 Remove from oven and immediately place in desiccator until they cool to room temperature. Reweigh immediately upon removal from the desiccator and record as w_3 .

6. Calculation

6.1 Calculate the volatile content, V , as follows:

$$V, \% = 100 - \left[\frac{w_3 - w_1}{w_2 - w_1} \times 100 \right]$$

where:

w_1 = weight of aluminum dish, g,

w_2 = weight of aluminum dish and specimen used, g, and

w_3 = weight of aluminum dish and specimen after 2 h in oven, g.

7. Report

7.1 Report the following information:

7.1.1 Resin identification, time, and temperature.

7.1.2 Percent of volatile matter, or volatile content (average of duplicate determinations).

8. Precision and Bias

8.1 The precision and bias for this method have not been determined.

9. Keywords

9.1 phenolic resins; volatile content