



Standard Specification for Silicone Fluid Used for Electrical Insulation¹

This standard is issued under the fixed designation D4652; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers silicone fluid for use in transformers, capacitors, and electronic assemblies as an insulating or cooling medium, or both.

1.2 Silicone fluid covered by this specification is polydimethylsiloxane having a nominal viscosity of 50 cSt at 25°C and a fire point of 340°C or greater. This specification applies only to new silicone fluid. Information on in-service maintenance testing is available in appropriate guides.²

2. Referenced Documents

2.1 ASTM Standards:³

- D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester
- D97 Test Method for Pour Point of Petroleum Products
- D445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and Calculation of Dynamic Viscosity)
- D664 Test Method for Acid Number of Petroleum Products by Potentiometric Titration
- D877 Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using Disk Electrodes
- D923 Practices for Sampling Electrical Insulating Liquids
- D924 Test Method for Dissipation Factor (or Power Factor) and Relative Permittivity (Dielectric Constant) of Electrical Insulating Liquids
- D974 Test Method for Acid and Base Number by Color-Indicator Titration
- D1169 Test Method for Specific Resistance (Resistivity) of Electrical Insulating Liquids
- D1298 Test Method for Density, Relative Density, or API

¹ This specification is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.02 on Gases and Non-Mineral Oil Liquids.

Current edition approved Oct. 15, 2012. Published October 2012. Originally approved in 1992. Last previous edition approved in 2005 as D4652 – 05. DOI: 10.1520/D4652-05R12.

² IEEE C57.111, IEEE Guide for Acceptance of Silicone Insulating Fluid and its Maintenance in Transformers is published by the Insulating Fluids Subcommittee of the IEEE Power Engineering Society Transformers Committee.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method
- D1481 Test Method for Density and Relative Density (Specific Gravity) of Viscous Materials by Lipkin Bicapillary Pycnometer
- D1533 Test Method for Water in Insulating Liquids by Coulometric Karl Fischer Titration
- D1807 Test Methods for Refractive Index and Specific Optical Dispersion of Electrical Insulating Liquids (Withdrawn 2014)⁴
- D1816 Test Method for Dielectric Breakdown Voltage of Insulating Liquids Using VDE Electrodes
- D2129 Test Method for Color of Clear Electrical Insulating Liquids (Platinum-Cobalt Scale)
- D2161 Practice for Conversion of Kinematic Viscosity to Saybolt Universal Viscosity or to Saybolt Furol Viscosity
- D2225 Test Methods for Silicone Fluids Used for Electrical Insulation
- D2864 Terminology Relating to Electrical Insulating Liquids and Gases
- D4052 Test Method for Density, Relative Density, and API Gravity of Liquids by Digital Density Meter
- D4059 Test Method for Analysis of Polychlorinated Biphenyls in Insulating Liquids by Gas Chromatography
- D4559 Test Method for Volatile Matter in Silicone Fluid

3. Terminology

3.1 Definitions and descriptions of terms specific to this specification are given in Methods D2225 and Terminology D2864.

4. Sampling and Testing

4.1 Take all samples in accordance with Methods D923.

4.2 Test in accordance with the methods specified in Table 1.

NOTE 1—Because of the different needs of the various users, items relating to packaging, labeling, and quality assurance are subject to buyer-seller agreement.

NOTE 2—In addition to all other tests listed herein, it is sound engineering practice for the apparatus manufacturer to perform a functional evaluation of silicone fluid in insulation systems, prototype

⁴ The last approved version of this historical standard is referenced on www.astm.org.

TABLE 1 Detail Requirements for Silicone Fluid

Property	Limit	ASTM Test Method
<i>Physical:</i>		
Color, max	15	D2129
Flash point, °C, min	300	D92
Fire point, °C, min	340	D92
Pour point, °C, max	-50	D97
Refractive index, 25°C	1.4010 to 1.4040	D1807
Viscosity, cSt, at:		D445, D2161
0°C	81 to 92	
25°C	47.5 to 52.5	
40°C	35 to 39	
100°C	15 to 17	
Specific gravity, 25/25°C	0.957 to 0.964	D1298, D1481, D4052
Volatile matter, weight, max%	0.5	D4559
<i>Electrical Properties:</i>		
Dielectric breakdown voltage at 60 Hz		
Disk electrodes, kV, min	30	D877 ^A
VDE electrodes, kV, min at:		
1 mm (0.04 in.) gap	20	D1816 ^B
2 mm (0.08 in.) gap	35	
Dissipation factor ^C at 60 Hz, 25°C, %, max	0.01	D924
Volume resistivity at 25°C, Ω·cm, min	1 × 10 ¹⁴	D1169
<i>Chemical:</i>		
Neutralization number, mg KOH/g, max	0.01	D664, D974
Water content, ppm, max	50	D1533 ^D
PCB content, ppm	not detectable	D4059

^A This test method must be modified as described in Methods D2225.

^B Use of this test method requires the discharge energy meet the limits of Section 1.4 of the test method.

^C Dissipation factor and power factor are numerically equal up to 0.5 %.

^D With modifications as indicated for silicone fluid.

structures, or full-scale apparatus, or any combination thereof, to assure suitable service life.

5. Detail Requirements

5.1 The silicone fluid, as received, shall conform to the requirements of **Table 1**. The significance of these properties is covered in Methods D2225.

6. Keywords

6.1 electrical insulating liquid; silicone fluid

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).