



Standard Test Method for Nonvolatile Content of Latexes¹

This standard is issued under the fixed designation D 4758; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a quality control test for nonvolatile content of latex vehicles. The specified time-temperature conditions (180°C, 20 min) were selected to allow test completion in 1 h or less. For latex vehicles used in certain air-dry or low-temperature bake coatings, as well as for those that contain temperature-sensitive materials, the use of a lower temperature and other bake time will more accurately reflect the effective nonvolatile content (Note 1). Alternative time-temperature conditions should be agreed upon between the producer and user.

NOTE 1—The test conditions of Test Method D 2369 (110°C, 60 min) have been found suitable for use with many latex vehicles.

1.2 This test method is not intended to be employed for determining the volatile organic content (VOC) of formulated coatings.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is responsibility of the user of this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 2369 Test Method for Volatile Content of Coatings²

E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens³

E 300 Practice for Sampling Industrial Chemicals⁴

3. Significance and Use

3.1 This test method is designed to quantify the weight percent of a commercial, synthetic latex product that, when incorporated into a coating product, constitutes the binder content of the applied coating.

¹ This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.33 on Polymers and Resins.

Current edition approved May 15, 1992. Published July 1992. Originally published as D4758 – 88. Last previous edition D4758 – 88.

² *Annual Book of ASTM Standards*, Vol 06.01.

³ *Annual Book of ASTM Standards*, Vol 14.02.

⁴ *Annual book of ASTM Standards*, Vol 15.05.

4. Apparatus

4.1 *Oven*, forced-ventilation Type IIB, as specified in Specification E 145, with closed vent.

4.2 *Balance*, sensitive to 0.1 mg.

4.3 *Desiccator*.

4.4 *Weighing dish*, aluminum, approximately 57 mm in diameter by 18 mm deep.

4.5 *Syringe*, 5-mL disposable.

5. Sampling

5.1 Procedures described in the Slurry Sampling section of Practice E 300 shall be used for sampling latexes.

6. Procedure

6.1 For each latex to be tested, wash two aluminum dishes with a suitable reagent grade solvent (for example, toluene) or heat to constant weight to assure that volatile contaminants are removed. Determine the tare weight of the aluminum dishes to 0.1 mg.

6.2 Thoroughly mix the sample on a mechanical shaker or can roller to assure homogeneity.

6.3 Draw 3.5 mL of the sample into the syringe and weigh to 0.1 mg.

6.4 Transfer 1.5 ± 0.1 mL of the latex into a tared weighing dish and reweigh the syringe to 0.1 mg. Calculate the latex specimen weight, S , as follows:

$$S = w_1 - w_2 \quad (1)$$

where:

w_1 = initial weight of syringe and latex, g,

w_2 = weight of syringe and latex remaining after discharging specimen, g.

6.5 Repeat 6.4 for the duplicate determination.

6.6 Transfer the aluminum dishes to an oven operating at 180 ± 4°C and heat for 20.0 ± 1 min. (Note 2). Remove from the oven, cool in a desiccator for 5 min at room temperature and weigh to 0.1 mg. Determine the weight of residue, N , in each dish as follows:

$$N = W_1 - W_2 \quad (2)$$

where:

W_1 = weight of dish and residue, g,

W_2 = tare weight of aluminum dish, g.

NOTE 2—Add distilled water to viscous test specimen prior to baking.

7. Calculation

7.1 Calculate the mean weight percent nonvolatile material (% NVM) where Subscripts 1 and 2 refer to the individual data from the duplicate determinations:

$$\% NV = \frac{N_1/S_1 + N_2/S_2}{2} \times 100 \quad (3)$$

8. Report

8.1 Report the nonvolatile content to 0.01 weight %.

9. Precision and Bias

9.1 An interlaboratory study was conducted on this test method in which one operator in each of five laboratories made duplicate determinations on each of two days on six commercial latices containing 44 and 65% nonvolatile matter. The latex polymer types were three all-acrylics, a vinyl acetate-acrylic copolymer, and acrylic terpolymer and a vinyl acetate-vinyl chloride-ethylene copolymer. Two laboratories could not run the test on two latexes because they had gelled, and in the statistical analysis all results obtained on one latex were

rejected because they differed significantly from the others. The pooled within-laboratory standard deviation was found to be 0.09% absolute with 20 degrees of freedom and the between-laboratories standard deviation 0.16% absolute with 16 degrees of freedom. Based on these standard deviations, the following criteria should be used for judging the acceptability of results at the 95 % confidence level:

9.1.1 *Repeatability*—Two results, each the mean of duplicate determinations, obtained by the same operator should be considered suspect if they differ by more than 0.27% absolute.

9.1.2 *Reproducibility*—Two results, each the mean of duplicate determinations obtained by operators in different laboratories, should be considered suspect if they differ by more than 0.48 % absolute.

9.2 *Bias*—Bias cannot be determined as no standard latex is available.

10. Keywords

10.1 accelerated testing; air dry coatings; baked coatings; latex paints; latex vehicles; low temperature bake coatings; nonvolatile matter content; temperature tests (subheading low)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).