



# Standard Test Method for Nitrogen Content of Soluble Nitrocellulose—Alternative Method<sup>1</sup>

This standard is issued under the fixed designation D4795; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 Test Methods **D301** for measuring nitrogen content in nitrocellulose by nitrometer are the accepted standard. However, the glassware is specialized and the precision is dependent on the development of a high level of skill by the operator. The ferrous-sulfate titration of nitrate is a classical procedure. By controlling critical variables and automating the actual titration, precision equivalent to the nitrometer can be achieved with nitrocellulose. This test method describes such a procedure.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 8.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**D301 Test Methods for Soluble Cellulose Nitrate** (Withdrawn 2011)<sup>3</sup>

**D1193 Specification for Reagent Water**

## 3. Summary of Test Method

3.1 A weighed specimen of nitrocellulose is dissolved in sulfuric acid and titrated automatically with ferrous sulfate. The nitrogen content of the specimen is calculated using the equivalence factor of the ferrous sulfate.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **D01** on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee **D01.36** on Cellulose and Cellulose Derivatives.

Current edition approved June 1, 2008. Published June 2008. Originally approved in 1988. Last previous edition approved in 2003 as D4795 – 94 (2003). DOI: 10.1520/D4795-94R08.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

## 4. Significance and Use

4.1 This test method provides a simpler means for measuring the nitrogen content of nitrocellulose than the nitrometer described in Test Methods **D301**. Under controlled conditions, the procedure described is capable of results equivalent to those obtained by the nitrometer.

## 5. Interferences

5.1 The presence of moisture (or other volatile components) in the specimen will affect results. It is recommended that only thoroughly dry specimens be used.

5.2 Temperature rise must be controlled during the titration. The cooling bath provides that control. However, if the rate of titrant addition is too fast, temperature may rise out of control. Results may then be erratic. Adherence to the procedure will avoid temperature excursions. For optimum system efficiency, room temperature should be maintained at  $23 \pm 2^\circ\text{C}$ .

5.3 The strength of the sulfuric acid used to dissolve the specimen is very important. Too low an acid strength slows the rate of solution which, in turn, causes titrations to be abnormally slow. Results then become erratic.

## 6. Apparatus

6.1 *Acid Bottle Safety Dispenser.*

6.2 *Brinkman 20 Titration System*, or equivalent, with 25 mL amber buret:

6.2.1 *Electrode*, platinum.

6.2.2 *Electrode*, glass.

6.3 *Desiccator*, with drying agent.

6.4 *Weighing bottles*, 12-mL capacity, aluminum (preferred) or glass.

6.5 *Analytical Balance*, accurate to  $\pm 0.1$  mg.

6.6 *Ovens*— $135^\circ\text{C}$ , for drying standards, and  $100^\circ\text{C}$ , for drying specimens, having unexposed heating elements and the door latch removed.

6.7 *Circulating Unit*, for chilled water,  $5 \pm 2^\circ\text{C}$ .

6.8 *Blender*, with 0.25-L (8-oz) blender jar.

## 7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>4</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type III of Specification **D1193**.

7.3 *Sulfuric Acid (H<sub>2</sub>SO<sub>4</sub>)* 95 to 98 %.

7.4 *Ferrous Sulfate Solution*—Dissolve 350 g of ferrous sulfate crystals (FeSO<sub>4</sub>) in 1000 mL of distilled water. Add 1000 mL of 1+1 H<sub>2</sub>SO<sub>4</sub> solution. Makes 2 L.

7.5 *Potassium Nitrate (KNO<sub>3</sub>) Standard* or an equivalent nitrate primary standard.

7.6 *Nitrocellulose Standard*—A sample with a known nitrogen value or other known organic nitrate.

## 8. Hazards

8.1 Since the sample of nitrocellulose must be dried, it is imperative that care be exercised in storage, handling, and disposal. Dry nitrocellulose is extremely flammable. Refer to the Procedure section for Drying Samples of Test Methods **D301**.

8.2 Strong sulfuric acid used as the solvent for the specimen can burn the skin. The ferrous sulfate titrant is also strongly acidic. Take proper precautions to protect the operator and the equipment.

8.3 To prevent burns from acid dripping off the electrodes and dispenser tip, always wipe the electrodes and dispenser tip with a tissue before reaching under them to retrieve a beaker.

## 9. Preparation of Apparatus

9.1 If the system has been down for at least 8 h, purge the system with 40 mL of ferrous sulfate solution.

## 10. Calibration and Standardization

10.1 Weigh a sample bottle containing  $0.5000 \pm 0.05$  g of KNO<sub>3</sub> that has been dried in a 135°C oven for a minimum of 4 h and stored in a desiccator. If KNO<sub>3</sub> has been out of the oven for 4 h or more, redry in a 135°C oven for a minimum of 2 h. (Nitrocellulose specimens are dried in a 100°C oven for a minimum of 1 h. If out of the oven more than 2 h, redry for ½ h.) Turn on the pump of the chilled water circulator to start water flowing through the cooling bath.

<sup>4</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

10.2 Place the magnetic stirring bar into a dry 250-mL beaker and fill the beaker with 150 mL of H<sub>2</sub>SO<sub>4</sub> ( $20 \pm 2^\circ\text{C}$ ).

10.3 Place the beaker in the cooling bath on the stirrer unit. Start the stirrer and adjust the speed for a *slight* vortex. Too vigorous a vortex can cause the nitrocellulose to splash onto the sides of the beaker.

10.4 With the stirrer operating and the electrodes up in the air away from the acid, slowly pour the specimen into the vortex of the swirl. Be careful not to touch the dispensing tip or electrodes with the weighing bottle. Reweigh the weighing bottle to find the weight of the standard by difference.

10.5 Allow most of the KNO<sub>3</sub> to dissolve. Visually inspect the solution until no more chunks or chips of KNO<sub>3</sub> remain. The solution may be cloudy.

10.6 Lower the electrodes and the dispensing tip into the H<sub>2</sub>SO<sub>4</sub>.

10.7 Set the controls to the desired settings.

10.8 As the KNO<sub>3</sub> dissolves and HNO<sub>3</sub> is formed by the reaction of H<sub>2</sub>SO<sub>4</sub> and the specimen, a millivolt potential change is evident by a rising recorder pen.

10.8.1 When the pen shows a leveling off, it is an indication that the majority of the KNO<sub>3</sub> is in solution. Visually inspect the solution to verify the fact that chips are no longer present.

10.9 Set the buret control to a rate of about 5 mL/min. Allow  $10 \pm 0.1$  mL to dispense at this rate.

10.10 Stop the buret, switch the dispense-rate switch to automatic, and restart. Allow the titration to proceed automatically to the end point.

10.11 At the completion of the automatic titration, immediately record the millilitre reading. Switch the electrode setting to STANDBY.

10.12 Raise the electrodes from the acid and allow most of the acid to drip into the titration beaker. Carefully wipe by dabbing the electrodes and dispensing tip with a tissue. (**Warning**—See Section 8.) Discard the tissue into a container of water. **DO NOT** allow acid to drip into the circulating-bath water.

10.13 Remove the completed titration beaker from the cooling bath.

10.14 Lower the electrodes and pipet into a beaker of clean H<sub>2</sub>SO<sub>4</sub> for soaking. Make sure the acid is not contaminated with FeSO<sub>4</sub>. (It may bleed from the dispenser tip giving a reddish tint to the acid.) Replace with clean H<sub>2</sub>SO<sub>4</sub> if this occurs.

NOTE 1—It is important to soak the electrodes in between each analysis and while the titrators are not in use. Cleanliness of equipment is of the utmost importance in this method of analysis.

10.15 Calculate the nitrogen equivalence factor *F* for the standard KNO<sub>3</sub> as follows:

$$F = (A \times 13.855)/B \quad (1)$$

where:

*A* = weight of KNO<sub>3</sub>, g,

13.855 = nitrogen equivalence of nitrogen in  $\text{KNO}_3$  or in the standard material used, and  
*B* = amount of  $\text{FeSO}_4$  used to titrate  $\text{KNO}_3$ , mL.

## 11. Specimen Preparation

### 11.1 Cutting:

11.1.1 Use a sample size of approximately 2 heaping tablespoons of wet nitrocellulose.

11.1.2 For high viscosity types, place the sample into a small 0.25-L (8-oz) plastic blender jar. Fill to the fill line with tap water, and screw on the cap with a 4-blade cutter unit inside.

11.1.3 Place on the blender base and blend for 7 min at high speed.

11.1.4 For 11 % nitrogen and low viscosity types, grind in a tissue disintegrator using a 0.5-L (16-oz) glass jar about  $\frac{3}{4}$  full of tap water.

11.1.5 Grind each sample at high speed for their respective times as follows:

Hercules Designation	Time, min
SS, all	5
RS $\frac{1}{2}$	4
RS $\frac{1}{4}$	4
RS $\frac{1}{8}$	3
AS, all	3

11.2 At the completion of cutting, remove the sample container and draw off the excess water from the nitrocellulose by filtering on a Büchner funnel through a circular filter paper.

11.3 Dry the material in accordance with the paragraph on small quantities in the Procedure section for Drying Samples of Test Methods **D301**.

11.4 After drying, weigh 3 replicate specimens of 0.4500 ± 0.0075 g each into a weighing can or bottle.

11.5 It is desirable to analyze the specimens as soon as they are taken out of the oven. Allow time for cooling in a desiccator before weighing. If specimens are out of the oven for more than 2 h, redry for  $\frac{1}{2}$  h at 100°C.

**TABLE 1 Suggested Settings for Brinkman 20**

	EP-1	Select	EP-1 Setting, mV	Proposed Band <sup>A</sup>	Minimum Delivery <sup>A</sup>
Standardizations with $\text{KNO}_3$	-mV	EP-1	350	80	100
Analysis of nitro-cellulose	-mV	EP-1	200	80	100

<sup>A</sup> These are approximations only. Settings can vary between instruments.

## 12. Procedure

12.1 Prepare specimens in accordance with Section **11**.

12.2 Repeat **10.1-10.15**, using the settings for the specimen given in **Table 1**.

12.3 Dispose of any excess  $\text{H}_2\text{SO}_4$  standard down the sink and rinse with large quantities of water.

## 13. Calculation

13.1 Calculate the percent of nitrogen *N* as follows:

$$N = (C \times F) / D \quad (2)$$

where:

*C* =  $\text{FeSO}_4$  to titrate specimen, mL,

*F* = equivalence factor from **10.15**, and

*D* = weight of specimen, g.

## 14. Precision and Bias<sup>5</sup>

14.1 *Precision*—Tests by two laboratories on two samples gave results equivalent to the nitrometer in precision and bias. No more extensive interlaboratory testing has been undertaken as yet.

14.2 *Bias*—No statement on bias can be made as no suitable reference material is available as a standard.

## 15. Keywords

15.1 nitrogen content; soluble nitrocellulose

<sup>5</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report: RR:D01-1056.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*