



Designation: D4850 – 13 (Reapproved 2017)

Standard Terminology Relating to Fabrics and Fabric Test Methods¹

This standard is issued under the fixed designation D4850; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology covers definitions of technical terms used in the industry related to textile fabrics. Terms that are generally understood or adequately defined in other readily available sources are not included. Other terminology standards that have terms related to textile fabrics are shown in 2.1

1.2 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- D737 Test Method for Air Permeability of Textile Fabrics
- D1230 Test Method for Flammability of Apparel Textiles
- D1336 Test Method for Distortion of Yarn in Woven Fabrics
- D1388 Test Method for Stiffness of Fabrics
- D1424 Test Method for Tearing Strength of Fabrics by Falling-Pendulum (Elmendorf-Type) Apparatus
- D1775 Test Method for Tension and Elongation of Wide Elastic Fabrics (Withdrawn 2000)³
- D1777 Test Method for Thickness of Textile Materials
- D2261 Test Method for Tearing Strength of Fabrics by the Tongue (Single Rip) Procedure (Constant-Rate-of-Extension Tensile Testing Machine)
- D2594 Test Method for Stretch Properties of Knitted Fabrics Having Low Power

- D2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics
- D2906 Practice for Statements on Precision and Bias for Textiles (Withdrawn 2008)³
- D3107 Test Methods for Stretch Properties of Fabrics Woven from Stretch Yarns
- D3511 Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Brush Pilling Tester
- D3512 Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Random Tumble Pilling Tester
- D3514 Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Elastomeric Pad
- D3773 Test Methods for Length of Woven Fabric
- D3774 Test Method for Width of Textile Fabric
- D3775 Test Method for Warp (End) and Filling (Pick) Count of Woven Fabrics
- D3776 Test Methods for Mass Per Unit Area (Weight) of Fabric
- D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method
- D3787 Test Method for Bursting Strength of Textiles—Constant-Rate-of-Traversal (CRT) Ball Burst Test
- D3789 Practice for Labeling Cans of Consumer Spray Paint (Withdrawn 1997)³
- D3882 Test Method for Bow and Skew in Woven and Knitted Fabrics
- D3883 Test Method for Yarn Crimp and Yarn Take-up in Woven Fabrics
- D3884 Guide for Abrasion Resistance of Textile Fabrics (Rotary Platform, Double-Head Method)
- D3885 Test Method for Abrasion Resistance of Textile Fabrics (Flexing and Abrasion Method)
- D3886 Test Method for Abrasion Resistance of Textile Fabrics (Inflated Diaphragm Apparatus)
- D3887 Specification for Tolerance for Knitted Fabrics (Withdrawn 2017)³
- D3939 Test Method for Snagging Resistance of Fabrics (Mace)
- D3990 Terminology Relating to Fabric Defects

¹ This terminology is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.59 on Fabric Test Methods, General.

Current edition approved July 15, 2017. Published August 2017. Originally approved in 1989. Last previous edition approved in 2013 as D4850 – 13. DOI: 10.1520/D4850-13R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

D4032 Test Method for Stiffness of Fabric by the Circular Bend Procedure

D4033 Test Method for Resistance to Yarn Slippage at the Sewn Seam in Upholstery Fabrics (Dynamic Fatigue Method) (Withdrawn 2001)³

D4034 Test Method for Resistance to Yarn Slippage at the Sewn Seam in Woven Upholstery Fabrics (Withdrawn 2001)³

D4157 Test Method for Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method)

D4158 Guide for Abrasion Resistance of Textile Fabrics (Uniform Abrasion)

D4390 Practice for Evaluation of the Performance of Terry Bathroom Products for Household Use (Withdrawn 1994)³

D4772 Test Method for Surface Water Absorption of Terry Fabrics (Water Flow)

D4350 Test Method for Corrosivity Index of Plastics and Fillers

D4685 Test Method for Pile Fabric Abrasion

D4848 Terminology Related to Force, Deformation and Related Properties of Textiles

D4850 Terminology Relating to Fabrics and Fabric Test Methods

D4851 Test Methods for Coated and Laminated Fabrics for Architectural Use

D4964 Test Method for Tension and Elongation of Elastic Fabrics (Constant-Rate-of-Extension Type Tensile Testing Machine)

D4966 Test Method for Abrasion Resistance of Textile Fabrics (Martindale Abrasion Tester Method)

D4970 Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Martindale Tester

D5034 Test Method for Breaking Strength and Elongation of Textile Fabrics (Grab Test)

D5035 Test Method for Breaking Force and Elongation of Textile Fabrics (Strip Method)

D5103 Test Method for Length and Length Distribution of Manufactured Staple Fibers (Single-Fiber Test)

D5278 Test Method for Elongation of Narrow Elastic Fabrics (Static-Load Testing)

D5362 Test Method for Snagging Resistance of Fabrics (Bean Bag)

D5378 Performance Specification for Woven and Knitted Shower Curtains for Institutional and Household Use

D5426 Practices for Visual Inspection and Grading of Fabrics Used for Inflatable Restraints

D5430 Test Methods for Visually Inspecting and Grading Fabrics

D5446 Practice for Determining Physical Properties of Fabrics, Yarns, and Sewing Thread Used in Inflatable Restraints

D5587 Test Method for Tearing Strength of Fabrics by Trapezoid Procedure

D5684 Terminology Relating to Pile Floor Coverings

D5793 Test Method for Binding Sites per Unit Length or Width of Pile Yarn Floor Coverings

D6207 Test Method for Dimensional Stability of Fabrics to Changes in Humidity and Temperature

D6614 Test Method for Stretch Properties of Textile Fabrics – CRE Method

D6674 Guide for Proficiency Test Program for Fabrics

D6770 Test Method for Abrasion Resistance of Textile Webbing (Hex Bar Method)

D6797 Test Method for Bursting Strength of Fabrics Constant-Rate-of-Extension (CRE) Ball Burst Test

3. Terminology

3.1 Definitions:

abrasion, *n*—the wearing away of any part of a material by rubbing against another surface. **D3884, D3885, D3886, D4157, D4158, D4685, D4966**

abrasion cycle, *n*—one complete movement across the surface of a material.

DISCUSSION—The complete movement for an abrasion cycle is dependent on the action of the abrasion machine and the test method used. It may consist of one back-and-forth unidirectional movement or one circular movement, or a combination of both. **D3885**

abrasion cycle, *n*—for the Martindale Abrasion Tester, 16 rubs required to complete a geometric shape, known as a Lissajous. **D4966**

abrasion cycle, *n*—in abrasion testing, one or more movements of the abradant across a material surface, or the material surface across the abradant, that permits a return to its starting position.

DISCUSSION—The abrasion cycle is dependent on the programmed motions of the abrasion machine and the test standard used. It may consist of one back-and-forth unidirectional movement such as for the flexing and abrasion test method; a circular movement such as for the rotary platform test method, or a combination of both such as for the inflated diaphragm test method. For the oscillatory cylinder abrasion method, an abrasion cycle consists of one double-rub. **See double-rub.**

[D13.60] D4157, D6770

absorption, *n*—a process in which one material (the absorbent) takes in or absorbs another (the absorbate); as the absorption of moisture by fibers. **[D13.59] D4772**

accuracy, *n*—of a test method, the degree of agreement between the true value of the property being tested (or accepted standard value) and the average of many observations made according to the test method, preferably by many observers. **[D13.60] D2906, D6674**

air permeability, *n*—the rate of air flow passing perpendicular through a known area under a prescribed air pressure differential between the two surfaces of a material.

DISCUSSION—Air permeability of fabric at a stated pressure differential between two surfaces of the fabric is generally expressed in SI units as cm³/s/cm² and in inch-pound units as ft³/min/ft² calculated in operating conditions. (See **permeability, porosity.**) **D737**

air-supported roof, *n*—a fabric roof-system that is properly secured and primarily supported and held in place by air pressure. **D4851**

architectural-use, *n*—in the building trade, a descriptive term for fabrics used in fabric roof-systems or similar industrial applications. (See also **fabric roof-system.**) **D4851**

bagging, *n*—any material, such as fabric or other suitable material used to protect commodities during shipment and/or storage.

DISCUSSION—Fabrics may be of the woven, knitted, or non-woven type, and are typically produced with cotton, jute, polyethylene, or polypropylene fibers. **D4850**

batch sample, *n*—the material(s) used for the proficiency test study taken from a common roll or garment lot and distributed to the participants. **[D13.60] D6674**

bending length, *n*—(1) *general*—a measure of the interaction between fabric weight and fabric stiffness as shown by the way in which a fabric bends under its own weight. It reflects the stiffness of a fabric when bent in one plane under the force of gravity, and is one component of drape; (2) *specific*—the cube root of the ratio of the flexural rigidity to the weight per unit area. **D1388**

bias, *n*—*in statistics*, a constant or systematic error in test results. **[D13.60] D6674**

blister, *n*—*in bonded, fused, or laminated fabrics*, a bulge, swelling, or similar surface condition on either the face fabric or the backing fabric characterized by the fabric being raised from the plane of the underlying component over a limited area to give a puffy appearance. **D2724**

bond strength, *n*—*of bonded, fused, or laminated fabrics*, the tensile force expressed in ounces per 25 mm (1 in.) of width, required to separate the component layers under specified conditions. **D2724**

bonded fabric, *n*—a layered fabric structure wherein a face or shell fabric is joined to a backing fabric, such as tricot, with an adhesive that does not significantly add to the thickness of the combined fabrics. (See also **laminated fabric**, **coated fabric**.) **D2724**

book fold, *n*—a fabric doubled selvage to selvage, then folded back and forth upon itself in predetermined lengths. (See also **shoe fold**.)

DISCUSSION—When the piece is completed, the fold-edges on each side are folded once more upon themselves so that the fold-edges are inside, forming a compact package as long as one half the width of the fabric. **D4850**

bow, *n*—a fabric condition resulting when filling yarns or knitted courses are displaced from a line perpendicular to the selvages and form one or more arcs across the width of the fabric. (See also **double bow**.) **D3882, D3990**

braided fabric, *n*—a structure produced by interlacing three or more ends of yarns in a manner such that the paths of the yarns are diagonal to the vertical axis of the fabric. **D4850**

breaking force, *n*—the maximum force applied to a material carried to rupture (compare *breaking point*, *breaking strength*). **[D13.60] D3884, D3885, D4157, D4848, D5034, D5035, D6770**

breaking load, *n*—deprecated term. Use *breaking force*. **[D13.60] D4848, D5034**

broken end, *n*—*in woven fabrics*, a void in the warp direction due to yarn breakage. **D3990**

bubble—See preferred term *blister*. **[D13.59] D2724**

burlap, *n*—a coarse, heavy, plain weave fabric of yarns, such as bast or cotton fiber yarn. **D4850**

bursting strength, *n*—the force or pressure required to rupture a textile by distending it with a force, applied at right angles to the plane of the fabric, under specified conditions.

DISCUSSION—The angle of application of force, and the area of the fabric upon which the force is applied varies continuously as the fabric stretches when it is tested as directed in this method. **D6797**

bursting strength, *n*—the force or pressure required to rupture a fabric by distending it with a force, applied at right angles to the plane of the fabric, under specified conditions. **D3786, D3787, D3887**

calibrate, *n*—to determine and record the relationship between a set of standard units of measure and the output of an instrument or test procedure. **[D13.60] D6674**

circular bend, *n*—simultaneous, multidirectional deformation of a fabric in which one face of a flat specimen becomes concave and the other becomes convex. **D4032**

coated fabric, *n*—a flexible material composed of a fabric and any adherent polymeric material applied to one or both surfaces. (See also **laminated fabric**.) **D4850, D4851, D5446**

color contrast, *n*—*in textiles*, a general term for a visible color difference between two adjacent areas.

DISCUSSION—For the purpose of Test Methods **D3939** and **D5362**, a color contrast is a visible color difference between a snag and the immediate surrounding area of the fabric that has no defects. Color contrasts often occur when printed fabrics are snagged. **D3939, D5362**

constant-rate-of-extension tensile testing machine (CRE), *n*—a testing machine in which the rate of increase of the specimen length is uniform with time. **D6797**

constant-rate-of-extension (CRE) tensile testing machine—a testing machine in which the rate of increase of specimen length is uniform with time. **[D13.60] D5035**

constant-rate-of-extension type tensile testing machine (CRE), *n*—*in tensile testing*, an apparatus in which the pulling clamp moves at a uniform rate, and the force-measuring mechanism moves a negligible distance with increasing force, less than 0.13 mm (0.005 in.). **D3787**

constant-rate-of-load (CRL) tensile testing machine—a testing machine in which the rate of increase of the load being applied to the specimen is uniform with time after the first 3 s. **[D13.60] D4964, D5035, D5034**

constant-rate-of-traverse (CRT) tensile testing machine—a testing machine in which the pulling clamp moves at a uniform rate and the load is applied through the other clamp which moves appreciably to actuate a weighing mechanism, so that the rate of increase of load or elongation is dependent

- upon the extension characteristics of the specimen. [D13.60] **D3787, D5035, D5034**
- corduroy**, *n*—a filling cut-pile fabric in which the cut fibers form a surface of wales (rounded cords or ribs) which usually run warpwise. **D4685, D4850**
- count**, *n*—*in woven fabric*, the number of warp yarns (ends) and filling yarns (picks) per unit distance as counted while the fabric is held under zero tension, and is free of folds and wrinkles. **D3775**
- count**, *n*—*in knitted fabrics*, the number (counted units) of wale loops and course loops per 25 mm (1 in.). **D3787**
- course**, *n*—*in knitted fabrics*, a row of successive loops in the width direction of the fabric. **D2594**
- crack mark**, *n*—*in bonded, fused, or laminated fabrics*, a sharp break or crease in the surface contour of either the face fabric or the backing fabric that becomes evident when the bonded, fused, or laminated composite is rolled, bent, draped, or folded. [D13.54] **D2724**
- crease retention**, *n*—that property of a fabric which enables it to maintain an inserted crease. **D4850**
- critical defect**, *n*—a serious defect that judgment and experience indicate is likely to prevent the usability or proper performance of a product from its intended purpose. **D5430**
- cross-machine direction**, **CD**, *n*—the direction in the plane of the fabric perpendicular to the direction of manufacture.
DISCUSSION—This term is used to refer to the direction analogous to coursewise or filling direction in knitted or woven fabrics, respectively. [D13.59, D13.60] **D737, D1388, D1424, D1777, D2261**
- cut**, *n*—*as applied to woven fabric*, a length approximately 60 yard in the greige. **D4850**
- cut strip test**, *n*—*in fabric testing*, a strip test in which the specimen is cut to the specified testing width. **D5035**
- cycle**, *n*—16 movements required for the completion of one Lissajous figure on a Martindale tester. [D13.60] **D4970**
- cycle**, *n*—in the Martindale tester, the sixteen movements required to complete one Lissajous figure. [D13.60] **D4966**
- defect**, *n*—*in inspection and grading*, the departure or non-conformance of some characteristic from its intended level or state.
DISCUSSION—In inspection and grading the characteristic is usually a visual one. However, defects such as heat damage or poorly finished textiles grading by hand may be required. **D5430**
- denim**, *n*—a durable woven twill fabric, usually of all cotton or a blend of cotton and manufactured fibers, made from a variety of yarn numbers, and in various fabric weights, colors, designs, and finishes. **D4850**
- dimensional change**, *n*—a generic term for changes in length, width, or thickness of a specimen subjected to specified conditions.
DISCUSSION—Dimensional change is usually expressed as a percent of the original dimension of the specimen. When a dimension increases it is often referred to as growth. When a dimension decreases it is often referred to as shrinkage. **D4850**
- dimensional stability**, *n*—the ability of a material to retain its length and width dimensions under specified conditions.
DISCUSSION—The dimensions are length and width and the specified conditions are those of cycled humidity and temperature. **D6207**
- direction of slippage**, *n*—*at the seam*, the line of movement parallel to either the filling or the warp on a woven fabric in which minimum force is required to produce yarn slippage.
DISCUSSION—The fabric may be pulled in both directions in many cases. **D4034**
- distortion**, *n*—*in fabrics*, a general term for a visible defect in the texture of a fabric.
DISCUSSION—For the purpose of Test Methods **D3939** and **D5362**, snags are composed of different combinations of protrusions and distortions. A distortion is characterized by a group of fibers, yarn, or a yarn segment that is displaced from its normal pattern so that there is a visible change in the texture of the fabric; however, the displaced group of fibers, yarn, or yarn segment does not extend above the fabric surface. Distortions include conditions where (1) tension on a snagged yarn has changed the size of some loops within a knitted fabric and the result is a pucker on the surface of the fabric, and (2) tension on a snagged yarn has caused a yarn to break off within a woven fabric and the result is a change in the texture where the yarn used to be. **D3939, D5362**
- double bow**, *n*—two fabric bows, arcing in the same direction, as in a flattened M or W depending on the viewing angle. (Compare **double reverse bow** and **double bow**.)
DISCUSSION—In tubular knits, there may be differential bowing between the top and the bottom of the tube. **D3882, D3990**
- double hooked bow**, *n*—one hooked bow at each side of the fabric that arc in opposite directions. (See also **hooked bow**.) **D3882, D3990**
- double reverse bow**, *n*—two fabric bows arcing in opposite directions. (See also **bow**. Compare **double bow**.) **D3882**
- double-rub**, *n*—*in oscillatory cylinder abrasion testing*, one forward and one backward motion required to complete one cycle. [D13.60] **D4157**
- double-stroke**, *n*—*in flex and abrasion testing*, an abrasion cycle that consists of one forward and one backward motion. **D3885**
- duck**, *n*—a compact, firm, heavy, plain-weave cotton fabric, mass per square yard 6 to 50 oz. (See also **flat duck**, and **plied yarn duck**.) **D4850**
- durable-press**, *adj*—having the ability to retain substantially the initial shape, flat seams, pressed-in creases, and un-wrinkled appearance during use and after laundering or drycleaning. (See **wash and wear**.)
DISCUSSION—The use of the term **permanent-press**, *adj*, as a substitute for **durable-press** is not recommended. **D4850**
- elastic fabric**, *n*—a fabric made from an elastomer either alone or in combination with other textiles.
DISCUSSION—At room temperature an elastic fabric will stretch under tension and will return quickly and forcibly to substantially its original dimensions and shape when tension is removed.

Elastic fabrics may be manufactured by weaving, braiding, knitting, or other processes. **D1775, D4850, D4964**

elastic tape, *n*—a tape containing rubber or other elastomers to permit rubber-like stretch in at least one direction. **D4850**

elastic webbing, *n*—a webbing containing rubber or other elastomers to permit rubber-like stretch in at least one direction. **D4850**

elongation, *n*—the ratio of the extension of a material to the length of the material prior to stretching, expressed as a percent. **[D13.60] D4848, D4964, D5034, D5035**

elongation, *n*—the ratio of the extension of a material to the length of the material prior to stretching. (Compare extension.) **[D13.59] D4848, D5278**

end, *n*—*in woven fabric*, an individual warp yarn (single or ply) or cord. **D3775**

end count, *n*—*in woven fabric*, the number of individual warp yarns per inch of fabric regardless of whether they are comprised of single or plied components **D3775**

extension, *n*—the change in length of a material due to stretching. **[D13.59, D13.60] D4848, D4964, D5034**

extension-recovery cycle, *n*—*in tension testing*, the continuous extension of a specimen, with a momentary hold at a specified extension, followed by a controlled rate of return to zero extension. **[D13.59] D4848, D4964**

fabric, *n*—in textiles, planar structure consisting of yarns or fibers. **D6797**

fabric, *n*—*in textiles*, a planar structure consisting of yarns or fibers. **D737, D1388, D1424, D3787, D4850, D5587**

fabric growth, *n*—*in stretch testing*, the increase in the original dimension of a specimen after the application of a specified force for a prescribed time and subsequent removal of the force. (Compare **fabric stretch**.)

DISCUSSION—Fabric growth is usually expressed as a percentage of the specimen prior to application of force (see also **permanent deformation**).

fabric roof-system, *n*—a system of coated fabric or laminated fabric along with support cables, edge ropes, clamps, neoprene, roof drains, arch wear strips, and anchor bolts that constitutes the outside top covering of a building. **D4851**

fabric stretch, *n*—the increase in the dimension of a specimen of fabric resulting from a force applied under specified conditions. (Compare **elongation**, **extension**, **fabric growth**.)

DISCUSSION—The difference is usually expressed as a percentage of the initial dimension of the specimen.

fatiguing force, *n*—*in testing sewn seams*, the force that is repeatedly applied to a test specimen. **D4033**

filler, *n*—*in testing sewn seams* nonfibrous material, such as insoluble clays or gypsum, together with starches, gums, and so forth, added to a fabric to increase its weight or to modify

the appearance or handle of the fabric. (*Syn.* back-sizing.) (Compare **sizing**.) **D4850**

filling, *n*—*in woven fabric*, an individual yarn running from selvage to selvage at right angles to the warp in a woven fabric. **D3775**

filling elongation and tension, *n*—stretch or tension measured at right angles to the warp direction of the fabric. **D1775**

filling-faced twill, *n*—a weave in which filling yarns float over warp yarns, to produce a diagonal effect in the resulting fabric. (See also **twill weave** and **warp faced twill**.) **D4850**

filling tests, *n*—*in fabric testing*, tests in which the filling yarns are torn. **D1424**

filling-to-filling seam, *n*—a sewn seam in which the yarns in the filling direction on both sides of the sewn seam are perpendicular to the seam. **D4033**

finished fabric weight, *n*—mass per unit area expressed in grams per square metre (ounces per square yard), grams per linear metre (ounces per linear yard), or inversely as metres per kilogram (linear yards per pound), or square metres per kilogram (square yards per pound). **D3887**

finished yield, *n*—*in knitted fabrics*, the number of finished square metres per kilogram (square yards per pound) of finished fabric. **D3887**

flagging, *n*—*in sewn seams*, a mode of failure evidenced by slippage of one or more yarns entirely out of the original seam. **D4033**

flat duck, *n*—duck fabric having the warp of two single yarns woven as one and either single or plied filling yarn. (See also **duck**.) **D4850**

flexibility, *n*—that property of a material to endure repeated flexing, bending, or bowing without rupture. **D3885, D4850**

flexural rigidity, *n*—*general*—resistance to bending; *specific*—work per unit width which is required to bend a fabric to unit radius of curvature. **D1388**

float, *n*—*in woven fabrics*, that portion of a warp or filling yarn that extends unbound over two or more warp or filling yarns; *in knitted fabrics*, that portion of a yarn that is not knitted into loops.

DISCUSSION—If intentionally introduced, floats are a constructional characteristic of knit or woven fabrics. If unintentionally present, they are considered to be defects. **D4850**

foam tear, *n*—a condition wherein the foam portion of a laminated fabric ruptures prior to the failure of the bond. **D2724**

force, *n*—a physical influence exerted by one body on another which produces acceleration of bodies that are free to move and deformation of bodies that are not free to move. **[D13.59] D4848, D4964**

force-recovery cycle, *n*—*in elastic fabric testing*, a continuous curve or plot of force versus elongation (with movement stopped momentarily at point of reversal) describing the

- elongation and recovery of an elastic fabric; also known as the loading and unloading cycle. **D1775**
- fused fabric**, *n*—a type of bonded fabric made by adhering a fusible fabric to another fabric, such as for use in an interlining. **D2724**
- fusible fabric**, *n*—a utilitarian fabric which has a thermoplastic adhesive applied to one side, sometimes in a pattern of dots, so that the surface can be bonded to another fabric surface by the use of heat and pressure. **D2724**
- fuzz**, *n*—tangled fiber ends that protrude from the surface of a yarn or fabric. [**D13.60**]**D3511, D3512, D4970**
- gage**, *n*—*in knitted fabrics*, a measure of fineness expressing the number of needles per unit of width (across the wales). **D4850**
- gage**, *n*—*in full-fashioned hosiery*, a measure of fineness expressing the number of needles per 38 m (1.5 in.) on the needle bar. **D4850**
- gage**, *n*—*in warp knitting*, for simplex, tricot, milanese, number of needles per English inch; for raschel, kayloom, twice the number of needles per English inch. **D4850**
- gaiting**, *n*—*in warp knitting*, the setting of a guide bar one or more needle spaces to the right or left in order to increase the pattern possibilities. **D4850**
- grab test**, *n*—*in fabric testing*, a tensile test in which the central part of the width of the specimen is gripped in the clamps.
DISCUSSION—For example, if the specimen width is 100 mm (4.0 in.) and the width of the jaw faces 25 mm (1.0 in.), the specimen is gripped in the clamp with approximately 37.5 mm (1.5 in.) of fabric protruding from each side of the jaws. **D4850, D5034**
- grade**, *n*—*in warp knitting*, a term used to indicate the defect index evaluation of fabric determined by the number of defects per unit, for example per pound, per linear yard, or per square yard. **D4350, D4850**
- grade**, *v*—to assign a numerical value based on number, size, and severity of defects seen during a visual inspection. **D5430**
- hooked bow**, *n*—a fabric condition in which the filling yarns or knitted courses are in the proper position for most of the fabric width but are pulled out of alignment at one side of the fabric. (See also **double hooked bow**.) **D3882**
- impregnated fabric**, *n*—a fabric in which the interstices between the yarns are completely filled with the impregnating compound throughout the thickness of the fabric, as distinguished from sized or coated fabrics, where these interstices are not completely filled.
DISCUSSION—A fabric woven from impregnated yarns, but not impregnated after weaving, is not an impregnated fabric. **D4850**
- inspection**, *n*—the process of measuring, examining, testing, gaging, or otherwise comparing a characteristic or property of a material with applicable requirements. In this case only by visual examination. **D5430**
- interlining**, *n*—any textile which is intended for incorporation into an article of wearing apparel as a layer between an outer shell and inner lining. **D2724**
- jacket**, *n*—a textile, woven or felted into tubular or sleeve form, ready for covering and shrinking on a machine roll. **D4850**
- knitted fabric**, *n*—a structure produced by interlooping one or more ends of yarn or comparable material. **D3786, D3787, D3789, D3882, D3887, D4850, D5378**
- laid fabric**, *n*—a fabric made without filling yarn, the parallel warp yarns being held together by means of rubber latex or other binding material. **D4850**
- laminated fabric**, *n*—a layered fabric structure wherein a face or outer fabric is joined to a continuous sheet material, such as polyurethane foam, in such a way that the identity of the continuous sheet material is retained, either by the flame method or by an adhesive, and this in turn normally, but not always, is joined on the back with a backing fabric such as tricot. (**D2724**
- laminated fabric**, *n*—*in fabric roof systems*, a flexible fabric system composed of superimposed layers of fabric firmly united by bonding or impregnating with an adherent polymeric material to one or more surfaces. **D4851**
- length**, *n*—*of a fabric*, the distance from one end of a fabric to the other, measured parallel to the side edge of the fabric while it is under zero tension and is free of folds or wrinkles. **D3773, D3887**
- length of tear**, *n*—*in tear testing of fabrics*, the measured distance propagated in a specimen by a tearing force from the initiation of the test to the termination of the test. **D1424**
- length of tear**, *n*—*in tear testing of fabrics*, the measured distance propagated in a specimen by a tearing force from the initiation of the test to the termination of the test. **D1424**
- lisle**, *n*—a plied cotton yarn, comprising highly twisted single yarn components, produced with combed, long staple fibers.
DISCUSSION—Typically, lisle yarns are used for hosiery, and are singed to remove fibrils and to obtain a smooth surface. **D4850**
- Lissajous figure**, *n*—geometric figure that starts as a straight line, then becomes a widening ellipse and narrows to again become a straight line. There are 16 rubs in one Lissajous figure. [**D13.60**]**D4966**
- loop tension**, *n*—*in elastic material testing*, the total tension at any specified extension that is exerted on a specimen in a loop formation. **D4964**
- lot**, *n*—*in bonded, fused, or laminated fabric*, a single run on the bonding or laminating machine in which the processing is carried out without stopping or changing processing conditions, and consisting of either a single dye lot or a single gray goods lot. **D2724**
- low-power stretch**, *n*—that property of a fabric whereby it exhibits high fabric stretch and good recovery from low tension. **D2594**
- machine direction**, **MD**, *n*—the direction in the plane of the fabric parallel to the direction of manufacture.

DISCUSSION—This term is used to refer to the direction analogous to warpwise or warp direction in knitted or woven fabrics, respectively.

[D13.59] **D737, D1388, D1424, D1777, D2261**

major defect, *n*—a defect other than critical, that judgment and experience indicate is likely to materially reduce the usability of a product for its intended purpose. **D5430**

median force, *n*—in tensile testing, that force level that is exceeded by half the recorded peaks and which in turn exceeds the other half of the recorded peaks, in a specified distance of cross-head travel. **D2261**

minor defect, *n*—a defect that is not likely to materially reduce the usability of the product from its intended purpose, or is a departure from established standards having little bearing on the effective use of operation of a product. **D5430**

modified grab test, *n*—*in fabric testing*, a tensile test in which the control part of the width of the specimen is gripped in the clamps and in which lateral slits are made midlength of the specimen severing all yarns bordering that portion of the specimen held between the two clamps.

DISCUSSION—The slit modification reduces the fabric assistance inherent in the grab test procedure to a practical minimum. **D4850, D5034**

movement, *n*—one rotation of the outer gearing of the Martindale tester. [D13.60] **D4970**

narrow elastic fabric, *n*—an elastic fabric that is less than 150 mm, (6 in.), in width. (Compare **wide elastic fabric.**) **D1775, D4848, D5278, D4964**

narrow fabric, *n*—a fabric not exceeding 300 mm (12 in.) in width.

DISCUSSION—The category of narrow fabrics includes tapes, ribbons, and webbings. Narrow fabrics can be produced from any fiber, including elastomers, by weaving, braiding, knitting, or other methods. They can also be made by cutting or slitting wider fabrics into narrow strips. The term “narrow fabric” is incorrectly applied in the trade to fabrics which are narrower than the normal width for a specific fabric type. For example, woolens and worsteds under 52 in. (1.3 m) wide and cotton sheetings under 40 in. (1.0 m) are often called “narrow fabrics.” **D4850**

nonwoven fabric, *n*—a textile structure produced by bonding or interlocking of fibers, or both, accomplished by mechanical, chemical, thermal, or solvent means and combinations thereof. **D3786**

peak force, *n*—*in tear testing of fabrics*, the maximum force required to break one or more yarn components in a woven or knitted fabric specimen, or break the fiber, fiber bonds or fiber interlocks in other manufactured forms.

DISCUSSION—The peak force may consist of a single peak or a series of peaks depending upon the nature of the fabric. Typically for woven fabrics, if a small decrease in force occurs when the force is increasing, it is not considered to peak unless the indicated force exceeds the force required to break a yarn. Lower shifts corresponding to yarn movement do not qualify as peaks since no yarns are broken. **D2261, D5587**

permeability, *n*—the rate of flow of a fluid under a differential pressure through a material

DISCUSSION—Fluid under differential pressure includes:

- (1) Gas under differential gas pressure,
- (2) Vapor under differential vapor pressure, and
- (3) Water under differential hydrostatic pressure. (See also **air permeability.**) **D4850**

pick, *n*—*in woven fabric*, an individual filling yarn (single or ply) or cord source. **D3775**

pick count, *n*—*in woven fabrics*, the number of individual filling yarns per inch of fabric regardless of whether they are comprised of single or plied components. **D3775**

pile, *n*—*in pile fabric*, the raised loops or tufts (cut loops) that form all or part of the fabric surface. (See also **cut pile floor covering** and **looped pile floor covering.**) **D4850, D4772**

pile fabric, *n*—a fabric in which certain yarns project from the weave structure to form a rib or wale (not to be confused with knitted construction column of looped yarns) on the face of the fabric that can be cut or remain uncut.

DISCUSSION—Corduroy and velveteen are examples of cut filling pile fabrics. [D13.59] **D4685**

pile retention, *n*—*in corduroy*, the degree to which cut-pile yarns are held secure and intact during wear. (Ant. pile loss, pile pull-out). **D4685**

pilling resistance, *n*—resistance to the formation of pills on the surface of a textile fabric. **D4970, D3511, D3512, D3514**

plain surface textile fabric, *n*—any textile fabric which does not have an intentionally raised fiber or yarn surface such as a pile, nap, or tuft, but shall include those fabrics that have fancy woven, knitted or flock-printed surfaces. **D1230**

pills, *n*—bunches or balls of tangled fibers which are held to the surface of a fabric by one or more fibers. (Compare **fuzz ball.**) **D3511, D3512, D3514, D3990, D4970**

plain weave, *n*—a fabric pattern in which each yarn of the filling passes alternately over and under a yarn of warp and each yarn of the warp passes alternately over and under a yarn of the filling. **D4850**

pleat, *n*—three layers of fabric involving two folds or reversals of direction; the back fold may be replaced by a seam.

DISCUSSION—Pleats may be either pressed to give sharp creases or left unpressed to give soft folds. **D4850**

plied yarn duck, *n*—duck fabric with plied yarns in both warp and filling. (See **flat duck.**) **D4850**

porosity, *n*—the ratio of the volume of air or void contained within the boundaries of a material to the total volume (solid matter plus air or void) expressed as a percentage.

DISCUSSION—Porosity accordingly equals:

$$(V \times 100)/T$$

where:

V = volume of voids, and
 T = total volume.

(See also **air permeability** and **permeability.**) **D4850**

precision, *n*—the degree of agreement within a set of observations or test results obtained as directed in a method.

DISCUSSION—The term “precision,” delimited in various ways, is used to describe different aspects of precision. This usage was chosen in preference to the use of “repeatability” and “reproducibility.”

[D13.60] **D6674**

precision, *n*—under conditions of between-laboratory precision, the multi-laboratory single sample, single operator-apparatus-day (within laboratory) precision of a method; the precision of a set of statistically independent test results all of which are obtained by testing the same sample of material and each of which is obtained in a different laboratory by one operator using one apparatus to obtain the same number of observations by testing randomly drawn specimens over the shortest practical time interval. For a more detailed definition, refer to **D2906**. [D13.60] **D6674**

pressed-in crease, *n*—a sharp crease inserted intentionally in a fabric usually by application of pressure, heat, and moisture. **D4850**

pressure, *n*—the force exerted to a surface per unit area.

DISCUSSION—Pressure may be expressed in any appropriate or specified units, such as pascals (PA), newtons per square meter (N/m²), or pounds-force per square inch (psi). **D1777**

proficiency testing, *n*—determination of the laboratory testing performance by means of interlaboratory comparisons. [D13.60] **D6674**

program coordinator, *n*—the person(s) responsible for management of all logistical issues, data collection, and report preparation. [D13.60] **D6674**

protrusion, *n*—in fabrics, a general term for a visible group of fibers, a yarn, or a yarn segment that extends above the fabric surface. **D3939, D5362**

puckering, *n*—in bonded, fused, or laminated fabrics, a wavy, three-dimensional effect typified by closely spaced wrinkles, on either the face fabric or the backing fabric, or both. **D2724**

rack, *n*—in warp knitting, a unit of length measure consisting of 480 courses. **D4850**

rack length, *n*—in warp knitting, the length of the fabric produced by knitting one rack, measured on the machine under operating take-up tension.

DISCUSSION—Rack length is usually expressed in “inches-per-rack” (IPR). **D4850**

raised fiber surface, *n*—in textile fabrics, intentionally lifted fibers or yarns such as pile, napped, tufted, flocked, or similar surfaces. **D1230**

raveled strip test, *n*—in fabric testing, a strip test in which the specimen is cut wider than the specified testing width and an approximately even number of yarns are removed from each side to obtain the required testing width. **D5035**

reinforced seam, *n*—in sewn seams, a seam that includes an additional layer of material on the face or back side of the seam allowance.

DISCUSSION—The added material is used to strengthen the seam and delay failure of the seam beyond the minimal acceptable limits and so enable the specimen to pass a specified cyclic impact test. **D4033**

repeatability, *n*—in statistics, the distribution of several measurements on the same part by one operator with the same gage. [D13.60] **D6674**

reproducibility, *n*—in statistics, the distribution of several measurements on the same part by several operators with the same gage. [D13.60] **D6674**

resilience, *n*—that property of a material to recover to approximately its original size and shape after deformation. **D4850**

resistance to yarn slippage, *n*—at the seam, the force required to displace one or more yarns in a fabric from the original position, causing differences in alignment, or spacing, or both. **D4033, D4034**

ribbon, *n*—a fine-textured, narrow fabric which weighs less than 510 g/m² (approximately 2.6 lb/100 yd per inch of width or 15 oz/yd²) and which is used primarily for trimming or decorative purposes. (See also **narrow fabric**.)

DISCUSSION—Usually ribbons are woven fabrics less than 4 in. (100 mm) wide. **D4850**

rotation, *n*—one count on the counter which is roughly equivalent to one cycle. [D13.60] **D4158**

rub, *n*—one rotation of the two outer gearings of the Martindale tester.

DISCUSSION—The term movement has been used to represent one rotation of the two outer gearings of the Martindale tester. However, rub is a less confusing term and is preferred to the term movement. **D4966**

sample, *n*—(1) a portion of material which is taken for testing or record purposes. (2) a group of specimens used, or of observations made, which provide information that can be used for making statistical inferences about the population(s) from which the specimens are drawn. [D13.60] **D6674**

selvage, *n*—the woven edge portion of a fabric parallel to the warp.

DISCUSSION—The selvage usually has an increased number of ends per inch. **D4850**

shoe fold, *n*—a fabric folded from both ends into twelve or sixteen folds to the piece, the length of the fold depending upon the length of the piece. (Compare **book fold**.) **D4850**

sizing, *n*—a generic term for compounds which, when applied to yarn or fabric, form a more or less continuous solid film around the yarn and individual fibers.

DISCUSSION—Sizing varieties include:

(a) *Sizing*—Applied to warp yarn to bind the fibers together and stiffen the yarn.

(b) *Dope*—Applied to crepe yarn to set the twist and assist creping.

(c) *Dressing*—Applied to sewing thread to bind the strands together and leave a pliable yarn.

Varieties applied to fabric include:

(a) *Sizing*—Applied to fabrics to improve their physical properties such as mass, stiffness, and so forth.

(b) *Dope*—Applied to airplane fabrics to make them taut and to

balloon fabrics to make them less permeable to gases.

(c) *Dressing*—Applied to fabrics to produce a glazed, lustrous effect. (Compare *filler*.) **D4850**

skew, *n*—a fabric condition resulting when filling yarns or knitted courses are angularly displaced from a line perpendicular to the edge or side of the fabric.

DISCUSSION—Knitted courses or filling yarns usually appear as straight lines at right angles to the edge or side of the fabric. When tubular knitted fabric is finished, differential skew may occur on the top and bottom part of the tube. **D3882, D3990**

sley, *n*—the number of warp ends per 25 mm (1 in.) of fabric width, exclusive of selvage. **D4850**

snag, *n*—*in fabrics*, a yarn or part of a yarn pulled or plucked from the surface.

DISCUSSION—For the purpose of Test Methods **D3939** and **D5362**, a snag is created when an object pulls, plucks, scratches, or drags a group of fibers, a yarn, or a yarn segment from its normal pattern. Snags can be classified into three types: (1) snags that have a protrusion and no distortion, (2) snags that have a distortion and no protrusion, and (3) snags that have both a protrusion and a distortion. Other changes in appearance, such as color contrasts, should be reported because they affect the visibility of a protrusion or a distortion. **D3939, D3990, D5362, D3882**

snagging resistance, *n*—*in fabrics*, the property of a fabric whereby yarns or parts of yarns are prevented or inhibited from being pulled or plucked from the surface. **D3939, D5362**

solvent relative humidity, *n*—the humidity of air over a drycleaning bath and in equilibrium with the solvent and its small amount of water. **D2724**

specimen, *n*—a specific portion of a material or a laboratory sample upon which a test is performed or which is selected for that purpose. **[D13.60] D6674**

stable fabric, *n*—a fabric, the dimensions of which do not change significantly during processing or use.

DISCUSSION—A stable fabric is also a fabric that does not change significantly with multiple passes through measuring devices. **D3773**

stain, *n*—an area of discoloration that penetrates the fabric surface. **D3990, D5426**

standard atmosphere for preconditioning textiles, *n*—an atmosphere having a relative humidity of 10 to 25 % and a temperature not over 122°F (50°C). **D3885, D4966, D6770**

standard atmosphere for testing, in textiles, *n*—an atmosphere for testing in which the air is maintained at a relative humidity of 65 ± 2 % and at a temperature of 70 ± 2°F (21 ± 1°C). **D4966**

standard atmosphere for testing textiles, *n*—laboratory conditions for testing fibers, yarns, and fabrics in which air temperature and relative humidity are maintained at specific levels with established tolerances.

DISCUSSION—Textile materials are used in a number of specific end-use applications that frequently require different testing temperatures and relative humidities. Specific conditioning and testing of textiles for end-product requirements can be carried out using Table 1 in Practice D 1776. **[D13.60] D3882, D3885, D6770**

static force, *n*—*in textile testing*, a mass which exerts a force by means of the mass alone without motion. (*Syn.* dead load.) **D5278**

static load, *n*—*in textile testing*, a mass which exerts a force by means of the mass alone without motion (synonym, dead load). **[D13.59] D5278**

stiffness, *n*—resistance to bending. **D1388, D4032**

stiffness, *n*—*with regard to circular bending of textiles*, resistance to multidirectional bending. **D4032**

stretch woven fabric, *n*—a woven fabric which is capable of at least 20 % stretch in either warp or filling direction, or both, under forces and conditions encountered in use, and almost complete recovery after removal of the force.

DISCUSSION—There are currently two main classes of woven stretch fabrics:

(1) Fabrics which rely more on force of recovery than on stretch for their utility. This class includes most of the woven elastic fabrics containing 15 % or more elastomer. These fabrics are sometimes referred to as power stretch fabrics.

(2) Fabrics which rely more on stretch than on force of recovery for their utility. This class includes most of the woven elastic fabrics containing less than 15 % elastomer, most woven fabrics containing stretch yarns, and many other woven fabrics with built-in stretch characteristics. These fabrics are sometimes referred to as comfort stretch fabrics.

The term stretch fabric is sometimes applied to knitted and other types of fabrics which are capable of high stretch and recovery.

D4850, D3787

stretch yarn, *n*—a generic term for filament or spun yarns having a high degree of potential elastic stretch and a rapid recovery.

DISCUSSION—Stretch yarns are generally produced by an appropriate combination of deforming, heat setting, and developing treatments to attain elastic properties. **D6614**

strip test, *n*—*in fabric testing*, a tensile test in which the full width of the specimen is gripped in the clamps. **D5035**

stroke, *n*—*in hex bar abrasion testing*, one-half of an abrasion cycle that consists of one forward or one backward motion. **[D13.60] D6770**

surface contour, *n*—divergence of a surface from planeness rough (high) to smooth (low). **D4850**

surface friction, *n*—resistance to slipping offered by surface harsh (high) to slippery (low). **D4850**

surface water absorption, *n*—*by a fabric*, the process of removing liquid water from a surface such as human skin, dishes, or furniture. **D4772**

take-up, *n*—*in fabrics*, the difference in distance between two points in a yarn as it lies in a fabric and the same two points after the yarn has been removed from the fabric and straightened under a specified tension, expressed as a percentage of the straightened length. **D3883**

tearing force, *n*—*in fabric*, the force required either (1) to start or (2) to continue or propagate a tear in a fabric under specified conditions. **D1424, D2261, D2262, D5587, D5034, D4350**

- tearing energy**, *n*—the work done in tearing a material. **D1424**
- tear resistance**, *n*—*in fabrics*, the resistance to a tearing force. **D1424**
- tearing strength**, *n*—*in fabric*, the capacity of a material to withstand the ultimate tearing force required to propagate a tear after its initiation. **D1424, D2261, D5587, D5034**
- tensile test**, *n*—*in textiles*, a test in which a textile material is stretched in one direction to determine the load-elongation characteristics, the breaking load, or the breaking elongation. **[D13.60] D5034, D4850**
- tension**, *n*—a uniaxial force tending to cause the stretching of a material. **D1775, D3107, D4848, D4964**
- tension-recovery chart**, *n*—*in tension testing*, a continuously plotted graph of tension versus extension resulting from a tension-recovery cycle. (Compare to **extension-recovery chart**. See also **extension-recovery cycle** and **tension-recovery cycle**.) **[D13.60] D4850**
- tension-supported roof**, *n*—a fabric roof-system, that is properly secured and primarily held in place by tensile forces applied across the system. **D4851**
- tension test**, *n*—*in textiles*, a test designed to measure the tautness of a textile strand or fabric. **D1775, D4848, D4964**
- terry fabric**, *n*—a fabric with a woven warp pile or a knitted pile, with uncut loops on a single side or uncut loops on both sides, and which is used for such products as toweling, beachwear, and bathrobes. **D4390, D4772**
- test result**, *n*—a value obtained by applying a given test method, expressed as a single determination or a specified combination of a number of determinations. **[D13.60] D6674**
- testing laboratory**, *n*—laboratory that performs tests (including calibration) (also referred to as “participating laboratory,” or just “laboratory”). **[D13.60] D6674**
- texture**, *n*—the surface appearance and hand of a textile.
DISCUSSION—Texture is independent of the color of the textile. **D4850**
- thermal character**, *n*—that property of a fabric that makes it feel warm to the touch. **D4850**
- thickness**, *n*—the distance between one surface and its opposite.
DISCUSSION—In textiles, thickness is the distance measured between the upper and lower surfaces of the material as measured under a specified pressure. It is usually determined as the distance between an anvil or base and a presser foot used to apply the specified pressure. **D1777**
- thread break**, *n*—*in sewn seams*, a mode of failure evidenced by rupture of the sewing thread.
DISCUSSION—A sewing thread break is not construed as a failure unless the test is being performed as a sewing thread analysis. **D4033**
- tufted fabric**, *n*—a fabric with a pile consisting of tufts or loops formed by inserting yarn into a previously prepared backing fabric. **D4850, D5684, D5793**
- twill weave**, *n*—a weave characterized by diagonal lines produced by a series of floats staggered in the warp or filling direction. (See also **warp-faced twill** and **filling-faced twill**.) **D4850**
- velveteen**, *n*—a woven fabric in twill or plain weave made with a short closely packed filling pile in imitation of velvet. **D4685, D5103**
- wale**, *n*—*in woven fabric*, one of a series of raised portions or ribs lying warpwise in the fabric. **D4850, D5684**
- wale**, *n*—*in knitted fabrics*, a column of successive loops in the length direction of the fabric. **D4850**
- warp**, *n*—(1) the yarn running lengthwise in a woven fabric; (2) a group of yarns in long lengths and approximately parallel, put on beams or warp reels for further textile processing including weaving, knitting, twisting, dyeing, and so forth. **D4850**
- warp elongation and tension**, *n*—stretch or tension measured in the warp direction of the fabric. **D1775**
- warp-faced twill**, *n*—a weave in which warp yarns float over filling yarns, to produce a diagonal effect in the resulting fabric. (See also **twill weave** and **filling-faced twill**.) **D4850**
- warp tests**, *n*—*in fabric testing*, tests in which the warp yarns are torn. **D1424**
- warp-to-filling seam**, *n*—a sewn seam in which the warp yarns are perpendicular to the sewn seam on one side of the seam and parallel to the seam on the opposite side of that seam. **D4033**
- warp-to-warp seam**, *n*—a sewn seam in which the yarns in the warp direction on both sides of the seam are perpendicular to the seam. **D4033**
- warp-faced twill**, *n*—a weave in which warp yarns float over filling yarns, to produce a diagonal effect in the resulting fabric. (See also **twill weave** and **filling-faced twill**.)
- wash-and-wear**, *adj*—a generic term applied to fabrics or garments which satisfactorily retain a neat appearance after repeated wearing and suitable home laundering with little or no pressing or ironing. (Compare **durable-press**.)
DISCUSSION—The wash-and-wear performance of a fabric or garment depends on several factors including the types and amounts (percentages) of fibers used, the fabric construction, the finishing treatment, the presence of a colored pattern (either woven or printed), and the methods used for washing and drying. All of these factors contribute to the overall performance and determine, in any specific instance, how closely a fabric or garment will approach acceptance. **D4850**
- webbing**, *n*—*in textiles*, a stout narrow fabric with a mass per unit area of at least 0.5 kg/m² (0.1 lb/ft²) for each 25.4 mm (1 in.) of width. (Compare *narrow fabric*, *ribbon*, and *tape*.) **[D13.60] D6770**
- weight**, *n*—*in warp knitting*, the number of tex (yards per pound) of finished fabric.
DISCUSSION—This may be expressed as square metres per kilogram or linear metres per kilogram (square yards per pound or linear yards per pound), in which case the width must be stated. **D4850**

weight, n—*as used with fabrics*, mass per unit area.

DISCUSSION—Fabric mass per unit area is expressed either as grams per square meter (ounces per square yard) or grams per linear meter (ounces per linear yard). Fabric mass is also sometimes expressed inversely as linear meters per kilogram (yards per pound) with the fabric width stated. **D3776**

wide elastic fabric, n—an elastic fabric that is at least 150 mm (6 in.) in width. (Compare **narrow elastic fabric**.) **D1775, D4964**

width, n—*of flat knit fabrics*, the perpendicular distance between the selvages when the fabric is under zero tension and free of folds or wrinkles. **D3887**

width, n—*of circular knit fabrics*, twice the perpendicular distance between the enclosed edges of a flattened tube of fabric that is under zero tension and free of folds or wrinkles. **D3887**

width, n—*of a raised-surface fabric*, the dimension included within the outer limits of the nap or pile, but excluding the selvages, or as otherwise agreed upon by the purchaser and supplier. **D3774**

width, n—*of a fabric*, the distance from the outer edge of one selvage to the outer edge of the other selvage, measured perpendicular to the selvages while the fabric is held under zero tension and is free of folds and wrinkles. **D3774**

width, n—*of a fabric woven on a shuttleless loom*, the distance from the outer warp on one side to the outer warp on the other side, measured perpendicular to the warp yarns while the fabric is held under zero tension and is free of folds and wrinkles. **D3774**

woven fabric, n—a structure produced when at least two sets of strands are interlaced, usually at right angles to each other, according to a predetermined pattern of interlacing, and such

that at least one set is parallel to the axis along the lengthwise direction of the fabric. **D3773, D5378, D3786**

wrinkle recovery, n—that property of a fabric which enables it to recover from folding deformations. **D4850**

wrinkle resistance, n—that property of a fabric which enables it to resist the formation of wrinkles when subjected to a folding deformation.

DISCUSSION—“Crease resistance” is a term commonly used in place of the preferred term “wrinkle resistance.” **D4850**

yarn break, n—*in sewn seams*, a mode of failure evidenced by yarns rupturing at the seam or at any other area in the test specimen. (*Syn.* yarn burst and yarn tear.) **D4033**

yarn crimp, n—*in fabric*, the undulations or waviness in a yarn due to interactions with other yarns.

DISCUSSION—Yarn crimp in a fabric is the difference in the measured distance between two points on a yarn as it lies in the fabric, and the same two points when the yarn has been removed from the fabric and straightened under a specified tension, expressed as a percent based on the in-fabric distance. **D3883**

yarn distortion, n—*in woven fabrics*, a condition in which the symmetrical surface appearance of a fabric is altered by the shifting or sliding of warp or filling yarns. **D1336**

yarn slippage, n—*at the seam in sewn fabrics*, the displacement of one or more yarns from the original position, causing differences in alignment, spacing, or both. **D4033, D4034**

yarn take-up, n—*in fabric*, the additional length of yarn used to make a given length of fabric. **D3883**

yield, n—*in knitted fabrics*, the number of finished square metres per kilogram (square yards per pound) of greige fabric. **D4850, D3883**

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/